Kinetic Isolation between Turnovers on Au₁₈ Nanoclusters: Formic Acid Decomposition One Molecule at a Time

Benjamin W. J. Chen¹, Michail Stamatakis², Manos Mavrikakis*¹

¹*Department of Chemical and Biological Engineering, University of Wisconsin – Madison,
Madison, WI 53706*

²*Thomas Young Centre and Department of Chemical Engineering, University College London,
Roberts Building, Torrington Place, London WC1E 7JE, United Kingdom*

*corresponding author emavrikakis@wisc.edu

Abstract

Formic acid (HCOOH or FA) is a clean, safe, and renewable hydrogen storage material. Although Au catalysts decompose vapor-phase FA with high activity and selectivity towards hydrogen, the active site and reaction mechanism remain unclear. Here, we show that the subnanometric Au₁₈ cluster (0.8 nm in diameter) is likely the active species for FA decomposition. We performed coverage self-consistent, density functional theory-based kinetic Monte Carlo simulations of FA decomposition on gas-phase Au₁₈ clusters, predicting 100% selectivity towards hydrogen and turnover frequencies close to experimentally determined values. The active site is made up of a triangular ensemble of three atoms each possessing a coordination number of 5. Although there are two active site ensembles on the Au₁₈ cluster, their occupations are strongly correlated due to strong, stabilizing, interactions between pairs of open-shell adsorbates mediated by the superatomic nature of the cluster. Because the occupation of the active sites blocks the dissociation of additional HCOOH molecules, there is kinetic isolation between turnovers: only one HCOOH molecule can dissociate on the cluster at a time. This explains the extraordinary, experimentally-

observed selectivity of Au catalysts towards HD during decomposition of HCOOD and DCOOH. Our work offers nanoscale insights into the reaction mechanisms of FA decomposition over Au. To our knowledge, this represents the first example of heterogeneous catalysis by a cluster that catalyzes reactants one molecule at a time. Our work on Au₁₈ thus sheds light on how the unique electronic properties of subnanometric clusters can be used to design quasi-molecular catalysts with high activity and selectivity.

1. Introduction

The continued consumption of fossil-fuels has led to multiple societal challenges such as pollution and climate change. Efforts to pivot towards a hydrogen-based economy with cleaner and more renewable sources of energy have however been stymied by a lack of ways to safely and efficiently store hydrogen.¹⁻³ Formic acid (FA, chemical formula: HCOOH) is a promising hydrogen carrier;^{4,5} it is energy dense (4.4 wt. % H₂, 53 g H₂ L⁻¹ at 298 K), and widely available from renewable sources such as biomass, making it an intense topic of current research.⁶⁻¹¹ Compared with other forms of hydrogen storage, FA possesses many advantages. For example, direct formic acid fuel cells exhibit larger open-circuit potentials and less fuel crossover from the anode to the cathode, a problem for direct methanol fuel cells.^{12,13} Further, FA can act as an *in situ* H₂ source, e.g. for converting levulinic acid to γ -valerolactone, a valuable precursor to various fuels and chemicals.¹⁴⁻¹⁷ It is also commercially appealing; being a non-toxic and non-flammable liquid, current hydrocarbon-based infrastructure can be easily adapted for FA, lowering the barriers for market entry.¹⁸

Decomposition of FA to release H₂ however presents a selectivity challenge. FA can either *i*) dehydrate into CO + H₂O, or *ii*) dehydrogenate to CO₂ + H₂.¹⁹ For technological applications like fuel cells, CO-free H₂ is required. Recently, Ojeda and Iglesia found that finely-dispersed Au

catalysts supported on Al_2O_3 decomposed FA at near-ambient temperatures,²⁰ with complete selectivity towards H_2 and rates surpassing that of Pt, one of the most active catalysts for FA decomposition²¹. The authors hypothesized, and others subsequently concurred,^{7,22} that small Au clusters, difficult to detect by transmission electron microscopy, were the active species on Au/ Al_2O_3 . A combined theoretical and experimental study by Singh et al. indeed ruled out Au(111), Au(100), and Au(211), which are found on larger nanoparticles, as possible active sites.²³ Since this discovery, well-dispersed Au catalysts supported on ZrO_2 ,^{7,24,25} TiO_2 ,²⁶ CeO_2 ,^{22,24,27} and SiC²³ have also been found to exhibit high catalytic activity and selectivity for FA decomposition.

The underlying reasons for the high activity and selectivity of these Au catalysts however remain unidentified, in part due to the extraordinary and complex catalytic properties of small clusters,^{28,29} first brought to light by the pioneering work by Haruta with Au.^{30,31} The reactivity of a cluster differs not only from that of the bulk material, but also from that of other clusters with different sizes down to the addition or removal of single atoms.^{32–36} With this in mind, Li et al. screened a series of subnanometric Au_n ($n=4\text{--}25$) clusters with density functional theory (DFT)-based microkinetic modeling, and proposed Au_{18} (~0.8 nm in diameter) as the active Au species for Au/SiC catalysts, as it required the least adjustment from their density functional theory (DFT)-calculated reaction parameters to explain the experimental data³⁷

Despite the success of the work by Li et al. in achieving semi-quantitative agreement with experimental measurements, crucial features—one being the sole production of HD from the decomposition of singly-deuterated FA isotopomers²⁰—could not be explained by their microkinetic models. Additionally, they were unable to gain detailed molecular insights into the reaction mechanism. These shortcomings are rooted in three unique properties of the Au_{18} cluster that they were unable to address: *i*) Au_{18} is very small, exhibiting discrete adsorbate coverages; *ii*)

Au₁₈ exposes many unique site types, resulting in a spatially inhomogeneous surface; and *iii*) adsorbates bound to Au₁₈ nanoclusters experience strong lateral interactions due to quantum-size effects and the superatomic nature of Au clusters³⁸ (elaborated upon in the Results), therefore surface adsorbates are not well-mixed. These factors lead to a breakdown in the mean-field approximation, necessitating the use of methods that are able to capture local, discrete, fluctuations in adsorbate coverages with high-fidelity, such as on-lattice kinetic Monte Carlo (KMC) simulations.^{39,40}

On-lattice KMC simulations overcome the fundamental limitations of microkinetic modeling and capture the complexities of catalysis on small clusters by tracking of the positions of each vacant site and adsorbate.⁴¹ State-of-the-art implementations can also include coverage effects self-consistently with energetics models that adapt on-the-fly to changes in adsorbate coverages.⁴² One way to build such an energetics model is to fit a cluster expansion (CE)^{43,44} Hamiltonian with DFT-based calculations, which can then be used to rapidly evaluate the energy of any adsorbate configuration encountered in the KMC simulations. This approach rigorously accounts for the effects of lateral interactions on reaction energies, as well as activation energies via Brønsted–Evans–Polanyi (BEP) relations.⁴⁵

Here, we develop a DFT-based KMC model on a Au₁₈ cluster to determine the nature of the active site and the reaction mechanism for FA decomposition. We first gain thermodynamic and kinetic insights from DFT calculations of minimum energy pathways (MEPs) for FA decomposition. Next, we perform coverage self-consistent KMC simulations using our calculated pathways with a CE Hamiltonian to incorporate adsorbate-adsorbate interactions. Lastly, we show how our results lead us to a hypothesis regarding the mechanistic pathways for FA decomposition on Au₁₈ and the

discovery of the unique atomic-scale nature of Au_{18} with dual active sites, which explains the observed selectivity towards HD for the decomposition of singly-deuterated FA isotopomers.²⁰

Figure 1 Structure and lattice representation of Au_{18} cluster. (a-c) Structure of Au_{18} , in (a) top and (b,c) side views. Representative high-symmetry adsorption sites are shown in turquoise and annotated by their site name, where ‘t’, ‘b’, ‘h’ and ‘f’ refer to top, bridge, hcp-like, and fcc-like sites respectively. Color code for atoms: red – Au with coordination number of 3 (CN=3), pink – Au, CN=5, purple – Au, CN=6, green – Au, CN=9. (d) Lattice representation of the Au_{18} surface. Circles, squares, triangles, and inverted triangles represent top, bridge, hcp-like, and fcc-like sites respectively. Top sites share the same color code as the atoms in (a-c); and bridge, hcp-like, and fcc-like sites are colored based on their neighboring top sites. Lines connect neighboring sites and are colored similarly to the sites they connect; connections between sites which are far apart in this representation are not shown for clarity. A full listing of site neighbors can be found in Table S4.

2. Methods

2.1. Kinetic Monte Carlo Simulations

Kinetic Monte Carlo (KMC) simulations were performed with *Zacros*, an on-lattice, graph-theoretical KMC code.^{41,42} A 2-dimensional lattice representation of the surface of the Au_{18} cluster was constructed by first mapping out the unique high-symmetry site types (Figure 1a-c). Neighbouring connections were then defined by considering the physical distances between sites, as well as the ease of representing reaction events. The resulting lattice is shown in Figure 1d;

Table S2 contains all information needed to reproduce this lattice. We only consider bridge sites at the edges of the cluster and not bridge sites on the facets as they bind adsorbates weakly and would greatly increase the number of sites and thus the computational costs involved.

Binding and activation energies were obtained from rigorous density functional theory (DFT)-based calculations. For each species, we first probed all unique high-symmetry sites to locate stable adsorption structures. Starting from each of these obtained structures, we then attempted to locate transition states for possible reactions of that species. Barriers for diffusions were defined to be 0.12 times of the absolute binding energy of initial or final state, whichever binds stronger to the surface. This was found to be a good approximation for both clusters⁴⁶ and extended surfaces⁴⁷. To improve the agreement of the simulated apparent activation energies with experiment, we destabilized the binding of only two HCOO species by 0.2 eV. This parameter adjustment is discussed further in the Results section. Accounting for multiple topological variants of species and reactions due to the multiple unique high-symmetry sites involved, a final total of 112 species and 322 elementary steps were employed in our KMC simulations.

Adsorbate-adsorbate interactions were accounted for self-consistently in our simulations, with interaction energies derived from our Cluster Expansion (CE) Hamiltonian. Adsorbate-adsorbate interactions may lead to changes in the reaction energy, ΔE_r , and thus also changes in the activation energy, ΔE_a , of a reaction. *Zacros* calculates the ΔE_r for every time step, and the ΔE_a are accounted for on-the-fly in our simulations via Brønsted Evans Polanyi (BEP) relations:

$$\Delta E_a = \alpha \Delta E_r, \quad (1)$$

where α is the BEP proximity factor. We set α to 0.5 for quasi-equilibrated elementary steps. This approximation does not affect the overall rate of FA decomposition. However, for elementary steps

which are determined not to be quasi-equilibrated, we explicitly calculated α from first-principles calculations to more accurately describe these elementary steps as they may critically affect the overall rate of FA decomposition.

Due to the presence of reactions with widely varying activation energies, we automatically scaled the rate constants of quasi-equilibrated steps to increase sampling of reactions with large barriers to accelerate the simulations.

To handle the large number of species, interactions, and reactions employed in our simulations, we built an in-house MATLAB framework that interfaced with the *Zacros* code. This framework then created the required *Zacros* input files automatically.

Each simulation simulates 25 Au₁₈ clusters at a time, and was run until a minimum of 6 simulated seconds. Details of the parameter adjustment, energetics model, and reactions model can be found in Sections S1, S2, and S3 of the Supporting Information (SI) respectively, and a list of adsorbates and reactions employed in our KMC simulations can be found in Tables S6 and S7 respectively.

2.2. Cluster Expansion

Adsorbate-adsorbate interactions, i.e. pair-wise and higher order interaction terms, were accounted for in our KMC simulations with a CE Hamiltonian. Binding energies on the clean cluster were used for the single-body terms. Only open-shell species (i.e. species that show significant binding to the cluster) in the HCOO pathway, i.e. H, HCOO, and inverted HCOO (HCOOi), were considered for the CE. For species in the COOH pathway, i.e. COOH, OH, and CO, interactions were calculated manually from configurations containing pairs of these species. Only a basic level of interactions necessary for correctly describing reaction energetics were considered, since there is no flux through the COOH pathway (see Results).

The total energies of multiple configurations were first obtained by DFT-based calculations using the PW91 functional. Each configuration was then mapped on to the lattice representation of the Au₁₈ surface, enabling us to subsequently expand their total energies in terms of point, pairwise, and three-body interactions: effective cluster interactions (ECIs). The total energies of arbitrary configurations can thus be rapidly evaluated as linear combinations of these ECIs. The CE model was refined via an iterative procedure that involved fitting of training configurations, prediction of new configurations via simulated annealing using the CE Hamiltonian, evaluation of the new configurations using DFT-based calculations, and refitting of the CE with the new configurations. The procedure was stopped when no new configurations that were more stable than those in the training set were found. In total, ~4200 training configurations were evaluated. The resulting CE model had a 10-fold cross validation score of 0.16 eV and a root mean square error (RMSE) of 0.23 eV when evaluated against a set of ~1000 verification configurations. More information about the fitted CE Hamiltonian can be found in Section S2; the ECIs are tabulated in Table S8.

2.3. Density Functional Theory (DFT)-based calculations

We performed periodic plane wave DFT-based calculations with the Vienna *ab initio* Simulation Package (VASP).^{48,49} Core states were represented by projector augmented wave (PAW) pseudopotentials^{50,51}, while valence states were expanded in a plane wave basis set with a cutoff energy of 400 eV. Geometries were obtained with the Perdew-Wang 91 (PW91) form of the generalized gradient approximation (GGA),⁵² and energies were obtained by single-point calculations with the optB88-vdW functional⁵³. This approach is a good balance of computational speed and accuracy since the average errors compared with fully optimized optB88-vdW calculations are just -0.02 eV (negative errors reflect stronger binding for the fully optimized optB88-vdW calculations), with a maximum error of -0.05 eV for weakly-binding species such as

CO₂ (Table S5). Ionic relaxation was stopped when forces on all atoms were less than 0.02 eV Å⁻¹. All calculations were done with spin-polarization. The Brillouin zone was sampled at the gamma point, and the Fermi surface treated with Gaussian smearing with a Fermi temperature of 0.1 eV. Final energies were obtained by extrapolating to a Fermi temperature of 0 eV.

The climbing-image nudged elastic band (CI-NEB) method was used to locate transition states. Transition states were optimized until forces on all atoms were less than 0.02 eV Å⁻¹, and were confirmed by the presence of a single imaginary frequency.

Vibrational frequencies were obtained by calculation of the Hessian by numerical differentiation of the energies using a second-order finite differences approach with four displacements in each direction. Step-sizes of ±0.007 Å were used for two displacements and step-sizes of ±0.014 Å were used for the other two displacements. These step-sizes were chosen to be small enough for accurately calculating the Hessian but large enough to avoid issues due to numerical noise in the energies. The Hessian was mass-weighted and diagonalized to yield the normal mode frequencies.

2.4. Structural Model for Au₁₈

We used the most stable pyramidal structure of clean Au₁₈ obtained by *ab initio* molecular dynamics simulations, as described in a previous publication.³⁷ Strong evidence for the existence of this structure was found using photoelectron spectroscopy^{54,55} and trapped ion electron diffraction (TIED) measurements⁵⁶. Besides the most stable pyramidal structure, a nearby low-energy isomer, the hollow-cage isomer, is also suspected to exist.⁵⁴ Such low-energy isomers have been shown by studies by Alexandrova to be important for some chemistries at elevated temperatures and at high adsorbate coverages.⁵⁷

During the course of our DFT calculations, however, we did not observe any cluster reconstruction or isomerizations from the pyramidal structure to the hollow-cage structure when 1 HCOO and 1 H—corresponding to one dissociated FA molecule, the highest possible coverage on the Au₁₈ cluster under reaction conditions as predicted from our simulations (see Results)—was adsorbed on the cluster. We thus believe that the most stable pyramidal structure we employed in our calculations is a good representation of the cluster even under reaction conditions, and so we focused our computational resources on this structure, striving for a rigorous description of the effects of coverage instead of pursuing studies on the hollow-cage isomer.

3. Results

3.1. Minimum Energy Pathways

Au₁₈ (Figure 1a-c) exposes atoms with varying degrees of coordination, ranging from CN=3 (coordination number of 3, red atoms), to CN=9 (green atoms). To determine the reactivity of the cluster, we rigorously probed all unique high-symmetry site types to obtain the most stable minima and transition states (TSSs) for each species. We considered two well-known pathways: the HCOO pathway and the COOH pathway. We do not consider pathways involving HCO species as these pathways are highly unfavorable; HCOOH decomposition to HCO + OH has a barrier that is 0.16 and 0.72 eV larger than that of HCOOH decomposition to COOH + H and HCOO + H respectively. Also, decomposition of HCOO to HCO + O has barriers in excess of 3 eV. We also do not consider the water-gas-shift (WGS) reaction, which interconverts CO and CO₂, as high WGS activities are only seen for Au catalysts supported on reducible supports such as CeO₂ and TiO₂, and only at temperatures above 473 K,^{58,59} 60 K above the highest temperatures studied for FA decomposition.²³

Figure 2 Structures of adsorbates relevant in the HCOO pathway on Au₁₈. (a) Most stable minima. (b) Most stable transition states. In both (a) and (b), top rows portray views from the side of the Au₁₈ cluster, whereas bottom rows show views from the top of the cluster. Pink triangles mark the Au atoms with coordination number of 5. Color code: gold – Au, grey – C, red – O, blue –H.

The minima and TS structures relevant for the HCOO pathway are illustrated in Figure 2; those relevant for the COOH pathway are illustrated in Figure S6. All states are most stably adsorbed on triangular ensembles of Au atoms marked by pink triangles—the same pink Au atoms with CN=5 in Figure 1a-c. This suggests that these atoms might be the active sites for the reaction. A variety of different site types are present on these triangular ensembles, namely the b2, b3, t1, t2, and f1 sites. For convenience, we refer to these sites as CN=5 sites.

Figure 3 Minimum energy pathways for decomposition of formic acid on clean Au₁₈. The DFT-calculated energies of states with HCOO are adjusted by +0.2 eV (see main text). Minima are denoted by bold lines and transition states are denoted by fine lines connecting the minima. ‘|’ denotes infinitely-separated species, ‘+’ denotes coadsorbed species, and ‘(g)’ denotes gas-phase species. Energies are referenced to gas-phase CO₂, CO, and H₂. Top views of the structures of the coadsorbed states are shown on the right. Pink triangles mark the Au atoms with coordination number of 5. Color code for structures: gold – Au, grey – C, red – O, blue – H.

The MEPs for FA decomposition are plotted in Figure 3. These MEPs include a destabilization of the DFT-calculated binding energies of two HCOO species by 0.2 eV—within the typical error of DFT calculations. These adjustments, also applied in our subsequent kinetic Monte Carlo (KMC) simulations, were carefully chosen using theoretical kinetic analyses so as to give better agreement with experimental²³ reaction orders and apparent activation energies, while not significantly affecting the turnover frequencies (TOFs). More information about this parameter adjustment and results from the unadjusted model are provided in Section S1 of the Supporting Information (SI).

Comparing first the COOH and HCOO pathways with energetics evaluated at infinite separation (dark blue and red lines respectively), the COOH pathway is likely inactive for FA decomposition on Au₁₈. The barrier for producing COOH (1.20 eV) is much higher than that for forming HCOO (0.64 eV). Additionally, the TS energy for C-H bond breaking lies above any point along the

HCOO pathway. If COOH was somehow formed, it would readily dissociate to CO + OH (red lines) instead of CO₂ (g) + H (pink lines). Subsequent recombination of OH + H to form H₂O as well as desorption of CO (g) is however difficult, with barriers of 0.82 and 1.07 eV respectively, which implies that an active COOH pathway would poison Au₁₈ by CO.

On the more favorable HCOO pathway, further dehydrogenation of HCOO to CO₂ (g) + H is easiest if HCOO first flips into an inverted state (HCOOi) with its C-H bond pointing towards the surface (Figure 2a). This is highly endothermic and has a large barrier of 0.80 eV. However, subsequent C-H bond breaking is facile with a barrier of just 0.09 eV. Finally, H₂ recombination occurs with a barrier of 0.52 eV, cleaning up the cluster and closing the catalytic cycle. This relatively activated H₂ recombination is due to the stable binding of H on the cluster, consistent with previous studies studying H₂ adsorption and desorption on Au clusters^{60–62}.

Our analysis so far however neglects the interactions between adsorbates, which may be significant for the small Au₁₈ cluster. We therefore recalculated all minima and TSs in the HCOO pathway with explicit coadsorbates where applicable. Structures of the most stable coadsorbed states are shown on the right of Figure 3; as on the clean cluster, the coadsorbates prefer the CN=5 sites. Comparing the MEP of the HCOO pathway constructed with infinite-separation energetics (dark blue lines) to the MEP constructed with coadsorbed energetics (light blue lines), we find a significant, approximately uniform, shift of the PES of around 0.2 – 0.3 eV towards lower energies, indicating a strong stabilization for coadsorbed states.

These strong stabilizing interactions between open-shell species such as H, HCOO, and HCOOi can be explained by the phenomenon of superatomicity, which affects the electronic structure of small clusters of up to 100 atoms with weakly bound *s* electrons.^{38,63–65} Au₁₈ is one example of a superatom; the 18 valence electrons of Au₁₈ are delocalized, filling up orbitals of discrete energy

that encompass the entire cluster, similar to how electrons fill up atomic orbitals. As the electrons fill up these superatomic orbitals in pairs, there is a strong odd-even electron effect⁶³—adsorption of open-shell species is weak if the cluster has an even number of electrons, and strong if the cluster has an odd number of electrons. Adsorption of a single open-shell species on a clean Au₁₈ cluster is weak as it has 18 valence electrons, but adsorption on a cluster with a pre-adsorbed open-shell species is strong as the system now has 19 valence electrons. In this way, the coadsorption of two open-shell species on Au₁₈ gives rise to strong stabilizing interactions. The mediation of these effects via orbitals delocalized over the cluster allows these interactions to persist even when the two species are far apart.

3.2. Kinetic Monte Carlo Simulations

We next used our DFT-based energetics to perform kinetic Monte Carlo (KMC) simulations of FA decomposition on Au₁₈, which will allow us to compare our results with macroscopic experimental observables. All elementary steps shown in Figure 3 were included, except those involving H₂O. Our tests show that inclusion of elementary steps involving H₂O do not affect the results since COOH is not formed (shown later). To account for adsorbate-adsorbate interactions, we fitted a cluster expansion (CE) Hamiltonian that captured the strong stabilizing interactions between coadsorbed states. These interaction energies not only affect reaction energetics, but also activation energies via the use of Brønsted-Evans-Polanyi (BEP) relations (proximity factors in Table S7).

Table 1 Experiments versus KMC simulations. Turnover frequencies (TOFs), apparent activation energies (E_{app}), reaction orders (η), and H₂ selectivity are compared. An average of 12 KMC simulations was used. Reported experimental TOFs for Au/SiO₂⁶⁶ and Au/Al₂O₃²⁰ were extrapolated to 413 K to facilitate comparison. Simulations were carried out under nominal conditions of 413 K, a total pressure of 1 bar, and a FA partial pressure of 0.025 bar; balance inert. Dashes indicate that data is unavailable.

Experiments ^a	Simulations
--------------------------	-------------

	Au/SiC	Au/SiO ₂	Au/Al ₂ O ₃	
H₂ TOF / mol s⁻¹ mol_{Au}⁻¹	0.06 ^b / 10 ^c	0.22 ^d	0.77 ^e	0.08
E_{app} / eV	0.62 ± 0.02	0.61	0.55 ± 0.02	0.56
Reaction Orders				
η(FA)	0.95 ± 0.06	0	0	0.72
η(CO ₂)	0.01 ± 0.00	-	-	0.00
η(H ₂)	0.01 ± 0.00	-	-	0.00
H₂ Selectivity / %	100	98	100	100

^a From references 23, 66, and 20 for Au/SiC, Au/SiO₂, and Au/Al₂O₃ respectively

^b With respect to the number of atoms in all clusters (see Supporting Information, Section S4)

^c With respect to the number of atoms in subnanometric clusters only (see Supporting Information, Section S4)

^d With respect to the number of surface atoms, extrapolated from T=473 K, TOF=1.951 mol s⁻¹ mol_{Au}⁻¹

^e With respect to the number of surface atoms, extrapolated from T=353 K, TOF=0.0558 mol s⁻¹ mol_{Au}⁻¹

Our simulations were conducted at nominal conditions of a total pressure of 1 bar, and FA, H₂, and CO₂ partial pressures of 0.025, 0.000, and 0.000 bar respectively (balance inert), and a temperature of 413 K, corresponding to conditions used in experiments on Au/SiC.²³ Our results are summarized in Table 1, together with experimental data for FA decomposition on Au/SiC²³, Au/SiO₂⁶⁶, and Au/Al₂O₃²⁰ catalysts.

The average H₂ TOF from our simulations is 0.08 mol_{H₂} s⁻¹ mol_{Au}⁻¹ (Table 1), which is close to experimental values on Au/SiC (0.06, normalized to the total number of Au atoms), as well as on Au/SiO₂ and Au/Al₂O₃ (0.22 and 0.77 respectively, normalized to the total number of surface Au atoms). As not all Au species are present in the form of Au₁₈ however, these methods of normalization overestimate the number of active Au atoms and underestimate the intrinsic activity of Au₁₈ (assuming it is the only active species).

To obtain a more appropriate comparison with experiment, it would be ideal to normalize the experimental rates based on the number of atoms in Au₁₈ clusters only. To this end, we used the particle size distributions of the Au/SiC catalysts²³ to calculate the total amount of Au in *subnanometric clusters* only (Section S4). This still overestimates the number of Au atoms that are in the form of Au₁₈ clusters, but gives a more realistic lower bound to the intrinsic TOF of Au₁₈.

From this analysis, subnanometric clusters contain 0.5% of the total amount of Au, which translates to a normalized TOF of approximately $10 \text{ mol}_{\text{H}_2} \text{ s}^{-1} \text{ mol}_{\text{Au}}^{-1}$, ~2 orders of magnitude larger than our simulated TOF.

Only CO_2 (g) and H_2 (g) are formed in our simulations; no CO (g) was produced, in agreement with experimental findings showing nearly complete selectivity towards H_2 (Table 1). All H_2 was formed through the HCOO pathway, with no contribution from the COOH pathway, reflecting the high barriers we calculated for creating COOH. This also explains the absence of CO (g) as COOH is the only precursor to CO in our model (CO may also be formed from HCO ⁶⁷, but formation of HCO is unfavorable). The TOFs do not vary over the course of our simulation (Supporting Figure 6), indicating that poisoning of Au_{18} does not occur in the timespan studied (6 seconds), consistent with experiments showing no deactivation of Au/SiO₂ even after several hours of FA decomposition.⁶⁶

Our calculated apparent activation energy of 0.56 eV (Figure S8) agrees well with experimental apparent activation energies ranging from 0.52 to 0.62 eV. Our simulated CO_2 and H_2 reaction orders of 0.00 and 0.00 (Figure S9) respectively also agree with those measured on Au/SiC²³. Our simulated FA reaction order of 0.72 (Figure S9) is closer to the measured value of 0.95 on Au/SiC as compared with the values of 0 on Au/SiO₂ and Au/Al₂O₃; possible reasons are noted in the Discussion.

Figure 4 Species fluxes and reaction occurrences. (a) Net species fluxes over all reactions for formic acid decomposition over Au_{18} , from a kinetic Monte Carlo (KMC) simulation with 25 Au_{18} clusters. Green and yellow ovals/circles represent gas-phase reactants and products respectively; purple, orange, blue ovals/circles represent adsorbed HCOOH, HCOO/HCOOi, and H species respectively. The direction and thickness of the arrows denote the direction and magnitude of the flux; numbers quantify the flux. Where the input flux does not equal the output flux, the species remains adsorbed on the clusters. Only species with non-zero net fluxes between any pair of species are displayed. (b) Occurrences of elementary steps that are not diffusion or adsorption events, and have a non-zero net occurrence from an average of 12 KMC simulations. Adsorbates are displayed as: [name][site type]. For bidentate adsorbates, two site types are displayed, one for each dentate. For HCOO, both dentates are O, whereas for HCOOi, the first dentate is O, and the second dentate is H.

Figure 5 Configurational analyses from kinetic Monte Carlo simulations on Au₁₈. An average of 12 simulations, done under nominal conditions, was used. (a) Coverage versus time of species with coverages of at least 0.001. (b) Probability of observing given configurations on the cluster at any time for configurations with probabilities of at least 0.01. (c) Occupancy of different site types by various species for occupancies of at least 0.01.

3.3. Reaction Mechanism and Nature of the Active Site

Analysis of the species fluxes (Figure 4a) and occurrences of the elementary steps (Figure 4b) strongly support the hypothesis from our DFT-based calculations that the CN=5 sites are the active sites for FA decomposition on Au₁₈. Our results show that HCOOH enters the reaction system by adsorption on the t2 sites. It then dissociates creating H on t1 sites and HCOO on t2 sites. Although H diffuses significantly (blue circles), the only H species directly contributing to the H₂(g) flux are bound to the b3 and b4 site types. Also, the flipping of HCOO to HCOOi and the subsequent decomposition of HCOOi to CO₂(g) involves species bound only to either of the t1 or t2 site types

(orange ovals). All elementary steps involve at least one of the t1, t2, or b3 site types, confirming that these CN=5 sites are the active sites for the reaction.

To further flesh out the reaction mechanism, we also probed the coverages of various adsorbates on Au₁₈ as a function of time (Figure 5a). Only HCOO, H, and HCOOH were observed, consistent with the HCOO pathway being the sole active pathway. Interestingly, the coverage of HCOO is almost exactly twice that of H, equivalent to a 1:1 ratio of these adsorbates as HCOO is bidentate and H is monodentate. This suggests that there is a highly stable state with 1 H and 1 HCOO coadsorbed on Au₁₈. To ascertain that this 1:1 ratio is not due to an average of different states, for example, states with 2 H and states with 2 HCOO, we sampled the cluster at regular intervals to calculate the probabilities of finding unique discrete configurational states (Figure 5b). The clean state has the largest probability (~0.6) of occurring; the state with the second largest probability (~0.3) is that of 1 H + 1 HCOO, which validates our hypothesis and is consistent with spectroscopic evidence of HCOO on Au/SiO₂⁶⁶.

From the configurational states present and the lack of higher coverage states, it is likely that the *clean* Au₁₈ cluster is the active state — Au₁₈ dissociates only one HCOOH at a time, without any spectator species. Our proposed reaction mechanism, summarized in Figure 6, is thus as follows: starting from a clean state, Au₁₈ dissociates a HCOOH molecule, leading to a state with 1 H + 1 HCOO. Given the absence of 2 H states, the rate determining step (RDS) is decomposition of HCOO from the 1 H + 1 HCOO state, after which H₂ recombination is fast. Degree of rate control analysis^{68,69} on reactions relevant to HCOO decomposition (HCOO flipping and HCOO_i decomposition) and H₂ recombination corroborates this: HCOO flipping reactions have higher degrees of rate control than H₂ recombination (Figure S10).

Figure 6 Proposed reaction mechanism for formic acid decomposition on Au_{18} . Descriptions of elementary events, the number of free active sites, and whether the processes are fast or slow, are inscribed in the concentric blue, pink, and purple rings respectively. TS marks structures that are transition states, and RDS marks the transition state associated with the step with the highest degree of rate control (Figure S10). Color code for structures: gold – Au, grey – C, red – O, blue – H. Pink triangles mark the Au atoms with coordination number of 5.

It is however possible that the longest-lived states, which are the ones captured in our state probability analysis, are resting states, whereas the active states at which catalytic turnovers occur are fleeting and thus not captured. To confirm our proposed reaction mechanism, we thus sampled the cluster at the occurrence of each of the elementary steps shown in Figure 4b. The results of these samplings (not shown) reveal that all steps occur without spectator species, confirming that clean Au_{18} is the active state.

types, and H prefers to bind on the b2 and b3 site types, showing that adsorbates concentrate on the CN=5 sites; they are not evenly distributed around the cluster.

Additionally, HCOO and H almost always occupy both CN=5 active sites *concurrently*; rarely are the CN=5 sites singly occupied. To show this, we plot coverage heat maps in Figure 7a-d that visually illustrate the sites occupied by each species. Consistent with our site occupation probabilities, H is largely found on the b2 site (Figure 7a, blue regions), and the dentates of HCOO are largely bound on the t2 sites (Figure 7c, blue regions). To determine how the adsorbates are positioned when both H and HCOO are present, we analyze the coverages of each species conditional upon adsorption of the other. When HCOO is present at one of the CN=5 sites (Figure 7b, green regions), H occupies the CN=5 site opposite to it, with equal probabilities of being at either of the two b2 sites. When H is present on one of the b2 sites (Figure 7d, green region), HCOO occupies the opposite CN=5 sites. Due to the strong intrinsic binding of both H and HCOO on the CN=5 sites, and to the large stabilizing interactions (0.31 eV) between H and HCOO on opposite CN=5 sites, the adsorbates are thus coupled—when one adsorbate occupies a CN=5 site, the other does so as well.

With the active CN=5 sites occupied, dissociating a second HCOOH molecule becomes kinetically prohibited. Figure 7e shows calculated MEPs for two diverging pathways starting from 1 H + 1 HCOO: *i*) the single HCOOH pathway, where HCOO dehydrogenates with a coadsorbed HCOOH, and *ii*) the second HCOOH pathway, where the coadsorbed HCOOH dissociates producing 2 H + 2 HCOO. Dissociation of a second HCOOH entails a 0.12 eV higher barrier than for dehydrogenation of HCOO from the first HCOOH, the RDS in our proposed reaction mechanism, indicating that HCOO decomposes and Au₁₈ reverts to a clean state 30 times faster than subsequent FA molecules can dissociate (at 413 K). Besides these kinetic limitations, there is also no

thermodynamic driving force for dissociating a second HCOOH molecule: the energy of the most stable $2 \text{ HCOO} + 2 \text{ H}$ state is 0.19 eV less stable than that of the most stable $1 \text{ HCOO} + 1 \text{ H}$ state with coadsorbed HCOOH.

4. Discussion

4.1. Comparison with Experimental and Theoretical Literature

Our results strongly suggest that Au_{18} is an active species for formic acid (FA) decomposition. We predict full selectivity to H_2 via the HCOO pathway, in agreement with experiments on Au catalysts on several different supports. Our calculated turnover frequencies (TOFs), apparent activation energies, and reaction orders also agree well with experiment—especially with Au/SiC catalysts. The predicted activity of the Au_{18} cluster is within ~ 2 orders of magnitude of that of Au/SiC, which is remarkable considering that the Au(111), Au(100), and Au(211) surfaces catalyze FA decomposition with TOFs that are ~ 11 , ~ 5 , and ~ 5 orders of magnitude lower respectively than the experimental TOF normalized to all atoms ($0.06 \text{ mol}_{\text{H}_2} \text{ s}^{-1} \text{ mol}_{\text{Au}}^{-1}$).²³ Our subnanometric Au_{18} cluster also fits in with hypotheses that the active Au species is small, difficult to detect by transmission electron microscopy, and possesses highly undercoordinated sites that lead to lower reaction barriers.

In agreement with the microkinetic modeling studies by Li et al³⁷, we demonstrated that the CN=5 sites on the Au_{18} cluster are the active sites for FA decomposition. Although the atoms at the corner of Au_{18} are more undercoordinated (CN=3) and thus might be thought to be more reactive, they are however isolated, whereas the CN=5 atoms are grouped into triangular ensembles. This is beneficial in the case of FA decomposition, where the active site needs to accommodate bidentate species such as HCOO and HCOOi. These species bind much more weakly (~ 0.5 eV and ~ 0.3 eV

respectively) on the CN=3 sites than on the CN=5 sites, as only one dentate can bind onto CN=3 atom. Interestingly, similar triangular ensembles have also been proposed to be active for CO oxidation on small Au⁷⁰ and Cu⁷¹ clusters, as well as for H₂ evolution from Au⁶² clusters and hydrogenation of alkynes on Pd⁷² and In₂O₃⁷³ catalysts. In none of these cases, however, have dual triangular ensembles been suggested for rationalizing experimental results, as done in this present case.

One limitation of our work is modeling Au₁₈ as an unsupported, gas-phase cluster, which neglects possibly significant support effects.^{74–76} This may be the cause of our need to adjust the binding energies of two HCOO species by 0.2 eV to gain better agreement with experimental quantities, although the magnitude of the adjustment is within the typical errors of DFT-based calculations (0.2 eV)⁷⁷. Building a coverage-consistent supported-cluster model is however computationally prohibitive. In the case of Au₁₈, we believe that adsorbate-adsorbate interactions have a greater impact on reactivity compared with support effects, and we have thus chosen to focus on rigorously describing these interactions.

As we do not model support effects, we expect our results to match more closely with results from Au/SiC²³ catalysts due to the chemical inertness of SiC and its weak interactions with the catalytic Au nanoparticles^{78,79}. The better agreement of the HCOOH reaction order from our simulations (0.72) with that from Au/SiC (0.95) versus those from Au/SiO₂ and Au/Al₂O₃ (both 0) may thus be because our model resembles Au/SiC catalysts more closely.

4.2. Comparison with Isotope Studies and Explaining HD Selectivity

A crucial test for the validity our proposed reaction pathway is its whether it explains why HD was produced exclusively from the decomposition of singly-deuterated FA isotopomers, HCOOD and

DCOOH, over Au/Al₂O₃²⁰ (also observed for aqueous-phase heterogeneous FA decomposition over Au/Zr₂O₃⁷). This is an intriguing phenomenon unique to Au — binomial distributions of H₂, HD, and D₂ were observed when Pt/Al₂O₃ was used for this chemistry.²⁰ There are two possible reaction mechanisms consistent with this finding: *i*) H₂ is formed by reaction of H from the O-H bond of a FA molecule, with the C-H bond of the same molecule, that is, H-assisted C-H bond breaking, or *ii*) H atoms from the O-H and C-H bonds of the same molecule recombine before subsequent turnovers of HCOOH.

Kinetic isotope effect (KIE) measurements suggest that mechanism *i* is the more likely mechanism. On Au/Al₂O₃, measured KIE values for HCOOD, DCOOH, and DCOOD were 1.6, 2.5, and 4.7 respectively.²⁰ Normal KIEs (i.e. above unity) for both the HCOOD and DCOOH isotopomers suggest that H₂ formation, and not HCOO decomposition, is kinetically relevant — HCOOD would not usually show a significant KIE if the latter was kinetically relevant. However, a simple H₂ recombination reaction would give similar rates for both HCOOD and DCOOH, which is also not the case. It thus appears that the KIE data can only be explained if the rate determining step is a combination of the H₂ recombination and HCOO decomposition steps, that is, H-assisted C-H bond breaking, mechanism *i*.

To test the viability of mechanism *i*, we performed calculations where a surface H adatom directly attacks HCOO, breaking the C-H bond and releasing H₂ (g) and CO₂ (g). The most stable transition state for this reaction has an energy of 0.87 eV with respect to H₂ (g) and CO₂ (g), much higher than that of the highest energy transition state (0.10 eV) in the unassisted pathway. Our calculations hence exclude H-assisted C-H bond breaking as a possible reaction pathway.

We thus suggest that mechanism *ii* is responsible for the HD selectivity. In our proposed reaction mechanism, each discrete Au₁₈ cluster catalyzes the decomposition of one HCOOH molecule at a

time, providing kinetic isolation between HCOOH turnovers. The dual CN=5 active site ensembles found on Au₁₈, which are vital for this mechanism and thus the exclusive production of HD, are not found on other Au_n (n=4-25) clusters.³⁷ This provides additional support to our claim that Au₁₈ is the dominant contributor to the experimentally observed activity of Au catalysts, even though in reality these catalysts would be made up of a collection of Au clusters and particles of different sizes.

Although a normal KIE value for decomposition of HCOOD normally precludes unimolecular HCOO decomposition from being kinetically relevant, the strong coupling between active sites on Au₁₈ may lead to convolution of the KIE for HCOO flipping with the thermodynamic isotope effects (TIEs) of the preceding elementary steps^{80,81}, as was found in other catalytic systems.^{82,83} We calculated the KIE values expected from our model in Section S5 of the SI, finding normal KIE values greater than 1 for all isotopomers, including HCOOD even though HCOO flipping is rate-determining. This is mainly because of the convolution of the TIE for the O-H bond scission step, which is significant for isotopomers with an O-D moiety, with the KIE for the C-H bond scission step, which is significant for isotopomers with a C-D moiety. Our proposed reaction mechanism thus also offers a possible explanation for the experimentally-observed KIEs.

5. Conclusions

In summary, our work combined DFT-based calculations, the cluster expansion method, and KMC simulations to offer a rigorous and novel description of the reaction mechanisms for FA decomposition on Au₁₈ while highlighting the central role of adsorbate-adsorbate interactions in cluster-catalyzed reactions.

We demonstrate that Au₁₈ is highly active and selective for FA decomposition; triangular ensembles of atoms with coordination numbers of 5 (CN=5 sites) are the likely active sites. Even

though there are two active CN=5 sites on Au₁₈, only one HCOOH molecule can be dehydrogenated at a time. This is because once a HCOOH molecule dissociates, both active sites are simultaneously occupied by a pair of H and HCOO adsorbates due to strong, stabilizing, interactions acting across the cluster. Dissociation of additional HCOOH molecules is thus kinetically prohibited due to transient poisoning of the active sites while HCOO is waiting to be dissociated. As a direct consequence, dissociation of HCOOD or DCOOH over Au₁₈ produces HD exclusively, thus explaining a unique, experimentally-observed phenomenon.

Au₁₈, although having many possible adsorption sites, is in essence a dual-site, quasi-molecular catalyst which affords extraordinary catalytic selectivity by kinetic isolating turnovers of FA from each other. To our knowledge, this is the first example of heterogeneous catalysis by clusters one molecule at a time. Insights derived here may guide the design of cluster catalysts with improved activity and selectivity for FA decomposition and other reactions. For example, coupling between the active sites may be harnessed as a potential mechanism, unique to clusters, for achieving high catalytic selectivity. Further studies in this exciting research area may bring the fields of heterogeneous, homogeneous, and enzymatic catalysis closer to each other.

References

- (1) Schlapbach, L.; Züttel, A. Hydrogen-Storage Materials for Mobile Applications. *Nature* **2001**, *414*, 353–358.
- (2) Graetz, J. New Approaches to Hydrogen Storage. *Chem. Soc. Rev.* **2009**, *38*, 73–82.
- (3) Schlapbach, L. Hydrogen-Fuelled Vehicles. *Nature* **2009**, *460*, 809–811.
- (4) Grasemann, M.; Laurenczy, G. Formic Acid as a Hydrogen Source – Recent Developments and Future Trends. *Energy Environ. Sci.* **2012**, *5*, 8171.
- (5) Álvarez, A.; Bansode, A.; Urakawa, A.; Bavykina, A. V; Wezendonk, T. A.; Makkee, M.; Gascon, J.; Kapteijn, F. Challenges in the Greener Production of Formates/Formic Acid, Methanol, and DME by Heterogeneously Catalyzed CO₂ Hydrogenation Processes. *Chem. Rev.* **2017**, *117*, 9804–9838.
- (6) Tedsree, K.; Li, T.; Jones, S.; Chan, C. W. A.; Yu, K. M. K.; Bagot, P. A. J.; Marquis, E. A.; Smith, G. D. W.; Tsang, S. C. E. Hydrogen Production from Formic Acid Decomposition at Room Temperature Using a Ag–Pd Core–Shell Nanocatalyst. *Nat.*

- Nanotechnol.* **2011**, *6*, 302–307.
- (7) Bi, Q.-Y.; Du, X.-L.; Liu, Y.-M.; Cao, Y.; He, H.-Y.; Fan, K.-N. Efficient Subnanometric Gold-Catalyzed Hydrogen Generation via Formic Acid Decomposition under Ambient Conditions. *J. Am. Chem. Soc.* **2012**, *134*, 8926–8933.
 - (8) Reichert, J.; Brunner, B.; Jess, A.; Wasserscheid, P.; Albert, J. Biomass Oxidation to Formic Acid in Aqueous Media Using Polyoxometalate Catalysts – Boosting FA Selectivity by in-Situ Extraction. *Energy Environ. Sci.* **2015**, *8*, 2985–2990.
 - (9) Yu, W.-Y.; Mullen, G. M.; Flaherty, D. W.; Mullins, C. B. Selective Hydrogen Production from Formic Acid Decomposition on Pd–Au Bimetallic Surfaces. *J. Am. Chem. Soc.* **2014**, *136*, 11070–11078.
 - (10) Gao, W.; Keith, J. A.; Anton, J.; Jacob, T. Theoretical Elucidation of the Competitive Electro-Oxidation Mechanisms of Formic Acid on Pt(111). *J. Am. Chem. Soc.* **2010**, *132*, 18377–18385.
 - (11) Gu, X.; Lu, Z.-H.; Jiang, H.-L.; Akita, T.; Xu, Q. Synergistic Catalysis of Metal–Organic Framework-Immobilized Au–Pd Nanoparticles in Dehydrogenation of Formic Acid for Chemical Hydrogen Storage. *J. Am. Chem. Soc.* **2011**, *133*, 11822–11825.
 - (12) Jeong, K.; Miesse, C. M.; Choi, J.; Lee, J.; Han, J.; Yoon, S. P.; Nam, S. W.; Lim, T.; Lee, T. G.; Pil, S.; et al. Fuel Crossover in Direct Formic Acid Fuel Cells. *J. Power Sources* **2007**, *168*, 119–125.
 - (13) Steele, B. C. H.; Heinzl, A. Materials for Fuel-Cell Technologies. *Nature* **2001**, *414*, 345–352.
 - (14) Rahimi, A.; Ulbrich, A.; Coon, J. J.; Stahl, S. S. Formic-Acid-Induced Depolymerization of Oxidized Lignin to Aromatics. *Nature* **2014**, *515*, 249–252.
 - (15) Wang, L.; Zhang, B.; Meng, X.; Su, D. S.; Xiao, F.-S. Hydrogenation of Biofuels with Formic Acid over a Palladium-Based Ternary Catalyst with Two Types of Active Sites. *ChemSusChem* **2014**, *7*, 1537–1541.
 - (16) Gilkey, M. J.; Xu, B. Heterogeneous Catalytic Transfer Hydrogenation as an Effective Pathway in Biomass Upgrading. *ACS Catal.* **2016**, *6*, 1420–1436.
 - (17) Singh, A. K.; Jang, S.; Kim, J. Y.; Sharma, S.; Basavaraju, K. .; Kim, M.-G.; Kim, K.-R.; Lee, J. S.; Lee, H. H.; Kim, D.-P. One-Pot Defunctionalization of Lignin-Derived Compounds by Dual-Functional Pd₅₀Ag₅₀/Fe₃O₄/N-RGO Catalyst. *ACS Catal.* **2015**, *5*, 6964–6972.
 - (18) Huang, K.; Eppinger, J.; Huang, K. Formic Acid as a Hydrogen Energy Carrier. *ACS Energy Lett.* **2017**, *2*, 188–195.
 - (19) Jiang, K.; Xu, K.; Zou, S.; Cai, W. Bin. B-Doped Pd Catalyst: Boosting Room-Temperature Hydrogen Production from Formic Acid-Formate Solutions. *J. Am. Chem. Soc.* **2014**, *136*, 4861–4864.
 - (20) Ojeda, M.; Iglesia, E. Formic Acid Dehydrogenation on Au-Based Catalysts at near-Ambient Temperatures. *Angew. Chemie Int. Ed.* **2009**, *48*, 4800–4803.
 - (21) Barteau, M. A. Linear Free Energy Relationships for C1-Oxygenate Decomposition on Transition Metal Surfaces. *Catal. Letters* **1991**, *8*, 175–183.
 - (22) Ciftci, A.; Ligthart, D. A. J. M.; Pastorino, P.; Hensen, E. J. M. Nanostructured Ceria Supported Pt and Au Catalysts for the Reactions of Ethanol and Formic Acid. *Appl. Catal. B Environ.* **2013**, *130–131*, 325–335.
 - (23) Singh, S.; Li, S.; Carrasquillo-Flores, R.; Alba-Rubio, A. C.; Dumesic, J. A.; Mavrikakis, M. Formic Acid Decomposition on Au Catalysts: DFT, Microkinetic Modeling, and

- Reaction Kinetics Experiments. *AIChE J.* **2014**, *60*, 1303–1319.
- (24) Zacharska, M.; Chuvilin, A. L.; Kriventsov, V. V.; Beloshapkin, S.; Estrada, M.; Simakov, A.; Bulushev, D. A. Support Effect for Nanosized Au Catalysts in Hydrogen Production from Formic Acid Decomposition. *Catal. Sci. Technol.* **2016**, *6*, 6853–6860.
 - (25) Bi, Q. Y.; Lin, J. D.; Liu, Y. M.; He, H. Y.; Huang, F. Q.; Cao, Y. Gold Supported on Zirconia Polymorphs for Hydrogen Generation from Formic Acid in Base-Free Aqueous Medium. *J. Power Sources* **2016**, *328*, 463–471.
 - (26) Bulushev, D. A.; Beloshapkin, S.; Ross, J. R. H. Hydrogen from Formic Acid Decomposition over Pd and Au Catalysts. *Catal. Today* **2010**, *154*, 7–12.
 - (27) Yi, N.; Saltsburg, H.; Flytzani-Stephanopoulos, M. Hydrogen Production by Dehydrogenation of Formic Acid on Atomically Dispersed Gold on Ceria. *ChemSusChem* **2013**, *6*, 816–819.
 - (28) Häkkinen, H.; Landman, U. Gas-Phase Catalytic Oxidation of CO by Au₂⁺. *J. Am. Chem. Soc.* **2001**, *123*, 9704–9705.
 - (29) Oliver-Meseguer, J.; Cabrero-Antonino, J. R.; Dominguez, I.; Leyva-Perez, A.; Corma, A. Small Gold Clusters Formed in Solution Give Reaction Turnover Numbers of 10⁷ at Room Temperature. *Science* **2012**, *338*, 1452–1455.
 - (30) Haruta, M. Catalysis: Gold Rush. *Nature* **2005**, *437*, 1098–1099.
 - (31) Haruta, M. When Gold Is Not Noble: Catalysis by Nanoparticles. *Chem. Rec.* **2003**, *3*, 75–87.
 - (32) Crampton, A. S.; Rötzer, M. D.; Ridge, C. J.; Schweinberger, F. F.; Heiz, U.; Yoon, B.; Landman, U. Structure Sensitivity in the Non-scalable Regime Explored via Catalysed Ethylene Hydrogenation on Supported Platinum Nanoclusters. *Nat. Commun.* **2016**, *7*, 10389.
 - (33) Proch, S.; Wirth, M.; White, H. S.; Anderson, S. L. Strong Effects of Cluster Size and Air Exposure on Oxygen Reduction and Carbon Oxidation Electrocatalysis by Size-Selected Pt_n (n ≤ 11) on Glassy Carbon Electrodes. *J. Am. Chem. Soc.* **2013**, *135*, 3073–3086.
 - (34) Trevor, D. J.; Whetten, R. L.; Cox, D. M.; Kaldor, A. Gas-Phase Platinum Cluster Reactions with Benzene and Several Hexanes: Evidence of Extensive Dehydrogenation and Size-Dependent Chemisorption. *J. Am. Chem. Soc.* **1985**, *107*, 518–519.
 - (35) Kaden, W. E.; Wu, T.; Kunkel, W. A.; Anderson, S. L. Electronic Structure Controls Reactivity of Size-Selected Pd Clusters Adsorbed on TiO₂ Surfaces. *Science* **2009**, *326*, 826–830.
 - (36) Heiz, U.; Sanchez, A.; Abbet, S.; Schneider, W. D. Catalytic Oxidation of Carbon Monoxide on Monodispersed Platinum Clusters: Each Atom Counts. *J. Am. Chem. Soc.* **1999**, *121*, 3214–3217.
 - (37) Li, S.; Singh, S.; Dumesic, J. A.; Mavrikakis, M. On the Nature of Active Sites for Formic Acid Decomposition on Gold Catalysts. *Catal. Sci. Technol.* **2019**, *9*, 2836–2848.
 - (38) Häkkinen, H. Electronic Shell Structures in Bare and Protected Metal Nanoclusters. *Adv. Phys. X* **2016**, *1*, 467–491.
 - (39) Stamatakis, M.; Piccinin, S. Rationalizing the Relation between Adlayer Structure and Observed Kinetics in Catalysis. *ACS Catal.* **2016**, *6*, 2105–2111.
 - (40) Prats, H.; Illas, F.; Sayós, R. General Concepts, Assumptions, Drawbacks, and Misuses in Kinetic Monte Carlo and Microkinetic Modeling Simulations Applied to Computational Heterogeneous Catalysis. *Int. J. Quantum Chem.* **2018**, *118*, e25518.
 - (41) Stamatakis, M.; Vlachos, D. G. A Graph-Theoretical Kinetic Monte Carlo Framework for

- on-Lattice Chemical Kinetics. *J. Chem. Phys.* **2011**, *134*, 214115.
- (42) Nielsen, J.; D’Avezac, M.; Hetherington, J.; Stamatakis, M. Parallel Kinetic Monte Carlo Simulation Framework Incorporating Accurate Models of Adsorbate Lateral Interactions. *J. Chem. Phys.* **2013**, *139*, 224706.
 - (43) Miller, S. D.; Kitchin, J. R. Uncertainty and Figure Selection for DFT Based Cluster Expansions for Oxygen Adsorption on Au and Pt (111) Surfaces. *Mol. Simul.* **2009**, *35*, 920–927.
 - (44) Han, B. C.; Van der Ven, A.; Ceder, G.; Hwang, B.-J. Surface Segregation and Ordering of Alloy Surfaces in the Presence of Adsorbates. *Phys. Rev. B* **2005**, *72*, 205409.
 - (45) Bligaard, T.; Nørskov, J. K.; Dahl, S.; Matthiesen, J.; Christensen, C. H.; Sehested, J. The Brønsted-Evans-Polanyi Relation and the Volcano Curve in Heterogeneous Catalysis. *J. Catal.* **2004**, *224*, 206–217.
 - (46) Peng, G.; Mavrikakis, M. Adsorbate Diffusion on Transition Metal Nanoparticles. *Nano Lett.* **2015**, *15*, 629–634.
 - (47) Nilekar, A. U.; Greeley, J.; Mavrikakis, M. A Simple Rule of Thumb for Diffusion on Transition-Metal Surfaces. *Angew. Chemie - Int. Ed.* **2006**, *45*, 7046–7049.
 - (48) Kresse, G.; Furthmüller, J. Efficiency of Ab-Initio Total Energy Calculations for Metals and Semiconductors Using a Plane-Wave Basis Set. *Comput. Mater. Sci.* **1996**, *6*, 15–50.
 - (49) Kresse, G.; Furthmüller, J. Efficient Iterative Schemes for Ab Initio Total-Energy Calculations Using a Plane-Wave Basis Set. *Phys. Rev. B* **1996**, *54*, 11169–11186.
 - (50) Blöchl, P. E. Projector Augmented-Wave Method. *Phys. Rev. B* **1994**, *50*, 17953–17979.
 - (51) Kresse, G.; Joubert, D. From ultrasoft pseudopotentials to the projector augmented-wave method. *Phys. Rev. B* **1999**, *59*, 1758–1775.
 - (52) Perdew, J. P.; Wang, Y. Accurate and simple analytic representation of the electron-gas correlation-energy. *Phys. Rev. B* **1992**, *45*, 13244–13249.
 - (53) Klimeš, J.; Bowler, D. R.; Michaelides, A. Chemical Accuracy for the van Der Waals Density Functional. *J. Phys. Condens. Matter* **2010**, *22*, 022201.
 - (54) Huang, W.; Bulusu, S.; Pal, R.; Zeng, X. C.; Wang, L. S. Structural Transition of Gold Nanoclusters: From the Golden Cage to the Golden Pyramid. *ACS Nano* **2009**, *3*, 1225–1230.
 - (55) Huang, W.; Bulusu, S.; Pal, R.; Zeng, X. C.; Wang, L.-S. CO Chemisorption on the Surfaces of the Golden Cages. *J. Chem. Phys.* **2009**, *131*, 234305.
 - (56) Xing, X.; Yoon, B.; Landman, U.; Parks, J. H. Structural Evolution of Au Nanoclusters: From Planar to Cage to Tubular Motifs. *Phys. Rev. B* **2006**, *74*, 165423.
 - (57) Jimenez-Izal, E.; Alexandrova, A. N. Computational Design of Clusters for Catalysis. *Annu. Rev. Phys. Chem.* **2018**, *69*, 377–400.
 - (58) Si, R.; Tao, J.; Evans, J.; Park, J. B.; Barrio, L.; Hanson, J. C.; Zhu, Y.; Hrbek, J.; Rodriguez, J. A. Effect of Ceria on Gold–Titania Catalysts for the Water–Gas Shift Reaction: Fundamental Studies for Au/CeO_x/TiO₂ (110) and Au/CeO_x/TiO₂ Powders. *J. Phys. Chem. C* **2012**, *116*, 23547–23555.
 - (59) Rodriguez, J. A.; Ma, S.; Liu, P.; Hrbek, J.; Evans, J.; Perez, M. Activity of CeO_x and TiO_x Nanoparticles Grown on Au(111) in the Water-Gas Shift Reaction. *Science* **2007**, *318*, 1757–1760.
 - (60) Li, Z.; Li, Y.; Li, J. Support Effects on the Dissociation of Hydrogen over Gold Clusters on ZnO(101) Surface: Theoretical Insights. *J. Chem. Phys.* **2012**, *137*, 234704.
 - (61) Hu, G.; Wu, Z.; Jiang, D. E. Stronger-than-Pt Hydrogen Adsorption in a Au₂₂ Nanocluster

- for the Hydrogen Evolution Reaction. *J. Mater. Chem. A* **2018**, *6*, 7532–7537.
- (62) Choi, W.; Hu, G.; Kwak, K.; Kim, M.; Jiang, D. E.; Choi, J. P.; Lee, D. Effects of Metal-Doping on Hydrogen Evolution Reaction Catalyzed by MAu₂₄ and M₂Au₃₆ Nanoclusters (M = Pt, Pd). *ACS Appl. Mater. Interfaces* **2018**, *10*, 44645–44653.
 - (63) Taylor, K. J.; Pettiette-Hall, C. L.; Cheshnovsky, O.; Smalley, R. E. Ultraviolet Photoelectron Spectra of Coinage Metal Clusters. *J. Chem. Phys.* **1992**, *96*, 3319–3329.
 - (64) Knight, W. D.; Clemenger, K.; de Heer, W. A.; Sauder, W. A.; Chou, M. Y.; Cohen, M. L. Electronic Shell Structure and Abundance of Sodium Clusters. *Phys. Rev. Lett.* **1984**, *52*, 2141–2143.
 - (65) Qian, J.; Hastie, T.; Friedman, J.; Tibshirani, R. and Simon, N. Glmnet for Matlab (2013) http://www.stanford.edu/~hastie/glmnet_matlab/ (accessed May 26, 2019).
 - (66) Gazsi, A.; Bánsági, T.; Solymosi, F. Decomposition and Reforming of Formic Acid on Supported Au Catalysts: Production of CO-Free H₂. *J. Phys. Chem. C* **2011**, *115*, 15459–15466.
 - (67) Scaranto, J.; Mavrikakis, M. Density Functional Theory Studies of HCOOH Decomposition on Pd(111). *Surf. Sci.* **2016**, *650*, 111–120.
 - (68) Campbell, C. T. The Degree of Rate Control: A Powerful Tool for Catalysis Research. *ACS Catal.* **2017**, *7*, 2770–2779.
 - (69) Stegelmann, C.; Andreasen, A.; Campbell, C. T. Degree of Rate Control: How Much the Energies of Intermediates and Transition States Control Rates. *J. Am. Chem. Soc.* **2009**, *131*, 8077–8082.
 - (70) Liu, C.; Tan, Y.; Lin, S.; Li, H.; Wu, X.; Li, L.; Pei, Y.; Zeng, X. C. CO Self-Promoting Oxidation on Nanosized Gold Clusters: Triangular Au₃ Active Site and CO Induced O-O Scission. *J. Am. Chem. Soc.* **2013**, *135*, 2583–2595.
 - (71) Chen, Z. W.; Yan, J. M.; Zheng, W. T.; Jiang, Q. Cu₄ Cluster Doped Monolayer MoS₂ for CO Oxidation. *Sci. Rep.* **2015**, *5*, 11230.
 - (72) Albani, D.; Shahrokhi, M.; Chen, Z.; Mitchell, S.; Hauert, R.; López, N.; Pérez-Ramírez, J. Selective Ensembles in Supported Palladium Sulfide Nanoparticles for Alkyne Semi-Hydrogenation. *Nat. Commun.* **2018**, *9*, 1–11.
 - (73) Albani, D.; Capdevila-Cortada, M.; Vilé, G.; Mitchell, S.; Martin, O.; López, N.; Pérez-Ramírez, J. Semihydrogenation of Acetylene on Indium Oxide: Proposed Single-Ensemble Catalysis. *Angew. Chemie Int. Ed.* **2017**, *56*, 10755–10760.
 - (74) Nevalaita, J.; Häkkinen, H.; Honkala, K. Gold Assisted Oxygen Dissociation on a Molybdenum-Doped CaO(001) Surface. *Catal. Sci. Technol.* **2016**, *6*, 6784–6793.
 - (75) Li, L.; Gao, Y.; Li, H.; Zhao, Y.; Pei, Y.; Chen, Z.; Zeng, X. C. CO Oxidation on TiO₂ (110) Supported Subnanometer Gold Clusters: Size and Shape Effects. *J. Am. Chem. Soc.* **2013**, *135*, 19336–19346.
 - (76) Yoon, B.; Häkkinen, H.; Landman, U.; Wörz, A. S.; Antonietti, J.-M.; Abbet, S.; Judai, K.; Heiz, U. Charging Effects on Bonding and Catalyzed Oxidation of CO on Au₈ Clusters on MgO. *Science* **2005**, *307*, 403–407.
 - (77) Norskov, J. K.; Abild-Pedersen, F.; Studt, F.; Bligaard, T. Density Functional Theory in Surface Chemistry and Catalysis. *Proc. Natl. Acad. Sci.* **2011**, *108*, 937–943.
 - (78) Jin, G.; Gu, F.; Liu, Q.; Wang, X.; Jia, L.; Xu, G.; Zhong, Z.; Su, F. Highly Stable Ni/SiC Catalyst Modified by Al₂O₃ for CO Methanation Reaction. *RSC Adv.* **2016**, *6*, 9631–9639.
 - (79) Ledoux, M. J.; Pham-Huu, C. Silicon Carbide a Novel Catalyst Support for Heterogeneous Catalysis. *Cattech* **2001**, *5*, 226–246.

- (80) Hu, Y. H.; Feeley, J. S. Thermodynamic Isotope Effect in Partial Oxidation of Methane to Syngas. *Aiche J.* **2003**, *49*, 3253–3259.
- (81) Bai, Y.; Chen, B. W. J.; Peng, G.; Mavrikakis, M. Density Functional Theory Study of Thermodynamic and Kinetic Isotope Effects of H₂/D₂ Dissociative Adsorption on Transition Metals. *Catal. Sci. Technol.* **2018**, *8*, 3321–3335.
- (82) Wang, J.-H.; Chiang, C.-M. Observation of β -C–H Bond Activation of Allyl Groups Adsorbed on Ag(111) and an Unusual Deuterium Isotope Effect. *J. Am. Chem. Soc.* **2000**, *122*, 11521–11522.
- (83) Ojeda, M.; Li, A. W.; Nabar, R.; Nilekar, A. U.; Mavrikakis, M.; Iglesia, E. Kinetically Relevant Steps and H₂/D₂ Isotope Effects in Fischer-Tropsch Synthesis on Fe and Co Catalysts. *J. Phys. Chem. C* **2010**, *114*, 19761–19770.

Acknowledgements

B.W.J.C and M.M.'s modeling for this work was supported by the Department of Energy-Basic Energy Sciences, Division of Chemical Sciences (Grant DE-FG02-05ER15731). M.S.'s algorithm and *Zacros* software development work has been partially supported by the embedded Computer Science and Engineering (eCSE) program of the ARCHER UK National Supercomputing Service (grants eCSE01-001, eCSE10-8) and the Leverhulme Trust (grant RPG-2017-361). B.W.J.C thanks the Agency for Science, Technology and Research (A*STAR) Singapore for support via a graduate fellowship, and the Thomas Young Centre for support via the Junior Research Fellowship Scheme. Part of the computational work conducted by B.W.J.C, and M.M. in this study was carried out through external computational resource facilities at: the National Energy Research Scientific Computing Center (NERSC) through the U.S. DOE, Office of Science under Contract No. DE-AC02-05CH11231; and the Center for Nanoscale Materials (CNM) at Argonne National Laboratory (ANL) through the U.S. DOE, Office of Science under Contract No. DE-AC02-06CH11357. The authors thank Dr. Sha Li for providing an initial set of DFT data for reference, as well as Dr. Florian Göeltl and Dr. Thomas Kropp for insightful comments on the manuscript.

Competing Interests

The authors declare no competing interests.

For Table of Contents Only

Supporting Information

Kinetic Isolation between Turnovers on Au₁₈ Nanoclusters: Formic Acid Decomposition One Molecule at a Time

Benjamin W. J. Chen¹, Michail Stamatakis², Manos Mavrikakis*¹

¹*Department of Chemical and Biological Engineering, University of Wisconsin – Madison,
Madison, WI 53706*

²*Department of Chemical Engineering, University College London, Roberts Building, Torrington
Place, London WC1E 7JE, United Kingdom*

*corresponding author emavrikakis@wisc.edu

Table of Contents

List of Figures	2
List of Tables	3
S1. Model Parameter Adjustments	4
S2. Energetics Model	10
S3. Reactions Model	13
S4. TOF Calculations for Au/SiC	15
S5. Theoretical Calculation of Kinetic Isotope Effects	16
S5. Supplementary Figures	21
S6. Supplementary Tables	28

List of Figures

Figure S1 Effect of adjustments to the density functional theory (DFT)-calculated binding energies of HCOO adsorbed on the t1-t2 and t2-t2 sites	8
Figure S2 Histograms of the fraction of configurations versus the differences of model-predicted versus DFT-calculated energies before (pink) and after (cyan) introducing interaction energies from the cluster expansion model	11
Figure S3 Histogram of particle sizes for Au/SiC, as synthesized in reference 1.	15
Figure S4 Effect of errors in vibrational frequencies on calculated kinetic isotope effects (KIEs).	19
Figure S5 Convergence of the H ₂ turnover frequencies (TOF) of kinetic Monte Carlo simulations for formic acid decomposition on Au ₁₈ with respect to the min_separation and max_separation stiffness scaling parameters in Zacros ^{14,15}	21
Figure S6 Structures of the most stable (a) minima and (b) transition states in side (above) and top (below) views.....	22
Figure S7 Turnover frequencies (TOFs) versus time for formic acid decomposition over Au ₁₈ , evaluated as a moving average of the number of species produced/consumed per 0.5 seconds, of various gas species.....	23
Figure S8 Arrhenius plot for formic acid decomposition over Au ₁₈ from kinetic Monte Carlo simulations.	24
Figure S9 Reaction order plots for formic acid decomposition over Au ₁₈	25
Figure S10 Campbell's degree of kinetic rate control from kinetic Monte Carlo simulations for reactions relevant for HCOO decomposition and H ₂ recombination.....	26
Figure S11 Illustration of the site numbers which specify the positions on the adsorbates on the clusters.	27

List of Tables

Table S1 Experimental versus KMC simulation turnover frequencies (TOFs), apparent activation energies (E_{app}), and reaction orders (η).....	4
Table S2 Calculated thermodynamic and kinetic isotope effects (TIEs and KIEs) for elementary steps, as well as the overall KIE, for decomposition of formic acid isotopomers over Au ₁₈ . All isotope effects were evaluated at 353 K for comparison with the experimental KIEs.	18
Table S3 Calculated vibrational frequencies for crucial species and states in the decomposition of formic acid isotopomers on Au ₁₈	28
Table S4 Sites in the lattice employed in kinetic Monte Carlo simulations of formic acid decomposition over Au ₁₈	29
Table S5 Formation energies calculated with the optB88-vdw functional with respect to CO(g), CO ₂ (g), and H ₂ (g) for various adsorbates, adsorbed at their most stable sites, with optB88-vdW geometries (fully optimized with optB88-vdw) and PW91 geometries (single point with optB88-vdw).	31
Table S6 Formation energies, including parameter adjustment of + 0.2 eV for HCOO t1-t2 and HCOO t2-t2, of adsorbate species employed in kinetic Monte Carlo simulations of formic acid decomposition on Au ₁₈	32
Table S7 Reaction energies (ΔE_{rxn}), activation energies (E_a), forward preexponential factors (A_{fwd}), backward preexponential factors (A_{bwd}), and Brønsted–Evans–Polanyi (BEP) proximity factors, for reactions used in kinetic Monte Carlo simulations of formic acid decomposition on Au ₁₈	35
Table S8 List of clusters and their effective cluster interactions (ECI) (eV), for clusters with absolute ECIs above 0.01 eV.	42
Table S9 List of clusters penalized with a 20 eV interaction energy to prevent adsorbates from coming unphysically close to each other.	58

S1. Model Parameter Adjustments

Kinetic data from our *ab initio* kinetic Monte Carlo (KMC) model for the decomposition of formic acid (FA, HCOOH) on Au₁₈ before and after parameter adjustment are shown in Table S1. In the absence of any adjustments, our model gave good agreement with most experimental observations, such as the H₂ turnover frequency (TOF) and H₂ selectivity, and also with the reaction orders of H₂ and CO₂ with the measurements obtained on Au/SiC¹.

Table S1 Experimental versus KMC simulation turnover frequencies (TOFs), apparent activation energies (E_{app}), and reaction orders (η). An average of 12 KMC simulations was used. Reported experimental TOFs for Au/SiO₂² and Au/Al₂O₃³ were extrapolated to 413 K to facilitate comparison. Simulations were carried out under nominal conditions of 413 K, a total pressure of 1 bar, and a FA partial pressure of 0.025 bar, balance inert. Dashes indicate that data is unavailable. For details of parameter adjustment, see text below this Table.

	Experiments ^a			Simulations	
	Au/SiC	Au/SiO ₂	Au/Al ₂ O ₃	Before Adjustment	After Adjustment
H₂ TOF / mol s⁻¹ mol_{Au}⁻¹	0.06 ^b /10 ^c	0.22 ^d	0.77 ^e	0.2	0.08
E_{app} / eV	0.62 ± 0.02	0.61	0.55 ± 0.02	1.00	0.56
Reaction Orders					
$\eta(\text{FA})$	0.95 ± 0.06	0	0	0.07	0.72
$\eta(\text{CO}_2)$	0.01 ± 0.00	-	-	0.00	0.00
$\eta(\text{H}_2)$	0.01 ± 0.00	-	-	0.00	0.00
H₂ Selectivity / %	100	98	100	100	100

^a From references 1, 2, and 3 for Au/SiC, Au/SiO₂, and Au/Al₂O₃ respectively

^b With respect to the number of atoms in all clusters (see section S4)

^c With respect to the number of atoms in subnanometric clusters only (see section S4)

^d With respect to the number of surface atoms, extrapolated from T=473 K, TOF=1.951 mol s⁻¹ mol_{Au}⁻¹

^e With respect to the number of surface atoms, extrapolated from T=353 K, TOF=0.0558 mol s⁻¹ mol_{Au}⁻¹

There are, however, significant differences for two quantities: i) Our unadjusted model predicted a value of ~0.07 for the HCOOH reaction order. Experimental values for HCOOH reaction order vary greatly based on the support used, from 0.95 for Au/SiC¹, to 0 for Au/SiO₂² and Au/Al₂O₃³. We suggest that our model, which neglects support effects, should have properties similar to Au/SiC as SiC is a relatively inert support. ii) Our unadjusted apparent activation energy of

approximately 1 eV was also higher than all experimental apparent activation energies, which were around 0.6 eV.

The typical errors in density functional theory (DFT) calculations may be as large as 0.2 eV,⁴ and thus may be a possible cause of the inconsistencies between theory and experiment. Support effects, which were not considered here, may also lead to differences in simulated and experimental results. Often times, small adjustments in the DFT-derived energies can result in large improvements in the agreement with macroscopic reaction observables.⁵ To selectively determine which parameters were in need of adjustment, we performed a kinetic analysis with a general, simplified reaction mechanism as shown below:

where * denotes an empty site.

Motivated by the results of our DFT calculations, we assumed R3 as the rate determining step (RDS), and all other steps to be quasi-equilibrated. The rate, r , is thus:

$$r = k_3 \theta_{\text{HCOO}}, \quad (1)$$

where k_i , $i=1-5$ is the rate constant for reaction R_i , and θ_x , $x=\text{H}, \text{HCOO}, \text{HCOOi}, \text{H}$, and $*$, is the coverage of species x , defined as the number of species per surface atom. These coverages can be expressed as:

$$\theta_{\text{HCOOH}} = K_1 P_{\text{HCOOH}} \theta_*, \quad (2)$$

$$\theta_{\text{H}} = K_5^{-0.5} P_{\text{H}_2}^{0.5} \theta_*, \quad (3)$$

$$\theta_{\text{HCOO}} = \frac{K_2 \theta_{\text{HCOOH}} \theta_*}{\theta_{\text{H}}}, \quad (4)$$

$$\theta_* = \frac{1}{1 + K_1 P_{\text{HCOOH}} + K_1 K_2 K_5^{0.5} P_{\text{HCOOH}} P_{\text{H}_2}^{-0.5} + K_5^{-0.5} P_{\text{H}_2}^{0.5}}, \quad (5)$$

where K_i are the equilibrium constants for reaction R_i , and P_{HCOOH} and P_{H_2} are the partial pressures of HCOOH and H_2 respectively.

The reaction order with respect to formic acid, $\eta(\text{FA})$, is:

$$\begin{aligned} \eta(\text{FA}) &= \frac{d \ln(r)}{d \ln(P_{\text{HCOOH}})} \\ &= P_{\text{HCOOH}} \frac{d \ln(r)}{d P_{\text{HCOOH}}} \\ &= P_{\text{HCOOH}} \frac{d}{d P_{\text{HCOOH}}} \ln \left[\frac{k_3 K_2 \theta_{\text{HCOOH}} \theta_*}{\theta_{\text{H}}} \right] \\ &= P_{\text{HCOOH}} \frac{d}{d P_{\text{HCOOH}}} \ln [k_3 K_1 K_2 K_5^{0.5} P_{\text{HCOOH}} P_{\text{H}_2}^{-0.5} \theta_*] \\ &= P_{\text{HCOOH}} \frac{d}{d P_{\text{HCOOH}}} \ln [P_{\text{HCOOH}} \theta_*] \\ &= P_{\text{HCOOH}} \left[\frac{1}{P_{\text{HCOOH}} \theta_*} \right] \left[\theta_* + P_{\text{HCOOH}} \frac{d \theta_*}{d P_{\text{HCOOH}}} \right] \\ &= 1 - P_{\text{HCOOH}} (K_1 + K_1 K_2 K_5^{0.5} P_{\text{H}_2}^{-0.5}) \theta_* \\ &= 1 - \theta_{\text{HCOOH}} - \theta_{\text{HCOO}}, \end{aligned} \quad (6)$$

and the apparent activation energy, E_{app} , for H_2 formation is:

$$\begin{aligned}
E_{\text{app}} &= RT^2 \frac{d \ln(r)}{dT} \\
&= RT^2 \frac{d}{dT} \ln[k_3 K_1 K_2 K_5^{0.5} P_{\text{HCOOH}} P_{\text{H}_2}^{-0.5} \theta_*] \\
&= RT^2 \frac{d}{dT} \ln[k_3 K_1 K_2 K_5^{0.5} \theta_*] \\
&= RT^2 \left[\frac{E_3}{RT^2} + \frac{\Delta H_1}{RT^2} + \frac{\Delta H_2}{RT^2} + \frac{0.5 \Delta H_5}{RT^2} + \frac{d \ln(\theta_*)}{dT} \right] \\
&= E_3 + \Delta H_1 + \Delta H_2 + 0.5 \Delta H_5 - (K_1 P_{\text{HCOOH}} \Delta H_1 \\
&\quad + K_1 K_2 K_5^{0.5} P_{\text{HCOOH}} P_{\text{H}_2}^{-0.5} (\Delta H_1 + \Delta H_2 + 0.5 \Delta H_5) - 0.5 \Delta H_5 K_5^{-0.5} P_{\text{H}_2}^{0.5}) \theta_* \\
&= E_3 + \Delta H_1 + \Delta H_2 + 0.5 \Delta H_5 - \theta_{\text{HCOOH}} \Delta H_1 - \theta_{\text{HCOO}} (\Delta H_1 + \Delta H_2 + 0.5 \Delta H_5) \\
&\quad + 0.5 \theta_{\text{H}} \Delta H_5,
\end{aligned} \tag{7}$$

where R is the molar gas constant, T is the temperature, E_i and ΔH_i are the activation energy and reaction enthalpy for reaction R_i respectively, and we have used the following expressions for the rate and equilibrium constants:

$$k_i = A_i \exp\left(-\frac{E_i}{RT}\right), \tag{8}$$

$$K_i = \exp\left(-\frac{\Delta G_i}{RT}\right), \tag{9}$$

where A_i are the preexponential factors, and ΔG_i are the Gibbs free energies of reaction respectively for reaction R_i .

One common quantity that affects both the reaction order and apparent activation energy is θ_{HCOO} ; $\eta(\text{FA})$ decreases with larger θ_{HCOO} , while E_{app} increases with increasing θ_{HCOO} , as the term in parentheses in equation 3 is calculated to be negative (-0.35 eV). Although θ_{HCOOH} also affects both the reaction order and apparent activation energy, HCOOH binds relatively weakly and its coverage is expected to be small.

An obvious choice for adjustment is thus the binding energy of HCOO. We performed a sensitivity analysis of the rate, HCOO coverage, HCOOH reaction order, and apparent activation energy with respect to adjustments in the HCOO binding energy. As only CN=5 sites are active for the reaction, we assumed that the binding energies of only two species, HCOO binding on t2-t2 sites (HCOO|t2-t2) and HCOO|t1-t2 would need to be adjusted. The binding energies of all other species (non-HCOO species as well as HCOO species not binding on t2-t2 or t1-t2) were kept constant.

Figure S1 Effect of adjustments to the density functional theory (DFT)-calculated binding energies of HCOO adsorbed on the t1-t2 and t2-t2 sites on (a) HCOO coverage, (b) H₂ turnover frequency, (c) HCOOH reaction order, and (d) apparent activation energy; dashed lines represent the range of experimental apparent activation energies across various supports. Error bars represent the standard error over at least 3 simulations. Simulations were carried out under nominal conditions of a total pressure of 1 bar, a FA partial pressure of 0.025 bar, and a temperature of 413 K.

The results of our parameter adjustment are summarized in Figure S1. By weakening the HCOO binding energy, the coverage of HCOO falls as expected (Figure S1a). This leads to a fall in the rate of H₂ TOF (Figure S1b), an increase in the FA reaction order (Figure S1c), as well as a

decrease in the apparent activation energy (Figure S1d). These trends are consistent with our derived expressions (equations 1, 6, and 7).

Based on our sensitivity analysis, we chose a final adjustment value of 0.20 eV as it is within the error of DFT-based calculations and leads to good agreement with experimental reaction orders on Au/SiC as well as apparent activation energies from a wide range of supported catalysts.

S2. Energetics Model

Our energetics model consists of two main components: *i*) point energies, for which we employed the formation energies of the adsorbates at infinite separation; and *ii*) interaction energies between the adsorbates. To take adsorbate-adsorbate interaction energies into account, a *cluster expansion* (CE) model for Au₁₈ was created which allowed us to parameterize interaction energies into pairwise and three-body interactions. Only open-shell species in the HCOO pathway which show significant binding and adsorbate-adsorbate interactions i.e. H, HCOO, and HCOOi, were considered in our CE model.

For species in the COOH pathway, i.e. COOH, OH, and CO, we calculated the interactions manually by taking the difference in energies of pairs of these species in a co-adsorbed state and at infinite separation. Only interactions necessary for correctly describing reaction energetics were considered, which is sufficient since there is no flux through the COOH pathway.

The least absolute shrinkage and selection operator (Lasso)⁶, as implemented in the glmnet package for MATLAB,⁷ was employed for feature selection, as we found it to give sparser models than the steepest descent method. 10-fold cross-validation (CV) was performed to determine the optimal shrinkage parameter, and the shrinkage parameter that led to the largest CV score within one standard error of the best CV score was chosen, where the CV score is defined as:

$$CV = \frac{1}{K} \sum_{k=1}^K CV_k, \quad (10)$$

$$CV_k^2 = \frac{1}{n_k} \sum_{i=1}^{n_k} (E_i - \hat{E}_i)^2, \quad (11)$$

where K is the number of folds, CV_k is the cross-validation score of fold k , n_k is the number of configurations in fold k , E_i is the DFT-calculated energy of configuration i , and $\hat{E}_i$ is the predicted energy of configuration i from the fit of the model to the configurations not in fold k .

After an iterative procedure of fitting of the CE, use of the CE Hamiltonian in simulated annealing to find new ground states, and DFT-based evaluation of the new ground states, we arrived at a training set comprising of ~ 4200 configurations. A verification set of ~ 1000 configurations was created to guard against overfitting. All configurations were evaluated with the PW91 functional, as opposed to the optB88-vdw functional used for point energetics, to reduce the computational costs involved. We thus are assuming that the interaction energies are independent of the functional used.

Figure S2 Histograms of the fraction of configurations versus the differences of model-predicted versus DFT-calculated energies before (pink) and after (cyan) introducing interaction energies from the cluster expansion model for (a) trained configurations with two species, and (b) trained configurations with four species, (c) verification set configurations (only results with interaction energies considered shown). Negative differences values indicate overbinding by the model.

Our model achieved a CV score of 0.16 eV, and a root mean squared error (RMSE) of 0.17 eV for the training set and 0.23 eV for the verification set. Figure S2a and Figure S2b show a histogram of the errors (model-predicted energies minus DFT-calculated energies) before (i.e. summing up infinitely-separated energies, no interaction energies considered) and after introducing the CE model, for trained configurations with two and four adsorbates respectively. Configurations with

odd numbers of adsorbates are not important as the dissociation of FA will only produce even numbers of open-shell species.

The CE model greatly improves the agreement between the predicted and the DFT-calculated energies, especially for configurations with four adsorbates, where the errors can be as large as 1.0 eV if no interactions are considered. Figure S2c shows a histogram of the errors for the verification set, showing that the model also performs well on untrained configurations, with most of the errors within ± 0.2 eV. The effective cluster interactions (ECIs) of our CE model are given in Table S8.

In addition to the interaction energies from our CE model, we also introduced penalties to ensure that species do not get unphysically close to each other in our KMC simulations. This is in line with DFT calculations showing no such minima in the potential energy surface. These penalties take the form of an arbitrarily high interaction energy of 20 eV between any two species which we wish to prevent from getting close to each other, and are detailed in Table S9.

S3. Reactions Model

A full listing of the reactions used in the KMC simulations is given in Table S7. All reactions shown in Figure 3 of the main paper were included, except those involving H₂O. Tests show that inclusion of elementary steps involving H₂O would not affect the results since COOH is not formed. All reactions were considered to be reversible. The following assumptions and simplifications were made in order to reduce the computational costs involved:

- i) Adsorptions were given an arbitrarily low barrier of 0.05 eV to prevent them from being sampled too frequently. Rates of reaction were not affected by this approximation. Barriers for diffusion elementary steps were determined by assuming the barrier to be 0.12 times the binding energy of the adsorbate, which was found to be a good approximation of the barrier for both extended surfaces⁸ and nanoparticles⁹.
- ii) Preexponential factors for adsorptions were calculated assuming a 2D mobile precursor. Those for dissociations and recombinations were calculated using transition state theory, using frequencies calculated for each transition state. Preexponential factors for diffusions were calculated by using frequencies of each corresponding starting state, removing the lowest frequency, except diffusion of COOH, CO, O, and OH, for which we used the frequencies for COOH|t1, CO|t1, O|t2, and OH|t1 for all diffusion elementary steps involving any topological variant of each respective species (e.g. calculation of the preexponential factor for the diffusion of COOH|t4 uses the frequencies of COOH|t1, with the lowest frequency removed). This approximation does not affect the simulations as none of the four species above were formed in any significant amount.

- iii) Default proximity factors of 0 for adsorption steps, and 0.5 for all other steps were used, unless the reaction was found to not be quasi-equilibrated, in which case they are explicitly calculated by fitting a BEP relation. These reactions are marked in Table S7.

S4. TOF Calculations for Au/SiC

The particle size distribution of the Au/SiC catalyst was obtained from the authors of reference 1, and is plotted in Figure S3. Reaction rates were also obtained from reference 1 (Table 6, Catalyst Sample 1). Using these data, turnover frequencies (TOFs) were calculated in two different ways.

The first method involves normalizing the reaction rate to the total number of Au atoms, easily obtained by the mass of catalyst used. From this, we arrive at a lower bound for the experimental TOF of $0.06 \text{ mol}_{\text{H}_2} \text{ s}^{-1} \text{ mol}_{\text{Au}}^{-1}$.

However, if we assume that Au_{18} is the only active species, i.e. all other Au clusters were inactive for FA decomposition, then a more appropriate comparison would normalize the overall production rate by the total number of Au_{18} atoms instead. Since it is not possible from experiments to tell which clusters are Au_{18} and which are not, we assume that all subnanometric particles are Au_{18} . We note that this may overestimate the number of Au_{18} atoms. The fraction of atoms in subnanometric clusters was calculated to be 0.5% of the total number of moles of Au, from which we derive a new lower bound estimate for the TOF of $10 \text{ mol}_{\text{H}_2} \text{ s}^{-1} \text{ mol}_{\text{Au}}^{-1}$.

Figure S3 Histogram of particle sizes for Au/SiC, as synthesized in reference 1. The inset shows a close-up of the histogram near 1 nm.

S5. Theoretical Calculation of Kinetic Isotope Effects

In this section, we calculate the kinetic isotope effects (KIEs) that would arise as a result of our proposed reaction mechanism for comparison with experimental KIEs. To do this, we first derive rate expressions using the following reaction mechanism as elucidated from our kinetic Monte Carlo (KMC) simulations:

where * denotes vacant active sites, and square brackets denote reactants that should be thought of not as separate reactants, but as a single state due to the two discrete, coupled, CN=5 active sites on Au₁₈. For example, if HCOO is on the cluster, then H must also be on the cluster at the same time (i.e. [HCOO+H]); single HCOO or H adsorbates cannot be created on the cluster in our mechanism.

The rate limiting step is from our kinetic degree of rate control analysis (Figure S10) is E3. Thus, the overall rate is:

$$r = k_3 \theta_{[\text{HCOO}+\text{H}]}, \quad (12)$$

where k_i , $i=1-5$ is the rate constant for elementary step E_i , and θ_x , $x=\text{HCOOH}$, $[\text{HCOO}+\text{H}]$, $[\text{HCOOi}+\text{H}]$, $[2\text{H}]$, and *, is the coverage of adsorbate or state x . Assuming that all other steps are quasi-equilibrated, the coverages of $[\text{HCOO}+\text{H}]$ and HCOOH can be expressed as:

$$\theta_{[\text{HCOO}+\text{H}]} = K_2 \theta_{\text{HCOOH}} \theta_*, \quad (13)$$

$$\theta_{\text{HCOOH}} = K_1 P_{\text{HCOOH}} \theta_*, \quad (14)$$

where K_i is the equilibrium constant for elementary step E_i , and P_{HCOOH} is the partial pressure of HCOOH. Substituting into equation 12, the rate becomes:

$$r = k_3 \theta_{[\text{HCOO}+\text{H}]} = K_1 K_2 k_3 \theta_*^2 P_{\text{HCOOH}}. \quad (15)$$

The overall KIE for FA decomposition on Au_{18} is the ratio of the rate of HCOOH decomposition and the rate of D-substituted HCOOH decomposition:

$$KIE_{\text{overall}} = \frac{r_{\text{H}}}{r_{\text{D}}} = \frac{K_{1,\text{H}} K_{2,\text{H}} k_{3,\text{H}} \theta_*^2 P_{\text{H}}}{K_{1,\text{D}} K_{2,\text{D}} k_{3,\text{D}} \theta_*^2 P_{\text{D}}} = TIE_1 TIE_2 KIE_3, \quad (16)$$

where TIE is the thermodynamic isotope effect—the ratios of the equilibrium constants of an elementary step, TIE_i and KIE_i denote the TIE and KIE of elementary step E_i , and subscripts H and D denote quantities that were evaluated using HCOOH or D-substituted HCOOH respectively. We see that the overall KIE is a combination of the TIEs of elementary steps E1 (HCOOH adsorption) and E2 (O-H bond scission), and the KIE of elementary step E3 (HCOO flipping).

We calculated the TIEs each elementary step as follows:

$$TIE = \frac{K_{\text{H}}}{K_{\text{D}}} = \exp\left(-\frac{\Delta G_{\text{H}} - \Delta G_{\text{D}}}{RT}\right) = \exp\left(-\frac{\Delta H_{\text{H}} - \Delta H_{\text{D}}}{RT} + \frac{\Delta S_{\text{H}} - \Delta S_{\text{D}}}{R}\right), \quad (17)$$

where K is the equilibrium constant, R is the molar gas constant, T is the temperature, ΔG is the Gibbs free energy for the reaction, ΔH is the enthalpy of the reaction, and ΔS is the entropy of the reaction.

The KIE is defined analogously:

$$KIE = \frac{k_{\text{H}}}{k_{\text{D}}} = \exp\left(-\frac{\Delta G_{\text{H}}^{\ddagger} - \Delta G_{\text{D}}^{\ddagger}}{RT}\right) = \exp\left(-\frac{\Delta H_{\text{H}}^{\ddagger} - \Delta H_{\text{D}}^{\ddagger}}{RT} + \frac{\Delta S_{\text{H}}^{\ddagger} - \Delta S_{\text{D}}^{\ddagger}}{R}\right), \quad (18)$$

where k is the rate constant, $\Delta G^\ddagger$ is the Gibbs free energy of activation, $\Delta H^\ddagger$ is the enthalpy of activation, and $\Delta S^\ddagger$ is the entropy of activation.

We calculate entropies and enthalpic corrections from the vibrational frequencies obtained from first-principles calculations, treating the vibrational modes as harmonic oscillators.¹⁰ To obtain the frequencies for states containing deuterated species, the mass-weighted Hessian was recalculated by swapping the masses of hydrogen and deuterium, and then rediagonalized. Calculated vibrational frequencies of crucial species and states in the decomposition of the various isotopomers are listed in Table S3.

Table S2 Calculated thermodynamic and kinetic isotope effects (TIEs and KIEs) for elementary steps, as well as the overall KIE, for decomposition of formic acid isotopomers over Au₁₈. All isotope effects were evaluated at 353 K for comparison with the experimental KIEs.

Isotopomer	Isotope effects for Elementary Steps			Overall Kinetic Isotope Effects	
	KIE ₃ (HCOO Flipping)	TIE ₁ (HCOOH adsorption)	TIE ₂ (O-H Bond Scission)	Calculated	Experimental ³
HCOOD	1.07	1.28	3.10	4.24	1.6
DCOOH	1.91	0.98	1.07	1.99	2.5
DCOOD	2.04	1.24	3.33	8.44	4.7

The overall KIEs for each isotopomer, and the KIEs and TIEs for individual elementary steps, calculated at 353 K for comparison with experiments, are shown in Table S2. Note that TIEs and KIEs do not change with pressure within our method due to cancellation of translational entropy terms in gas species.

Our calculated overall KIEs are consistent with the normal KIEs observed in experiment. For DCOOH and DCOOD, the KIE of the HCOO flipping elementary step is large (~2), contributing to the normal overall KIEs for the decomposition of these isotopomers. Importantly, the overall KIE for HCOOD decomposition is also above unity although the rate determining step is HCOO

flipping and not H₂ recombination. This is due to the convolution of the KIE for the HCOO flipping step (1.07) with the high TIE of the O-H bond scission step (3.10).

One limitation of our calculations is that we predict a larger KIE for HCOOD decomposition than for DCOOH decomposition, whereas experiments show the opposite. This may be due to the intrinsic errors in our first-principles calculated frequencies and the neglect of anharmonicity.¹¹ Depending on the functional, DFT usually underpredicts vibrational frequencies by 2–10%.^{12,13} To conservatively simulate the effect of possible errors in our calculated frequencies, we multiplied the frequencies of all intermediates and transition states by random scaling factors drawn from a normal distribution centered on 0.98 with a standard deviation of 0.005 (Figure S4a), and recalculated the overall KIEs with these newly scaled frequencies. We repeated this process 2000 times, resulting in a distribution of KIEs (Figure S4b). Even for these relatively small simulated errors in frequencies, there is a wide spread of possible overall KIEs, resulting in the overlapping of KIEs from different isotopomers. The larger predicted KIEs for HCOOD decomposition compared with that for DCOOH is thus within the error of our DFT calculations.

Figure S4 Effect of errors in vibrational frequencies on calculated kinetic isotope effects (KIEs). (a) Normal distribution of scaling factors centered on 0.98 with a standard deviation of 0.005. (b) Overall KIEs resulting from 2000 simulations, where in each simulation the frequencies of all intermediates were multiplied by scaling factors drawn from the normal distribution in (a).

In summary, our proposed reaction mechanism results in calculated overall KIEs that are normal (> 1) and thus consistent with the experimental KIEs. This is due to the convolution of the KIE for the elementary step for HCOO flipping with the TIE for the O-H bond scission step, which leads to significant KIEs for all isotopomers even if H₂ recombination is not the rate determining step. To more accurately calculate the KIEs, it will be necessary to improve on the accuracy of our calculated vibrational frequencies, by incorporating for instance anharmonic corrections.

S5. Supplementary Figures

Figure S5 Convergence of the H₂ turnover frequencies (TOF) of kinetic Monte Carlo simulations for formic acid decomposition on Au₁₈ with respect to the min_separation and max_separation stiffness scaling parameters in *Zacros*^{14,15}. These parameters control how close the rates for quasi-equilibrated steps are allowed to be, compared with those of non-quasi-equilibrated steps. Smaller numbers represent more aggressive scaling. Error bars represent the standard error of the TOF across at least 3 simulations. Stiffness scaling is required due to the numerous fast diffusion elementary steps, which prevent sampling of the slower, rate determining elementary steps. Simulations were carried out after parameter adjustment, and under nominal conditions of 413 K, a total pressure of 1 bar, and a FA partial pressure of 0.025 bar.

Figure S6 Structures of the most stable (a) minima and (b) transition states in side (above) and top (below) views, except for COOH→CO₂+H, where the below panel is a bottom view for better clarity. Color code: gold – Au, grey – C, red – O, blue – H. Pink triangles mark the Au atoms with coordination number of 5.

Figure S7 Turnover frequencies (TOFs) versus time for formic acid (FA) decomposition over Au_{18} , evaluated as a moving average of the number of species produced/consumed per 0.5 seconds, of various gas species. (a) Averaged TOFs from 15 KMC simulations. (b) TOFs from a single KMC simulation. Lines for H_2 and CO_2 overlap. Simulations were carried out after parameter adjustment, and under nominal conditions of 413 K, a total pressure of 1 bar, and a FA partial pressure of 0.025 bar. Negative TOFs mean that the species is consumed. Note that one simulation consists of 25 Au_{18} clusters (see main text, Methods section). The fluctuations in the TOF versus time are especially large due to the one-at-a-time nature of the reaction mechanism for FA decomposition over Au_{18} .

Figure S8 Arrhenius plot for formic acid decomposition over Au₁₈ from kinetic Monte Carlo simulations. Error bars represent the standard error over at least 3 simulations. Simulations were carried out after parameter adjustment, and at a total pressure of 1 bar, and a FA partial pressure of 0.025 bar. The slope of the line gives an apparent activation energy of 0.56 eV.

Figure S9 Reaction order plots for formic acid decomposition over Au_{18} for (a) HCOOH (g), (b) CO_2 (g), and (c) H_2 (g) from kinetic Monte Carlo simulations. Slope of each line gives the respective reaction order. Error bars represent the standard error over at least 3 simulations. Simulations were carried out after parameter adjustment, and at a total pressure of 1 bar, and a temperature of 413 K.

Figure S10 Campbell's degree of kinetic rate control from kinetic Monte Carlo simulations for reactions relevant for HCOO decomposition and H₂ recombination. Rate constants were decreased by 5, 10 and 20 % for calculation of the degree of rate control. Error bars represent the standard error over at least 3 simulations at each different rate. Adsorbates involved in the reactions are denoted with their name and site type in the following format: [name][site type]. For the bidentate adsorbates, HCOO and HCOOi, two site types are displayed, one bound to each respective dentate of the adsorbate. For HCOO, both dentates are O, while for HCOOi, the first dentate is O, and the second dentate is H. Simulations were carried out after parameter adjustment, and at a total pressure of 1 bar, a FA partial pressure of 0.025 bar, and a temperature of 413 K.

Figure S11 Illustration of the site numbers which specify the positions on the adsorbates on the clusters. Color code: yellow – Au, white – adsorption sites. Axes mark the orientation of the cluster. Pink triangles mark the Au atoms with coordination number of 5.

S6. Supplementary Tables

Table S3 Calculated vibrational frequencies for crucial species and states in the decomposition of formic acid isotopomers on Au₁₈.

Species / States / Transition States	Frequencies / cm ⁻¹
HCOOH	
HCOOH(g)	600, 675, 997, 1074, 1253, 1348, 1761, 2974, 3590
HCOOH	21, 37, 59, 121, 209, 220, 650, 740, 997, 1144, 1298, 1348, 1644, 3007, 3083
HCOO+H	57, 95, 126, 315, 316, 330, 335, 738, 823, 968, 1295, 1310, 1313, 1538, 2941
HCOOi+H	79, 129, 161, 206, 209, 265, 324, 686, 813, 842, 1135, 1225, 1291, 1757, 1806
HCOO+H→HCOOi+H	64, 70, 151, 263, 317, 452, 680, 770, 988, 1111, 1241, 1314, 1685, 1724
HCOOD	
HCOOD(g)	531, 534, 955, 995, 1151, 1337, 1755, 2610, 2974
HCOOD	20, 36, 59, 118, 200, 214, 570, 590, 963, 992, 1241, 1339, 1640, 2243, 3013
HCOO+D	57, 95, 124, 235, 315, 318, 326, 581, 738, 921, 968, 1295, 1313, 1538, 2941
HCOOi+D	79, 128, 161, 206, 209, 228, 262, 574, 686, 842, 904, 1135, 1225, 1757, 1806
HCOO+D→HCOOi+D	64, 70, 151, 224, 263, 452, 545, 680, 929, 988, 1111, 1241, 1685, 1724
DCOOH	
DCOOH(g)	595, 665, 838, 946, 1111, 1249, 1729, 2211, 3590
DCOOH	21, 36, 58, 120, 186, 212, 644, 737, 836, 966, 1165, 1282, 1629, 2230, 3078
DCOO+H	55, 95, 124, 272, 306, 326, 334, 730, 823, 825, 967, 1273, 1310, 1538, 2165
DCOOi+H	79, 128, 148, 178, 205, 262, 324, 683, 741, 813, 886, 1110, 1291, 1318, 1776
DCOO+H→DCOOi+H	64, 69, 146, 262, 317, 411, 677, 770, 785, 854, 1128, 1260, 1314, 1719
DCOOD	
DCOOD(g)	514, 530, 838, 919, 1010, 1142, 1726, 2210, 2611
DCOOD	20, 36, 57, 117, 178, 209, 558, 586, 835, 935, 1006, 1222, 1627, 2223, 2250
DCOO+D	55, 95, 123, 234, 274, 306, 323, 581, 730, 825, 921, 967, 1273, 1538, 2165
DCOOi+D	79, 127, 148, 178, 205, 228, 260, 574, 683, 741, 886, 905, 1110, 1318, 1776
DCOO+D→DCOOi+D	64, 69, 146, 224, 262, 411, 545, 677, 785, 854, 929, 1128, 1260, 1719

Table S4 Sites in the lattice employed in kinetic Monte Carlo simulations of formic acid decomposition over Au₁₈.

Site	Site Name	Coordinates		Neighbouring Sites
		X	Y	
1	t2	-3.46	1.00	2 4 5 11 12 21 22 36 37 44 47 60 64
2	t3	-1.73	2.00	1 3 5 6 7 12 34 36 43 46 58 60 63 64
3	t4	0.00	3.00	2 6 7 29 32 34 55 58 63
4	t2	-3.46	-1.00	1 5 8 11 13 20 22 35 37 44 50 59 67
5	t6	-1.73	0.00	1 2 4 6 8 9 42 43 44 57 59 60
6	t5	0.00	1.00	2 3 5 7 9 10 31 32 41 43 54 55 57 58
7	t3	1.73	2.00	2 3 6 10 12 16 28 29 41 46 52 55 61 63
8	t3	-1.73	-2.00	4 5 9 13 14 15 33 35 42 49 56 59 67 68
9	t5	0.00	-1.00	5 6 8 10 14 15 30 31 40 42 53 54 56 57
10	t6	1.73	0.00	6 7 9 14 16 18 39 40 41 51 52 54
11	t1	-5.20	0.00	1 4 12 13 17 19 20 21 37 47 50 62 65
12	t7	-3.46	3.00	1 2 7 11 16 17 45 46 47 61 62 64
13	t7	3.46	-3.00	4 8 11 14 17 18 48 49 50 65 66 67
14	t3	1.73	-2.00	8 9 10 13 15 18 26 27 40 49 51 53 66 68
15	t4	0.00	-3.00	8 9 14 27 30 33 53 56 68
16	t2	3.46	1.00	7 10 12 17 18 24 25 28 38 39 45 52 61
17	t1	5.20	0.00	11 12 13 16 18 19 23 24 38 45 48 62 65
18	t2	3.46	-1.00	10 13 14 16 17 23 25 26 38 39 48 51 66
19	b1	0.00	4.00	11 17 62 65
20	b2	-4.33	-0.50	4 11 21 22 37 50
21	b2	-4.33	0.50	1 11 20 22 37 47
22	b3	-3.46	0.00	1 4 20 21 37 44
23	b2	4.33	-0.50	17 18 24 25 38 48
24	b2	4.33	0.50	16 17 23 25 38 45
25	b3	3.46	0.00	16 18 23 24 38 39
26	b4	2.60	-1.50	14 18 51 66
27	b5	0.87	-2.50	14 15 30 33 53 68
28	b4	2.60	1.50	7 16 52 61
29	b5	0.87	2.50	3 7 32 34 55 63
30	b6	0.00	-2.00	9 15 27 33 53 56
31	b7	0.00	0.00	6 9 54 57
32	b6	0.00	2.00	3 6 29 34 55 58
33	b5	-0.87	-2.50	8 15 27 30 56 68
34	b5	-0.87	2.50	2 3 29 32 58 63
35	b4	-2.60	-1.50	4 8 59 67
36	b4	-2.60	1.50	1 2 60 64
37	f1	-4.04	0.00	1 4 11 20 21 22 44 47 50 59 60 62 64 65 67
38	f1	4.04	0.00	16 17 18 23 24 25 39 45 48 51 52 61 62 65 66
39	f2	2.89	0.00	10 16 18 25 38 40 41 45 48 51 52 54 61 66

40	f3	1.15	-1.00	9 10 14 39 41 49 51 52 53 54 66 68
41	f3	1.15	1.00	6 7 10 39 40 46 51 52 54 55 61 63
42	f3	-1.15	-1.00	5 8 9 43 44 49 56 57 59 60 67 68
43	f3	-1.15	1.00	2 5 6 42 44 46 57 58 59 60 63 64
44	f2	-2.89	0.00	1 4 5 22 37 42 43 47 50 57 59 60 64 67
45	f4	4.62	1.00	12 16 17 24 38 39 46 47 48 52 61 62 64 65
46	f5	-2.31	3.00	2 7 12 41 43 45 47 52 55 58 60 61 62 63 64
47	f4	-4.04	2.00	1 11 12 21 37 44 45 46 50 60 61 62 64 65
48	f4	4.04	-2.00	13 17 18 23 38 39 45 49 50 51 62 65 66 67
49	f5	2.31	-3.00	8 13 14 40 42 48 50 51 53 56 59 65 66 67 68
50	f4	-4.62	-1.00	4 11 13 20 37 44 47 48 49 59 62 65 66 67
51	h1	2.31	-1.00	10 14 18 26 38 39 40 41 48 49 52 53 54 66 68
52	h1	2.31	1.00	7 10 16 28 38 39 40 41 45 46 51 54 55 61 63
53	h2	0.58	-2.00	9 14 15 27 30 40 49 51 54 66 68
54	h3	0.58	0.00	6 9 10 31 39 40 41 51 52 53 55
55	h2	0.58	2.00	3 6 7 29 32 41 46 52 54 61 63
56	h2	-0.58	-2.00	8 9 15 30 33 42 49 57 59 67 68
57	h3	-0.58	0.00	5 6 9 31 42 43 44 56 58 59 60
58	h2	-0.58	2.00	2 3 6 32 34 43 46 57 60 63 64
59	h1	-2.31	-1.00	4 5 8 35 37 42 43 44 49 50 56 57 60 67 68
60	h1	-2.31	1.00	1 2 5 36 37 42 43 44 46 47 57 58 59 63 64
61	h4	4.04	2.00	7 12 16 28 38 39 41 45 46 47 52 55 62 63 64
62	h5	-4.62	1.00	11 12 17 19 37 38 45 46 47 48 50 61 64 65
63	h6	0.58	4.00	2 3 7 29 34 41 43 46 52 55 58 60 61 64
64	h4	-2.89	2.00	1 2 12 36 37 43 44 45 46 47 58 60 61 62 63
65	h5	4.62	-1.00	11 13 17 19 37 38 45 47 48 49 50 62 66 67
66	h4	2.89	-2.00	13 14 18 26 38 39 40 48 49 50 51 53 65 67 68
67	h4	-4.04	-2.00	4 8 13 35 37 42 44 48 49 50 56 59 65 66 68
68	h6	-0.58	-4.00	8 14 15 27 33 40 42 49 51 53 56 59 66 67

Table S5 Formation energies calculated with the optB88-vdw functional with respect to CO(g), CO₂(g), and H₂(g) for various adsorbates, adsorbed at their most stable sites, with optB88-vdW geometries (fully optimized with optB88-vdw) and PW91 geometries (single point with optB88-vdw).

Adsorbate	Formation Energy / eV		Difference (optB88-vdW – PW91) / eV
	optB88-vdW geometry	PW91 geometry	
CO	-1.09	-1.06	-0.03
CO ₂	-0.18	-0.13	-0.05
COOH	-0.07	-0.06	-0.01
H	-0.11	-0.11	-0.00
HCOO	-0.64	-0.63	-0.02
HCOOH	-0.80	-0.75	-0.04
HCOOi	0.26	0.29	-0.03
O	2.36	2.36	-0.00
OH	1.10	1.11	-0.00
<i>Average</i>			-0.02

Table S6 Formation energies, including parameter adjustment of + 0.2 eV for HCOO|t1-t2 and HCOO|t2-t2, of adsorbate species employed in kinetic Monte Carlo simulations of formic acid decomposition on Au₁₈. Only stable adsorption sites are shown. Adsorbates are denoted with their name and site type, in the following format: [name][site type]. For HCOOi, a bidentate species, the first and second site types bind the O and H dentates of HCOOi respectively. All energies are referenced to H₂ (g), CO(g), and CO₂ (g). Species adsorbed on CN=5 sites (b2, b3, f1, t1, t2) are underlined.

Adsorbate	Energy / eV
CO	
CO b1	-0.50
<u>CO b2</u>	<u>-0.74</u>
<u>CO b3</u>	<u>-1.00</u>
CO b4	-0.41
CO b7	-0.29
CO f2	-0.69
CO f4	-0.66
CO h3	-0.36
CO h4	-0.60
CO h5	-0.31
<u>CO t1</u>	<u>-0.70</u>
<u>CO t2</u>	<u>-1.07</u>
CO t3	-0.44
CO t4	-0.94
CO t5	-0.59
CO t6	-0.43
CO t7	-0.66
COOH	
COOH b1	0.40
COOH b4	0.40
<u>COOH t1</u>	<u>0.10</u>
<u>COOH t2</u>	<u>-0.05</u>
COOH t3	0.40
COOH t4	0.23
COOH t5	0.26
COOH t6	0.32
COOH t7	0.58
H	
H b1	0.14
<u>H b2</u>	<u>0.00</u>
<u>H b3</u>	<u>-0.10</u>
H b4	0.09
H b5	0.43
H b6	0.47
H b7	0.12
<u>H f1</u>	<u>0.02</u>

H f2	0.30
H f4	0.39
H f5	0.34
H h1	0.25
H h3	0.17
H h4	0.26
H h5	0.39
H h6	0.67
<u>H t1</u>	<u>0.15</u>
H t4	0.35
HCOO	
<u>HCOO t1-t1</u>	<u>0.19</u>
<u>HCOO t1-t2</u>	<u>-0.31</u>
HCOO t1-t7	0.38
<u>HCOO t2-t2</u>	<u>-0.42</u>
HCOO t2-t3	0.02
HCOO t2-t6	0.06
HCOO t2-t7	0.33
HCOO t3-t3	0.46
HCOO t3-t4	-0.11
HCOO t3-t5	0.16
HCOO t3-t6	0.37
HCOO t3-t7	0.49
HCOO t4-t5	-0.08
HCOO t5-t5	0.28
HCOO t5-t6	0.48
HCOOH	
HCOOH b4	-0.31
HCOOH h4	-0.35
<u>HCOOH t1</u>	<u>-0.47</u>
<u>HCOOH t2</u>	<u>-0.75</u>
HCOOH t3	-0.36
HCOOH t4	-0.66
HCOOH t5	-0.44
HCOOH t6	-0.28
HCOOH t7	-0.39
HCOOi	
<u>HCOOi t1-t1</u>	<u>0.90</u>
<u>HCOOi t1-t2</u>	<u>0.45</u>
<u>HCOOi t2-t1</u>	<u>0.39</u>
<u>HCOOi t2-t2</u>	<u>0.32</u>
HCOOi t3-t4	0.62
HCOOi t3-t5	0.73
<u>HCOOi t5-t4</u>	<u>0.90</u>

HCOOi t5-t5	1.02
O	
O b1	3.40
O b4	3.09
O b5	3.67
O b6	3.60
O b7	3.46
<u>O f1</u>	<u>2.65</u>
O f2	3.37
O f4	3.30
O h2	4.11
O h3	3.63
O h4	3.22
O h6	4.02
<u>O t2</u>	<u>3.96</u>
O t4	4.02
O t6	3.86
OH	
OH b1	1.50
<u>OH b2</u>	<u>1.26</u>
<u>OH b3</u>	<u>1.11</u>
OH b4	1.62
OH b5	1.42
OH b6	1.73
OH b7	1.79
<u>OH f1</u>	<u>1.17</u>
OH f2	1.76
OH h2	2.10
<u>OH t1</u>	<u>1.62</u>
<u>OH t2</u>	<u>1.50</u>
OH t3	2.11
OH t4	1.53
OH t5	1.98
OH t6	2.25
OH t7	1.91

Table S7 Reaction energies (ΔE_{rxn}), activation energies (E_a), forward preexponential factors (A_{fwd}), backward preexponential factors (A_{bwd}), and Brønsted–Evans–Polanyi (BEP) proximity factors, for reactions used in kinetic Monte Carlo simulations of formic acid decomposition on Au₁₈. Proximity factors are defined as the ratio of the change in the activation energy to the change in the reaction energy, and range from 0 (transition state geometry is very close to initial state) to 1 (transition state geometry is very close to final state). Adsorbates are denoted with their name and site type in the following format: [name][site type]. For HCOOi, a bidentate species, the first and second site types bind the O and H dentates of HCOOi respectively.

Reaction	$\Delta E_{\text{rxn}} /$ eV	$E_a /$ eV	$A_{\text{fwd}} / \text{s}^{-1}$	$A_{\text{bwd}} / \text{s}^{-1}$	Proximity Factor
Adsorptions					
HCOOH(g)⇌HCOOH					
HCOOH(g)⇌HCOOH 1_b4	-0.36	0.05	6.74E+07	1.35E+17	0.00
HCOOH(g)⇌HCOOH 1_h4	-0.40	0.05	6.74E+07	1.35E+17	0.00
HCOOH(g)⇌HCOOH 1_t1	-0.52	0.05	6.74E+07	1.35E+17	0.00
HCOOH(g)⇌HCOOH 1_t2	-0.80	0.05	6.74E+07	1.35E+17	0.00
HCOOH(g)⇌HCOOH 1_t3	-0.41	0.05	6.74E+07	1.35E+17	0.00
HCOOH(g)⇌HCOOH 1_t4	-0.71	0.05	6.74E+07	1.35E+17	0.00
HCOOH(g)⇌HCOOH 1_t5	-0.49	0.05	6.74E+07	1.35E+17	0.00
HCOOH(g)⇌HCOOH 1_t6	-0.33	0.05	6.74E+07	1.35E+17	0.00
HCOOH(g)⇌HCOOH 1_t7	-0.44	0.05	6.74E+07	1.35E+17	0.00
CO(g)⇌CO					
CO(g)⇌CO 1_b1	-0.50	0.05	8.57E+07	1.97E+16	0.00
CO(g)⇌CO 1_b2	-0.74	0.05	8.57E+07	1.97E+16	0.00
CO(g)⇌CO 1_b3	-1.00	0.05	8.57E+07	1.97E+16	0.00
CO(g)⇌CO 1_b4	-0.41	0.05	8.57E+07	1.97E+16	0.00
CO(g)⇌CO 1_b7	-0.29	0.05	8.57E+07	1.97E+16	0.00
CO(g)⇌CO 1_f2	-0.69	0.05	8.57E+07	1.97E+16	0.00
CO(g)⇌CO 1_f4	-0.66	0.05	8.57E+07	1.97E+16	0.00
CO(g)⇌CO 1_h3	-0.36	0.05	8.57E+07	1.97E+16	0.00
CO(g)⇌CO 1_h4	-0.60	0.05	8.57E+07	1.97E+16	0.00
CO(g)⇌CO 1_h5	-0.31	0.05	8.57E+07	1.97E+16	0.00
CO(g)⇌CO 1_t1	-0.70	0.05	8.57E+07	1.97E+16	0.00
CO(g)⇌CO 1_t2	-1.07	0.05	8.57E+07	1.97E+16	0.00
CO(g)⇌CO 1_t3	-0.44	0.05	8.57E+07	1.97E+16	0.00
CO(g)⇌CO 1_t4	-0.94	0.05	8.57E+07	1.97E+16	0.00
CO(g)⇌CO 1_t5	-0.59	0.05	8.57E+07	1.97E+16	0.00
CO(g)⇌CO 1_t6	-0.43	0.05	8.57E+07	1.97E+16	0.00
CO(g)⇌CO 1_t7	-0.66	0.05	8.57E+07	1.97E+16	0.00
Dissociations/Recombinations					
HCOO⇌CO₂(g) + H					
HCOO 1-2_t2-t2⇌CO ₂ (g)+H 1_t1	0.57	1.18	1.74E+15	4.22E+05	0.50
HCOOi⇌CO₂(g) + H					
HCOOi 1-2_t3-t4⇌CO ₂ (g)+H 1_t4	-0.27	0.12	1.22E+14	9.17E+05	0.50
HCOOi 1-2_t3-t5⇌CO ₂ (g)+H 1_b4	-0.64	0.33	1.70E+14	7.82E+05	0.50

$\text{HCOO}i 1-2_t3-t5 \rightleftharpoons \text{CO}_2(g) + \text{H} 1_b6$	-0.26	0.19	7.09E+13	1.76E+05	0.50
$\text{HCOO}i 1-2_t3-t5 \rightleftharpoons \text{CO}_2(g) + \text{H} 1_h3$	-0.56	0.18	7.27E+13	6.97E+04	0.50
$\text{HCOO}i 1-2_t5-t4 \rightleftharpoons \text{CO}_2(g) + \text{H} 1_t4$	-0.55	0.07	1.11E+14	2.16E+06	0.50
$\text{HCOO}i 1-2_t2-t2 \rightleftharpoons \text{CO}_2(g) + \text{H} 1_b3$	-0.42	0.09	1.99E+14	9.64E+05	0.09 ^a
$\text{HCOO}i 1-2_t2-t2 \rightleftharpoons \text{CO}_2(g) + \text{H} 1_h3$	-0.15	0.58	8.02E+13	2.27E+05	0.50
$\text{H} + \text{H} \rightleftharpoons \text{H}_2(g)$					
$\text{H} 1_b4 + \text{H} 1_b5 \rightleftharpoons \text{H}_2(g)$	-0.52	0.45	3.62E+13	6.71E+06	0.50
$\text{H} 1_b6 + \text{H} 1_b7 \rightleftharpoons \text{H}_2(g)$	-0.59	0.30	5.45E+13	1.72E+07	0.50
$\text{H} 1_b1 + \text{H} 1_f1 \rightleftharpoons \text{H}_2(g)$	-0.16	0.74	1.15E+12	2.15E+06	0.50
$\text{H} 1_b3 + \text{H} 1_b4 \rightleftharpoons \text{H}_2(g)$	0.01	0.77	7.21E+13	1.57E+07	0.88 ^a
$\text{H} 1_b6 + \text{H} 1_t4 \rightleftharpoons \text{H}_2(g)$	-0.82	0.52	7.42E+12	1.21E+06	0.50
$\text{H} 1_b5 + \text{H} 1_t4 \rightleftharpoons \text{H}_2(g)$	-0.78	0.69	6.67E+12	1.40E+06	0.50
$\text{H} 1_b2 + \text{H} 1_t1 \rightleftharpoons \text{H}_2(g)$	-0.15	0.39	3.23E+12	2.28E+06	0.50
$\text{COOH} \rightleftharpoons \text{CO}_2(g) + \text{H}$					
$\text{COOH} 1_t1 \rightleftharpoons \text{CO}_2(g) + \text{H} 1_f1$	-0.08	1.34	5.27E+15	8.97E+04	0.50
$\text{COOH} 1_t2 \rightleftharpoons \text{CO}_2(g) + \text{H} 1_b3$	-0.05	1.64	1.51E+15	1.13E+05	0.50
$\text{COOH} 1_t3 \rightleftharpoons \text{CO}_2(g) + \text{H} 1_b5$	0.03	0.92	7.44E+15	3.62E+05	0.50
$\text{COOH} 1_t5 \rightleftharpoons \text{CO}_2(g) + \text{H} 1_b6$	0.21	1.03	2.85E+15	2.60E+05	0.50
$\text{COOH} 1_t5 \rightleftharpoons \text{CO}_2(g) + \text{H} 1_b7$	-0.14	0.86	2.86E+15	2.03E+05	0.50
$\text{COOH} 1_t6 \rightleftharpoons \text{CO}_2(g) + \text{H} 1_h3$	-0.15	0.73	1.84E+15	7.74E+04	0.50
$\text{COOH} \rightleftharpoons \text{CO} + \text{OH}$					
$\text{COOH} 1_t1 \rightleftharpoons \text{OH} 1_b3 + \text{CO} 1_t1$	0.31	0.18	2.01E+14	4.79E+12	0.50
$\text{COOH} 1_t2 \rightleftharpoons \text{OH} 1_t2 + \text{CO} 1_t2$	0.48	0.44	3.21E+14	7.65E+12	0.50
$\text{COOH} 1_t4 \rightleftharpoons \text{OH} 1_b6 + \text{CO} 1_t4$	0.56	1.42	1.79E+15	4.87E+13	0.50
$\text{HCOOH} \rightleftharpoons \text{HCOO} + \text{H}$					
$\text{HCOOH} 1_t1 \rightleftharpoons \text{H} 1_f1 + \text{HCOO} 1-2_t1-t1$	0.68	1.20	3.56E+14	1.94E+12	0.50
$\text{HCOOH} 1_t2 \rightleftharpoons \text{H} 1_b3 + \text{HCOO} 1-2_t1-t2$	0.34	1.03	5.91E+14	5.06E+13	0.50
$\text{HCOOH} 1_t2 \rightleftharpoons \text{H} 1_f4 + \text{HCOO} 1-2_t2-t2$	0.72	1.29	1.21E+14	5.04E+12	0.50
$\text{HCOOH} 1_t2 \rightleftharpoons \text{H} 1_h1 + \text{HCOO} 1-2_t2-t2$	0.58	0.80	9.69E+13	4.33E+12	0.50
$\text{HCOOH} 1_t2 \rightleftharpoons \text{H} 1_t1 + \text{HCOO} 1-2_t2-t2$	0.48	0.64	3.00E+14	1.80E+13	0.77 ^a
$\text{HCOOH} 1_t3 \rightleftharpoons \text{H} 1_b3 + \text{HCOO} 1-2_t2-t3$	0.28	1.04	2.01E+14	1.40E+13	0.50
$\text{HCOOH} 1_t3 \rightleftharpoons \text{H} 1_b6 + \text{HCOO} 1-2_t3-t4$	0.72	0.97	2.76E+14	2.96E+13	0.50
$\text{HCOOH} 1_t4 \rightleftharpoons \text{H} 1_b4 + \text{HCOO} 1-2_t3-t4$	0.64	1.26	4.35E+14	1.11E+14	0.50
$\text{HCOOH} \rightleftharpoons \text{COOH} + \text{H}$					
$\text{HCOOH} 1_t1 \rightleftharpoons \text{H} 1_b3 + \text{COOH} 1_t1$	0.47	1.37	1.37E+15	3.30E+14	0.50
$\text{HCOOH} 1_t2 \rightleftharpoons \text{H} 1_b2 + \text{COOH} 1_t2$	0.70	1.20	2.37E+14	4.75E+13	0.50
$\text{HCOOH} 1_t2 \rightleftharpoons \text{H} 1_b4 + \text{COOH} 1_t2$	0.79	1.28	4.42E+13	2.77E+13	0.50
$\text{HCOOH} 1_t4 \rightleftharpoons \text{H} 1_b5 + \text{COOH} 1_t4$	1.32	1.37	1.95E+14	5.61E+13	0.50
$\text{HCOOH} 1_t5 \rightleftharpoons \text{H} 1_b6 + \text{COOH} 1_t5$	1.17	1.45	6.07E+14	2.18E+14	0.50
$\text{HCOOH} 1_t6 \rightleftharpoons \text{H} 1_b3 + \text{COOH} 1_t6$	0.50	1.14	4.34E+14	1.05E+14	0.50
$\text{HCOO} \rightleftharpoons \text{HCOO}i$					
$\text{HCOO} 1-2_t1-t2 \rightleftharpoons \text{HCOO}i 1-2_t1-t2$	0.76	1.05	8.32E+13	1.70E+12	0.77 ^a
$\text{HCOO} 1-2_t2-t2 \rightleftharpoons \text{HCOO}i 1-2_t2-t1$	0.81	1.01	2.50E+13	1.45E+12	0.61 ^a
$\text{HCOO} 1-2_t2-t2 \rightleftharpoons \text{HCOO}i 1-2_t2-t2$	0.74	1.10	2.49E+14	1.27E+13	0.97 ^a

HCOO 1-2_t1-t2 $\rightleftharpoons$ HCOOi 1-2_t2-t1	0.70	0.89	2.84E+13	1.02E+12	0.50
HCOO 1-2_t1-t2 $\rightleftharpoons$ HCOOi 1-2_t2-t2	0.63	0.96	6.92E+13	2.49E+12	0.44 ^a
HCOO 1-2_t1-t1 $\rightleftharpoons$ HCOOi 1-2_t1-t1	0.71	0.71	2.84E+14	3.33E+13	0.50
HCOO 1-2_t4-t5 $\rightleftharpoons$ HCOOi 1-2_t5-t4	0.98	1.05	1.02E+14	1.50E+12	0.50
HCOO 1-2_t3-t4 $\rightleftharpoons$ HCOOi 1-2_t3-t4	0.73	1.15	7.06E+13	3.70E+12	0.50
HCOO 1-2_t3-t4 $\rightleftharpoons$ HCOOi 1-2_t3-t5	0.84	0.83	1.11E+14	9.59E+12	0.50
Diffusions					
CO					
CO 1_b1 $\rightleftharpoons$ CO 1_t1	-0.20	0.07	2.22E+12	2.22E+12	0.50
CO 1_b2 $\rightleftharpoons$ CO 1_t1	0.04	0.14	2.22E+12	2.22E+12	0.50
CO 1_b2 $\rightleftharpoons$ CO 1_t2	-0.33	0.11	2.22E+12	2.22E+12	0.50
CO 1_b3 $\rightleftharpoons$ CO 1_t2	-0.07	0.15	2.22E+12	2.22E+12	0.50
CO 1_b4 $\rightleftharpoons$ CO 1_t2	-0.66	0.06	2.22E+12	2.22E+12	0.50
CO 1_b4 $\rightleftharpoons$ CO 1_t3	-0.03	0.06	2.22E+12	2.22E+12	0.50
CO 1_b7 $\rightleftharpoons$ CO 1_t5	-0.30	0.05	2.22E+12	2.22E+12	0.50
CO 1_f2 $\rightleftharpoons$ CO 1_b3	-0.31	0.10	2.22E+12	2.22E+12	0.50
CO 1_f2 $\rightleftharpoons$ CO 1_t2	-0.38	0.10	2.22E+12	2.22E+12	0.50
CO 1_f2 $\rightleftharpoons$ CO 1_t6	0.26	0.32	2.22E+12	2.22E+12	0.50
CO 1_f4 $\rightleftharpoons$ CO 1_b2	-0.08	0.10	2.22E+12	2.22E+12	0.50
CO 1_f4 $\rightleftharpoons$ CO 1_t1	-0.04	0.10	2.22E+12	2.22E+12	0.50
CO 1_f4 $\rightleftharpoons$ CO 1_t2	-0.41	0.10	2.22E+12	2.22E+12	0.50
CO 1_f4 $\rightleftharpoons$ CO 1_t7	0.00	0.10	2.22E+12	2.22E+12	0.50
CO 1_h3 $\rightleftharpoons$ CO 1_b7	0.07	0.12	2.22E+12	2.22E+12	0.50
CO 1_h3 $\rightleftharpoons$ CO 1_t5	-0.23	0.05	2.22E+12	2.22E+12	0.50
CO 1_h3 $\rightleftharpoons$ CO 1_t6	-0.07	0.05	2.22E+12	2.22E+12	0.50
CO 1_h4 $\rightleftharpoons$ CO 1_b4	0.19	0.25	2.22E+12	2.22E+12	0.50
CO 1_h4 $\rightleftharpoons$ CO 1_f4	-0.06	0.09	2.22E+12	2.22E+12	0.50
CO 1_h4 $\rightleftharpoons$ CO 1_t2	-0.47	0.09	2.22E+12	2.22E+12	0.50
CO 1_h4 $\rightleftharpoons$ CO 1_t3	0.16	0.23	2.22E+12	2.22E+12	0.50
CO 1_h4 $\rightleftharpoons$ CO 1_t7	-0.06	0.09	2.22E+12	2.22E+12	0.50
CO 1_h5 $\rightleftharpoons$ CO 1_b1	-0.19	0.05	2.22E+12	2.22E+12	0.50
CO 1_h5 $\rightleftharpoons$ CO 1_f4	-0.35	0.05	2.22E+12	2.22E+12	0.50
CO 1_h5 $\rightleftharpoons$ CO 1_t1	-0.39	0.05	2.22E+12	2.22E+12	0.50
CO 1_h5 $\rightleftharpoons$ CO 1_t7	-0.35	0.05	2.22E+12	2.22E+12	0.50
CO 1_t1 $\rightleftharpoons$ CO 1_t1	0.00	0.10	2.22E+12	2.22E+12	0.50
CO 1_t2 $\rightleftharpoons$ CO 1_t1	0.37	0.47	2.22E+12	2.22E+12	0.50
CO 1_t2 $\rightleftharpoons$ CO 1_t2	0.00	0.16	2.22E+12	2.22E+12	0.50
CO 1_t3 $\rightleftharpoons$ CO 1_t2	-0.63	0.07	2.22E+12	2.22E+12	0.50
CO 1_t3 $\rightleftharpoons$ CO 1_t3	0.00	0.07	2.22E+12	2.22E+12	0.50
CO 1_t4 $\rightleftharpoons$ CO 1_t3	0.50	0.57	2.22E+12	2.22E+12	0.50
CO 1_t5 $\rightleftharpoons$ CO 1_t3	0.15	0.22	2.22E+12	2.22E+12	0.50
CO 1_t5 $\rightleftharpoons$ CO 1_t4	-0.35	0.09	2.22E+12	2.22E+12	0.50
CO 1_t5 $\rightleftharpoons$ CO 1_t5	0.00	0.09	2.22E+12	2.22E+12	0.50
CO 1_t6 $\rightleftharpoons$ CO 1_t2	-0.64	0.06	2.22E+12	2.22E+12	0.50

CO 1_t6 $\rightleftharpoons$ CO 1_t3	-0.01	0.06	2.22E+12	2.22E+12	0.50
CO 1_t6 $\rightleftharpoons$ CO 1_t5	-0.16	0.06	2.22E+12	2.22E+12	0.50
CO 1_t7 $\rightleftharpoons$ CO 1_t1	-0.04	0.10	2.22E+12	2.22E+12	0.50
CO 1_t7 $\rightleftharpoons$ CO 1_t2	-0.41	0.10	2.22E+12	2.22E+12	0.50
CO 1_t7 $\rightleftharpoons$ CO 1_t3	0.22	0.29	2.22E+12	2.22E+12	0.50
COOH					
COOH 1_b1 $\rightleftharpoons$ COOH 1_t1	-0.30	0.24	2.75E+12	2.75E+12	0.50
COOH 1_b4 $\rightleftharpoons$ COOH 1_t2	-0.45	0.24	2.75E+12	2.75E+12	0.50
COOH 1_b4 $\rightleftharpoons$ COOH 1_t3	0.00	0.24	2.75E+12	2.75E+12	0.50
COOH 1_t1 $\rightleftharpoons$ COOH 1_t1	0.00	0.28	2.75E+12	2.75E+12	0.50
COOH 1_t2 $\rightleftharpoons$ COOH 1_t1	0.15	0.43	2.75E+12	2.75E+12	0.50
COOH 1_t2 $\rightleftharpoons$ COOH 1_t2	0.00	0.30	2.75E+12	2.75E+12	0.50
COOH 1_t3 $\rightleftharpoons$ COOH 1_t2	-0.45	0.24	2.75E+12	2.75E+12	0.50
COOH 1_t3 $\rightleftharpoons$ COOH 1_t3	0.00	0.24	2.75E+12	2.75E+12	0.50
COOH 1_t4 $\rightleftharpoons$ COOH 1_t3	0.17	0.41	2.75E+12	2.75E+12	0.50
COOH 1_t5 $\rightleftharpoons$ COOH 1_t3	0.14	0.38	2.75E+12	2.75E+12	0.50
COOH 1_t5 $\rightleftharpoons$ COOH 1_t4	-0.03	0.26	2.75E+12	2.75E+12	0.50
COOH 1_t5 $\rightleftharpoons$ COOH 1_t5	0.00	0.26	2.75E+12	2.75E+12	0.50
COOH 1_t6 $\rightleftharpoons$ COOH 1_t2	-0.37	0.25	2.75E+12	2.75E+12	0.50
COOH 1_t6 $\rightleftharpoons$ COOH 1_t3	0.08	0.32	2.75E+12	2.75E+12	0.50
COOH 1_t6 $\rightleftharpoons$ COOH 1_t5	-0.06	0.25	2.75E+12	2.75E+12	0.50
COOH 1_t7 $\rightleftharpoons$ COOH 1_t1	-0.48	0.21	2.75E+12	2.75E+12	0.50
COOH 1_t7 $\rightleftharpoons$ COOH 1_t2	-0.63	0.21	2.75E+12	2.75E+12	0.50
COOH 1_t7 $\rightleftharpoons$ COOH 1_t3	-0.18	0.21	2.75E+12	2.75E+12	0.50
H					
H 1_b1 $\rightleftharpoons$ H 1_h5	0.25	0.26	2.93E+13	1.43E+13	0.50
H 1_b1 $\rightleftharpoons$ H 1_t1	0.01	0.30	1.89E+13	1.64E+13	0.50
H 1_b2 $\rightleftharpoons$ H 1_b1	0.14	0.44	1.32E+13	1.85E+13	0.50
H 1_b2 $\rightleftharpoons$ H 1_b4	0.09	0.47	1.39E+13	4.42E+13	0.50
H 1_b2 $\rightleftharpoons$ H 1_f1	0.02	0.05	2.14E+13	7.49E+12	0.50
H 1_b2 $\rightleftharpoons$ H 1_t1	0.15	0.44	1.32E+13	1.62E+13	0.50
H 1_b3 $\rightleftharpoons$ H 1_b4	0.19	0.48	1.58E+13	3.79E+13	0.50
H 1_b4 $\rightleftharpoons$ H 1_h1	0.16	0.18	4.60E+13	8.35E+12	0.50
H 1_b4 $\rightleftharpoons$ H 1_h4	0.17	0.20	3.61E+13	8.28E+12	0.50
H 1_b5 $\rightleftharpoons$ H 1_b4	-0.34	0.05	2.13E+13	4.19E+13	0.50
H 1_b5 $\rightleftharpoons$ H 1_h6	0.24	0.26	2.95E+13	8.19E+12	0.50
H 1_b7 $\rightleftharpoons$ H 1_b6	0.35	0.40	2.33E+13	2.80E+13	0.50
H 1_b7 $\rightleftharpoons$ H 1_h3	0.05	0.12	1.39E+13	6.90E+12	0.50
H 1_f1 $\rightleftharpoons$ H 1_b3	-0.12	0.05	9.51E+12	3.27E+13	0.50
H 1_f2 $\rightleftharpoons$ H 1_b3	-0.40	0.08	4.10E+12	2.22E+13	0.50
H 1_f2 $\rightleftharpoons$ H 1_h1	-0.05	0.05	5.62E+12	1.32E+13	0.50
H 1_f4 $\rightleftharpoons$ H 1_b2	-0.39	0.05	1.26E+13	2.73E+13	0.50
H 1_f4 $\rightleftharpoons$ H 1_h4	-0.13	0.05	9.07E+12	1.27E+13	0.50
H 1_f4 $\rightleftharpoons$ H 1_h5	0.00	0.05	6.16E+12	8.17E+12	0.50

H 1_f5 $\rightleftharpoons$ H 1_h6	0.33	0.35	6.63E+12	1.08E+13	0.50
H 1_h1 $\rightleftharpoons$ H 1_h3	-0.08	0.08	1.35E+13	1.70E+13	0.50
H 1_h4 $\rightleftharpoons$ H 1_f5	0.08	0.09	1.46E+13	6.16E+12	0.50
H 1_t4 $\rightleftharpoons$ H 1_b5	0.08	0.27	5.98E+13	3.14E+13	0.50
H 1_t4 $\rightleftharpoons$ H 1_b6	0.12	0.25	6.72E+13	4.10E+13	0.50
HCOO					
HCOO 1-2_t1-t2 $\rightleftharpoons$ HCOO 1-2_t1-t2	0.00	0.42	3.31E+12	3.31E+12	0.50
HCOO 1-2_t1-t7 $\rightleftharpoons$ HCOO 1-2_t1-t1	-0.19	0.29	3.84E+12	6.32E+11	0.50
HCOO 1-2_t1-t7 $\rightleftharpoons$ HCOO 1-2_t1-t2	-0.69	0.29	3.84E+12	3.06E+12	0.50
HCOO 1-2_t1-t7 $\rightleftharpoons$ HCOO 1-2_t1-t7	0.00	0.29	3.84E+12	3.84E+12	0.50
HCOO 1-2_t2-t2 $\rightleftharpoons$ HCOO 1-2_t1-t2	0.11	0.53	2.29E+12	3.35E+12	0.50
HCOO 1-2_t2-t6 $\rightleftharpoons$ HCOO 1-2_t2-t2	-0.48	0.34	1.77E+12	2.20E+12	0.50
HCOO 1-2_t2-t6 $\rightleftharpoons$ HCOO 1-2_t2-t3	-0.04	0.34	1.77E+12	2.44E+12	0.50
HCOO 1-2_t2-t6 $\rightleftharpoons$ HCOO 1-2_t2-t6	0.00	0.34	1.77E+12	1.77E+12	0.50
HCOO 1-2_t2-t7 $\rightleftharpoons$ HCOO 1-2_t1-t2	-0.64	0.30	2.60E+12	3.14E+12	0.50
HCOO 1-2_t2-t7 $\rightleftharpoons$ HCOO 1-2_t1-t7	0.05	0.34	2.60E+12	3.91E+12	0.50
HCOO 1-2_t2-t7 $\rightleftharpoons$ HCOO 1-2_t2-t3	-0.31	0.30	2.60E+12	2.38E+12	0.50
HCOO 1-2_t3-t4 $\rightleftharpoons$ HCOO 1-2_t3-t3	0.57	0.85	3.28E+12	2.46E+12	0.50
HCOO 1-2_t3-t4 $\rightleftharpoons$ HCOO 1-2_t3-t4	0.00	0.36	3.28E+12	3.28E+12	0.50
HCOO 1-2_t3-t5 $\rightleftharpoons$ HCOO 1-2_t3-t4	-0.27	0.32	3.14E+12	3.32E+12	0.50
HCOO 1-2_t3-t6 $\rightleftharpoons$ HCOO 1-2_t2-t3	-0.35	0.29	2.08E+12	2.50E+12	0.50
HCOO 1-2_t3-t6 $\rightleftharpoons$ HCOO 1-2_t2-t6	-0.31	0.29	2.08E+12	1.81E+12	0.50
HCOO 1-2_t3-t6 $\rightleftharpoons$ HCOO 1-2_t3-t5	-0.21	0.29	2.08E+12	3.19E+12	0.50
HCOO 1-2_t3-t7 $\rightleftharpoons$ HCOO 1-2_t2-t3	-0.47	0.27	1.61E+12	2.33E+12	0.50
HCOO 1-2_t3-t7 $\rightleftharpoons$ HCOO 1-2_t2-t7	-0.16	0.27	1.61E+12	2.57E+12	0.50
HCOO 1-2_t3-t7 $\rightleftharpoons$ HCOO 1-2_t3-t3	-0.03	0.27	1.61E+12	2.40E+12	0.50
HCOO 1-2_t3-t7 $\rightleftharpoons$ HCOO 1-2_t3-t7	0.00	0.27	1.61E+12	1.61E+12	0.50
HCOO 1-2_t4-t5 $\rightleftharpoons$ HCOO 1-2_t3-t4	-0.03	0.36	4.04E+12	3.11E+12	0.50
HCOO 1-2_t4-t5 $\rightleftharpoons$ HCOO 1-2_t3-t5	0.24	0.56	4.04E+12	2.95E+12	0.50
HCOO 1-2_t5-t6 $\rightleftharpoons$ HCOO 1-2_t3-t5	-0.32	0.27	2.01E+12	3.16E+12	0.50
HCOO 1-2_t5-t6 $\rightleftharpoons$ HCOO 1-2_t3-t6	-0.11	0.27	2.01E+12	2.06E+12	0.50
HCOO 1-2_t5-t6 $\rightleftharpoons$ HCOO 1-2_t5-t5	-0.20	0.27	2.01E+12	1.56E+12	0.50
HCOO 1-2_t5-t6 $\rightleftharpoons$ HCOO 1-2_t5-t6	0.00	0.27	2.01E+12	2.01E+12	0.50
HCOOi					
HCOOi 1-2_t1-t2 $\rightleftharpoons$ HCOOi 1-2_t1-t2	0.00	0.28	1.21E+12	1.21E+12	0.50
HCOOi 1-2_t2-t1 $\rightleftharpoons$ HCOOi 1-2_t2-t1	0.00	0.29	2.11E+12	2.11E+12	0.50
HCOOi 1-2_t2-t2 $\rightleftharpoons$ HCOOi 1-2_t1-t2	0.13	0.41	2.07E+12	1.28E+12	0.50
HCOOi 1-2_t2-t2 $\rightleftharpoons$ HCOOi 1-2_t2-t1	0.07	0.36	2.07E+12	2.16E+12	0.50
HCOOi 1-2_t3-t4 $\rightleftharpoons$ HCOOi 1-2_t3-t4	0.00	0.25	3.09E+12	3.09E+12	0.50
HCOOi 1-2_t3-t5 $\rightleftharpoons$ HCOOi 1-2_t3-t4	-0.11	0.24	5.38E+12	3.10E+12	0.50
HCOOi 1-2_t5-t4 $\rightleftharpoons$ HCOOi 1-2_t3-t4	-0.28	0.21	1.14E+12	2.90E+12	0.50
O					
O 1_b4 $\rightleftharpoons$ O 1_t2	0.87	1.20	9.42E+12	9.42E+12	0.50
O 1_b5 $\rightleftharpoons$ O 1_b4	-0.58	0.38	9.42E+12	9.42E+12	0.50

O 1_b5 $\rightleftharpoons$ O 1_t4	0.35	0.67	9.42E+12	9.42E+12	0.50
O 1_b6 $\rightleftharpoons$ O 1_t4	0.42	0.74	9.42E+12	9.42E+12	0.50
O 1_b7 $\rightleftharpoons$ O 1_b6	0.14	0.53	9.42E+12	9.42E+12	0.50
O 1_f1 $\rightleftharpoons$ O 1_t2	1.31	1.64	9.42E+12	9.42E+12	0.50
O 1_f2 $\rightleftharpoons$ O 1_f1	-0.72	0.42	9.42E+12	9.42E+12	0.50
O 1_f2 $\rightleftharpoons$ O 1_t2	0.59	0.92	9.42E+12	9.42E+12	0.50
O 1_f2 $\rightleftharpoons$ O 1_t6	0.49	0.84	9.42E+12	9.42E+12	0.50
O 1_f4 $\rightleftharpoons$ O 1_f1	-0.65	0.43	9.42E+12	9.42E+12	0.50
O 1_f4 $\rightleftharpoons$ O 1_f4	0.00	0.43	9.42E+12	9.42E+12	0.50
O 1_f4 $\rightleftharpoons$ O 1_t2	0.66	0.99	9.42E+12	9.42E+12	0.50
O 1_h2 $\rightleftharpoons$ O 1_b5	-0.44	0.31	9.42E+12	9.42E+12	0.50
O 1_h2 $\rightleftharpoons$ O 1_b6	-0.51	0.31	9.42E+12	9.42E+12	0.50
O 1_h2 $\rightleftharpoons$ O 1_t4	-0.09	0.31	9.42E+12	9.42E+12	0.50
O 1_h3 $\rightleftharpoons$ O 1_b7	-0.17	0.38	9.42E+12	9.42E+12	0.50
O 1_h3 $\rightleftharpoons$ O 1_h2	0.48	0.79	9.42E+12	9.42E+12	0.50
O 1_h3 $\rightleftharpoons$ O 1_t6	0.23	0.58	9.42E+12	9.42E+12	0.50
O 1_h4 $\rightleftharpoons$ O 1_b4	-0.13	0.44	9.42E+12	9.42E+12	0.50
O 1_h4 $\rightleftharpoons$ O 1_f4	0.08	0.51	9.42E+12	9.42E+12	0.50
O 1_h4 $\rightleftharpoons$ O 1_h2	0.89	1.20	9.42E+12	9.42E+12	0.50
O 1_h4 $\rightleftharpoons$ O 1_h4	0.00	0.44	9.42E+12	9.42E+12	0.50
O 1_h4 $\rightleftharpoons$ O 1_t2	0.74	1.07	9.42E+12	9.42E+12	0.50
O 1_h6 $\rightleftharpoons$ O 1_b5	-0.35	0.32	9.42E+12	9.42E+12	0.50
O 1_h6 $\rightleftharpoons$ O 1_h4	-0.80	0.32	9.42E+12	9.42E+12	0.50
O 1_h6 $\rightleftharpoons$ O 1_t4	0.00	0.32	9.42E+12	9.42E+12	0.50
O 1_t2 $\rightleftharpoons$ O 1_t2	0.00	0.33	9.42E+12	9.42E+12	0.50
O 1_t6 $\rightleftharpoons$ O 1_t2	0.10	0.43	9.42E+12	9.42E+12	0.50
OH					
OH 1_b1 $\rightleftharpoons$ OH 1_t1	0.12	0.44	4.92E+12	4.92E+12	0.50
OH 1_b2 $\rightleftharpoons$ OH 1_t1	0.36	0.68	4.92E+12	4.92E+12	0.50
OH 1_b2 $\rightleftharpoons$ OH 1_t2	0.24	0.58	4.92E+12	4.92E+12	0.50
OH 1_b3 $\rightleftharpoons$ OH 1_t2	0.39	0.73	4.92E+12	4.92E+12	0.50
OH 1_b4 $\rightleftharpoons$ OH 1_t2	-0.12	0.32	4.92E+12	4.92E+12	0.50
OH 1_b4 $\rightleftharpoons$ OH 1_t3	0.49	0.74	4.92E+12	4.92E+12	0.50
OH 1_b5 $\rightleftharpoons$ OH 1_t3	0.69	0.94	4.92E+12	4.92E+12	0.50
OH 1_b5 $\rightleftharpoons$ OH 1_t4	0.11	0.45	4.92E+12	4.92E+12	0.50
OH 1_b6 $\rightleftharpoons$ OH 1_t4	-0.20	0.30	4.92E+12	4.92E+12	0.50
OH 1_b6 $\rightleftharpoons$ OH 1_t5	0.25	0.52	4.92E+12	4.92E+12	0.50
OH 1_b7 $\rightleftharpoons$ OH 1_t5	0.19	0.46	4.92E+12	4.92E+12	0.50
OH 1_f1 $\rightleftharpoons$ OH 1_b2	0.09	0.47	4.92E+12	4.92E+12	0.50
OH 1_f1 $\rightleftharpoons$ OH 1_b3	-0.06	0.39	4.92E+12	4.92E+12	0.50
OH 1_f1 $\rightleftharpoons$ OH 1_t1	0.45	0.77	4.92E+12	4.92E+12	0.50
OH 1_f1 $\rightleftharpoons$ OH 1_t2	0.33	0.67	4.92E+12	4.92E+12	0.50
OH 1_f2 $\rightleftharpoons$ OH 1_b3	-0.65	0.30	4.92E+12	4.92E+12	0.50
OH 1_f2 $\rightleftharpoons$ OH 1_t2	-0.26	0.30	4.92E+12	4.92E+12	0.50

OH 1_f2 $\rightleftharpoons$ OH 1_t6	0.49	0.72	4.92E+12	4.92E+12	0.50
OH 1_h2 $\rightleftharpoons$ OH 1_b5	-0.68	0.25	4.92E+12	4.92E+12	0.50
OH 1_h2 $\rightleftharpoons$ OH 1_b6	-0.37	0.25	4.92E+12	4.92E+12	0.50
OH 1_h2 $\rightleftharpoons$ OH 1_t3	0.01	0.26	4.92E+12	4.92E+12	0.50
OH 1_h2 $\rightleftharpoons$ OH 1_t4	-0.57	0.25	4.92E+12	4.92E+12	0.50
OH 1_h2 $\rightleftharpoons$ OH 1_t5	-0.12	0.25	4.92E+12	4.92E+12	0.50
OH 1_t1 $\rightleftharpoons$ OH 1_t1	0.00	0.32	4.92E+12	4.92E+12	0.50
OH 1_t2 $\rightleftharpoons$ OH 1_t1	0.12	0.44	4.92E+12	4.92E+12	0.50
OH 1_t2 $\rightleftharpoons$ OH 1_t2	0.00	0.34	4.92E+12	4.92E+12	0.50
OH 1_t3 $\rightleftharpoons$ OH 1_t2	-0.61	0.25	4.92E+12	4.92E+12	0.50
OH 1_t3 $\rightleftharpoons$ OH 1_t3	0.00	0.25	4.92E+12	4.92E+12	0.50
OH 1_t4 $\rightleftharpoons$ OH 1_t3	0.58	0.83	4.92E+12	4.92E+12	0.50
OH 1_t5 $\rightleftharpoons$ OH 1_t3	0.13	0.38	4.92E+12	4.92E+12	0.50
OH 1_t5 $\rightleftharpoons$ OH 1_t4	-0.45	0.27	4.92E+12	4.92E+12	0.50
OH 1_t5 $\rightleftharpoons$ OH 1_t5	0.00	0.27	4.92E+12	4.92E+12	0.50
OH 1_t6 $\rightleftharpoons$ OH 1_t2	-0.75	0.23	4.92E+12	4.92E+12	0.50
OH 1_t6 $\rightleftharpoons$ OH 1_t3	-0.14	0.23	4.92E+12	4.92E+12	0.50
OH 1_t6 $\rightleftharpoons$ OH 1_t5	-0.27	0.23	4.92E+12	4.92E+12	0.50
OH 1_t7 $\rightleftharpoons$ OH 1_t1	-0.29	0.28	4.92E+12	4.92E+12	0.50
OH 1_t7 $\rightleftharpoons$ OH 1_t2	-0.41	0.28	4.92E+12	4.92E+12	0.50
OH 1_t7 $\rightleftharpoons$ OH 1_t3	0.20	0.45	4.92E+12	4.92E+12	0.50

^a Proximity factors explicitly calculated by fitting BEP relations.

Table S8 List of clusters and their effective cluster interactions (ECI) (eV), for clusters with absolute ECIs above 0.01 eV. Adsorbates are denoted with their name, site type, and representative site number, in the following format: [name][site type]@[site number]. For HCOOi, a bidentate species, the first and second site types bind the O and H dentates of HCOOi respectively. Site numbers are required to unambiguously identify unique clusters; illustrations of the site numberings can be found in Figure S11.

Cluster	ECI /eV	Cluster	ECI /eV
2 Species			
CO t1@11, OH b3@22	-0.40	H f2@39, H h4@64	-0.05
CO t2@1, OH t2@4	-0.10	H f2@39, HCOOi t2@1-t1@11	0.22
CO t4@3, OH b6@32	-0.20	H f2@44, HCOOi t1@11-t2@1	0.48
COOH t1@11, H b3@22	-0.24	H f2@44, HCOOi t3@2-t4@3	0.13
COOH t2@1, H b2@21	-0.18	H f4@48, HCOOi t1@11-t2@1	0.05
COOH t2@16, H b4@26	-0.23	H f4@48, HCOOi t1@11-t2@1	0.18
COOH t6@5, H b3@22	-0.36	H f4@50, HCOOi t2@1-t2@4	-0.21
H b1@19, H b2@20	-0.10	H h1@51, HCOOi t1@11-t2@4	0.26
H b1@19, H b4@26	0.03	H h1@51, HCOOi t2@16-t2@18	0.30
H b1@19, H f1@37	-0.12	H h1@52, HCOOi t1@11-t2@4	0.05
H b1@19, H h1@51	-0.05	H h1@52, HCOOi t3@2-t4@3	0.02
H b1@19, HCOOi t3@2-t3@7	-0.38	H h1@52, HCOOi t2@1-t2@4	0.05
H b1@19, HCOOi t3@2-t4@3	-0.04	H h1@52, HCOOi t2@4-t1@11	0.22
H b1@19, HCOOi t4@3-t5@6	-0.27	H h1@59, HCOOi t4@3-t5@6	-0.25
H b1@19, HCOOi t2@1-t1@11	0.06	H h1@59, HCOOi t2@1-t1@11	-0.06
H b1@19, HCOOi t2@4-t2@1	-0.10	H h1@59, HCOOi t2@1-t2@4	-0.15
H b2@20, H b4@26	0.04	H h3@54, HCOOi t1@11-t1@17	0.48
H b2@20, HCOOi t1@11-t2@1	0.27	H h3@54, HCOOi t2@16-t2@18	-0.23
H b2@20, HCOOi t2@18-t2@16	-0.31	H h3@54, HCOOi t4@3-t5@6	0.15
H b2@20, HCOOi t2@18-t3@14	0.14	H h3@57, HCOOi t1@11-t2@1	0.15
H b2@20, HCOOi t2@1-t2@4	-0.04	H h3@57, HCOOi t1@11-t2@1	0.13
H b2@20, HCOOi t2@1-t3@2	-0.22	H h3@57, HCOOi t2@4-t2@1	-0.15
H b2@20, HCOOi t3@14-t6@10	0.10	H h4@61, H h5@62	0.06
H b2@20, HCOOi t3@2-t4@3	-0.24	H h4@61, HCOOi t3@2-t5@6	0.67
H b2@20, HCOOi t3@7-t5@6	0.32	H h4@61, HCOOi t3@8-t4@15	0.10
H b2@20, HCOOi t4@15-t5@9	-0.31	H h4@64, HCOOi t4@3-t5@6	-0.09
H b2@20, HCOOi t4@3-t5@6	-0.32	H h4@64, HCOOi t1@11-t2@1	0.33
H b2@20, HCOOi t1@11-t2@1	0.45	H h4@66, H h4@64	-0.04
H b2@20, HCOOi t2@16-t2@18	-0.23	H h4@66, HCOOi t1@11-t2@1	0.26
H b2@20, HCOOi t2@18-t2@16	-0.25	H h4@67, HCOOi t1@11-t2@1	0.20
H b2@20, HCOOi t2@1-t1@11	0.16	H h4@67, HCOOi t2@4-t2@1	-0.19
H b2@20, HCOOi t2@1-t2@4	-0.06	H h5@65, HCOOi t1@11-t2@1	-0.08
H b2@20, HCOOi t2@4-t2@1	0.06	H h5@65, HCOOi t2@1-t1@11	0.02
H b2@21, H b2@20	0.47	H h5@65, HCOOi t2@4-t1@11	0.07
H b2@21, H b4@26	0.10	H h5@65, HCOOi t2@4-t2@1	-0.29
H b2@21, H b5@27	0.11	H t1@11, H b2@20	0.26

H b2@21, H b7@31	0.06	H t1@11, H f1@37	0.03
H b2@21, H h1@51	0.04	H t1@11, HCOO t1@17-t2@16	0.07
H b2@21, HCOO t2@18-t3@14	0.23	H t1@11, HCOO t2@1-t2@4	-0.26
H b2@21, HCOO t2@1-t6@5	-0.16	H t1@11, HCOO t3@2-t4@3	0.19
H b2@21, HCOO t3@2-t4@3	0.06	H t1@11, HCOO t2@16-t1@17	0.45
H b2@23, H b3@22	-0.16	H t1@11, HCOO t2@1-t2@4	-0.20
H b2@23, H b4@26	0.05	H t1@17, H b2@20	0.05
H b2@23, H f1@37	0.25	H t1@17, H b5@33	0.13
H b2@23, H h4@61	0.13	H t1@17, H f1@37	0.20
H b2@23, H h5@62	-0.06	H t1@17, H h3@54	0.17
H b2@23, HCOO t1@11-t1@17	-0.48	H t1@17, HCOO t2@1-t2@4	0.06
H b2@23, HCOO t1@11-t2@1	-0.30	H t4@15, H b2@20	-0.13
H b2@23, HCOO t3@2-t7@12	-0.31	H t4@15, H b4@26	-0.09
H b2@23, HCOO t1@11-t2@1	-0.12	H t4@15, H f5@46	-0.25
H b2@23, HCOO t1@17-t1@11	-0.23	H t4@15, H h4@61	-0.18
H b2@23, HCOO t2@1-t1@11	-0.14	H t4@15, H h5@62	-0.25
H b2@24, H b4@26	0.34	H t4@15, H t4@3	-0.05
H b2@24, H h3@54	0.29	H t4@15, HCOO t2@1-t2@4	0.42
H b2@24, H h4@61	0.04	H t4@15, HCOO t2@4-t2@1	0.07
H b2@24, HCOO t1@11-t2@1	-0.33	H t4@3, H b2@20	-0.18
H b2@24, HCOO t1@11-t2@1	-0.13	H t4@3, H b5@29	-0.65
H b2@24, HCOO t2@1-t1@11	-0.18	H t4@3, H b6@32	-0.50
H b3@22, H b4@26	-0.12	H t4@3, H f5@46	-0.03
H b3@22, H b5@27	-0.07	H t4@3, H h1@51	-0.06
H b3@22, H b7@31	-0.06	H t4@3, H h3@54	-0.05
H b3@22, H h5@62	-0.03	H t4@3, H h6@63	-0.49
H b3@22, HCOO t1@17-t2@16	-0.28	H t4@3, H t1@11	0.04
H b3@22, HCOO t2@16-t2@18	0.55	H t4@3, HCOO t2@1-t3@2	0.58
H b3@22, HCOO t2@16-t3@7	0.10	H t4@3, HCOO t3@8-t4@15	0.03
H b3@22, HCOO t2@4-t6@5	0.69	H t4@3, HCOO t1@11-t2@4	0.07
H b3@22, HCOO t3@2-t4@3	-0.23	H t4@3, HCOO t2@4-t1@11	0.02
H b3@22, HCOO t3@2-t6@5	-0.41	HCOO t1@11-t1@17, HCOO t2@1-t2@4	-0.23
H b3@22, HCOO t4@3-t5@6	-0.20	HCOO t1@11-t2@1, HCOO t1@17-t2@16	-0.41
H b3@22, HCOO t1@11-t2@1	0.15	HCOO t1@11-t2@1, HCOO t1@17-t2@18	-0.42
H b3@22, HCOO t1@17-t2@16	-0.10	HCOO t1@11-t2@1, HCOO t3@2-t4@3	-0.31
H b3@22, HCOO t2@16-t1@17	-0.06	HCOO t1@11-t2@1, HCOO t4@3-t5@6	0.10
H b3@22, HCOO t2@16-t2@18	0.33	HCOO t1@11-t2@1, HCOO t1@17-t2@16	-0.23
H b3@22, HCOO t2@1-t1@11	0.31	HCOO t1@11-t2@1, HCOO t1@17-t2@18	-0.23

H b3@25, H b3@22	0.38	HCOO t1@11-t2@1, HCOO t2@16-t1@17	0.04
H b3@25, H b4@26	-0.13	HCOO t1@11-t2@1, HCOO t2@16-t2@18	-0.21
H b3@25, H b5@27	-0.13	HCOO t1@11-t2@1, HCOO t2@18-t1@17	-0.19
H b3@25, H f1@37	-0.07	HCOO t1@11-t2@1, HCOO t2@18-t2@16	-0.23
H b3@25, H f4@45	-0.16	HCOO t1@11-t2@4, HCOO t3@2-t4@3	0.10
H b3@25, H h1@51	-0.07	HCOO t1@11-t2@4, HCOO t4@3-t5@6	-0.28
H b3@25, H h3@54	-0.07	HCOO t1@11-t7@12, HCOO t1@17-t2@16	-0.12
H b3@25, H h4@61	-0.08	HCOO t1@11-t7@12, HCOO t1@17-t2@18	-0.35
H b4@26, H b5@27	0.05	HCOO t1@11-t7@12, HCOO t2@16-t1@17	-0.10
H b4@26, H h3@54	0.06	HCOO t1@11-t7@12, HCOO t2@16-t2@18	-0.28
H b4@26, H h4@64	0.03	HCOO t1@11-t7@12, HCOO t2@18-t1@17	-0.38
H b4@26, HCOO t1@11-t2@4	0.10	HCOO t1@11-t7@12, HCOO t2@18-t2@16	-0.25
H b4@26, HCOO t2@1-t2@4	-0.23	HCOO t1@17-t1@11, HCOO t2@1-t2@4	-0.23
H b4@26, HCOO t2@1-t3@2	-0.23	HCOO t2@1-t2@4, HCOO t1@11-t1@17	-0.26
H b4@26, HCOO t2@1-t6@5	-0.41	HCOO t2@1-t2@4, HCOO t1@17-t2@16	-0.25
H b4@26, HCOO t4@3-t5@6	-0.30	HCOO t2@1-t2@4, HCOO t3@2-t6@5	-0.62
H b4@26, HCOO t1@11-t2@1	0.08	HCOO t2@1-t2@4, HCOO t3@7-t6@10	-0.33
H b4@26, HCOO t1@11-t2@4	0.05	HCOO t2@1-t2@4, HCOO t1@17-t2@16	0.43
H b4@26, HCOO t2@1-t1@11	-0.02	HCOO t2@1-t2@4, HCOO t2@16-t1@17	0.02
H b4@26, HCOO t2@1-t2@4	-0.24	HCOO t2@1-t3@2, HCOO t1@11-t2@4	-0.36
H b4@26, HCOO t2@4-t1@11	-0.08	HCOO t2@1-t3@2, HCOO t1@17-t2@16	0.05
H b4@26, HCOO t2@4-t2@1	-0.28	HCOO t2@1-t3@2, HCOO t3@14-t6@10	-0.23
H b4@28, H b4@26	0.10	HCOO t2@1-t3@2, HCOO t4@15-t5@9	0.33
H b4@28, H f1@37	0.12	HCOO t2@1-t3@2, HCOO t4@3-t5@6	-0.30
H b4@28, H f2@39	-0.33	HCOO t2@1-t3@2, HCOO t1@17-t2@16	-0.10
H b4@28, HCOO t1@11-t1@17	-0.51	HCOO t2@1-t3@2, HCOO t2@16-t2@18	-0.15

H b4@28, HCOO t2@1-t3@2	0.11	HCOO t2@1-t3@2, HCOOi t2@18-t2@16	-0.12
H b4@35, H b4@26	0.10	HCOO t2@1-t3@2, HCOOi t2@4-t1@11	-0.15
H b4@35, H b5@27	0.17	HCOO t2@1-t6@5, HCOOi t1@11-t2@4	-0.08
H b4@35, HCOO t1@11-t2@1	-0.18	HCOO t2@1-t6@5, HCOOi t1@17-t2@16	0.07
H b4@35, HCOO t1@11-t7@12	-0.46	HCOO t2@1-t6@5, HCOOi t1@17-t2@18	0.03
H b4@35, HCOO t2@1-t2@4	-0.23	HCOO t2@1-t6@5, HCOOi t2@16-t1@17	0.14
H b4@35, HCOOi t2@1-t1@11	-0.07	HCOO t2@1-t6@5, HCOOi t2@16-t2@18	0.15
H b4@35, HCOOi t2@1-t2@4	-0.19	HCOO t2@1-t6@5, HCOOi t2@18-t1@17	0.06
H b4@35, HCOOi t2@4-t2@1	-0.15	HCOO t2@1-t6@5, HCOOi t2@18-t2@16	0.08
H b4@36, H b6@30	-0.07	HCOO t2@1-t6@5, HCOOi t2@4-t1@11	-0.06
H b4@36, H h4@61	0.04	HCOO t2@1-t7@12, HCOO t2@4-t7@13	-0.15
H b4@36, HCOO t3@2-t4@3	-0.47	HCOO t2@1-t7@12, HCOOi t1@11-t2@4	-0.02
H b4@36, HCOO t3@2-t5@6	0.88	HCOO t2@1-t7@12, HCOOi t1@17-t2@16	0.06
H b4@36, HCOO t4@3-t5@6	-0.31	HCOO t2@1-t7@12, HCOOi t1@17-t2@18	-0.38
H b4@36, HCOOi t1@11-t2@1	0.24	HCOO t2@1-t7@12, HCOOi t2@16-t2@18	-0.20
H b4@36, HCOOi t2@1-t1@11	0.04	HCOO t2@1-t7@12, HCOOi t2@18-t1@17	-0.41
H b5@27, H b6@30	-0.50	HCOO t2@1-t7@12, HCOOi t2@18-t2@16	-0.21
H b5@27, H h1@52	0.07	HCOO t2@1-t7@12, HCOOi t2@4-t1@11	-0.06
H b5@27, HCOO t1@17-t2@16	0.08	HCOO t3@2-t4@3, HCOO t4@15-t5@9	-0.25
H b5@27, HCOO t2@1-t2@4	-0.32	HCOO t3@2-t4@3, HCOO t5@6-t6@5	-0.11
H b5@27, HCOO t2@1-t7@12	-0.17	HCOO t3@2-t4@3, HCOOi t1@11-t2@1	-0.07
H b5@27, HCOO t3@2-t4@3	-0.05	HCOO t3@2-t4@3, HCOOi t1@11-t2@4	0.10
H b5@27, HCOO t4@3-t5@6	-0.26	HCOO t3@2-t4@3, HCOOi t1@17-t2@16	0.24
H b5@27, HCOOi t1@11-t2@1	0.06	HCOO t3@2-t4@3, HCOOi t2@16-t1@17	0.21
H b5@27, HCOOi t1@11-t2@4	0.06	HCOO t3@2-t4@3, HCOOi t2@18-t2@16	-0.05

H b5@27, HCOOi t2@16-t1@17	-0.10	HCOO t3@2-t4@3, HCOOi t2@1-t1@11	-0.10
H b5@27, HCOOi t2@1-t1@11	-0.09	HCOO t3@2-t4@3, HCOOi t2@1-t2@4	-0.16
H b5@27, HCOOi t2@1-t2@4	-0.25	HCOO t3@2-t4@3, HCOOi t2@4-t2@1	-0.15
H b5@27, HCOOi t2@4-t1@11	-0.06	HCOO t3@2-t5@6, HCOOi t1@11-t2@1	-0.10
H b5@27, HCOOi t2@4-t2@1	-0.24	HCOO t3@2-t5@6, HCOOi t1@11-t2@4	0.13
H b5@29, HCOO t3@2-t3@7	-0.04	HCOO t3@2-t5@6, HCOOi t2@1-t1@11	-0.15
H b5@29, HCOO t3@2-t5@6	-0.28	HCOO t3@2-t5@6, HCOOi t2@1-t2@4	-0.58
H b5@29, HCOO t4@3-t5@6	-0.71	HCOO t3@2-t5@6, HCOOi t2@4-t1@11	-0.13
H b5@33, H b5@27	-0.62	HCOO t3@2-t5@6, HCOOi t2@4-t2@1	-1.06
H b5@33, H h3@54	0.06	HCOO t3@2-t6@5, HCOOi t1@11-t2@1	-0.06
H b5@33, HCOO t2@18-t7@13	-0.07	HCOO t3@2-t6@5, HCOOi t1@17-t2@16	-0.24
H b5@33, HCOO t2@1-t2@4	-0.34	HCOO t3@2-t6@5, HCOOi t2@16-t1@17	-0.08
H b5@33, HCOOi t2@1-t2@4	-0.26	HCOO t3@2-t6@5, HCOOi t2@16-t2@18	-0.24
H b5@33, HCOOi t2@4-t2@1	-0.27	HCOO t3@2-t6@5, HCOOi t2@18-t2@16	-0.28
H b5@34, H h1@51	0.17	HCOO t3@2-t6@5, HCOOi t2@1-t1@11	-0.09
H b5@34, HCOO t5@6-t6@5	-0.19	HCOO t3@2-t6@5, HCOOi t2@1-t2@4	-0.21
H b5@34, HCOOi t2@1-t1@11	-0.12	HCOO t3@2-t6@5, HCOOi t2@4-t2@1	-0.25
H b6@30, HCOO t1@11-t1@17	-0.47	HCOO t3@2-t7@12, HCOO t4@3-t5@6	0.55
H b6@30, HCOO t1@11-t2@1	-0.20	HCOO t3@2-t7@12, HCOOi t1@17-t2@18	0.10
H b6@30, HCOO t1@11-t2@4	-0.25	HCOO t3@2-t7@12, HCOOi t2@18-t1@17	-0.05
H b6@30, HCOO t4@3-t5@6	-0.28	HCOO t3@2-t7@12, HCOOi t2@1-t1@11	0.09
H b6@30, HCOOi t1@11-t2@1	0.03	HCOO t3@2-t7@12, HCOOi t2@1-t2@4	0.23
H b6@30, HCOOi t1@11-t2@4	0.09	HCOO t3@7-t6@10, HCOO t3@2-t4@3	-0.14
H b6@30, HCOOi t2@1-t2@4	-0.11	HCOO t3@7-t7@12, HCOOi t1@17-t2@16	0.05
H b6@30, HCOOi t2@4-t1@11	0.13	HCOO t3@7-t7@12, HCOOi t2@18-t2@16	-0.05
H b6@30, HCOOi t2@4-t2@1	-0.12	HCOO t3@8-t6@5, HCOOi t1@11-t2@1	-0.17
H b6@32, H h1@51	0.14	HCOO t3@8-t6@5, HCOOi t2@1-t1@11	-0.24
H b6@32, HCOO t2@4-t3@8	0.23	HCOO t4@3-t5@6, HCOO t1@11-t1@17	0.29

H b6@32, HCOO t3@2-t4@3	-0.72	HCOO t4@3-t5@6, HCOO t4@15-t5@9	-0.25
H b6@32, HCOO t3@8-t4@15	-0.37	HCOO t4@3-t5@6, HCOO t1@11-t2@1	-0.07
H b7@31, H f1@37	0.03	HCOO t4@3-t5@6, HCOO t1@11-t2@4	-0.07
H b7@31, H f4@45	0.43	HCOO t4@3-t5@6, HCOO t2@1-t1@11	-0.07
H b7@31, H h5@62	0.38	HCOO t4@3-t5@6, HCOO t2@1-t2@4	0.18
H b7@31, HCOO t1@11-t1@17	0.21	HCOO t4@3-t5@6, HCOO t2@4-t1@11	-0.06
H b7@31, HCOO t1@11-t2@1	0.12	HCOO t4@3-t5@6, HCOO t2@4-t2@1	0.35
H b7@31, HCOO t2@1-t2@4	-0.35	HCOO t5@6-t5@9, HCOO t1@11-t2@1	-0.09
H b7@31, HCOO t2@1-t3@2	-0.35	HCOO t5@6-t5@9, HCOO t2@1-t1@11	-0.15
H b7@31, HCOO t4@3-t5@6	-0.16	HCOO t5@6-t5@9, HCOO t2@1-t2@4	-0.25
H b7@31, HCOO t1@11-t1@17	0.07	HCOO t5@6-t6@5, HCOO t1@11-t1@17	-0.13
H b7@31, HCOO t2@1-t1@11	-0.08	HCOO t5@6-t6@5, HCOO t1@11-t2@1	-0.12
H b7@31, HCOO t2@1-t2@4	-0.26	HCOO t5@6-t6@5, HCOO t1@11-t2@4	-0.13
H f1@37, HCOO t2@16-t2@18	0.04	HCOO t5@6-t6@5, HCOO t1@17-t2@16	0.04
H f1@37, HCOO t4@3-t5@6	0.15	HCOO t5@6-t6@5, HCOO t2@16-t1@17	0.03
H f1@37, HCOO t2@16-t2@18	0.02	HCOO t5@6-t6@5, HCOO t2@16-t2@18	-0.08
H f1@38, H f1@37	-0.19	HCOO t5@6-t6@5, HCOO t2@18-t1@17	-0.05
H f1@38, H h3@54	0.15	HCOO t5@6-t6@5, HCOO t2@18-t2@16	-0.11
H f1@38, HCOO t1@11-t1@17	-0.43	HCOO t5@6-t6@5, HCOO t2@1-t1@11	-0.19
H f1@38, HCOO t1@11-t2@1	-0.30	HCOO t5@6-t6@5, HCOO t2@1-t2@4	-0.18
H f1@38, HCOO t1@11-t2@1	-0.12	HCOO t5@6-t6@5, HCOO t2@4-t1@11	-0.20
H f1@38, HCOO t2@1-t1@11	0.12		
3 Species			
H b1@19, H b2@20, H b5@33	-0.19	H b4@26, HCOO t1@11-t1@17, HCOO t2@18-t2@16	0.14
H b1@19, H b2@20, H b5@34	-0.12	H b4@26, HCOO t1@11-t2@1, HCOO t1@17-t2@16	0.05
H b1@19, H b2@20, H h1@52	-0.07	H b4@26, HCOO t1@11-t2@1, HCOO t2@16-t2@18	0.28
H b1@19, H b2@20, HCOO t4@15-t5@9	0.18	H b4@26, HCOO t1@11-t2@1, HCOO t3@8-t4@15	0.13
H b1@19, H b2@20, HCOO t4@3-t5@6	0.09	H b4@26, HCOO t1@11-t2@1, HCOO t2@16-t2@18	0.19

H b1@19, H b2@21, H b2@20	0.24	H b4@26, HCOO t1@17-t1@11, HCOO t2@16-t2@18	0.33
H b1@19, H b2@23, H b2@21	-0.12	H b4@26, HCOO t1@17-t1@11, HCOO t2@18-t2@16	0.14
H b1@19, H b3@22, HCOO t4@15- t5@9	0.10	H b4@26, HCOO t1@17-t2@16, HCOO t2@1-t2@4	0.23
H b1@19, H b3@22, HCOO t1@11- t2@1	0.05	H b4@26, HCOO t1@17-t2@16, HCOO t2@4-t2@1	0.33
H b1@19, H b3@25, HCOO t1@11- t2@1	0.05	H b4@26, HCOO t2@1-t2@4, HCOO t3@14-t4@15	0.21
H b1@19, H b4@26, H f1@38	-0.08	H b4@26, HCOO t2@1-t2@4, HCOO t2@16-t1@17	0.18
H b1@19, H b4@26, HCOO t2@1- t3@2	0.02	H b4@26, HCOO t2@1-t3@2, HCOO t1@11-t2@4	0.19
H b1@19, H b4@36, H b5@33	-0.29	H b4@26, HCOO t2@1-t3@2, HCOO t2@16-t2@18	0.14
H b1@19, H b4@36, HCOO t4@15- t5@9	0.10	H b4@26, HCOO t2@1-t6@5, HCOO t2@16-t2@18	0.42
H b1@19, H b4@36, HCOO t2@18- t2@16	0.45	H b4@26, HCOO t2@4-t2@1, HCOO t1@17-t2@16	0.49
H b1@19, H b5@29, HCOO t4@3- t5@6	0.10	H b4@26, HCOO t2@4-t2@1, HCOO t4@15-t5@9	0.11
H b1@19, H b5@34, HCOO t3@14- t4@15	-0.08	H b4@26, HCOO t2@4-t2@1, HCOO t4@3-t5@6	0.21
H b1@19, H b5@34, HCOO t3@8- t4@15	-0.27	H b4@26, HCOO t2@4-t2@1, HCOO t2@16-t1@17	0.18
H b1@19, H f1@38, H f1@37	0.03	H b4@26, HCOO t3@14-t4@15, HCOO t2@1-t2@4	0.38
H b1@19, H f1@38, HCOO t1@11- t2@1	0.25	H b4@26, HCOO t3@7-t4@3, HCOO t4@15-t5@9	0.12
H b1@19, HCOO t1@11-t2@1, HCOO t1@17-t2@18	0.27	H b4@26, HCOO t3@7-t4@3, HCOO t2@4-t2@1	0.09
H b1@19, HCOO t1@11-t2@4, HCOO t4@3-t5@6	0.03	H b4@26, HCOO t4@15-t5@9, HCOO t1@17-t2@16	0.37
H b1@19, HCOO t1@17-t2@18, HCOO t2@1-t2@4	0.30	H b4@28, H b5@27, HCOO t1@17- t2@16	0.09
H b1@19, HCOO t2@16-t2@18, HCOO t1@11-t2@1	0.28	H b4@28, H b5@27, HCOO t2@18- t2@16	0.11
H b1@19, HCOO t2@1-t2@4, HCOO t2@18-t2@16	0.04	H b4@28, H b5@27, HCOO t2@4- t2@1	0.09
H b1@19, HCOO t2@1-t2@4, HCOO t4@3-t5@6	0.02	H b4@28, H b5@27, HCOO t2@4- t2@1	0.21
H b1@19, HCOO t2@1-t2@4, HCOO t2@16-t2@18	0.16	H b4@28, H b6@30, HCOO t1@11- t1@17	0.14
H b1@19, HCOO t2@4-t2@1, HCOO t2@16-t2@18	0.16	H b4@28, H b6@30, HCOO t1@11- t2@4	0.21
H b1@19, HCOO t4@3-t5@6, HCOO t4@15-t5@9	0.27	H b4@28, H b6@32, HCOO t1@11- t1@17	0.34
H b2@20, H b2@21, HCOO t1@11- t1@17	0.34	H b4@28, H b7@31, HCOO t2@16- t2@18	0.06

H b2@20, H b2@21, HCOO t2@16-t2@18	0.19	H b4@28, H f1@38, HCOO t1@11-t1@17	0.54
H b2@20, H b2@21, HCOO t2@4-t2@1	0.02	H b4@28, H f1@38, HCOO t3@2-t4@3	-0.13
H b2@20, H b2@23, H b6@32	-0.20	H b4@28, HCOO t1@11-t1@17,	0.19
H b2@20, H b2@23, HCOO t1@11-t1@17	0.13	H b4@28, HCOO t1@11-t1@17,	0.27
H b2@20, H b2@23, HCOO t1@11-t2@1	0.52	H b4@28, HCOO t1@11-t2@1,	0.21
H b2@20, H b2@23, HCOO t2@1-t2@4	0.08	HCOO t3@7-t4@3	0.19
H b2@20, H b2@24, H b4@28	-0.19	H b4@28, HCOO t1@17-t1@11,	0.27
H b2@20, H b2@24, H b5@29	-0.06	HCOO t2@1-t2@4	0.24
H b2@20, H b2@24, HCOO t2@1-t2@4	0.11	H b4@28, HCOO t1@17-t2@16,	0.36
H b2@20, H b3@22, H b4@35	0.13	HCOO t2@4-t2@1	0.12
H b2@20, H b3@22, H b4@36	-0.09	H b4@28, HCOO t1@17-t2@18,	0.03
H b2@20, H b3@22, H b5@34	0.04	HCOO t1@11-t2@1	0.27
H b2@20, H b3@22, H b6@30	0.39	H b4@28, HCOO t2@16-t2@18,	0.23
H b2@20, H b3@22, HCOO t1@11-t1@17	-0.38	HCOO t2@4-t2@1	0.27
H b2@20, H b3@22, HCOO t1@11-t2@1	0.09	H b4@28, HCOO t2@18-t2@16,	0.23
H b2@20, H b3@22, HCOO t4@3-t5@6	0.26	HCOO t2@4-t2@1	0.22
H b2@20, H b3@25, H b6@30	-0.06	H b4@28, HCOO t2@1-t2@4,	0.26
H b2@20, H b4@26, H b4@35	-0.07	HCOO t1@11-t1@17	0.22
H b2@20, H b4@26, H b5@33	-0.34	H b4@28, HCOO t2@1-t2@4,	0.18
H b2@20, H b4@26, HCOO t2@18-t2@16	0.03	HCOO t1@17-t2@16	0.09
H b2@20, H b4@26, HCOO t2@1-t2@4	0.07	H b4@28, HCOO t2@1-t2@4,	0.04
H b2@20, H b4@26, HCOO t3@14-t4@15	0.14	HCOO t2@18-t2@16	0.18
H b2@20, H b4@26, HCOO t4@15-t5@9	0.16	H b4@28, HCOO t2@1-t6@5,	0.09
H b2@20, H b4@26, HCOO t4@3-t5@6	0.09	HCOO t3@2-t4@3	-0.06
H b2@20, H b4@35, HCOO t2@18-t2@16	0.11	H b4@28, HCOO t2@4-t2@1,	0.03
		H b4@28, HCOO t2@16-t2@18	
		H b4@28, HCOO t2@4-t2@1,	
		H b4@35, H b5@27, HCOO t3@2-t4@3	
		H b4@35, H b5@33, HCOO t2@1-t2@4	

H b2@20, H b4@35, HCOO t3@8-t4@15	0.15	H b4@35, H b5@33, HCOO t2@4-t2@1	0.18
H b2@20, H b4@36, HCOO t2@16-t2@18	0.06	H b4@35, H b7@31, HCOO t2@1-t2@4	0.26
H b2@20, H b5@27, H b5@33	-0.02	H b4@35, H b7@31, HCOO t2@1-t2@4	0.24
H b2@20, H b5@27, H b6@30	-0.21	H b4@35, HCOO t3@8-t4@15, HCOO t1@11-t2@1	0.20
H b2@20, H b5@27, HCOO t2@18-t2@16	0.09	H b4@35, HCOO t4@15-t5@9, HCOO t2@1-t2@4	0.14
H b2@20, H b5@27, HCOO t4@15-t5@9	0.12	H b4@35, HCOO t4@3-t5@6, HCOO t2@1-t2@4	0.40
H b2@20, H b5@27, HCOO t4@3-t5@6	0.05	H b4@35, HCOO t4@3-t5@6, HCOO t3@8-t4@15	0.28
H b2@20, H b5@27, HCOO t2@18-t2@16	0.10	H b4@35, HCOO t4@3-t5@6, HCOO t4@15-t5@9	0.27
H b2@20, H b5@33, HCOO t2@18-t2@16	0.05	H b4@36, H b5@27, HCOO t2@4-t2@1	0.20
H b2@20, H b5@33, HCOO t2@1-t2@4	0.18	H b4@36, H b5@27, HCOO t2@1-t2@4	0.20
H b2@20, H b5@33, HCOO t3@14-t4@15	0.03	H b4@36, H b5@27, HCOO t2@4-t2@1	0.20
H b2@20, H b5@33, HCOO t4@15-t5@9	0.09	H b4@36, H b6@30, HCOO t3@2-t4@3	0.23
H b2@20, H b5@33, HCOO t2@18-t2@16	0.15	H b4@36, HCOO t1@11-t1@17, HCOO t3@2-t4@3	0.15
H b2@20, H b6@30, H b4@35	-0.19	H b4@36, HCOO t3@14-t4@15, HCOO t3@2-t4@3	0.07
H b2@20, H b6@30, HCOO t2@4-t2@1	0.30	H b4@36, HCOO t3@2-t4@3, HCOO t1@11-t2@1	0.41
H b2@20, H b7@31, HCOO t2@1-t2@4	0.03	H b4@36, HCOO t3@2-t4@3, HCOO t2@1-t2@4	0.41
H b2@20, H b7@31, HCOO t2@1-t3@2	0.21	H b4@36, HCOO t3@2-t4@3, HCOO t2@1-t2@4	0.59
H b2@20, H b7@31, HCOO t4@3-t5@6	0.11	H b4@36, HCOO t3@2-t4@3, HCOO t2@4-t2@1	0.27
H b2@20, H f1@38, HCOO t1@11-t2@1	0.08	H b5@27, H b5@29, HCOO t2@1-t3@2	-0.03
H b2@20, H h1@59, HCOO t2@1-t2@4	0.05	H b5@27, H b5@29, HCOO t4@3-t5@6	0.09
H b2@20, H h3@57, HCOO t2@16-t2@18	0.07	H b5@27, H b5@33, H f1@37	0.24
H b2@20, H h4@66, HCOO t1@17-t2@18	0.04	H b5@27, H b5@33, HCOO t1@11-t1@17	0.02
H b2@20, H h5@62, HCOO t2@1-t2@4	-0.15	H b5@27, H b5@33, HCOO t2@1-t2@4	0.20
H b2@20, HCOO t1@11-t1@17, HCOO t2@1-t2@4	0.40	H b5@27, H b5@33, HCOO t4@15-t5@9	1.01
H b2@20, HCOO t1@11-t1@17, HCOO t2@4-t2@1	0.25	H b5@27, H b5@33, HCOO t4@3-t5@6	0.18

H b2@20, HCOO t1@11-t2@1, HCOO t2@4-t3@8	0.09	H b5@27, H b6@30, H b5@33	0.73
H b2@20, HCOO t1@17-t1@11, HCOO t2@1-t2@4	0.40	H b5@27, H b6@30, HCOO t3@8- t4@15	1.00
H b2@20, HCOO t1@17-t1@11, HCOO t2@4-t2@1	0.25	H b5@27, H b6@30, HCOO t4@3- t5@6	0.17
H b2@20, HCOO t1@17-t2@16, HCOO t2@1-t2@4	0.24	H b5@27, H f1@38, HCOO t3@2-t4@3	-0.10
H b2@20, HCOO t1@17-t2@16, HCOO t2@4-t2@1	0.42	H b5@27, HCOO t1@11-t2@1, HCOO t2@18-t3@14	0.09
H b2@20, HCOO t1@17-t2@18, HCOO t2@1-t2@4	0.36	H b5@27, HCOO t1@11-t2@1, HCOO t3@8-t4@15	0.07
H b2@20, HCOO t1@17-t2@18, HCOO t2@4-t2@1	0.19	H b5@27, HCOO t1@11-t2@1, HCOO t4@15-t5@9	0.17
H b2@20, HCOO t2@1-t2@4, HCOO t1@11-t1@17	0.12	H b5@27, HCOO t1@11-t2@1, HCOO t2@18-t2@16	0.02
H b2@20, HCOO t2@1-t2@4, HCOO t3@2-t4@3	0.12	H b5@27, HCOO t1@11-t2@4, HCOO t2@16-t2@18	0.04
H b2@20, HCOO t2@1-t2@4, HCOO t4@3-t5@6	0.09	H b5@27, HCOO t1@11-t2@4, HCOO t3@8-t4@15	0.17
H b2@20, HCOO t2@1-t3@2, HCOO t4@3-t5@6	0.35	H b5@27, HCOO t1@11-t2@4, HCOO t2@16-t1@17	0.10
H b2@20, HCOO t2@4-t2@1, HCOO t3@14-t4@15	0.08	H b5@27, HCOO t1@11-t2@4, HCOO t2@16-t2@18	0.12
H b2@20, HCOO t3@14-t4@15, HCOO t2@18-t2@16	0.03	H b5@27, HCOO t1@17-t2@16, HCOO t2@1-t2@4	0.11
H b2@20, HCOO t3@2-t4@3, HCOO t1@17-t2@16	0.54	H b5@27, HCOO t2@16-t2@18, HCOO t2@1-t2@4	0.32
H b2@20, HCOO t3@2-t4@3, HCOO t2@16-t2@18	0.23	H b5@27, HCOO t2@16-t2@18, HCOO t2@4-t1@11	0.05
H b2@20, HCOO t3@2-t4@3, HCOO t4@15-t5@9	0.45	H b5@27, HCOO t2@16-t2@18, HCOO t2@4-t2@1	0.20
H b2@20, HCOO t3@2-t4@3, HCOO t2@16-t2@18	0.39	H b5@27, HCOO t2@18-t2@16, HCOO t2@1-t2@4	0.32
H b2@20, HCOO t3@2-t4@3, HCOO t2@18-t2@16	0.19	H b5@27, HCOO t2@18-t2@16, HCOO t2@4-t1@11	0.05
H b2@20, HCOO t3@2-t4@3, HCOO t2@1-t2@4	0.15	H b5@27, HCOO t2@18-t2@16, HCOO t2@4-t2@1	0.20
H b2@20, HCOO t4@15-t5@9, HCOO t1@17-t2@16	0.32	H b5@27, HCOO t2@1-t2@4, HCOO t2@16-t1@17	0.02
H b2@20, HCOO t4@15-t5@9, HCOO t2@18-t2@16	0.20	H b5@27, HCOO t2@1-t2@4, HCOO t2@16-t2@18	0.18
H b2@20, HCOO t4@15-t5@9, HCOO t2@18-t2@16	0.09	H b5@27, HCOO t2@1-t2@4, HCOO t2@18-t2@16	0.23
H b2@20, HCOO t4@3-t5@6, HCOO t2@16-t2@18	0.32	H b5@27, HCOO t2@4-t2@1, HCOO t1@17-t2@18	0.04
H b2@20, HCOO t4@3-t5@6, HCOO t3@8-t4@15	0.02	H b5@27, HCOO t2@4-t2@1, HCOO t2@16-t2@18	0.25
H b2@20, HCOO t4@3-t5@6, HCOO t4@15-t5@9	0.37	H b5@27, HCOO t2@4-t2@1, HCOO t4@3-t5@6	0.07

H b2@21, H b2@23, H b7@31	-0.03	H b5@27, HCOO t2@4-t2@1, HCOO i t2@16-t1@17	0.02
H b2@21, H b2@23, HCOO t3@8- t4@15	0.44	H b5@27, HCOO t2@4-t2@1, HCOO i t2@16-t2@18	0.18
H b2@21, H b5@27, HCOO t2@4- t2@1	0.18	H b5@27, HCOO t2@4-t2@1, HCOO i t2@18-t2@16	0.23
H b2@21, H b5@29, HCOO t3@2- t4@3	0.07	H b5@27, HCOO t2@4-t3@8, HCOO t2@16-t2@18	-0.03
H b2@21, HCOO t2@4-t2@1, HCOO t4@3-t5@6	0.07	H b5@27, HCOO t2@4-t3@8, HCOO i t2@18-t2@16	0.15
H b2@21, HCOO t2@4-t2@1, HCOO t5@6-t6@5	0.11	H b5@27, HCOO t3@8-t4@15, HCOO i t2@1-t2@4	0.15
H b2@21, HCOO t3@14-t4@15, HCOO t4@3-t5@6	0.45	H b5@27, HCOO t3@8-t4@15, HCOO i t2@4-t1@11	0.03
H b2@23, H b2@20, HCOO t4@3- t5@6	0.14	H b5@27, HCOO t3@8-t4@15, HCOO i t2@4-t2@1	0.31
H b2@23, H b3@22, H h4@64	0.18	H b5@27, HCOO t4@3-t5@6, HCOO t2@16-t2@18	0.10
H b2@23, H b3@22, HCOO t1@11- t1@17	0.12	H b5@27, HCOO t4@3-t5@6, HCOO t3@8-t4@15	0.35
H b2@23, H b3@22, HCOO t1@11- t2@1	0.53	H b5@27, HCOO t4@3-t5@6, HCOO t4@15-t5@9	0.09
H b2@23, H b3@22, HCOO t1@17- t2@16	0.08	H b5@29, H b5@27, HCOO t2@18- t2@16	0.05
H b2@23, H b3@22, HCOO t4@15- t5@9	0.19	H b5@29, H b5@27, HCOO i t2@18- t2@16	0.06
H b2@23, H b3@22, HCOO i t1@11- t2@1	0.03	H b5@29, H b5@33, HCOO t3@14- t4@15	0.03
H b2@23, H b3@25, H b2@20	0.05	H b5@29, H b6@30, HCOO t4@3- t5@6	0.09
H b2@23, H b3@25, HCOO t1@11- t2@1	0.74	H b5@29, H b7@31, HCOO t1@11- t2@4	-0.17
H b2@23, H b4@26, HCOO t1@11- t1@17	0.18	H b5@29, H b7@31, HCOO t2@18- t2@16	0.09
H b2@23, H b4@28, HCOO t1@11- t1@17	0.21	H b5@29, HCOO t2@1-t2@4, HCOO t4@3-t5@6	0.14
H b2@23, H b6@30, H b5@27	-0.10	H b5@29, HCOO t4@3-t5@6, HCOO t2@16-t3@7	0.32
H b2@23, H b6@30, HCOO t1@11- t1@17	0.16	H b5@29, HCOO t4@3-t5@6, HCOO i t2@1-t1@11	0.09
H b2@23, H b6@32, HCOO t1@11- t2@1	0.03	H b5@33, HCOO t3@14-t4@15, HCOO t2@1-t2@4	0.28
H b2@23, H b7@31, HCOO t2@1- t2@4	0.09	H b5@33, HCOO t3@14-t4@15, HCOO i t2@1-t1@11	0.02
H b2@23, H h1@51, HCOO t1@11- t2@1	0.31	H b5@33, HCOO t3@14-t4@15, HCOO i t2@4-t2@1	0.29
H b2@23, H h4@67, HCOO t4@3- t5@6	0.13	H b5@33, HCOO t3@2-t4@3, HCOO t2@1-t2@4	0.17
H b2@23, HCOO t1@11-t1@17, HCOO t2@1-t2@4	0.16	H b5@34, HCOO t2@1-t2@4, HCOO t3@2-t4@3	0.16

H b2@23, HCOO t1@11-t1@17, HCOO t2@1-t2@4	0.06	H b5@34, HCOO t3@2-t4@3, HCOO t2@4-t1@11	0.02
H b2@23, HCOO t1@11-t1@17, HCOO t2@4-t2@1	0.41	H b5@34, HCOO t4@3-t5@6, HCOO t2@1-t2@4	0.19
H b2@23, HCOO t1@17-t1@11, HCOO t2@1-t2@4	0.06	H b5@34, HCOO t4@3-t5@6, HCOO t2@1-t1@11	0.08
H b2@23, HCOO t1@17-t1@11, HCOO t2@4-t2@1	0.41	H b6@30, H b6@32, HCOO t3@2- t4@3	0.12
H b2@23, HCOO t1@17-t2@16, HCOO t1@11-t2@1	0.24	H b6@30, H b7@31, HCOO t4@3- t5@6	0.10
H b2@23, HCOO t2@16-t2@18, HCOO t1@11-t2@1	0.04	H b6@30, HCOO t1@11-t2@1, HCOO t1@17-t2@18	0.14
H b2@23, HCOO t2@16-t2@18, HCOO t3@2-t4@3	0.05	H b6@30, HCOO t1@11-t2@1, HCOO t3@14-t4@15	0.12
H b2@23, HCOO t2@16-t2@18, HCOO t2@1-t1@11	0.07	H b6@30, HCOO t1@11-t2@1, HCOO t4@3-t5@6	0.07
H b2@23, HCOO t2@18-t2@16, HCOO t2@1-t1@11	0.07	H b6@30, HCOO t1@11-t2@1, HCOO t2@16-t2@18	0.07
H b2@23, HCOO t3@2-t4@3, HCOO t1@11-t2@1	0.15	H b6@30, HCOO t1@11-t2@1, HCOO t2@18-t2@16	0.20
H b2@23, HCOO t4@3-t5@6, HCOO t3@8-t4@15	0.27	H b6@30, HCOO t1@11-t2@4, HCOO t1@17-t2@18	0.09
H b2@24, H b3@22, H b4@26	-0.13	H b6@30, HCOO t1@11-t2@4, HCOO t3@8-t4@15	0.17
H b2@24, H b3@22, HCOO t1@11- t2@1	0.36	H b6@30, HCOO t1@11-t2@4, HCOO t2@16-t2@18	0.13
H b2@24, H b3@25, H b2@20	0.23	H b6@30, HCOO t1@11-t2@4, HCOO t2@18-t2@16	0.09
H b2@24, H b3@25, HCOO t1@11- t2@1	0.51	H b6@30, HCOO t2@1-t2@4, HCOO t1@11-t1@17	0.16
H b2@24, H b5@27, HCOO t1@11- t2@4	0.49	H b6@30, HCOO t2@1-t2@4, HCOO t3@2-t4@3	0.19
H b2@24, H b5@27, HCOO t2@4- t2@1	0.23	H b6@30, HCOO t3@2-t4@3, HCOO t1@11-t1@17	0.10
H b2@24, H b5@33, HCOO t2@16- t3@7	-0.40	H b6@30, HCOO t3@2-t4@3, HCOO t1@11-t2@4	0.11
H b2@24, H b6@30, HCOO t3@2- t4@3	0.02	H b6@30, HCOO t3@2-t4@3, HCOO t3@8-t4@15	0.08
H b2@24, H b6@32, HCOO t1@11- t2@1	0.13	H b6@30, HCOO t3@8-t4@15, HCOO t2@1-t2@4	0.10
H b2@24, HCOO t1@17-t2@18, HCOO t1@11-t2@1	0.41	H b6@30, HCOO t3@8-t4@15, HCOO t2@4-t2@1	0.09
H b2@24, HCOO t1@17-t2@18, HCOO t2@1-t2@4	0.20	H b6@32, HCOO t1@11-t2@4, HCOO t3@2-t4@3	0.12
H b2@24, HCOO t2@16-t2@18, HCOO t2@1-t1@11	0.28	H b6@32, HCOO t1@11-t2@4, HCOO t3@8-t4@15	0.20
H b2@24, HCOO t2@16-t2@18, HCOO t2@1-t2@4	0.24	H b6@32, HCOO t3@7-t4@3, HCOO t1@11-t1@17	0.10
H b2@24, HCOO t2@16-t2@18, HCOO t2@4-t2@1	0.36	H b6@32, HCOO t4@15-t5@9, HCOO t1@11-t2@1	0.24

H b2@24, HCOO t2@18-t2@16, HCOO t1@11-t2@1	0.57	H b7@31, HCOO t1@17-t2@16, HCOO t3@8-t4@15	-0.21
H b2@24, HCOO t2@18-t2@16, HCOO t2@1-t2@4	0.30	H b7@31, HCOO t2@1-t2@4, HCOO t1@17-t2@16	0.05
H b2@24, HCOO t2@18-t2@16, HCOO t2@1-t1@11	0.28	H b7@31, HCOO t2@1-t2@4, HCOO t2@18-t2@16	0.47
H b2@24, HCOO t2@18-t2@16, HCOO t2@1-t2@4	0.24	H b7@31, HCOO t2@1-t2@4, HCOO t4@15-t5@9	0.15
H b2@24, HCOO t2@18-t2@16, HCOO t2@4-t2@1	0.36	H b7@31, HCOO t2@1-t2@4, HCOO t2@16-t2@18	0.35
H b2@24, HCOO t2@1-t2@4, HCOO t2@16-t2@18	0.24	H b7@31, HCOO t2@1-t3@2, HCOO t2@16-t2@18	0.10
H b2@24, HCOO t2@1-t2@4, HCOO t2@18-t2@16	0.23	H b7@31, HCOO t2@1-t3@2, HCOO t4@3-t5@6	0.17
H b2@24, HCOO t2@4-t2@1, HCOO t2@16-t2@18	0.24	H b7@31, HCOO t2@1-t3@2, HCOO t2@16-t2@18	0.16
H b2@24, HCOO t2@4-t2@1, HCOO t2@18-t2@16	0.23	H b7@31, HCOO t2@1-t3@2, HCOO t2@18-t2@16	0.22
H b2@24, HCOO t4@15-t5@9, HCOO t1@11-t2@1	0.25	H b7@31, HCOO t2@4-t2@1, HCOO t2@16-t2@18	0.35
H b2@24, HCOO t4@15-t5@9, HCOO t1@11-t2@1	0.08	H b7@31, HCOO t2@4-t3@8, HCOO t1@11-t2@1	0.16
H b3@22, H b4@26, HCOO t1@11- t2@1	0.09	H b7@31, HCOO t4@3-t5@6, HCOO t4@15-t5@9	0.44
H b3@22, H b4@26, HCOO t1@17- t1@11	0.10	H f1@37, HCOO t4@3-t5@6, HCOO t1@11-t2@4	0.12
H b3@22, H b4@26, HCOO t1@17- t2@18	0.16	H f1@38, HCOO t3@2-t4@3, HCOO t1@11-t2@1	0.17
H b3@22, H b4@26, HCOO t3@14- t4@15	0.21	H h1@51, HCOO t1@11-t2@1, HCOO t2@16-t2@18	0.37
H b3@22, H b4@26, HCOO t2@18- t2@16	0.10	H h1@59, HCOO t4@3-t5@6, HCOO t2@1-t2@4	0.39
H b3@22, H b4@28, HCOO t1@17- t2@18	0.13	H h3@54, HCOO t1@11-t2@4, HCOO t3@2-t4@3	-0.03
H b3@22, H b4@28, HCOO t4@3- t5@6	0.27	H h3@54, HCOO t1@17-t2@16, HCOO t3@14-t4@15	-0.03
H b3@22, H b4@28, HCOO t2@18- t1@17	0.08	H h3@54, HCOO t2@16-t2@18, HCOO t1@11-t2@1	0.12
H b3@22, H b4@35, HCOO t4@3- t5@6	0.04	H h3@54, HCOO t2@16-t2@18, HCOO t2@1-t2@4	0.37
H b3@22, H b4@35, HCOO t2@18- t1@17	0.09	H h3@54, HCOO t2@18-t2@16, HCOO t2@1-t2@4	0.37
H b3@22, H b4@36, HCOO t3@2- t4@3	0.30	H h3@54, HCOO t2@1-t2@4, HCOO t2@18-t2@16	0.22
H b3@22, H b5@27, H b6@30	-0.16	H h3@57, H h4@61, HCOO t1@11- t2@4	-0.10
H b3@22, H b5@27, HCOO t1@11- t2@4	0.11	H t1@11, H b2@20, H b5@33	0.09
H b3@22, H b5@27, HCOO t3@7- t4@3	-0.22	H t1@11, H b2@20, HCOO t2@1-t2@4	0.06

H b3@22, H b5@27, HCOO t4@15-t5@9	0.10	H t1@11, H b2@23, HCOO t2@1-t2@4 H t1@11, H b3@25, HCOO t4@15-t5@9	0.12 -0.12
H b3@22, H b5@29, H b5@27	-0.10		
H b3@22, H b5@29, H f1@38	0.07	H t1@11, H b4@36, HCOO t3@2-t4@3	0.12
H b3@22, H b5@29, HCOO t3@2-t4@3	0.12	H t1@11, H h3@57, HCOO t2@1-t2@4	0.12
H b3@22, H b5@34, HCOO t3@7-t4@3	0.13	H t1@11, H t1@17, H b6@32	-0.12
H b3@22, H b5@34, HCOO t4@3-t5@6	0.08	H t1@11, HCOO t2@1-t2@4, HCOO t1@17-t2@16	0.20
H b3@22, H b6@30, HCOO t1@11-t2@4	0.11	H t1@11, HCOO t2@1-t2@4, HCOO t4@3-t5@6	0.03
H b3@22, H b6@30, HCOO t3@2-t4@3	0.18	H t1@17, H b3@25, HCOO t2@16-t3@7	0.04
	0.17	H t1@17, H b5@27, HCOO t1@11-t2@1	-0.28
H b3@22, H b7@31, H f1@38			
H b3@22, H f1@38, HCOO t1@11-t2@1	0.63	H t1@17, H b5@27, HCOO t2@4-t3@8	-0.02
H b3@22, H h3@57, HCOO t1@11-t2@1	-0.18	H t1@17, H t1@11, H b2@23	0.20
H b3@22, H h4@64, HCOO t2@16-t2@18	-0.14	H t1@17, HCOO t2@18-t2@16, HCOO t2@1-t2@4	0.07
H b3@22, HCOO t1@11-t2@4, HCOO t3@8-t4@15	0.26	H t4@15, H b2@20, H b6@30	-0.04
H b3@22, HCOO t3@2-t4@3, HCOO t1@17-t2@16	0.30	H t4@15, H b2@24, H b5@27	0.07
H b3@22, HCOO t3@2-t4@3, HCOO t1@17-t2@18	0.03	H t4@15, H b2@24, HCOO t2@1-t2@4	0.14
H b3@22, HCOO t3@2-t4@3, HCOO t4@15-t5@9	0.39	H t4@15, H b3@22, H b5@27	0.06
H b3@22, HCOO t3@8-t4@15, HCOO t1@11-t2@4	0.52	H t4@15, H b4@35, HCOO t4@3-t5@6	0.14
H b3@22, HCOO t4@3-t5@6, HCOO t1@11-t2@4	0.24	H t4@15, H b5@27, H b5@33	0.91
H b3@22, HCOO t4@3-t5@6, HCOO t2@16-t2@18	-0.03	H t4@15, H b5@27, H b6@30	0.74
H b3@22, HCOO t4@3-t5@6, HCOO t4@15-t5@9	0.27	H t4@15, HCOO t2@1-t2@4, HCOO t3@2-t4@3	0.03
H b3@25, H b4@26, HCOO t1@11-t1@17	0.09	H t4@3, H b2@20, H b3@22	0.36
H b3@25, H b4@35, H h4@61	0.07	H t4@3, H b2@21, HCOO t2@1-t2@4	0.18
H b3@25, H b5@27, HCOO t1@11-t2@4	0.19	H t4@3, H b3@22, H b4@26	0.07
H b3@25, H b5@27, HCOO t3@2-t4@3	-0.04	H t4@3, H b3@22, H b4@36	-0.15
H b3@25, H b6@30, HCOO t1@11-t2@1	0.07	H t4@3, H b3@22, H b6@30	0.17
H b3@25, H b6@30, HCOO t1@11-t2@4	0.08	H t4@3, H b4@35, HCOO t1@11-t1@17	0.05

H b3@25, H b6@30, HCOO t3@2-t4@3	0.04	H t4@3, H b4@36, H b6@30	0.04
H b3@25, HCOO t1@11-t1@17, HCOO t2@1-t2@4	-0.09	H t4@3, H b5@29, H b7@31	0.05
H b3@25, HCOO t1@11-t2@1, HCOO t1@17-t2@16	0.03	H t4@3, H b5@29, HCOO t1@17-t2@16	0.08
H b3@25, HCOO t1@11-t2@1, HCOO t1@17-t2@18	0.09	H t4@3, H b5@29, HCOO t2@16-t2@18	0.23
H b3@25, HCOO t1@17-t2@16, HCOO t1@11-t2@1	0.37	H t4@3, H b5@29, HCOO t2@1-t2@4	0.19
H b3@25, HCOO t1@17-t2@16, HCOO t1@11-t2@1	0.57	H t4@3, H b6@32, H h3@54	-0.32
H b3@25, HCOO t1@17-t2@18, HCOO t1@11-t2@1	0.49	H t4@3, H b6@32, HCOO t1@11-t2@4	0.08
H b3@25, HCOO t1@17-t2@18, HCOO t1@11-t2@1	0.68	H t4@3, H b6@32, HCOO t2@1-t2@4	0.05
H b3@25, HCOO t1@17-t2@18, HCOO t2@1-t1@11	0.35	H t4@3, HCOO t1@11-t2@1, HCOO t4@15-t5@9	0.32
H b4@26, H b4@28, H b7@31	-0.06	H t4@3, HCOO t1@11-t2@4, HCOO t3@14-t4@15	0.11
H b4@26, H b4@28, HCOO t2@18-t2@16	0.11	H t4@3, HCOO t1@17-t2@16, HCOO t1@11-t2@1	0.04
H b4@26, H b4@28, HCOO t2@1-t2@4	0.10	H t4@3, HCOO t2@1-t2@4, HCOO t2@18-t2@16	0.12
H b4@26, H b4@28, HCOO t2@1-t2@4	0.08	HCOO t1@11-t2@1, HCOO t3@2-t4@3, HCOO t1@17-t2@16	0.14
H b4@26, H b4@35, HCOO t2@1-t2@4	0.26	HCOO t1@11-t2@1, HCOO t3@2-t4@3, HCOO t1@17-t2@18	0.05
H b4@26, H b5@27, H b6@30	-0.39	HCOO t1@11-t2@1, HCOO t3@2-t4@3, HCOO t2@16-t2@18	0.20
H b4@26, H b5@27, HCOO t1@11-t2@1	0.15	HCOO t1@11-t2@1, HCOO t3@2-t4@3, HCOO t2@16-t2@18	0.16
H b4@26, H b5@27, HCOO t2@1-t2@4	0.22	HCOO t1@11-t2@1, HCOO t4@3-t5@6, HCOO t1@17-t2@18	0.09
H b4@26, H b5@27, HCOO t4@15-t5@9	0.06	HCOO t1@17-t2@16, HCOO t4@15-t5@9, HCOO t1@11-t2@1	0.30
H b4@26, H b5@33, HCOO t2@1-t2@4	0.06	HCOO t1@17-t2@18, HCOO t3@8-t4@15, HCOO t4@3-t5@6	0.04
H b4@26, H b5@33, HCOO t3@14-t4@15	0.45	HCOO t1@17-t2@18, HCOO t4@3-t5@6, HCOO t2@1-t2@4	0.13
H b4@26, H b5@33, HCOO t2@4-t2@1	0.11	HCOO t2@16-t2@18, HCOO t3@14-t4@15, HCOO t1@11-t2@1	-0.02
H b4@26, H b6@30, H b5@33	-0.17	HCOO t2@16-t2@18, HCOO t4@15-t5@9, HCOO t1@11-t2@1	0.25
H b4@26, H b6@30, H h4@64	0.03	HCOO t2@16-t2@18, HCOO t4@3-t5@6, HCOO t2@1-t1@11	0.09
H b4@26, H b6@30, HCOO t1@11-t2@1	0.12	HCOO t2@18-t2@16, HCOO t3@8-t4@15, HCOO t1@11-t2@1	0.10
H b4@26, H b6@30, HCOO t3@14-t4@15	0.26	HCOO t2@18-t2@16, HCOO t4@3-t5@6, HCOO t2@1-t1@11	0.09

H b4@26, H b6@30, HCOO t3@8-t4@15	0.04	HCOO t2@1-t2@4, HCOO t3@2-t4@3, HCOO t1@17-t2@16	0.18
H b4@26, H b6@30, HCOO i t2@1-t2@4	0.09	HCOO t2@1-t2@4, HCOO t3@2-t4@3, HCOO t4@15-t5@9	0.05
H b4@26, H b7@31, H b4@35	-0.09	HCOO t2@1-t2@4, HCOO t4@3-t5@6, HCOO t4@15-t5@9	0.11
H b4@26, H b7@31, H b5@33	-0.28	HCOO t2@1-t3@2, HCOO t1@11-t2@4, HCOO t1@17-t2@18	0.14
H b4@26, H b7@31, H b6@32	-0.16	HCOO t2@1-t3@2, HCOO t1@11-t2@4, HCOO t2@16-t2@18	0.10
H b4@26, H b7@31, HCOO t1@11-t2@4	0.13	HCOO t2@1-t3@2, HCOO t1@11-t2@4, HCOO i t2@16-t2@18	0.07
H b4@26, H f1@38, HCOO t2@1-t2@4	0.19	HCOO t2@1-t3@2, HCOO t4@3-t5@6, HCOO t2@16-t2@18	0.03
H b4@26, H h3@57, HCOO t1@11-t2@1	0.34	HCOO t2@1-t3@2, HCOO t4@3-t5@6, HCOO i t2@16-t2@18	0.57
H b4@26, H h3@57, HCOO i t2@4-t2@1	0.11	HCOO t4@15-t5@9, HCOO t2@1-t2@4, HCOO t5@6-t6@5	0.23
H b4@26, HCOO t1@11-t1@17, HCOO t2@16-t2@18	0.27	HCOO t4@3-t5@6, HCOO t2@1-t3@2, HCOO t1@11-t2@4	0.42
H b4@26, HCOO t1@11-t1@17, HCOO i t2@16-t2@18	0.33		

Table S9 List of clusters penalized with a 20 eV interaction energy to prevent adsorbates from coming unphysically close to each other. Adsorbates are denoted with their name, site type, and representative site number, in the following format: [name]|[site type]|@[site number]. For HCOOi, a bidentate species, the first and second site types bind the O and H dentates of HCOOi respectively. Site numbers are required to unambiguously identify unique clusters; illustrations of the site numberings can be found in Figure S11.

Clusters	
CO b1@19, CO h5@62	O b7@31, HCOOH t5@6
CO b1@19, H h5@62	O b7@31, HCOOi t5@6-t5@9
CO b1@19, HCOO t1@11-t1@17	O b7@31, O h3@54
CO b1@19, HCOOi t1@11-t1@17	O b7@31, OH t5@6
CO b2@20, CO f4@50	O f1@37, CO b2@20
CO b2@20, H f1@37	O f1@37, CO b3@22
CO b2@20, H f4@50	O f1@37, CO t2@1
CO b2@21, HCOO t1@11-t2@1	O f1@37, COOH t2@1
CO b2@21, HCOOi t1@11-t2@1	O f1@37, H b2@20
CO b2@21, HCOOi t2@1-t1@11	O f1@37, H b3@22
CO b3@22, CO f2@44	O f1@37, HCOO t1@11-t2@1
CO b3@22, COOH t2@1	O f1@37, HCOO t2@1-t2@4
CO b3@22, H f1@37	O f1@37, HCOOH t2@1
CO b3@22, H f2@44	O f1@37, HCOOi t1@11-t2@1
CO b3@22, HCOO t2@1-t2@4	O f1@37, HCOOi t2@1-t1@11
CO b3@22, HCOOH t2@1	O f1@37, HCOOi t2@1-t2@4
CO b3@22, HCOOi t2@1-t2@4	O f1@37, OH b2@20
CO b4@26, CO h4@66	O f1@37, OH b3@22
CO b4@26, COOH t3@14	O f1@37, OH t2@1
CO b4@26, H h1@51	O f2@39, CO b3@25
CO b4@26, H h4@66	O f2@39, CO t2@16
CO b4@26, HCOOH h4@66	O f2@39, CO t6@10
CO b4@26, HCOOH t3@14	O f2@39, COOH t2@16
CO b4@36, HCOO t2@1-t3@2	O f2@39, COOH t6@10
CO b7@31, CO h3@54	O f2@39, H b3@25
CO b7@31, COOH t5@6	O f2@39, HCOOH t2@16
CO b7@31, H h3@54	O f2@39, HCOOH t6@10
CO b7@31, HCOO t5@6-t5@9	O f2@39, OH b3@25
CO b7@31, HCOOH t5@6	O f2@39, OH t2@16
CO b7@31, HCOOi t5@6-t5@9	O f2@39, OH t6@10
CO f2@39, COOH t2@16	O f2@44, HCOO t2@1-t2@4
CO f2@39, COOH t6@10	O f2@44, HCOO t2@1-t6@5
CO f2@39, H b3@25	O f2@44, HCOOi t2@1-t2@4
CO f2@39, HCOOH t2@16	O f4@45, CO b2@24
CO f2@39, HCOOH t6@10	O f4@45, CO t2@16
CO f2@44, HCOO t2@1-t2@4	O f4@45, CO t7@12
CO f2@44, HCOO t2@1-t6@5	O f4@45, COOH t2@16
CO f2@44, HCOOi t2@1-t2@4	O f4@45, COOH t7@12

CO f4@45, COOH t2@16	O f4@45, H b2@24
CO f4@45, COOH t7@12	O f4@45, HCOOH t2@16
CO f4@45, H b2@24	O f4@45, HCOOH t7@12
CO f4@45, HCOOH t2@16	O f4@45, OH b2@24
CO f4@45, HCOOH t7@12	O f4@45, OH t2@16
CO f4@47, HCOO t1@11-t2@1	O f4@45, OH t7@12
CO f4@47, HCOO t1@11-t7@12	O f4@47, HCOO t1@11-t2@1
CO f4@47, HCOO t2@1-t7@12	O f4@47, HCOO t1@11-t7@12
CO f4@47, HCOO i t1@11-t2@1	O f4@47, HCOO t2@1-t7@12
CO f4@47, HCOO i t2@1-t1@11	O f4@47, HCOO i t1@11-t2@1
CO h3@54, COOH t5@6	O f4@47, HCOO i t2@1-t1@11
CO h3@54, COOH t6@10	O h2@53, CO t3@14
CO h3@54, H b7@31	O h2@53, CO t5@9
CO h3@54, HCOO t5@6-t5@9	O h2@53, COOH t3@14
CO h3@54, HCOOH t5@6	O h2@53, COOH t5@9
CO h3@54, HCOOH t6@10	O h2@53, H b5@27
CO h3@54, HCOO i t5@6-t5@9	O h2@53, H b6@30
CO h3@57, HCOO t5@6-t6@5	O h2@53, HCOOH t3@14
CO h4@61, COOH b4@28	O h2@53, HCOOH t5@9
CO h4@61, COOH t2@16	O h2@53, OH b5@27
CO h4@61, COOH t3@7	O h2@53, OH b6@30
CO h4@61, COOH t7@12	O h2@53, OH t3@14
CO h4@61, H b4@28	O h2@53, OH t5@9
CO h4@61, HCOOH b4@28	O h2@55, HCOO t4@3-t5@6
CO h4@61, HCOOH t2@16	O h2@55, HCOO i t5@6-t4@3
CO h4@61, HCOOH t3@7	O h2@58, HCOO t3@2-t4@3
CO h4@61, HCOOH t7@12	O h2@58, HCOO t3@2-t5@6
CO h4@64, HCOO t2@1-t3@2	O h2@58, HCOO i t3@2-t4@3
CO h4@64, HCOO t2@1-t7@12	O h2@58, HCOO i t3@2-t5@6
CO h4@64, HCOO t3@2-t7@12	O h3@54, CO b7@31
CO h5@62, COOH b1@19	O h3@54, CO t5@6
CO h5@62, COOH t7@12	O h3@54, CO t6@10
CO h5@62, H b1@19	O h3@54, COOH t5@6
CO h5@62, HCOO t1@11-t1@17	O h3@54, COOH t6@10
CO h5@62, HCOO t1@11-t7@12	O h3@54, H b7@31
CO h5@62, HCOOH t7@12	O h3@54, HCOO t5@6-t5@9
CO h5@62, HCOO i t1@11-t1@17	O h3@54, HCOOH t5@6
CO t2@1, CO b3@22	O h3@54, HCOOH t6@10
CO t2@1, CO f2@44	O h3@54, HCOO i t5@6-t5@9
CO t2@1, CO f4@47	O h3@54, OH b7@31
CO t2@1, CO h4@64	O h3@54, OH t5@6
CO t2@1, H b3@22	O h3@54, OH t6@10
CO t2@1, H f1@37	O h3@57, HCOO t5@6-t6@5
CO t2@1, H f2@44	O h4@61, CO b4@28

CO t2@1, H f4@47	O h4@61, CO t2@16
CO t2@1, H h1@60	O h4@61, CO t3@7
CO t2@1, H h4@64	O h4@61, CO t7@12
CO t2@1, HCOOH h4@64	O h4@61, COOH b4@28
CO t3@2, CO b4@36	O h4@61, COOH t2@16
CO t3@2, CO h4@64	O h4@61, COOH t3@7
CO t3@2, COOH b4@36	O h4@61, COOH t7@12
CO t3@2, H b4@36	O h4@61, H b4@28
CO t3@2, H b5@34	O h4@61, HCOOH b4@28
CO t3@2, H f5@46	O h4@61, HCOOH t2@16
CO t3@2, H h1@60	O h4@61, HCOOH t3@7
CO t3@2, H h4@64	O h4@61, HCOOH t7@12
CO t3@2, H h6@63	O h4@61, OH b4@28
CO t3@2, HCOOH b4@36	O h4@61, OH t2@16
CO t3@2, HCOOH h4@64	O h4@61, OH t3@7
CO t5@6, CO b7@31	O h4@61, OH t7@12
CO t5@6, CO h3@54	O h4@64, HCOO t2@1-t3@2
CO t5@6, H b6@32	O h4@64, HCOO t2@1-t7@12
CO t5@6, H b7@31	O h4@64, HCOO t3@2-t7@12
CO t5@6, H h3@54	O h6@63, CO t3@2
CO t6@5, CO f2@44	O h6@63, COOH t3@2
CO t6@5, CO h3@57	O h6@63, H b5@29
CO t6@5, H f2@44	O h6@63, HCOO t3@2-t3@7
CO t6@5, H h1@59	O h6@63, HCOO t3@2-t4@3
CO t6@5, H h3@57	O h6@63, HCOOH t3@2
CO t7@12, CO f4@45	O h6@63, HCOO t3@2-t4@3
CO t7@12, CO h4@61	O h6@63, OH b5@29
CO t7@12, CO h5@62	O h6@63, OH t3@2
CO t7@12, H f4@45	O t2@1, CO b3@22
CO t7@12, H f5@46	O t2@1, CO f2@44
CO t7@12, H h4@61	O t2@1, CO f4@47
CO t7@12, H h5@62	O t2@1, CO h4@64
CO t7@12, HCOOH h4@61	O t2@1, H b3@22
COOH b1@19, HCOO t1@11-t1@17	O t2@1, H f1@37
COOH t3@2, COOH b4@36	O t2@1, H f2@44
H b1@19, H h5@62	O t2@1, H f4@47
H b1@19, HCOO t1@11-t1@17	O t2@1, H h1@60
H b1@19, HCOO t1@11-t1@17	O t2@1, H h4@64
H b2@20, H f1@37	O t2@1, HCOOH h4@64
H b2@20, H f4@50	O t2@1, O f1@37
H b2@21, HCOO t1@11-t2@1	O t2@1, O f2@44
H b2@21, HCOO t1@11-t2@1	O t2@1, O f4@47
H b2@21, HCOO t2@1-t1@11	O t2@1, O h4@64
H b3@22, COOH t2@1	O t2@1, OH b3@22

H b3@22, H f1@37	O t2@1, OH f1@37
H b3@22, H f2@44	O t2@1, OH f2@44
H b3@22, HCOO t2@1-t2@4	O t6@5, CO f2@44
H b3@22, HCOOH t2@1	O t6@5, CO h3@57
H b3@22, HCOO t2@1-t2@4	O t6@5, H f2@44
H b4@26, COOH t3@14	O t6@5, H h1@59
H b4@26, H h1@51	O t6@5, H h3@57
H b4@26, H h4@66	O t6@5, O f2@44
H b4@26, HCOOH h4@66	O t6@5, O h3@57
H b4@26, HCOOH t3@14	O t6@5, OH f2@44
H b4@36, HCOO t2@1-t3@2	OH b1@19, CO h5@62
H b5@27, COOH t3@14	OH b1@19, H h5@62
H b5@27, H h6@68	OH b1@19, HCOO t1@11-t1@17
H b5@27, HCOOH t3@14	OH b1@19, HCOO t1@11-t1@17
H b5@34, HCOO t3@2-t4@3	OH b2@20, CO f4@50
H b5@34, HCOO t3@2-t4@3	OH b2@20, H f1@37
H b6@30, HCOOH t5@9	OH b2@20, H f4@50
H b6@32, HCOO t4@3-t5@6	OH b2@20, OH f1@37
H b6@32, HCOO t5@6-t4@3	OH b2@21, HCOO t1@11-t2@1
H b7@31, COOH t5@6	OH b2@21, HCOO t1@11-t2@1
H b7@31, H h3@54	OH b2@21, HCOO t2@1-t1@11
H b7@31, HCOO t5@6-t5@9	OH b3@22, CO f2@44
H b7@31, HCOOH t5@6	OH b3@22, CO t2@1
H b7@31, HCOO t5@6-t5@9	OH b3@22, COOH t2@1
H f1@37, COOH t2@1	OH b3@22, H f1@37
H f1@37, HCOO t1@11-t2@1	OH b3@22, H f2@44
H f1@37, HCOO t2@1-t2@4	OH b3@22, HCOO t2@1-t2@4
H f1@37, HCOOH t2@1	OH b3@22, HCOOH t2@1
H f1@37, HCOO t1@11-t2@1	OH b3@22, HCOO t2@1-t2@4
H f1@37, HCOO t2@1-t1@11	OH b3@22, OH f1@37
H f1@37, HCOO t2@1-t2@4	OH b3@22, OH f2@44
H f2@39, COOH t2@16	OH b4@26, CO h4@66
H f2@39, COOH t6@10	OH b4@26, CO t3@14
H f2@39, HCOOH t2@16	OH b4@26, COOH t3@14
H f2@39, HCOOH t6@10	OH b4@26, H h1@51
H f2@44, HCOO t2@1-t2@4	OH b4@26, H h4@66
H f2@44, HCOO t2@1-t6@5	OH b4@26, HCOOH h4@66
H f2@44, HCOO t2@1-t2@4	OH b4@26, HCOOH t3@14
H f4@45, COOH t2@16	OH b4@36, HCOO t2@1-t3@2
H f4@45, COOH t7@12	OH b5@27, CO t3@14
H f4@45, HCOOH t2@16	OH b5@27, COOH t3@14
H f4@45, HCOOH t7@12	OH b5@27, H h6@68
H f4@47, HCOO t1@11-t2@1	OH b5@27, HCOOH t3@14
H f4@47, HCOO t1@11-t7@12	OH b5@27, OH h2@53

H f4@47, HCOO t2@1-t7@12	OH b5@34, HCOO t3@2-t4@3
H f4@47, HCOO i t1@11-t2@1	OH b5@34, HCOO i t3@2-t4@3
H f4@47, HCOO i t2@1-t1@11	OH b6@30, CO t5@9
H f5@46, COOH t3@2	OH b6@30, COOH t5@9
H f5@46, COOH t7@12	OH b6@30, HCOOH t5@9
H f5@46, HCOO t3@2-t3@7	OH b6@30, OH h2@53
H f5@46, HCOO t3@2-t7@12	OH b6@32, HCOO t4@3-t5@6
H f5@46, HCOOH t3@2	OH b6@32, HCOO i t5@6-t4@3
H f5@46, HCOOH t7@12	OH b7@31, CO h3@54
H h1@51, COOH b4@26	OH b7@31, CO t5@6
H h1@51, COOH t2@18	OH b7@31, COOH t5@6
H h1@51, COOH t3@14	OH b7@31, H h3@54
H h1@51, COOH t6@10	OH b7@31, HCOO t5@6-t5@9
H h1@51, HCOOH b4@26	OH b7@31, HCOOH t5@6
H h1@51, HCOOH t2@18	OH b7@31, HCOO i t5@6-t5@9
H h1@51, HCOOH t3@14	OH f1@37, CO b2@20
H h1@51, HCOOH t6@10	OH f1@37, CO b3@22
H h1@60, HCOO t2@1-t3@2	OH f1@37, CO t2@1
H h1@60, HCOO t2@1-t6@5	OH f1@37, COOH t2@1
H h1@60, HCOO t3@2-t6@5	OH f1@37, H b2@20
H h3@54, COOH t5@6	OH f1@37, H b3@22
H h3@54, COOH t6@10	OH f1@37, HCOO t1@11-t2@1
H h3@54, HCOO t5@6-t5@9	OH f1@37, HCOO t2@1-t2@4
H h3@54, HCOOH t5@6	OH f1@37, HCOOH t2@1
H h3@54, HCOOH t6@10	OH f1@37, HCOO i t1@11-t2@1
H h3@54, HCOO i t5@6-t5@9	OH f1@37, HCOO i t2@1-t1@11
H h3@57, HCOO t5@6-t6@5	OH f1@37, HCOO i t2@1-t2@4
H h4@61, COOH b4@28	OH f2@39, CO b3@25
H h4@61, COOH t2@16	OH f2@39, CO t2@16
H h4@61, COOH t3@7	OH f2@39, CO t6@10
H h4@61, COOH t7@12	OH f2@39, COOH t2@16
H h4@61, HCOOH b4@28	OH f2@39, COOH t6@10
H h4@61, HCOOH t2@16	OH f2@39, H b3@25
H h4@61, HCOOH t3@7	OH f2@39, HCOOH t2@16
H h4@61, HCOOH t7@12	OH f2@39, HCOOH t6@10
H h4@64, HCOO t2@1-t3@2	OH f2@44, HCOO t2@1-t2@4
H h4@64, HCOO t2@1-t7@12	OH f2@44, HCOO t2@1-t6@5
H h4@64, HCOO t3@2-t7@12	OH f2@44, HCOO i t2@1-t2@4
H h5@62, COOH b1@19	OH h2@53, CO t3@14
H h5@62, COOH t7@12	OH h2@53, CO t5@9
H h5@62, HCOO t1@11-t1@17	OH h2@53, COOH t3@14
H h5@62, HCOO t1@11-t7@12	OH h2@53, COOH t5@9
H h5@62, HCOOH t7@12	OH h2@53, H b5@27
H h5@62, HCOO i t1@11-t1@17	OH h2@53, H b6@30

H h6@63, COOH t3@2	OH h2@53, HCOOH t3@14
H h6@63, HCOO t3@2-t3@7	OH h2@53, HCOOH t5@9
H h6@63, HCOO t3@2-t4@3	OH h2@55, HCOO t4@3-t5@6
H h6@63, HCOOH t3@2	OH h2@55, HCOO t5@6-t4@3
H h6@63, HCOO t3@2-t4@3	OH h2@58, HCOO t3@2-t4@3
HCOO t1@11-t1@17, COOH b1@19	OH h2@58, HCOO t3@2-t5@6
HCOO t2@1-t3@2, COOH b4@36	OH h2@58, HCOO t3@2-t4@3
HCOOH b4@26, COOH t3@14	OH h2@58, HCOO t3@2-t5@6
HCOOH b4@26, HCOOH h4@66	OH t2@1, CO b3@22
HCOOH b4@36, HCOO t2@1-t3@2	OH t2@1, CO f2@44
HCOOH h4@61, COOH b4@28	OH t2@1, CO f4@47
HCOOH h4@61, COOH t2@16	OH t2@1, CO h4@64
HCOOH h4@61, COOH t3@7	OH t2@1, H b3@22
HCOOH h4@61, COOH t7@12	OH t2@1, H f1@37
HCOOH h4@64, HCOO t2@1-t3@2	OH t2@1, H f2@44
HCOOH h4@64, HCOO t2@1-t7@12	OH t2@1, H f4@47
HCOOH h4@64, HCOO t3@2-t7@12	OH t2@1, H h1@60
HCOOH t2@1, HCOOH h4@64	OH t2@1, H h4@64
HCOOH t3@2, COOH b4@36	OH t2@1, HCOOH h4@64
HCOOH t3@2, HCOOH b4@36	OH t2@1, OH b3@22
HCOOH t3@2, HCOOH h4@64	OH t2@1, OH f1@37
HCOOH t7@12, HCOOH h4@61	OH t2@1, OH f2@44
O b1@19, CO h5@62	OH t3@2, CO b4@36
O b1@19, H h5@62	OH t3@2, CO h4@64
O b1@19, HCOO t1@11-t1@17	OH t3@2, COOH b4@36
O b1@19, HCOO t1@11-t1@17	OH t3@2, H b4@36
O b4@26, CO h4@66	OH t3@2, H b5@34
O b4@26, CO t3@14	OH t3@2, H f5@46
O b4@26, COOH t3@14	OH t3@2, H h1@60
O b4@26, H h1@51	OH t3@2, H h4@64
O b4@26, H h4@66	OH t3@2, H h6@63
O b4@26, HCOOH h4@66	OH t3@2, HCOOH b4@36
O b4@26, HCOOH t3@14	OH t3@2, HCOOH h4@64
O b4@26, O h4@66	OH t3@2, OH b4@36
O b4@26, OH t3@14	OH t3@2, OH b5@34
O b4@36, HCOO t2@1-t3@2	OH t3@2, OH h2@58
O b5@27, CO t3@14	OH t5@6, CO b7@31
O b5@27, COOH t3@14	OH t5@6, CO h3@54
O b5@27, H h6@68	OH t5@6, H b6@32
O b5@27, HCOOH t3@14	OH t5@6, H b7@31
O b5@27, O h2@53	OH t5@6, H h3@54
O b5@27, O h6@68	OH t5@6, OH b6@32
O b5@27, OH h2@53	OH t5@6, OH b7@31
O b5@27, OH t3@14	OH t5@6, OH h2@55

O b5@34, HCOO t3@2-t4@3	OH t6@5, CO f2@44
O b5@34, HCOO t3@2-t4@3	OH t6@5, CO h3@57
O b6@30, CO t5@9	OH t6@5, H f2@44
O b6@30, COOH t5@9	OH t6@5, H h1@59
O b6@30, HCOOH t5@9	OH t6@5, H h3@57
O b6@30, O h2@53	OH t6@5, OH f2@44
O b6@30, OH h2@53	OH t7@12, CO f4@45
O b6@30, OH t5@9	OH t7@12, CO h4@61
O b6@32, HCOO t4@3-t5@6	OH t7@12, CO h5@62
O b6@32, HCOO t5@6-t4@3	OH t7@12, H f4@45
O b7@31, CO h3@54	OH t7@12, H f5@46
O b7@31, CO t5@6	OH t7@12, H h4@61
O b7@31, COOH t5@6	OH t7@12, H h5@62
O b7@31, H h3@54	OH t7@12, HCOOH h4@61
O b7@31, HCOO t5@6-t5@9	

References

- (1) Singh, S.; Li, S.; Carrasquillo-Flores, R.; Alba-Rubio, A. C.; Dumesic, J. A.; Mavrikakis, M. Formic Acid Decomposition on Au Catalysts: DFT, Microkinetic Modeling, and Reaction Kinetics Experiments. *AIChE J.* **2014**, *60*, 1303–1319.
- (2) Gazsi, A.; Bánsági, T.; Solymosi, F. Decomposition and Reforming of Formic Acid on Supported Au Catalysts: Production of CO-Free H₂. *J. Phys. Chem. C* **2011**, *115*, 15459–15466.
- (3) Ojeda, M.; Iglesia, E. Formic Acid Dehydrogenation on Au-Based Catalysts at near-Ambient Temperatures. *Angew. Chemie Int. Ed.* **2009**, *48*, 4800–4803.
- (4) Norskov, J. K.; Abild-Pedersen, F.; Studt, F.; Bligaard, T. Density Functional Theory in Surface Chemistry and Catalysis. *Proc. Natl. Acad. Sci.* **2011**, *108*, 937–943.
- (5) Rangarajan, S.; Maravelias, C. T.; Mavrikakis, M. Sequential-Optimization-Based Framework for Robust Modeling and Design of Heterogeneous Catalytic Systems. *J. Phys. Chem. C* **2017**, *121*, 25847–25863.
- (6) Tibshirani, R. Regression Selection and Shrinkage via the Lasso. *J. R. Stat. Soc. B* **1996**, *58*, 267–288.
- (7) Qian, J., Hastie, T., Friedman, J., Tibshirani, R. and Simon, N. Glmnet for Matlab (2013) http://www.stanford.edu/~hastie/glmnet_matlab/ (accessed May 26, 2019).
- (8) Nilekar, A. U.; Greeley, J.; Mavrikakis, M. A Simple Rule of Thumb for Diffusion on Transition-Metal Surfaces. *Angew. Chemie - Int. Ed.* **2006**, *45*, 7046–7049.
- (9) Peng, G.; Mavrikakis, M. Adsorbate Diffusion on Transition Metal Nanoparticles. *Nano Lett.* **2015**, *15*, 629–634.
- (10) Irikura, K. K. Appendix B: Essential Statistical Thermodynamics. In *Computational Thermochemistry: Prediction and Estimation of Molecular Thermodynamics*; Irikura, K. K., Frurip, D. J., Eds.; American Chemical Society: Washington, DC, 1998; pp 402–418.
- (11) Johnson, R. D.; Irikura, K. K.; Kacker, R. N.; Kessel, R. Scaling Factors and Uncertainties for Ab Initio Anharmonic Vibrational Frequencies. *J. Chem. Theory Comput.* **2010**, *6*, 2822–2828.
- (12) Alecu, I. M.; Zheng, J.; Zhao, Y.; Truhlar, D. G. Computational Thermochemistry: Scale Factor Databases and Scale Factors for Vibrational Frequencies Obtained from Electronic Model Chemistries. *J. Chem. Theory Comput.* **2010**, *6*, 2872–2887.
- (13) Scott, A. P.; Radom, L. Harmonic Vibrational Frequencies: An Evaluation of Hartree–Fock, Møller–Plesset, Quadratic Configuration Interaction, Density Functional Theory, and Semiempirical Scale Factors. *J. Phys. Chem.* **1996**, *100*, 16502–16513.
- (14) Stamatakis, M.; Vlachos, D. G. A Graph-Theoretical Kinetic Monte Carlo Framework for on-Lattice Chemical Kinetics. *J. Chem. Phys.* **2011**, *134*, 214115.
- (15) Nielsen, J.; D’Avezac, M.; Hetherington, J.; Stamatakis, M. Parallel Kinetic Monte Carlo Simulation Framework Incorporating Accurate Models of Adsorbate Lateral Interactions. *J. Chem. Phys.* **2013**, *139*, 224706.