Zhenyu Zhang, *^a Dongdong Liu,^a Fengwei Huo,^b Siling Huang,^a Junfeng Cui,^a Yao Lu, ^c Ivan P. Parkin ^d and Dongming Guo^a

Self-healing on fractured surfaces of silicon carbide (SiC) is highly desirable, to avoid the catastrophic failure of high-performance devices working at extreme environments. Nevertheless, self-healing on a fractured surface of an amorphous and crystalline (AAC) composite structure of a brittle nanowire (NW) has not been demonstrated. In this study, self-healing is demonstrated on mismatched fractured surfaces of the AAC composite structure of a brittle solid for a SiC NW with a diameter of 187 nm. Fracture strength is 10.18 GPa for the AAC structure, recovering 11.7% after self-healing on its mismatched fractured surfaces. To the best of our knowledge, we firstly report the self-healing on mismatched fractured surfaces of the AAC structure for a brittle NW. This is a breakthrough of the previous prediction that self-healing could not be realized on a brittle NW with a diameter over 150 nm. A growth of 3 nm was found after self-healing on the gap induced by mismatched fractured surfaces, which is different from previous reports for pure amorphous and monocrystalline brittle NWs. To reduce the potential energy, coherent rebonding and debonding were performed to realize the atomic migration to fill the gap, resulting in the growth of gap of 3 nm to perform self-healing. Our findings shed light on the potential of self-healing for design and fabrication of next-generation high-performance SiC devices used in the vacuum and aerospace industries.

Introduction

Silicon carbide (SiC) is a wide-bandgap and group IV semiconductor with well-established growth processes, and has been widely used for advanced electronic, optoelectronic and electromechanical devices.^{1–5} It has a large indirect bandgap (~ 3.2 eV), high breakdown electric field (2 MV cm^{-1}), great electron mobility ($900 \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$) and high thermal conductivity ($400 \text{ W m}^{-1} \text{ K}^{-1}$).⁶ The unique properties of SiC such as excellent thermal stability, chemical inertness and mechanical robustness make it suitable for applications in high power, high frequency and high temperature fields.^{7,8} For instance, temperatures vary from 300 to 600 °C for the significant applications of automotive and aerospace propulsion systems, deep-

well drilling and geothermal exploration, which is beyond the capability of silicon (Si) devices at temperatures higher than 300 °C. To date, SiC electronic platforms have become the most viable technology for high temperature applications, and field emission transistors of SiC are the most promising candidate for high temperature logic applications, as well as a promising material for next-generation electronic devices.^{7,9}

However, SiC undergoes phase transformation under ablation,¹⁰ irradiation¹¹ and deformation.¹² For instance, an amorphous-to-crystalline shell-core structure forms under neutron irradiation, becoming a kind of amorphous and crystalline (AAC) composite structure.¹³ SiC experiences crystalline-to-amorphous transformation by uniaxial compression,¹⁴ low energy ions,¹⁵ scratching,¹² nano-cutting,¹⁶ laser ablation driven shock compression,¹⁰ ion irradiation,¹⁷ and pressure and shear in a rotational diamond anvil cell,¹⁸ forming an AAC composite structure. After electrical discharge machining on a SiC surface, a re-solidified layer is produced, consisting of polycrystalline SiC, a graphite layer, amorphous Si, carbon (C) and nanocrystalline SiC, forming an AAC structure.¹⁹ Amorphous SiC recrystallizes, when subjected to ion irradiation at elevated temperatures, inducing nucleation and growth of nanoparticles and turning into an AAC structure.¹¹ SiC has an intrinsically brittle nature, and it is easy to crack, forming fractured surfaces. High performance SiC devices are

^aKey Laboratory for Precision and Non-Traditional Machining Technology of Ministry of Education, Dalian University of Technology, Dalian 116024, China.

E-mail: zzy@dlut.edu.cn

^bSchool of Mechanical and Power Engineering, Yingkou Institute of Technology, Yingkou 115014, China

^cDepartment of Chemistry, School of Biological and Chemical Sciences, Queen Mary University of London, London E1 4NS, UK

^dMaterials Chemistry Research Centre, Department of Chemistry, University College London, 20 Gordon Street, London, WC1H 0AJ, UK

widely employed in high power, high frequency and high temperature environments. Self-healing on the AAC composite surfaces of SiC is highly desirable to avoid catastrophic failure, as well as for the stability, reliability and longevity of high-performance devices. Nevertheless, self-healing on AAC composite surfaces has not been demonstrated yet, and the underlying mechanisms are elusive.

Cracks and microcracks greatly reduce the mechanical properties of materials, becoming the main cause of failure for materials. Nonetheless, they are difficult to detect and the repair processes are complex.²⁰ Self-healing on fractured AAC composite surfaces could repair the cracks and microcracks in the high-performance devices automatically, which is vital for the reliability, stability and longevity of devices serving under extreme conditions. Self-healing for polymeric composites consists of three key elements: healing agent and encapsulating and hardening the healing agent in the polymer matrix. Gold (Au) nanowires (NWs) with diameters of 60 and 110 nm realize self-healing, under cyclic deformation induced compressive stresses for cold-welding.²¹ The self-healing ability of layered GeP is provided by low formation energy during charging.²² Bimetallic Au/platinum (Pt) catalytically powered nanomotors autonomously heal microscopic mechanical cracks, in the presence of hydrogen peroxide (H₂O₂) fuel solution.²³ Self-healing of aluminum oxide is observed in an oxygen (O₂) environment during deformation by transmission electron microscopy (TEM).²⁴ A confined phase change memory device demonstrates the self-healing by a metallic surfactant layer.²⁵ The self-healing is performed using the voltage polarity to control the direction of electromigration of the phase change material and fill the nanoscale voids. The Au nanofilm undergoes self-healing through vigorous mechanical shaking.²⁶ Self-healing is reported on fractured gallium arsenide (GaAs) NWs.²⁷ However, the GaAs NW is not completely fractured, and there is an amorphous oxide layer on the fractured surface with a thickness of ~2 nm. Moreover, there is no *in situ* TEM nanomechanical testing on the recovered NWs. Si NW battery electrodes undergo self-healing induced by lithium-assisted electrochemical welding.²⁸ A pre-notched WS₂/a-C coating undergoes self-healing under sliding contact by forming tribofilms.²⁹ Self-healing is found on ultrathin gold NWs through mechanical manipulation.³⁰ It has attracted much attention, due to the significance in maintaining the reliability, stability and longevity of high-performance devices. Nevertheless, self-healing reported in the literature needs external interventions, such as healing agents, deformation, charging, fuel solution, voltage and surfactant layer, mechanical shaking, amorphous oxide layer, electrochemical welding, sliding and mechanical manipulation.

Recently, self-healing is confirmed on fractured surfaces of SiC with diameters of 87, 104 and 102 nm under vacuum without external interventions.^{31,32} However, the self-healing occurred on pure crystalline or amorphous fractured surfaces, resulting in applications that are limited dramatically under the two extreme conditions. For example, SiC undergoes phase transformation under deformation, stress and ion

irradiation,^{13–18} forming an AAC composite structure. Therefore, the AAC composite structure is a usual state of SiC under working conditions. Moreover, phase transformation induces mismatched fractured surfaces, in terms of the change of volume and mismatching for the crystalline lattice between two different phases. In this regard, mismatched surfaces form after fracture, rather than matched fractured surfaces on the pure crystalline or amorphous surfaces.³² It was predicted that self-healing could not be realized on fractured NWs with diameters more than 150 nm, on account of the big gap generated by the variation of height on the fractured rough surfaces.³¹ This prediction is based on the fact that the larger the diameter, the rougher the surfaces generated on the fractured parts. Previous research studies demonstrate that rough surfaces have extreme difficulty in undergoing self-healing, due to the big gap considerably impeding the contact of fractured surfaces. Without the discovery of the new mechanism and phenomenon, this common sense could not be broken. Hence, it is a challenge to perform self-healing on fractured surfaces of brittle NWs with diameters more than 150 nm. SiC is a hard-brittle material, which is easy to crack under deformation. For this reason, nonuniform NWs are used to conduct *in situ* TEM tensile tests, avoiding the fracture of several segments simultaneously.³² For a uniform NW, a purely local amorphous phase in a single crystal is employed to carry out the self-healing, because of the lower fracture strength (8.8 GPa)³¹ of the amorphous phase compared to that of the monocrystalline phase (13.4 GPa).³² When the amorphous phase accounts for a lower volume in the AAC composite structure of SiC, it is difficult to conduct self-healing on mismatched fractured surfaces. On the other hand, a focused ion beam (FIB) is widely used to manipulate NWs, unavoidably inducing contamination and damage to the NWs.^{31,32} The measured and characterized results obtained by the FIB have a risk of affecting the performance of devices, and hence the FIB could not be applied to design and fabricate high-performance devices. As a result, it is necessary to develop a setup and approach to manipulate the NWs without the FIB techniques.

In this study, self-healing is demonstrated on mismatched fractured surfaces of the AAC composite structure of a brittle solid with a uniform diameter of 187 nm, which is performed by *in situ* TEM nanomechanical tests. A new setup was developed to manipulate the NWs, to avoid the contamination and damage induced by FIB operations. The self-healing mechanisms on mismatched fractured surfaces of the AAC composite structure were explored and elucidated by molecular dynamics (MD) simulations.

Results

Fig. 1(a) illustrates the photograph of a mouse whisker Chinese brush. A mouse whisker has a tapered tip (Fig. 1(b)), facilitating the tip inserting in a hole of a copper (Cu) grid of TEM samples. A SiC NW was picked up using the mouse whisker tip (Fig. 1(c)), which is performed in a developed

Fig. 1 (a) Photograph of a mouse whisker Chinese brush, and (b) its SEM image of the tip for a mouse whisker, (c) optical image of picking up a SiC NW using the tip in (b), and by (d) a developed setup.

Fig. 2 SEM images of (a) a SiC NW fixed by conductive Ag epoxy on a PTP device, and (b) its enlarged view in (a) marked by a green square.

setup (Fig. 1(d)). The SiC NW was fixed by conductive silver (Ag) epoxy on a push-to-pull (PTP) device, as shown by the scanning electron microscopy (SEM) images in Fig. 2. After solidification of the conductive Ag epoxy in air, the NW is fixed well, and the Ag epoxy is within the two edges of the PTP device (Fig. 2(b)). It is difficult to control the volume of epoxy accurately to make the epoxy reaching the two edges without

leaking in the gap below the NW, which needs a highly skilled technique.

Fig. 3 shows the snapshots of TEM images for a SiC NW under electron irradiation at a beam density of 7.38 A cm^{-2} for 0, 20, 40, 60, 80, and 100 min, respectively. The irradiated part on the NW is marked by a red circle in Fig. 3(a). The SiC NW prior to electron irradiation exhibits monocrystalline character-

Fig. 3 Snapshots of TEM images for a SiC NW under electron irradiation at a beam density of 7.38 A cm^{-2} for (a) 0, (b) 20, (c) 40, (d) 60, (e) 80, and (f) 100 min. The insets in (a) and (f) are their corresponding SAED patterns taken from their red circles, respectively.

Fig. 4 HRTEM images of the AAC structure of SiC NW taken from the red circle in Fig. 3(f) (a) at the left edge, and (b) central area.

istics, as revealed by the selected area electron diffraction (SAED) pattern (inset of Fig. 3(a)). The axial direction of the NW is along the $\langle 111 \rangle$ orientation, as illustrated in the inset of Fig. 3(a). Under electron irradiation for 100 min, amorphous phase transformation takes place, which is indicated by a halo in the inset of Fig. 3(f). After electron irradiation, the AAC composite structure in the NW is formed (inset of Fig. 3(f)). At the left edge, the amorphous phase dominates, except two crystallites with sizes of 2 nm approximately (Fig. 4(a)), while the crystalline phase predominates at the central area (Fig. 4(b)). As the diameter of SiC is 187 nm, an electron beam has difficulty in penetrating the central area, resulting in the dark image (Fig. 4(b)).

Fig. 5 shows the snapshots of TEM images taken from *in situ* TEM fracture tests for the first fracture on a SiC NW and for the second fracture after self-healing on its mismatched fractured AAC surfaces. Movies S1 and S2† display the *in situ* TEM tests for the first fracture on a SiC NW and for the second fracture on the mismatched fractured surfaces of the AAC structure after self-healing, respectively. Prior to fracture tests,

the *in situ* TEM nanomechanical system was calibrated for load and displacement. Fracture tests were performed at displacement-controlled mode, and loading and unloading speeds were 5 nm s^{-1} . The maximum displacements were set to 250 and 100 nm for the first and second fracture tests, respectively. A uniform SiC NW was selected as the specimen with a diameter of 187 nm (Fig. 5(a)). It is fractured completely in Fig. 5(c). After fracture, the stress in the SiC NW was released, resulting in the misalignment of two axes of the two fractured parts and forming mismatched fractured AAC surfaces (Fig. 5(d)). The AAC structure has a lower fracture strength compared with a single crystal SiC NW, due to its outside amorphous layer with a lower fracture strength. This makes the fracture position occur at the AAC structure. The mismatched fractured surfaces come in contact only without exerted force, which is measured and confirmed using the *in situ* TEM nanomechanical system. After coming in contact, self-healing was started and continued for 20 min (Fig. 5(e)). During self-healing on the mismatched fractured surfaces, the electron beam was shut off from the start to the end. After self-

Fig. 5 Snapshots of TEM images taken from *in situ* TEM fracture tests for the first fracture (a), (b), (c), and (d) on a SiC NW, and for the second fracture after self-healing (e), (f), (g), and (h) on its mismatched fractured AAC surfaces.

Fig. 6 (a) Stress as a function of displacement for the first and second fracture tests, and TEM images prior to (b) and after (c) self-healing on the mismatched fractured surfaces of a SiC NW.

healing, the second fracture test was carried out to measure the effect of self-healing. After the second fracture test, the mismatched fractured surfaces are fractured completely (Fig. 5(g)).

Fig. 6(a) shows the drawing of the stress as a function of displacement for the first and second fracture tests. The stress was loaded on a SiC NW subtracting that on the PTP device. Fracture strength, σ_F , is measured and calculated,

$$\sigma_F = F_{\max}/A \quad (1)$$

where $F_{\max}$ is the maximum force at fracture, and A is the area of the fractured surface. Fracture strength was 10.18 and 1.19 GPa for the first and second fracture tests, respectively. This means that fracture strength recovered 11.7% after self-healing on the mismatched fractured surfaces, which is a breakthrough of the prediction that self-healing could not be realized when a brittle NW with a diameter more than 150 nm was used.³¹ Prior to self-healing, the mismatched fractured surfaces in contact have a gap with a length of 17 nm (Fig. 6(b)). After self-healing, the gap reduces to 14 nm (Fig. 6(c)), and a growth of 3 nm on the mismatched fractured surfaces took place to fill the gap. This is different from previous reports for self-healing on fractured surfaces of pure amorphous and monocrystalline SiC NWs, in which there is no such growth on the healed fractured surfaces.^{31,32}

Discussion

A new setup was developed to operate the NW and fix it using conductive Ag epoxy. Using this method, damage and contamination induced by the FIB are effectively avoided. Electron irradiation and *in situ* TEM fracture tests were performed, which showed that the dangling bonds are not passivated as those exposed in air. NWs have a large surface-to-volume ratio, compared with their bulk counterparts.^{33,34} This makes the dangling bonds prevalent on the mismatched fractured surfaces. As observed under vacuum using a TEM, dangling bonds have high energy on the mismatched fractured surfaces of the AAC structure, facilitating the rebonding and self-healing on the mismatched fractured surfaces of a SiC NW. In addition, SiC is a polar semiconductor, and there are opposite charges on the mismatched fractured surfaces.⁸ This results in the electrostatic force on the mismatched fractured surfaces, promoting the self-healing to take place. Another driving force for self-healing is to reduce the energy of system by reducing the surface area, as well as surface energy.²⁷

To elucidate the fundamental mechanisms of self-healing on the mismatched fractured surfaces of the AAC structure, MD simulations were conducted. Fig. 7(a) illustrates the side and front views of a constructed MD model for a SiC NW, which is consistent with the AAC structure in Fig. 3 and 4, *i.e.*

Fig. 7 (a) Side and front views of a constructed MD model for a SiC NW, (b) its front views prior to coming in contact and after self-healing on the mismatched fractured surfaces, and (c) energy and (d) load as a function of time and displacement, respectively.

an amorphous layer outside and a single crystal inside. The percentage between amorphous and crystalline phases was adjusted, according to the recovery rate of fracture strength between the first and second fracture. Fig. 7(b) shows the front views prior to coming in contact and after self-healing on mismatched fractured surfaces, which is in good agreement with the TEM images in Fig. 5 and 6. After fracture, amorphous atoms increase 12% on the fractured surfaces, compared with those before fracture. This is on account of the transformation from crystalline to amorphous atoms during fracture. The tendency between total and potential energy agrees well (Fig. 7(c)). The first fracture test continued from 0 to 150 ps, axis misalignment was from 150 to 210 ps, the backing process of the right fractured NW was from 210 to 350 ps, self-healing continued from 350 to 450 ps, and the second fracture test after self-healing was from 450 to 600 ps. The highest peak between 0 and 100 ps corresponds to the first fracture test. Energy increases sharply, on account of the increase of strain energy during the tensile test. With the release of strain energy in fracture, the energy decreases rapidly. Energy of a small peak between 300 and 400 ps increases firstly, in terms of the broken atoms on the fractured surfaces prior to coming in contact. It decreases because of the self-healing on mismatched fractured surfaces of the AAC structure. The peak between 400 and 500 ps is attributed to the second fracture test after self-healing. The energy increases firstly by the increase of strain energy, and then decreases with the release of strain energy during fracture. From Fig. 7(d) for the two frac-

ture tests, fracture strength restores 14.1% on the mismatched fractured surfaces, which is in good agreement with 11.7% in Fig. 6(a) measured using an *in situ* TEM nanomechanical system. There is a small discrepancy between the experimental and theoretical results, which is mainly attributed to the size effect. In experiments, the SiC NW has a diameter of 187 nm, which could not be simulated by MD at such a large scale. Generally, the simulated size of MD is at several nm, *e.g.* 8 nm in diameter used in this work. For a smaller diameter of NW, the surface-to-volume ratio is higher than that of a bigger one. The smaller the diameter of a NW, the lower the defects in a NW. On account of the brittle nature of SiC, a few materials might be lost during fracture, leading to a non-smooth surface and a gap between fractured surfaces formed after fracture. The bigger the diameter of a SiC NW, the rougher the surfaces and larger the gap generated, the more difficult for self-healing. For these cases, the fracture strength in experiment is lower than that of MD simulations.

Fig. 8 shows the snapshots of self-healing on mismatched fractured surfaces between amorphous phases of the AAC structure in a SiC NW, and their potential energy as a function of time. During self-healing on mismatched fractured surfaces between amorphous phases, C1 and Si1 atoms firstly rebond (Fig. 8(a) and (b)), then C1 and Si2 atoms rebond and afterwards debond, and finally C1 and C2 atoms rebond. During the rebonding between C1 and Si1 atoms, the potential energy decreases 1.86 and 1.97 eV for C1 and Si1 atoms (Fig. 8(d)), respectively, and the total potential energy decreases 3.83 eV.

Fig. 8 Snapshots (a), (b), and (c) of self-healing on mismatched fractured surfaces between amorphous phases of the AAC structure in a SiC NW, and (d) their potential energy as a function of time.

For rebonding and debonding between C1 and Si2 atoms, the potential energy decreases 2.78 eV firstly and then increases 2.65 eV. During the rebonding between C1 and C2 atoms, the potential energy decreases 2.97 eV.

Fig. 9 depicts the snapshots of self-healing on mismatched fractured surfaces between monocrystalline and amorphous phases of the AAC structure in a SiC NW, and their potential energy as a function of time. During self-healing on mismatched fractured surfaces between monocrystalline and amorphous phases, the Si4 atom rebonds Si2 firstly (Fig. 9(a) and (b)), then Si4 rebonds Si1 (Fig. 9(c)), and finally Si1 debonds Si2 and simultaneously Si1 rebonds the Si3 atom. During the rebonding between Si4 and Si2 atoms, the potential energy decreases 2.6 eV (Fig. 9(d)). For the rebonding between Si4 and Si1 atoms, the potential energy decreases 0.82 eV. During the coinstantaneous rebonding between Si1 and Si3 and debonding between Si1 and Si2 atoms, the potential energy decreases 0.2 eV for the Si3 atom and increases 0.25 eV for the Si2 atom, and that of the Si1 atom increases 0.07 eV.

Fig. 10 illustrates the snapshots of fracture after self-healing in Fig. 8 and their potential energy as a function of time. In the fracture after self-healing, C1 and Si1 atoms debond (Fig. 10(a) and (b)), then Si1 rebonds the Si2 atom (Fig. 10(c)), and finally Si1 and Si2 atoms debond. The potential energy increases 1.91 eV during the debonding between C1 and Si1 atoms (Fig. 10(d)). For the rebonding and debonding

between Si1 and Si2 atoms, the potential energy firstly decreases 0.49 eV and then increases 0.17 eV.

Fig. 11 shows the snapshots of fracture after self-healing in Fig. 9 and their potential energy as a function of time. For the fracture after self-healing between monocrystalline and amorphous phases, Si1 and Si4 atoms debond firstly (Fig. 11(a) and (b)), then Si1 rebonds the Si2 atom, afterwards Si1 rebonds Si4, and finally Si1 debonds the Si2 atom (Fig. 11(c)). The potential energy increases 0.78 eV during the debonding between Si1 and Si4 atoms (Fig. 11(d)). For the rebonding and debonding between Si1 and Si2 atoms, the potential energy reduces and increases 0.71 and 0.72 eV, respectively. In the rebonding between Si1 and Si4 atoms, the potential energy decreases 1.23 eV.

During self-healing on mismatched fractured surfaces between amorphous phases, rebonding occurs between C1 and C2, C1 and Si1, and C1 and Si2 atoms. Debonding occurs between C1 and Si2 atoms. Rebonding and debonding take place between C1 and Si2 atoms, after which the potential energy reduces 0.13 eV (Fig. 8). During self-healing between monocrystalline and amorphous phases, rebonding takes place between Si2 and Si4, Si1 and Si3, and Si1 and Si4 atoms. Debonding occurs between Si1 and Si2 atoms. Rebonding and debonding occur among Si1, Si2 and Si3 atoms, and after that the potential energy of the three atoms increases 0.12 eV (Fig. 9). During fracture after self-healing between the amorphous phases, C1-Si1 and Si1-Si2 bonds break, and Si1-Si2

Fig. 9 Snapshots (a), (b), and (c) of self-healing on mismatched fractured surfaces between monocrystalline and amorphous phases of the AAC structure in a SiC NW, and (d) their potential energy as a function of time.

Fig. 10 Snapshots (a), (b), and (c) of fracture after self-healing in Fig. 7, and (d) their potential energy as a function of time.

Fig. 11 Snapshots (a), (b), and (c) of fracture after self-healing in Fig. 8, and (d) their potential energy as a function of time.

bonds form. After the rebonding and debonding of Si1–Si2 bonds, the potential energy decreases 0.32 eV (Fig. 10). For the fracture after self-healing between monocrystalline and amorphous phases, Si1–Si4 and Si1–Si2 bonds break, while they form again during the process. Due to the debonding and rebonding, the potential energy reduces 0.45 eV for Si1–Si4 bonds, and increases 0.01 eV for Si1–Si2 bonds (Fig. 11).

Rebonding and debonding coherently occur for both self-healing and fracture after self-healing on mismatched fractured surfaces of the AAC structure. Rebonding decreases the potential energy, whereas debonding increases that. After synergistic rebonding and debonding, the potential energy reduces 0.13, 0.32, and 0.45 eV for C1–Si2, Si1–Si2 and Si1–Si4 atoms, respectively. It is a driving force to reduce the energy of system. Coherent rebonding and debonding correspond to the variation of locations of atoms, inducing atomic migration. This contributes the atomic growth of 3 nm on the mismatched fractured surfaces in Fig. 6. The potential energy increases 0.12 eV after synergistic rebonding and debonding among Si1, Si2 and Si atoms, indicating atomic migration taking place beyond two atoms. This makes the atomic migration extend to three atoms, resulting in effective atomic migration. Consistent rebonding and debonding for Si1 and Si2 atoms increase 0.01 eV, meaning the atomic migration costing only a bit potential energy. During self-healing, the potential energy reduces 3.83, 2.78, 2.97 and 2.6 eV by rebonding for C1–Si1, C1–Si2, C1–C2 and Si2–Si4 four pairs of atoms, respectively, which is responsible for the self-healing occurring on mismatched fractured surfaces in Fig. 5 and 6. Rebonding

could reduce the potential energy dramatically. Nevertheless, the gap in Fig. 6 is too large to rebond, which is formed by mismatched fractured rough surfaces on a SiC NW with a diameter of 187 nm. Coherent rebonding and debonding reduce the potential energy, as well as realizing the atomic migration to fill the gap for performing self-healing. To reduce the potential energy of the SiC NW, synergistic rebonding and debonding occur for the atomic migration to fill the gap, resulting in the growth of gap for 3 nm in Fig. 6 to conduct self-healing on the mismatched fractured surfaces.

Conclusions

In summary, a new setup was developed using a mouse whisker to manipulate a SiC NW, and fixing it by conductive Ag epoxy. After solidification, the epoxy glue reached two edges of a PTP device, without leaking to the gap in the PTP device. By this method, contamination and damage induced by the traditional FIB were effectively eliminated. Self-healing was demonstrated on the mismatched fractured surfaces of the AAC composite structure of a SiC NW. The NW has a diameter of 187 nm, and the self-healing breaks the previous prediction that a brittle NW could not perform self-healing when its diameter is more than 150 nm. MD simulations were conducted to elucidate the fundamental mechanisms of self-healing. Rebonding reduces the potential energy, whereas debonding increases the energy. The potential energy decreases 3.83, 2.97 and 2.6 eV by rebonding for C–Si, C–C

and Si-Si three pairs of atoms, respectively. Through coherent rebonding and debonding, the potential energy reduces 0.13 and 0.45 eV for C-Si and Si-Si atoms, respectively. To carry out the self-healing, atomic migration was carried out to fill the gap by synergistic rebonding and debonding to reduce the potential energy. Through the atomic migration on the gap, a growth of 3 nm was found by an *in situ* TEM nanomechanical test. With the growth on the gap, self-healing was performed on mismatched fractured surfaces of the AAC structure in a SiC NW with a diameter of 187 nm. These findings pave a way to improve greatly the performance of SiC-based devices, as well as polar semiconductors and ceramics, working in air-free environments under harsh conditions.

Experimental and simulations

A setup was developed using an optical microscope (Leica DM2500 M, Germany) and a three-dimensional (3D) micrometer platform (Shenzhen MISI precision machinery Co., Ltd). A mouse whisker was cut off from a mouse whisker Chinese brush. The mouse whisker was glued by conductive Ag epoxy on the tip of an embroidery needle. The needle was inserted into a red foam block inclined to 45° along the horizontal surface. Another side of the red foam block was glued on one side of a blue foam block using a double-faced adhesive tape. The blue foam block was fixed on a glass block by a double-faced adhesive tape, putting on a mechanical stage of the 3D micrometer platform.

Single crystal 3C-SiC NWs (Nanjing XFNANO Materials Tech Co., Ltd) were ultrasonically distributed in acetone solution for 3 min. A pipette was used to suck up the solution containing SiC NWs. A drop of solution was dripped on a Cu grid of TEM specimens, on which there were holes of 50 μm uniformly distributed without a C film. After evaporation of the acetone solution, SiC NWs were dispersed on the Cu grid. The Cu grid was put on a mechanical stage of the optical microscope. The mouse whisker was inserted in a hole under a NW, which was performed in the microscope by the micrometer platform. After touching the NW, it was picked up by the mouse whisker operated by the micrometer platform. Picking up the NW in air, the Cu grid was replaced by a PTP device of an *in situ* TEM nanomechanical system (PI 95 TEM PicoIndenter, Bruker, USA). Then, the NW was put on the PTP device at a suitable place manipulated by the mouse whisker tip in the optical microscope. The mouse whisker tip was employed to dip a drop of conductive Ag epoxy, touching two ends of the NW and leaving a small drop of epoxy glue. After 24 h in air, the conductive Ag epoxy glue was solidified, fixing the NW on the PTP device. After solidification, the PTP device was mounted on a PI 95 PicoIndenter system to perform *in situ* TEM nanomechanical tests, equipped with a TEM (Tecnai F20, FEI, USA). The NW was characterized using a SEM (Helios G4 CX DualBeam, Thermo Fisher Scientific, USA).

An MD model with the zinc blende structure for 3C-SiC was constructed with a crystalline lattice constant of 4.36 Å. The

model had a radius of 40 Å and a length of 180 Å, and the axis was along the X direction. X, Y and Z directions were set along the [111], $[-1-12]$ and $[1-10]$ orientations, respectively. The MD model had 86 271 atoms, and was calculated using LAMMPS software. Shrink-wrapped boundary conditions were applied to X, Y and Z directions. The model was relaxed at 300 K for 20 picoseconds (ps), and a constant volume and temperature (NVT) ensemble was applied to the calculating system. During the simulation, the temperature was set at 300 K, and the time step was 0.001 ps. To obtain the AAC composite structure, the temperature of the model was increased from 300 to 4000 K within 500 ps firstly, and then decreased rapidly from 4000 to 300 K for 30 ps. After 30 ps, the temperature reached 1160.5 K, and then decreased to 300 K in 20 ps. Finally, the temperature of the system was kept approximately at 300 K. By this method, an amorphous-to-crystalline structure was formed in the SiC NW.

Prior to a tensile test, two ends along the X direction were fixed for 40 Å respectively, and the middle part with a length of 100 Å was used for the tensile test. Keeping the left fixed part constant, the right fixed part was moved along the positive direction of X axis, *i.e.* [111] orientation at a speed of 0.08 Å ps^{-1} for 150 ps, and finally the SiC NW was fractured completely. Keeping the left fractured part stable, the right fractured part was moved along the positive direction of Y axis at a speed of 0.05 Å ps^{-1} for 60 ps, and finally the mismatched distance varied from 21.3 to 21.4 Å. The right fractured part was moved along the negative direction of X axis at a speed of 0.08 Å ps^{-1} for 150 ps, coming in contact with the left fixed fractured part and remaining constant for 100 ps. After coming in contact, the second fracture test on the mismatched surfaces of the SiC NW was started. The left mismatched part was kept constant, and the right mismatched part was moved along the positive direction of X axis at a speed of 0.08 Å ps^{-1} for 150 ps, and finally the right mismatched part was fractured completely. Simulation results were analyzed and visualized using Ovito software, and atomistic position, force and energy information was extracted and gained using the software. In the MD model, red color represents C atoms, and blue color denotes Si atoms.

Author contributions

Z. Y. Z. and D. M. G. conceived the projects. D. D. L. and J. F. C. performed the experiments. Z. Y. Z. wrote the paper. S. L. H. conducted the MD simulations. F. W. H., Y. L. and I. P. P. analyzed the self-healing mechanisms on the mismatched fractured surfaces of the AAC composite structure in SiC. All authors discussed the results and commented on the manuscript.

Conflicts of interest

There are no conflicts of interest to declare.

Acknowledgements

The authors acknowledge the financial support from the National Key R&D Program of China (2018YFA0703400), the Xinghai Science Funds for Distinguished Young Scholars and Thousand Youth Talents at Dalian University of Technology, and the Collaborative Innovation Center of Major Machine Manufacturing in Liaoning. Professor Parkin thanks the Chinese government for CSC scholarships and a visiting professorship, and EPSRC M3S CDT project (EP/L015862/1). Dr Y. Lu acknowledges the financial support from the QMUL-SBCS start up.

References

- 1 X. D. Han, Y. F. Zhang, K. Zheng, X. N. Zhang, Z. Zhang, Y. J. Hao, X. Y. Guo, J. Yuan and Z. L. Wang, *Nano Lett.*, 2007, **7**, 452–457.
- 2 G. M. Cheng, T. H. Chang, Q. Q. Qin, H. C. Huang and Y. Zhu, *Nano Lett.*, 2014, **14**, 754–758.
- 3 S. L. Wang, Y. Q. Wu, L. W. Lin, Y. H. He and H. Huang, *Small*, 2015, **11**, 1672–1676.
- 4 S. L. Wang, Z. W. Shan and H. Huang, *Adv. Sci.*, 2017, **4**, 1600332.
- 5 W. F. Koehl, B. B. Buckley, F. J. Heremans, G. Calusine and D. D. Awschalom, *Nature*, 2011, **479**, 84–87.
- 6 C. R. Eddy and D. K. Gaskill, *Science*, 2009, **324**, 1398–1400.
- 7 T. H. Lee, S. Bhunia and M. Mehregany, *Science*, 2010, **329**, 1316–1318.
- 8 R. Madar, *Nature*, 2004, **430**, 974–975.
- 9 D. Nakamura, I. Gunjishima, S. Yamaguchi, T. Ito, A. Okamoto, H. Kondo, S. Onda and K. Takatori, *Nature*, 2004, **430**, 1009–1012.
- 10 S. Zhao, R. Flanagan, E. N. Hahn, B. Kad, B. A. Remington, C. E. Wehrenberg, R. Cauble, K. More and M. A. Meyers, *Acta Mater.*, 2018, **158**, 206–213.
- 11 L. M. Zhang, W. L. Jiang, W. S. Ai, L. Chen and T. S. Wang, *J. Nucl. Mater.*, 2018, **505**, 249–254.
- 12 Y. Liu, B. Z. Li and L. F. Kong, *Ceram. Int.*, 2018, **44**, 11910–11913.
- 13 E. M. Huseynov, *Phys. B*, 2017, **510**, 99–103.
- 14 Z. H. Wu, W. D. Liu and L. C. Zhang, *J. Am. Ceram. Soc.*, 2018, **101**, 3585–3596.
- 15 A. Benyagoub, *Nucl. Instrum. Methods Phys. Res., Sect. B*, 2008, **266**, 2766–2771.
- 16 Z. H. Wu, W. D. Liu and L. C. Zhang, *Comput. Mater. Sci.*, 2017, **137**, 282–288.
- 17 Y. W. Zhang, M. Ishimaru, T. Varga, T. Oda, C. Hardiman, H. Z. Xue, Y. Katoh, S. Shannon and W. J. Weber, *Phys. Chem. Chem. Phys.*, 2012, **14**, 13429–13436.
- 18 V. I. Levitas, Y. Z. Ma, E. Selvi, J. Z. Wu and J. A. Patten, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2012, **85**, 054114.
- 19 T. H. Tan and J. W. Yan, *Acta Mater.*, 2017, **123**, 362–372.
- 20 F. Awaja, S. N. Zhang, M. Tripathi, A. Nikiforov and N. Pugno, *Prog. Mater. Sci.*, 2016, **83**, 536–573.
- 21 C. F. Guo, Y. C. Lan, T. Y. Sun and Z. F. Ren, *Nano Energy*, 2014, **8**, 110–117.
- 22 W. W. Li, X. W. Li, J. L. Yu, J. Liao, B. T. Zhao, L. Huang, A. Abdelhafiz, H. Y. Zhang, J. H. Wang, Z. P. Guo and M. L. Liu, *Nano Energy*, 2019, **61**, 594–603.
- 23 J. X. Li, O. E. Shklyae, T. L. Li, W. J. Liu, H. Shum, I. Rozen, A. C. Balazs and J. Wang, *Nano Lett.*, 2015, **15**, 7077–7085.
- 24 Y. Yang, A. Kushima, W. Z. Han, H. L. Xin and J. Li, *Nano Lett.*, 2018, **18**, 2492–2497.
- 25 Y. J. Xie, W. Kim, Y. Kim, S. Kim, J. Gonsalves, M. BrightSky, C. Lam, Y. Zhu and J. J. Cha, *Adv. Mater.*, 2018, **30**, 1705587.
- 26 E. Smirnov, P. Peljo, M. D. Scanlon, F. Gumy and H. H. Girault, *Nanoscale*, 2016, **8**, 7723–7737.
- 27 Y. B. Wang, H. J. Joyce, Q. A. Gao, X. Z. Liao, H. H. Tan, J. Zou, S. P. Ringer, Z. W. Shan and C. Jagadish, *Nano Lett.*, 2011, **11**, 1546–1549.
- 28 K. Karki, E. Epstein, J. H. Cho, Z. Jia, T. Li, S. T. Picraux, C. S. Wang and J. Cumings, *Nano Lett.*, 2012, **12**, 1392–1397.
- 29 H. T. Cao, J. T. M. De Hosson and Y. T. Pei, *Mater. Res. Lett.*, 2019, **7**, 103–109.
- 30 B. J. Wang, Y. Han, S. Xu, L. Qiu, F. Ding, J. Lou and Y. Lu, *Small*, 2018, **20**, 1704085.
- 31 J. F. Cui, Z. Y. Zhang, H. Y. Jiang, D. D. Liu, L. Zou, X. G. Guo, Y. Lu, I. P. Parkin and D. M. Guo, *ACS Nano*, 2019, **13**, 7483–7492.
- 32 Z. Y. Zhang, J. F. Cui, B. Wang, H. Y. Jiang, G. X. Chen, J. H. Yu, C. T. Lin, C. Tang, A. Hartmaier, J. J. Zhang, J. Luo, A. Rosenkranz, N. Jiang and D. M. Guo, *Nanoscale*, 2018, **10**, 6261–6269.
- 33 A. Banerjee, D. Bernoulli, H. T. Zhang, M. F. Yuen, J. B. Liu, J. C. Dong, F. Ding, J. Lu, M. Dao, W. J. Zhang, Y. Lu and S. Suresh, *Science*, 2018, **360**, 300–302.
- 34 Y. W. Hu, J. Li, J. F. Tian, Y. Xuan, B. W. Deng, K. L. McNear, D. G. Lim, Y. Chen, C. Yang and G. J. Cheng, *Nano Lett.*, 2016, **16**, 7536–7544.