**Liraglutide-loaded poly(lactic-co-glycolic acid) microspheres: Preparation and
in vivo evaluation**

Junzi Wu¹, Gareth R. Williams², Christopher Branford-White³, Heyu Li¹, Yan Li^{4*},
Li-Min Zhu^{1*}

¹College of Chemistry, Chemical Engineering and Biotechnology, Donghua University, Shanghai
201620, P.R. China

²UCL School of Pharmacy, University College London, 29-39 Brunswick Square, London,
WC1N 1AX, UK

³Faculty of Life Sciences & Computing, London Metropolitan University,
London N7 8DB, UK

⁴Department of Geriatrics, The First People's Hospital of Yunnan Province, Yunnan
650034, P.R. China

(phone numbers: + 86 021 67792655; E-mail: lzhu@dhu.edu.cn; liyanken@126.com)

Submitted to *European Journal of Pharmaceutical Sciences*

Abstract In this work, we sought to prepare sustained-release injectable microspheres loaded with the GLP-1 analogue liraglutide. Using water-in-oil-in-water double emulsion methods, poly(lactic-co-glycolic acid) (PLGA) microspheres loaded with liraglutide were prepared. The microspheres gave sustained drug release over 30 days with cumulative release of up to 90% reached *in vitro*. The microspheres were further studied in a rat model of diabetes over 30 days, and their performance compared with a group given daily liraglutide injections. Reduced blood sugar levels were seen in the microsphere treatment groups, with the results being similar to treatment with conventional injections between 10 and 25 days after the commencement of treatment. After 5 and 30 days of treatment, the microspheres seem a little slower to act than the injections. The pathology of the rats' spleen, heart, kidney and lungs was probed after the 30-day treatment period, and the results indicated that the microspheres were safe and had beneficial effects on the liver, reducing the occurrence of fatty deposits seen in untreated diabetic rats. Moreover, in terms of liver, renal and cardiac functions, and blood lipid and antioxidant levels, the microspheres were as effective as the injections. The expression of several proteases linked to the metabolism of aliphatic acids and homocysteine were promoted by the microsphere formulations. Inflammatory markers in the microsphere treatment groups were somewhat higher than the injection group, however. The liraglutide / PLGA microspheres prepared in this work are overall shown to be efficacious in a rat model of diabetes, and we thus believe they have strong potential for clinical use.

Keywords: Liraglutide; microspheres; poly (lactide-co-glycolide); water in oil in

water; type 2 diabetes mellitus

1. Introduction

Liraglutide is a powerful biologic drug used for the treatment of type 2 diabetes mellitus. The drug was introduced in the EU in 2009, and in the USA in 2010 [Lorenz M, et al., 2013]. In 2015, Novo Nordisk began to market liraglutide as a treatment for obese adults who have associated co-morbidities [Alfaris N, et al., 2013]. Liraglutide is an analogue of glucagon-like peptide 1 (GLP-1), with 97% sequence homology to human GLP-1, and is produced by recombination technologies using yeast [Gallwitz, B, 2008]. It is poorly water-soluble, and is mainly administered by injection as a solution with sodium dihydrogen phosphate in a mixed solvent system of water and 1,2-propanediol. The dose is 1.8 mg per day [Aimaretti G, 2010; Joffe D, 2010]. Such daily injection application causes significant patient discomfort, and thus there is a need to develop a pharmaceutical strategy to extend the release period and reduce the frequency of injections. In order to solve this problem, many scholars have explored a range of sustained release systems for proteins. For instance, Graf [Graf A, et al., 2009] prepared insulin-loaded poly(alkylcyanoacrylate) nanoparticles from microemulsions and were able to extend drug release over 36 h. In other work, Jiang et. al. [Jiang G, et al., 2015] prepared insulin-loaded polymeric micelles which they proposed to be effective candidate carriers for insulin release.

One route commonly used to extend release times is the preparation of microspheres constructed from biodegradable polymers. Poly(DL-lactic-co-glycolic acid) (PLGA) is an FDA certificated “generally regarded as safe” polymer, and has

attracted particular attention for the sustained delivery of protein and peptide drugs. For instance, Zhang and coworkers encapsulated erythropoietin in PLGA microspheres [Zhang W, et al., 2015]. *In vivo* experiments demonstrated that rats suffering from peripheral nerve injuries and treated with erythropoietin microspheres enjoyed enhanced recovery rates compared to those which received daily intraperitoneal injections of erythropoietin. Exenatide, an earlier synthetic GLP-1 receptor activator, has been loaded into a PLGA subcutaneous microsphere drug delivery system developed using a non-aqueous processing medium and found to be effective both *in vitro* and *in vivo* [Lim S M, et al., 2015; Xuan J, et al., 2013]. The microspheres displayed only a small amount of burst release after implantation, and high encapsulation efficiency. In other work, Feng et al. [Feng Q, et al., 2014] found PLGA microspheres loaded with exenatide could effectively reduce blood glucose levels without any inflammatory response being initiated.

There have been many studies in which drug loaded PLGA microspheres have been developed, and the drug loading capability, encapsulation efficiency, release rates and other properties have been investigated in detail [Niu X, et al., 2009; Luo Y, et al., 2014; Andreas K, et al., 2010]. This body of work clearly demonstrates that PLGA microspheres are highly suitable as sustained-release carriers [Ping, 2005], and once-weekly microsphere formulations of exenatide (Bydureon, AstraZeneca) are already available in the clinic [Painter N A, et al., 2013]. The production methods and exact compositions of the microsphere formulations will markedly affect the stability of the incorporated protein, however [Angkawinitwong U, et al., 2015]. To date, the

Commented [g1]: Initial missing

production methods used to generate PLGA microspheres include freeze-drying, spray drying, and emulsion methods [Prajapati V D, et al., 2015; Gavini E et al., 2004; Patel B B, et al., 2014]. Emulsion methods have been extensively investigated in pharmaceutical research for preparing polymeric particles both of small molecule active ingredients and therapeutic proteins. The process can be undertaken with a wide range of polymers, and is relatively easy to scale-up [Iqbal M, et al., 2015]. The oil-in-water emulsion and double emulsion ($w_1/o/w_2$) methods are most widely examined, although sterilization can be challenging and low encapsulation efficacy can be an issue as proteins are able to diffuse from the oil phase to the continuous aqueous phase [Carrascosa C, et al., 2003].

Many researchers have used $w_1/o/w_2$ methods to produce drug-loaded microspheres [e.g. Jiang H L, et al., 2004, 2002; Prieto M J B, et al., 1994]. However, the therapeutic effects of drug loaded PLGA microspheres in diabetic animals and the impacts on key organs such as the liver, kidney and heart remain uncertain. In this study, a water-in-oil-in-water solvent evaporation method was employed to prepare microsphere structures loaded with liraglutide; these were fully characterized and explored both *in vitro* and *in vivo* to evaluate their drug release properties and to determine their therapeutic efficacy in rats.

2. Materials and methods

2.1 Materials

PLGA (poly-D,L-lactide/glycolide 50/50; Mw 30 kDa) was purchased from the

Jinan Daigang Biomaterial Co., Ltd (Jinan, China). Liraglutide was kindly provided by the Wuxi Yatai Biotechnology Co., Ltd. (Wuxi, China). Poly(vinyl alcohol) (PVA-217, degree of polymerization 1700, degree of hydrolysis 88.5%, Mw 72 – 84 kDa) was purchased from Kuraray (Osaka, Japan). Acetonitrile and trifluoroacetic acid (both HPLC grade) were obtained from Sigma-Aldrich (St. Louis, MO, USA). All other reagents were of analytical grade.

Aspartate transaminase, alanine aminotransferase, alkaline phosphatase, lactate dehydrogenase, creatine kinase, creatine kinase-MB, creatinine, uric acid and blood urea nitrogen ELISA kits were all procured from the Wuhan Boster Biological Engineering Co. (Wuhan, China). Interleukin-1 α , interleukin-6 and interleukin-1 β ELISA kits were obtained from the Shanghai Meilian Bio Technology Co. Ltd. (Shanghai, China). High-density lipoprotein-cholesterol, low-density lipoprotein-cholesterol, triglyceride, total cholesterol, total antioxidant capacity, hemoglobin A1c, superoxide dismutase and glutathione ELISA kits were obtained from the Nanjing Jiancheng Biological Engineering Institute (Nanjing, China). Tumor necrosis factor- α kits were bought from the Shenzhen Juying Biotechnology Co. Ltd. (Shenzhen China).

Polyclonal antibodies including sterol regulatory element binding protein-1c, acetyl-CoA carboxylase, acyl-CoA oxidase-1, peroxisome proliferator-activated receptor, stearoyl-coenzyme A desaturase, methylenetetrahydrofolate reductase, cystathionine beta-synthase and methyltetrahydrofolate homocysteine were sourced from Santa Cruz Biotechnology Ltd (Dallas, TX, USA), as were monoclonal β -actin,

polyvinylidene fluoride touch and ECL kits. Secondary antibodies were provided by the Zhongshan Golden Bridge Company (Beijing, China).

2.2 Animals

Male Sprague Dawley (SD) rats weighing 160 – 180 g were provided by Kunming Medical University (Kunming, China). All animal experiments were performed under certificate number SYXK 2011-0004 issued by the Yunnan Science and Technology Agency. Ethical approval was obtained from the Kunming Medical University Ethics Committee prior to experimental work beginning.

2.3 Preparation of PLGA microspheres and yield

PLGA microspheres were prepared using the water/oil/water ($w_1/o/w_2$) double emulsion solvent evaporation method [Wischke C, et al., 2006]. First, an aqueous phase w_1 (3 mg liraglutide powder dissolved in 0.1 mL of a 1 % w/v aqueous solution of sodium acetate), was emulsified with 10 mL of a solution of PLGA in dichloromethane (1 % w/v) by ultrasonication (SL-900D instrument, Nanjing Shunliu Instrument Co., Ltd., Nanjing, China) using a sonochemical power of 120W. Second, the w_1/o emulsion was poured into 200 mL of w_2 , an aqueous solution containing PVA (2 % w/v) and NaCl (0.5 % w/v). This resulted in a coarse double emulsion ($w_1/o/w_2$). Next, the emulsions were stirred for 5h at room temperature and the resultant microspheres then collected by centrifugation (5810R instrument, Eppendorf, Hamburg, Germany) for 10 min at 10000 rpm. They were washed with distilled water (10 mL; 5 times) and then dispersed in a 5 % w/v mannitol solution prior to freeze-drying (10 Pa, -50 °C; SJIA-10N instrument, Ningbo Dual Ka Instrument Co.,

Ltd. Ningbo, China).

The presence of any residual dichloromethane (DCM) was quantified using headspace gas chromatography (GC 112A instrument, Shanghai Analytical Instrument Overall Factory, Shanghai, China). An equity-5 fused silica capillary column (30 mm × 0.53 mm, 1.0 µm; Supelco Co., Ltd., PA, USA) was first held at 90 °C for 2 min, then increased to 180 °C at 40 °C/min and held for 10 min. The gasification chamber temperature was 230 °C. Experiments were performed using nitrogen as a carrier gas (7 mL / min), a hydrogen flow rate of 45 mL / min and an air flow rate of 120 mL / min. A calibration curve with regression equation $y = 0.0194x + 0.0547$ ($r^2 = 0.9733$, $n = 6$) was determined and used for analysis. If the measured value of residual dichloromethane was less than 10 µg DCM / g PLGA microspheres, the formulations were deemed acceptable for further investigation and sterilized using ultraviolet irradiation.

The process yield was calculated by comparing the quantity of polymer and drug initially used and the amount of microspheres obtained, using the following equation [Jose S, et al., 2014]:

Microsphere yield (%) = $100\% \times \text{mass of lyophilized microspheres (mg)} / [(\text{mass of peptide added (mg)} + \text{mass of polymer added (mg)})]$

2.4 Particle size and morphology

The microspheres' particle size and morphology were evaluated using scanning electron microscopy (SEM) on a JSM-5600 instrument (JEOL, Tokyo, Japan). The freeze-dried microspheres were mounted onto an aluminum stub using double-sided

adhesive tape and sputter coated with a thin layer of gold under an argon atmosphere before examination. The coated specimen was then examined at an acceleration voltage of 10 kV. The average microsphere size for each sample was calculated from the analysis of around 200 microspheres in SEM images, using the Image J software [Guedes J C, et al., 2013].

2.5 Loading efficiency and encapsulation efficiency

Microspheres (5 mg) were dispersed in acetonitrile (150 μ L), before 0.01 M HCl (850 μ L) was added. The resultant mixture was agitated to ensure complete dissolution then filtered and reverse-phase HPLC employed to determine the liraglutide concentration. The HPLC system (L-2000, Hitachi, Tokyo, Japan) comprised a L-2130 quaternary pump, a L-2200 auto-sampler, a L-2420 UV-vis detector and a L-2300 column oven. The column was an Inertsil ODS-SP column (GL Sciences, Tokyo, Japan) with dimensions of 250 mm x 4.6 mm. The mobile phase comprised acetonitrile (solvent A) and a 0.05 M aqueous KH_2PO_4 solution (pH = 4.0, solvent B). The flow rate was set to 1.0 mL / min and a gradient method used (% v/v of solvent A: 0 – 30 min: 40 $\rightarrow$ 45 %; 30 – 33 min: 45 % $\rightarrow$ 80 %, 33.1 – 35 min: 80 % $\rightarrow$ 40 %). The column temperature was maintained at 30 $^{\circ}\text{C}$. A calibration curve with regression equation $y = 128.33x - 25.54$ ($r = 0.9999$, $n = 6$) was determined and used for analysis. The loading and encapsulation efficiencies (LE and EE respectively) were calculated using the equations [Vysloužil J, et al., 2014; Muralikrishnan A, et al., 2014]:

$$\text{LE (\%, w/w)} = 100\% \times \text{Mass of drug in microspheres} / \text{Mass of microspheres}$$

$EE (\%) = 100\% \times \text{Actual protein loading} / \text{Theoretical protein loading}$

2.6 Physical form and component compatibility

Differential scanning calorimetry (DSC) was performed using a **GIVE MODEL NUMBER** instrument (Mettler Toledo, Columbus, OH, United States). 3-5 mg samples were placed in an aluminum pan and heated at a constant rate of 10 °C/min from 20 to 150 °C, under a dry atmosphere of nitrogen (as carrier gas). The instrument temperature and energy scales were calibrated using an indium standard (99.9%).

Commented [g2]: Need to give the model number of the DSC here

The microspheres were also studied using X-ray powder diffraction (XRD) on a D/MAX-2500PC instrument (Rigaku, Tokyo, Japan) supplied with Cu K α radiation. Diffraction patterns were collected in the 2 θ range 3 – 50° with a step size of 0.01° (2 θ) and count time of 1 s per step.

Infrared (IR) spectra were recorded with a 5700 spectrometer (Nicolet, Madison, WI, USA). 5 mg of each formulation was mixed with 500 mg KBr in an agate mortar, before being compressed into a pellet. The measurement range was 4000–400 cm⁻¹; 32 scans **per** sample were collected at a resolution of 2 cm⁻¹.

2.7 In vitro drug release

The *in vitro* release of liraglutide from the microspheres was studied as follows. 10 mg microspheres were placed in an Eppendorf tube containing 1 mL buffer (10 mM HEPES, 100 mM NaCl, pH7.4) and incubated at **37 °C** under mild stirring (100 rpm) **by** a magnetic flea [Qi, F, et al., 2013]. A number of tubes were set up in parallel, and after predetermined time points the release medium was removed by

centrifugation at 10,000 rpm for 5 min. The solid residue was washed with fresh release buffer and the microspheres lyophilized for 24 h before the remaining liraglutide concentration was determined. Experiments were run in triplicate for each batch of microspheres.

2.8 Type 2 diabetes model

A Type 2 diabetes rat model was successfully established by feeding rats on a high-fat diet for 6 months [Mourad A A, et al., 2013]. The criterion for success in this regard was if, after 6 months, the fasting blood glucose level was greater than 11.1 mmol/L for seven consecutive days. Sixty rats were randomly divided into a negative control group (CG), a high fat group (HFG), and four groups treated with liraglutide. Three groups received different amounts of the liraglutide-loaded microspheres (low (LLG), medium (LMG), and high liraglutide (LHG) groups), and finally we established a liraglutide injection control group (LCIG). Each group contained 10 animals. Animals in the LLG, LMG, and LHG groups were given a subcutaneous injection of microspheres (containing 0.9, 1.8, or 3.6 mg of liraglutide, respectively) into the neck once on day zero of the experiment. The LCIG animals were injected daily with a solution containing 60 µg of liraglutide in 0.5 mL of a 1 % w/v aqueous sodium acetate solution (giving a total dose over 30 days of 1.8 mg), and the HFG and CG group with 100 mg of blank PLGA microspheres.

2.9 Blood sugar measurement

Glucose levels were recorded at days 5, 10, 15, 20, 25 and 30. Before each measurement, rats were fasted for 12 hours. One hour before each measurement, 5

mL of 10% (w/v) brown sugar water was used for gavage. Blood glucose was measured from the tail vein at hourly intervals over a 6 h period. This process mirrors those used in other studies [Suresha R N, et al., 2013; Debnath T, et al., 2013].

2.10 Biochemical analysis

The amounts of aspartate transaminase, alanine aminotransferase, alkaline phosphatase, total bile acid, creatine kinase, creatine kinase-MB, creatinine, uric acid, interleukin-1 α , interleukin-6 and interleukin-1 β and tumor necrosis factor- α were measured using ELISA, according to the manufacturers' instructions and with the aid of a microplate reader (DG5033A, Nanjing Huadong Electronics Group Co., Ltd., Nanjing, China). Blood insulin, serum high-density lipoprotein-cholesterol, serum low-density lipoprotein-cholesterol, serum triglycerides, serum total cholesterol, blood urea nitrogen, total antioxidant capacity, hemoglobin A1c, superoxide dismutase, glutathione, actate dehydrogenase, malondialdehyde and glutathione were quantified by spectrophotometry (W2-G12 instrument, Shanghai Jiabiao Co. Shanghai China).

2.11 Sacrifice and tissue collection

After 30 days, the rats were weighed and their tail vein glucose level quantified. Using a chloral hydrate (3 % w/v) intraperitoneal injection the rats were sacrificed after being anesthetized, and their abdominal cavities exposed. Samples of blood were collected rapidly from the heart, centrifuged and stored at -80 °C for future analysis. Liver, spleen, lung, heart and kidney samples were collected and stored at -80 °C.

2.12 Western blotting

Liver tissue was homogenized (D-8 high shear homogenizer, Micra, Müllheim, Germany) and the tissue lysate produced analysed for protein content using the BCA methodology. 60 µg of homogenized tissue was used for SDS-PAGE electrophoresis; proteins were transferred using a semi-dry transfer method to a PVDF membrane, which was then bathed in 5 % skimmed milk (20 mL) for 2 h. Polyclonal antibodies were added and the membranes stored overnight at 4 °C. The following day they were washed with 50 mL of phosphate buffered saline (PBS) before the addition of HRP-conjugated secondary antibodies and incubation for 2 h. After washing with 1 mL of the ECL luminescent reagent, the films were scanned and images processed using the ImageJ software (National Institutes of Health, Bethesda, MD, USA) to quantify the amounts of protein present using β-actin as an internal standard. Each experiment was repeated three times. Proteins detected were: sterol regulatory element binding protein-1c, acetyl-CoA carboxylase, acyl-CoA oxidase-1, peroxisome proliferator-activated receptor, stearyl-coenzyme desaturase methylenetetrahydrofolate reductase, cystathionine beta-synthase and methyltetrahydrofolate homocysteine.

2.13 Statistical processing

Data are reported as mean ± the standard error of the mean (SEM). Differences in parameter mean values were analyzed using one-way analysis of variance (ANOVA) tests followed by SNK-q multiple comparisons using the SPSS19.0 software (IBM, Armonk, NY, USA). A *p*-value of <0.05 was considered statistically significant.

3. Results

3.1 Optimisation of microsphere production process

A range of experimental parameters were explored (see Table 1), after which the optimal experimental parameters were set as follows: ultrasonication for 5 min, a 2 % w/v PVA solution, and volume ratios for w_1/o and o/w_2 of 1:100 and 1:20 respectively (serial 2, 11, 12 in Table 1). This formulation was selected because it offers the best balance of encapsulation efficiency, drug loading, and process yield. In all cases, the drug-loading is somewhat lower than other reports in the literature [Wei, G., et al., 2004; Qi F., et al., 2013], but the encapsulation efficiency is consistent with these.

3.2 Characterisation of microparticles

Microspheres were prepared using the optimized parameters above at three different mixing speeds (2400, 1200, and 600 rpm). SEM images are shown in Fig. 1: all the microspheres are spherical in shape, with some pores visible on their surfaces. The particle diameters are $16.19 \pm 5.32 \mu\text{m}$, $9.43 \pm 2.36 \mu\text{m}$ and $6.88 \pm 2.16 \mu\text{m}$ for the samples prepared at 600, 1200, and 2400 rpm respectively. The percentage relative standard deviation values are 32.8, 25.0, and 31.4 %.

The microspheres were next characterised by DSC, XRD and IR spectroscopy. DSC data are given in Fig. 2A. PLGA and liraglutide show clear melting endotherms at 42.8 °C and 88.3 °C respectively. The PLGA melt is also visible in the microspheres, at 46.2 °C (drug-free) and 48.8 °C (liraglutide-loaded), showing the polymer to be semi-crystalline in all cases. The liraglutide melt is not visible in the

microspheres, indicating that the drug is converted from crystalline to amorphous in the production process. The XRD data on the formulations are somewhat inconclusive (Fig. 2B). The pure liraglutide powder appears to be semi-crystalline, with some broad reflections present in the pattern. There are no clear reflections for the microsphere formulations, only broad halos centered at around 18° , which suggests that these are all amorphous materials. However, the DSC data clearly show the presence of some crystalline PLGA material in the microspheres. It is not clear why this is not detected by XRD, but it may be that the amount of crystalline material is below the limit of detection; in any case, these results are consistent with the literature [Guo W, et al., 2015]. Fig. 2C shows the IR spectra of the liraglutide loaded PLGA microspheres and the raw materials. There are no clear differences between the spectra of the blank microspheres and those containing liraglutide, which is as expected since the drug loading is very small.

3.3 In vitro drug release

The liraglutide release profiles from the three different sets of microspheres prepared under optimal conditions but at different mixing speeds are given in Fig. 3. The spheres prepared at 600 rpm release the embedded drug most quickly and also to the greatest extent. This is followed by the 1200 rpm formulation. The 2400 rpm sample releases at approximately the same rate as the 1200 rpm analogue, but reaches a lower release percentage after 30 days. Since it gives the best (slowest rate, maximum release percentage after 30 days) sustained release profile and also has the most uniform particles, the material prepared at 1200 rpm was taken forward into

further studies.

3.4 In vivo blood glucose, HbA1c and insulin levels

The observation of a hypoglycemic effect when the drug-loaded microspheres are injected into the body is vital for clinical application. We thus performed a series of *in vivo* experiments in which rats were given a sugar gavage and blood then periodically taken from the tail vein for analysis. Experiments were performed at 5-day intervals after the beginning of the experiment and the injection of microspheres. The results are presented in Fig. 4. The trends are the same for the samples taken at all timepoints, with the glucose level rising rapidly for all groups except the negative control between 0 and 1 h after application of the sugar gavage. The microsphere and injection-treated groups all have very similar ability to lower blood glucose levels, as is visible in all measurements. Looking at the results obtained 5 days after the start of the dosage regimen, it appears that the injection treatment (LGIC) is reducing the glucose levels slightly faster than the microsphere groups, but this effect is not particularly marked. After days 10, 15, 20 and 25 the microsphere and injection groups are virtually indistinguishable in terms of the changes in glucose concentration after gavage. On day 30, the glucose concentration profile again appears to show a more rapid decline with the injection formulation, indicating that maybe the microspheres are losing their potency at this time. The different amounts of microspheres injected (LLG, LMG, LHG groups, given spheres containing 0.9, 1.8, or 3.6 mg of liraglutide respectively) do not have any appreciable effect on the data obtained.

To further characterize the response *in vivo*, hemoglobin A1c (HbA1c, a more reliable marker of longer-term glucose levels than direct measurement) was also quantified. HbA1c and insulin levels after 30 days are presented in Fig. 5. The negative control group (CG) has the lowest levels of HbA1c, as would be intuitively expected, and the positive control high fat group (HFG) the highest. All the treatment groups display significantly lower HbA1c levels than the HFG ($p < 0.05$), but there are no significant differences between the LLG, LMG, and LHG groups which received microspheres and the injection LCIG group. Both the microsphere and injection groups showed higher values than the negative control group (CG). Comparing the microsphere and injection groups with the HFG, it is clear that insulin levels are increased both before and 2h after a meal. There are no statistically significance differences between the microsphere and injection groups, nor between the treatment groups and the CG.

3.5 Tissue staining

After treatment for 30 days, rats were sacrificed and the pathology of their lungs, spleens, hearts, livers, and kidneys observed by hematoxylin-eosin staining (Fig. 6). No major differences in the pathology of the heart, lungs, spleen, or kidneys can be seen. However, looking at the sections from the liver in the HFG group, many fatty deposits can be seen. The incidence of these is much reduced in the treatment groups, particularly the LMG, LHG and LCIG.

3.6 Heart, lung and kidney function, and blood markers

The elevated blood glucose levels arising during diabetes commonly lead to liver,

kidney and heart damage. The likelihood and extent of these problems arising can be assessed through proxy measures: abnormal lipid levels, inflammatory factors and oxidative stress. GLP-1 can regulate the blood lipid levels, inflammation, and antioxidant ability of diabetic rats and improve **their** liver, kidney and heart functions. Its efficacy post-loading into PLGA microspheres is not known, however, and thus to verify the utility of our formulations we explored these parameters after *in vivo* experiments. The results are detailed in Table 2 and Table 3.

The PLGA microspheres appeared **to influence positively** the blood lipid levels (lipoprotein-cholesterol, triglycerides, and total cholesterol), and have similar effects on regulating blood lipids to the injection group. The LMG and the LCIG groups show very similar values. In terms of oxidative stress (superoxide dismutase, glutathione and total antioxidant capacity), the LMG and the LCIG groups again give very similar results. Considering the inflammatory markers (tumor necrosis factor- α and the interleukins IL-1 α , IL-1 β and IL-6) it can be seen that the microspheres lead to significantly greater production of these than the LCIG animals. This is consistent with previous work [Yang J, 2011], and arises because PLGA frees lactic acid as it degrades.

The toxicity of the PLGA microspheres must also be established, and to this end liver function was assessed through measurements of the aspartate transaminase, alanine aminotransferase, alkaline phosphatase, and r-valley ammonia acyl transferase markers (Table 3). In the case of r-valley ammonia acyl transferase the LMG group presented lower values than the LCIG group ($p < 0.05$), while the LGIC

and LMG groups are almost identical. Considering the kidney function indicators (creatinine, uric acid, and blood urea nitrogen), in the case of creatinine, the LHG group value is significantly lower than the LCIG group ($p < 0.05$), and the LMG and LCIG groups present very similar values. Similar trends are found with the heart function indices (lactose dehydrogenase, creatine kinase and creatine kinase-MB), with the LHG group being significantly reduced compared to the LCIG group in terms of **the latter**. From these data, it can be concluded that loading liraglutide into PLGA microspheres did not affect its therapeutic effect: the formulations can improve the liver, kidney and heart functions of rats, and they performed very similarly to the injection control group.

3.7 Metabolic enzymes

The expression of key enzymes for lipid metabolism (sterol regulatory element binding protein-1c, acetyl-CoA carboxylase, acyl-CoA oxidase-1, peroxisome proliferator-activated receptor and stearoyl-coenzyme A desaturase) and for cysteine metabolism (methylenetetrahydrofolate reductase, cystathionine beta-synthase and methyltetrahydrofolate homocysteine) were quantified after the 30 day treatment regimen. **It** has been reported that activators of GLP-1 receptors can regulate lipid metabolism and homocysteine enzymes [Wang X, et al., 2014; Gao H, et al., 2015; Liu Y, et al., 2014; Niu S, et al., 2015]. From Fig 7, we can see that except for cystathionine beta-synthase, where similar quantities are observed for all groups, the three microsphere groups and the LCIG treatment group have distinct effects on the metabolic enzyme profile. The liraglutide formulations reduced sterol regulatory

element binding protein-1c and acetyl-CoA carboxylase protein expression and increased acyl-CoA oxidase-1, peroxisome proliferator-activated receptor, stearyl-coenzyme A desaturase, methylenetetrahydrofolate reductase and methyltetrahydrofolate homocysteine expression compared with the HFG group.

4. Discussion

As reported in other work [Abashzadeh S, et al., 2011; Rodríguez -Contreras A, et al., 2013; Xie X, et al., 2015], a range of factors including the ultrasonication time, the ratios of the different phases, the concentration of PVA employed, and the mixing speed are all important in determining the properties of microspheres produced in $w_1/o/w_2$ double emulsion processes, including their drug loadings and encapsulation efficiencies. In order to strike the best balance between the drug loading, encapsulation efficiency and process yield, we investigated a range of these parameters in our work. We found that a longer ultrasonication time leads to lower drug loadings. This agrees with the literature [Xia Z, et al., 2005], which reports that while long ultrasound times can give small microspheres excessive sonication damages their structures. As the w_1/o ratio decreases, the drug loading, encapsulation efficiency and production yield all decline. As w_2/o decreases, the drug loading increases but there are no clear trends in terms of encapsulation efficiency and production yield. The importance of these ratios has previously been identified by Parikh *et al.*, who prepared PLGA microspheres loaded with 5-fluorouracil using the same method as employed here [Parikh R H, et al., 2003]. These authors found that

the drug loadings and encapsulation efficiency were reduced with increases in the amount w_1 and w_2 used. These trends are somewhat different to those **observed** here, which can be ascribed to differences in the molecular weight and solubility of the **drugs** used.

The optimum PVA concentration was found to be 2 % w/v; this gave the highest drug loading, encapsulation efficiency and process yield. These were all reduced when the PVA concentration was 1% or 3%, with the 1% solution giving particularly low loading, encapsulation efficiency and process yield. This is consistent with the studies of Mao *et.al.* [Mao S, et al., 2008]. High concentrations of PVA can produce more stable microspheres and render them more compact, leading to high levels of drug entrapment. However, high concentrations of PVA can also lead to drug solubility increases, eventually leading to reduced entrapment [Yang Y Y, et al., 2001].

The drug loadings and encapsulation efficiency decrease with increasing stirring speed, as previously identified by Xuan [Xuan J, et al., 2013]. Overall, we found that the liraglutide loading is somewhat lower than the literature reports for other PLGA microsphere systems. For instance, Wei *et. al.* reported a loading of 2.59 % [Wei G, et al., 2004] for bovine serum albumin (BSA) in PLGA using a $w_1/o/w_2$ system, and Qi and coworkers achieved 5.13 % [Qi F, et al., 2013] for exenatide in PLGA. The encapsulation efficiency determined in our work is generally consistent with these previous reports, however [Wei G, et al., 2004; Qi F, et al., 2013].

The mechanical stirring speed has been widely reported to affect the size of the microspheres [Chaisri W, et al., 2009; Sun F, et al., 2010]. Here, we find that is a clear trend for faster mixing speeds to produce smaller particles, in accordance with reports in the literature. For instance, Chaisri *et al.* used speeds of 4000 rpm, 8000 rpm and 10000 rpm, and obtained microspheres of $16.50 \pm 2.60 \mu\text{m}$, $4.95 \pm 0.06 \mu\text{m}$ and $3.18 \pm 1.23 \mu\text{m}$ [Chaisri W, et al., 2009]. In other work speeds of 1000 and 1500 rpm yielded spheres of *ca.* 80 μm and 55 μm [Sun F, et al., 2010]. The mixing speed clearly also influences the release properties. The literature reports that PLGA microspheres can extend release to 7-40 days [Wang J W, et al., 2015; Vaughn W M, et al., 2003; Jiang, G., et al., 2003]. Although there are a number of differences between these studies and the work performed here, our results concur with the body of knowledge to date and show drug release over around 30 days, with very similar release profiles seen for all samples studied. The similarity of the profiles is attributed to PLGA degradation being the rate determining step in release. For this application, we hoped to achieve sustained release over around 30 days, as this is a clinically relevant injection interval.

As a result of the drug release experiments performed, it was clear that the microspheres have potential as once-monthly dosage forms for the treatment of diabetes. The literature reports that using PLGA-encapsulated insulin can give a hypoglycemic effect lasting from 5 to 15 days [Jiang G, et al., 2003; Kang F, et al., 2004]. Our research indicates that the hypoglycemic effect of liraglutide-loaded PLGA microspheres can be maintained for around 30 days. Three different doses

were explored (0.9, 1.8 and 3.6 mg), and the therapeutic effects of these were very similar. This may be related to the pharmacological activity of GLP-1 which generally does not cause low blood sugar [Briones M, et al., 2006]. Thus, after liraglutide is injected and helps return the blood sugar level to normal, it will not continue to have a hypoglycemic effect. From the data obtained in this work, it appears that no more than 0.9 mg over 30 days is required to produce the desired hypoglycemic outcomes in the rat model employed here.

To further characterize the response *in vivo*, hemoglobin A1c (HbA1c) and insulin were also quantified. HbA1c is a more reliable marker of longer - term glucose levels than direct measurement [Berger W, et al., 1980; Sikaris K, 2009], and insulin production is directly related to the pharmacological effect of liraglutide, which stimulates production of the latter through the islet B cells [Damdindorj B, et al., 2012]. Our research found that the microspheres can improve the HbA1c and insulin levels, in the latter case giving values very similar to the negative control group. The liraglutide-loaded PLGA microspheres thus can effectively exert a long-term hypoglycemic effect.

Tissue staining can give direct information on the effects of medicines [Qiao C, et al., 2013; Dang H, et al., 2015]. The results obtained from HE staining verify that the liraglutide-loaded PLGA microspheres are safe and non-toxic, as previously found by Kang and co-workers [Kang, S.W., et al. 2007].

The elevated blood glucose levels arising during diabetes commonly lead to liver, kidney and heart damage. The likelihood and extent of these problems arising can be

assessed through proxy measures: i.e. abnormal lipid levels, inflammatory factors and oxidative stress [Dall T M, et al., 2014; Mebazaa A, et al., 2013; Abarikwu S O. 2014]. GLP-1 can regulate the blood lipid levels, inflammation, and antioxidant ability of diabetic rats [Aassaloni C, 2005; Pickup J C, 2004; Gao H, et al., 2015] and improve the liver, kidney and heart functions [Mells J E, et al., 2012; Zavattaro M, et al., 2015; Rizzo M, et al., 2013], and this it was expected that liraglutide could act similarly. The liraglutide PLGA microspheres show improvements in all these measures, and were as effective as the liraglutide injection group. The only exception to this concerns inflammatory cytokines, where the microsphere groups caused slightly increased production. This is consistent with previous work [Yang J, et al., 2011], and arises because PLGA frees lactic acid as it degrades. The production of inflammatory molecules leads to diabetic complications, but given that the microsphere formulations lead to an improvement over the positive control it is not thought that their poorer performance than the injection in this regard should lead to any major problems.

It has been reported that activators of GLP-1 receptors can regulate lipid metabolism and homocysteine enzymes [Wang X, et al., 2014; Gao H, et al., 2015; Liu Y, et al., 2014; Niu S, et al., 2015], so we observed the effect of our liraglutide-loaded PLGA microspheres on these. The microspheres have positive effects in improving lipid metabolism and homocysteine enzyme levels.

Our results offer a significant addition to the extant studies using drug-loaded PLGA microspheres to treat diabetes, and add additional depth to these because often

detailed studies of hypoglycemic effect are not reported [Jiang G, et al., 2003; Kang F, et al., 2004]. There are many papers concerned with the toxicological and safety profiles of PLGA, and our data concur with these in demonstrating the safety of the materials [Semete B, et al., 2010; He Y, et al., 2006; Hara K, et al., 2008]. In one example of this, Kang implanted PLGA films into rats and mice, and observed toxicity and biocompatibility over 24 weeks [Kang B C, et al., 2005]. Attention was paid to body weight, food, water, eyes, urine, blood, metabolism and organ quality, and no serious inflammation or systemic toxicity was identified. As a result of all these studies and the new results reported here, we are confident that liraglutide-loaded PLGA microspheres are safe and non-toxic, and have great potential for translation to the clinic.

5. Conclusions

Extended-release injectable microspheres of poly(lactic-co-glycolic acid) containing liraglutide were prepared using a double emulsion method. Faster mixing speeds were found to result in smaller spheres, in accordance with previous findings in the literature. The microspheres give controlled release of the incorporated drug over around 30 days. *In vivo* studies demonstrated that injected microspheres are able to reduce blood glucose levels in a rat model of type 2 diabetes. At the very start and very end of a 30-day treatment period, the microspheres perform slightly less well than an injection formulation, but over the majority of the time course the microspheres are found to be as efficient as the injections. An investigation of the

pathology of key organs found that the fatty deposits seen in the liver with the diabetic rats are prevented when they are treated with liraglutide microspheres, and the heart, renal, and liver functions were unaffected by liraglutide treatment. The microsphere treatments were statistically no different from the injection group in this regard. Biochemical analyses of blood showed that blood lipids and oxidation/antioxidant markers were indistinguishable from the injection formulation, but inflammatory markers were somewhat raised. Levels of key enzymes involved in lipid and cysteine metabolism were approximately the same regardless of whether the liraglutide was delivered by injection or through the microspheres. Overall, our results show that the liraglutide microspheres have a powerful therapeutic effect in a rat model of diabetes, and may have great potential for clinical use.

6. Acknowledgements

This investigation was supported by the Yunnan Applied Basic Research Projects (2013FZ052), the Biomedical Textile Materials “111 Project” of the Ministry of Education of China (No. B07024), and the UK-China Joint Laboratory for Therapeutic Textiles.

7. Author disclosure statement

None of the authors has any conflict of interest to declare for the collection, analysis, and interpretation of data or for the writing of this manuscript and the decision to submit for publication.

8. References

- Aassaloni, C. 2005. Effect of atorvastatin and irbesartan, alone and in combination, on postprandial endothelial dysfunction, oxidative stress, and inflammation in type 2 diabetic patients. *Circulation*, 111, 2518-2524.
- Abashzadeh, S., Dinarvand, R., Sharifzadeh, M., Hassanzadeh, G., Amini, M., Atyabi, F. 2011. Formulation and evaluation of an in situ gel forming system for controlled delivery of triptorelin acetate. *European Journal of Pharmaceutical Sciences*, 44, 514-521.
- Abarikwu, S. O. 2014. Protective effect of quercetin on atrazine-induced oxidative stress in the liver, kidney, brain, and heart of adult wistar rats. *Toxicology International*, 21, 148-155.
- Alfaris, N., Minnick, A. M., Hopkins, C. M., Berkowitz, R. I., Wadden, T. A. 2015. Combination phentermine and topiramate extended release in the management of obesity. *Expert Opinion on Pharmacotherapy*, 16, 1263-1274.
- Aimaretti G. 2010, Liraglutide: a once-daily human glucagon-like peptide-1 analogue. *Journal of Endocrinological Investigation*. 67, 701-703.
- Andreas, K., Zehbe, R., Kazubek, M., Grzeschik, K., Sternberg, N., Bäuml, H. 2010. Biodegradable insulin-loaded PLGA microspheres fabricated by three different emulsification techniques: investigation for cartilage tissue engineering. *Acta Biomaterialia*, 7, 1485-1495.

Commented [g3]: Please check your reference formatting to make sure that it is correct and all first names / surnames are also correct!

- Angkawinitwong, U., Sharma, G., Khaw, P. T., Brocchini, S., Williams, G. R. 2015. Solid-state protein formulations. *Therapeutic Delivery*, 6, 59-82.
- Graf, A., Rades, T., Hook, S. M. 2009. Oral insulin delivery using nanoparticles based on microemulsions with different structure-types: optimisation and in vivo evaluation. *European Journal of Pharmaceutical Sciences*. 37, 53-61.
- APA Iqbal, M., Valour, J. P., Fessi, H., Elaissari, A. 2015. Preparation of biodegradable PCL particles via double emulsion evaporation method using ultrasound technique. *Colloid & Polymer Science*, 293, 861-873.
- Briones, M., Bajaj, M. 2006. Exenatide: a GLP-1 receptor agonist as novel therapy for type 2 diabetes mellitus. *Expert Opinion on Pharmacotherapy*, 7, 1055-1064.
- Berger W., Sonnenberg G. E. 1980. Daily blood sugar and hemoglobin A1 or A1c profile for the surveillance of diabetes therapy. *Schweizerische Medizinische Wochenschrift*, 110, 485-491.
- Carrascosa, C., Espejo, L., Torrado, S., Torrado, J. J. 2003. Effect of gamma-sterilization process on PLGA microspheres loaded with insulin-like growth factor-i (IGF-i). *Journal of Biomaterials Applications*, 18, 95-108.
- Chaisri W., Hennink W. E., Okonogi S. 2009. Preparation and characterization of cephalexin loaded PLGA microspheres. *Current Drug Delivery*, 6, 69-75.
- Dall, T. M., Yang, W., Halder, P., Pang, B., Massoudi, M., Wintfeld, N. 2014. The

- economic burden of elevated blood glucose levels in 2012: diagnosed and undiagnosed diabetes, gestational diabetes mellitus, and prediabetes. *Diabetes Care*, 37, 3172-3179.
- Damdindorj, B., Dezaki, K., Kurashina, T., Sone, H., Rita, R., Kakei, M. 2012. Exogenous and endogenous ghrelin counteracts GLP-1 action to stimulate camp signaling and insulin secretion in islet β -cells. *Febs Letters*, 586, 2555–2562.
- Dang, H., Wang, J., Cheng, J. X., Wang, P. Y., Wang, Y., Cheng, L. F. 2015. Efficacy of local delivery of ardisilloside I using biodegradable implants against cerebral tumor growth. *American Journal of Cancer Research*, 5, 243-254.
- Debnath, T., Radhakrishnan, R., Muruganathan, G., Talwar, S., K N. 2013. Hypoglycaemic effects of alcoholic root extract of *Borassus flabellifer* (Linn.) in normal and diabetic rats. *Pakistan Journal of Pharmaceutical Sciences*, 26, 673-679.
- Feng, Q., Wu, J., Yang, T., Ma, G., Su, Z. 2014. Mechanistic studies for monodisperse exenatide-loaded PLGA microspheres prepared by different methods based on spg membrane emulsification. *Acta Biomaterialia*, 10, 4247-4256.
- Gallwitz, B. 2008. Liraglutide. *Drugs Fut.*, 33, 13.
- Gao, H., Zeng, Z., Zhang, H., Zhou, X., Guan, L., Deng, W. 2015. The glucagon-like peptide-1 analogue liraglutide inhibits oxidative stress and inflammatory response in the liver of rats with diet-induced non-alcoholic fatty liver disease. *Biological & Pharmaceutical Bulletin*, 38, 694-702.

- Gavini, E., Chetoni, P., Cossu, M., Alvarez, M. G., Saettone, M. F., Giunchedi, P. 2004. Plga microspheres for the ocular delivery of a peptide drug, vancomycin using emulsification/spray-drying as the preparation method: in vitro/in vivo studies. *European Journal of Pharmaceutics & Biopharmaceutics*, 57, 207-212.
- Guedes, J. C., Park, J. H., Lakhkar, N. J., Kim, H. W., Knowles, J. C., Wall, I. B. 2013. TiO₂-doped phosphate glass microcarriers: a stable bioactive substrate for expansion of adherent mammalian cells. *Journal of Biomaterials Applications*, 28, 3-11.
- Guo W., Quan P., Fang L., Dong C., Ming Y. 2015. Sustained release donepezil loaded PLGA microspheres for injection: Preparation, in vitro, and in vivo, study. *Asian Journal of Pharmaceutical Sciences*, 10, 405-414.
- Hara, K., Tsujimoto, H., Tsukada, Y., Huang, C. C., Kawashima, Y., Tsutsumi, M. 2008. Histological examination of PLGA nanospheres for intratracheal drug administration. *International Journal of Pharmaceutics*, 356(1-2), 267–273.
- He, Y., Wang, J. C., Liu, Y. L., Ma, Z. Z., Zhu, X. A., Zhang, Q. 2006. Therapeutic and toxicological evaluations of cyclosporine a microspheres as a treatment vehicle for uveitis in rabbits. *Journal of Ocular Pharmacology & Therapeutics*, 22, 121-131.
- Jiang, G., Jiang, T., Chen, H., Li, L., Liu, Y., Zhou, H. 2015. Preparation of multi-responsive micelles for controlled release of insulin. *Colloid & Polymer Science*, 293, 209-215.

- Jiang, G., Qiu, W., Deluca, P. P. 2003. Preparation and in vitro/in vivo evaluation of insulin-loaded poly(acryloyl-hydroxyethyl starch)-PLGA composite microspheres. *Pharmaceutical Research*, 20, 452-459.
- Jiang, H. L., Jin, J. F., Hu, Y. Q., Zhu, K. J. 2004. Improvement of protein loading and modulation of protein release from poly(lactide-co-glycolide) microspheres by complexation of proteins with polyanions. *Journal of Microencapsulation*, 21, 615-624.
- Jiang, H. L., Zhu, K. J. 2002. Bioadhesive fluorescent microspheres as visible carriers for local delivery of drugs. I: preparation and characterization of insulin-loaded pcefb/plga microspheres. *Journal of Microencapsulation*, 19, 451-461.
- Joffe D. 2010. Liraglutide: a once-daily human glucagon-like peptide-1 analogue for type 2 diabetes mellitus. *American journal of health-system pharmacy : AJHP : official journal of the American Society of Health-System Pharmacists*. 67,1326-1336.
- Jose, S., Sowmya, S., Cinu, T. A., Aleykutty, N. A., Thomas, S., Souto, E. B. 2014. Surface modified PLGA nanoparticles for brain targeting of bacoside-a. *European Journal of Pharmaceutical Sciences Official Journal of the European Federation for Pharmaceutical Sciences*, 63, 29-35.
- Kang, B. C., Kang, K. S., Lee, Y. S. 2005. Biocompatibility and long-term toxicity of innopol implant, a biodegradable polymer scaffold. *Experimental Animals*, 54, 37-52.

- Kang, F., Singh, J. 2004. Preparation, in vitro release, in vivo absorption and biocompatibility studies of insulin. *AAPS Pharmscitech*, 6, E487-E494.
- Kang, S. W., Cho, E. R., Jeon, O., Kim, B. S. 2007. The effect of microsphere degradation rate on the efficacy of polymeric microspheres as bulking agents: an 18-month follow-up study. *Journal of Biomedical Materials Research Part B Applied Biomaterials*, 80, 253-259.
- Lim, S. M., Eom, H. N., Hai, H. J., Sohn, M., Kang, C. L. 2015. Evaluation of pegylated exendin-4 released from poly(lactic-co-glycolic acid) microspheres for antidiabetic therapy. *Journal of Pharmaceutical Sciences*, 104, 72-80.
- Liu, Y., Wei, R., Hong, T. P. 2014. Potential roles of glucagon-like peptide-1-based therapies in treating non-alcoholic fatty liver disease. *World Journal of Gastroenterology*, 20, 9090-9097.
- Lorenz, M., Evers, A., Wagner, M. 2013. Recent progress and future options in the development of GLP-1 receptor agonists for the treatment of diabetes. *Bioorganic & Medicinal Chemistry Letters*, 23, 4011-4018.
- Luo, Y., Mai, H., Li, N., Jin, Q., Huang, X., Zhang, Y. 2014. To compare the drug-loading characteristics and release behavior of interferon plga microspheres prepared by normal and modified double-emulsion methods. *Zhongshan Daxue Xuebao/acta Scientiarum Natralium Universitatis Sunyatseni*, 53, 110-114.
- Niu, X., Zou, W., Liu, C., Zhang, N., Fu, C. 2009. Modified nanoprecipitation

- method to fabricate DNA-loaded PLGA nanoparticles. *Drug Development & Industrial Pharmacy*, 35, 1375-1383.
- Mao, S., Yi, S., Li, L., Jing, X., Schaper, A., Kissel, T. 2008. Effects of process and formulation parameters on characteristics and internal morphology of poly(d,l-lactide-co-glycolide) microspheres formed by the solvent evaporation method. *European Journal of Pharmaceutics & Biopharmaceutics*, 19, 269-276.
- Mebazaa, A., Gayat, E., Lassus, J., Meas, T., Mueller, C., Maggioni, A. 2013. Association between elevated blood glucose and outcome in acute heart failure : results from an international observational cohort. *Journal of the American College of Cardiology*, 61, 820-829.
- Mells, J. E., Fu, P. P., Sharma, S., Olson, D., Cheng, L., Handy, J. A. 2011. GLP-1 analog, liraglutide, ameliorates hepatic steatosis and cardiac hypertrophy in C57Bl/6 mice fed a western diet. *AJP Gastrointestinal & Liver Physiology*, 302, G225-G235.
- Mourad, A. A., Heeba, G. H., Taye, A., El-Moselhy, M. A. 2013. Comparative study between atorvastatin and losartan on high fat diet-induced type 2 diabetes mellitus in rats. *Fundamental & Clinical Pharmacology*, 27, 489–497.
- Muralikrishnan, A., Nanjappa, S. H., Vijayasankar, R., Seongbong, J., Phaniraj, C., Narasimha, M. S. 2014. Controlled-release injectable containing terbinafine/PLGA microspheres for onychomycosis treatment. *Journal of Pharmaceutical Sciences*, 103, 1178-1183.

- Painter, N. A., Morello, C. M., Singh, R. F., Mcbane, S. E. 2013. An evidence-based and practical approach to using bydureon™ in patients with type 2 diabetes. *Journal of the American Board of Family Medicine*, 26, 203-210.
- Parikh, R. H., Parikh, J. R., Dubey, R. R., Soni, H. N., Kapadia, K. N. 2002. Poly(d,l-lactide-co-glycolide) microspheres containing 5-fluorouracil: optimization of process parameters. *Aaps Pharmscitech*, 4, 14-21.
- Patel, B. B., Patel, J. K., Chakraborty, S. 2014. Review of patents and application of spray drying in pharmaceutical, food and flavor industry. *Recent Patents on Drug Delivery & Formulation*, 8, 63-78.
- Pickup, J. C. 2004. Inflammation and activated innate immunity in the pathogenesis of type 2 diabetes. *Diabetes Care*, 27, 813-823.
- Ping, 2005. Effects of formulation factors on encapsulation efficiency and release behaviour in vitro of huperzine a-PLGA microspheres. *Chinese Medical Journal*, 22, 2478-2479.
- Prajapati, V. D., Jani, G. K., Kapadia, J. R. 2015. Current knowledge on biodegradable microspheres in drug delivery. *Expert Opinion on Drug Delivery*, 12, 1-17.
- Prieto, M. J. B., Delie, F., Fattal, E., Tartar, A., Puisieux, F., Gulik, A. 1994. Characterization of v3 bru peptide-loaded small PLGA microspheres prepared by a $w_1/o/w_2$ emulsion solvent evaporation method. *International Journal of Pharmaceutics*, 111, 137-145.
- Qi, F., Wu, J., Fan, Q., He, F., Tian, G., Yang, T. 2013. Preparation of uniform-sized

- exenatide-loaded PLGA microspheres as long-effective release system with high encapsulation efficiency and bio-stability. *Colloids & Surfaces B Biointerfaces*, 112, 492-498.
- Qiao, C., Zhang, K., Jin, H., Miao, L., Shi, C., Liu, X. 2013. Using poly(lactic-co-glycolic acid) microspheres to encapsulate plasmid of bone morphogenetic protein 2/polyethylenimine nanoparticles to promote bone formation in vitro and in vivo. *International Journal of Nanomedicine*, 8, 2985-2995.
- Rizzo, M., Nikolic, D., Banach, M., Giglio, R. V., Patti, A. M., Bartolo, V. D. 2013. The effects of liraglutide on glucose, inflammatory markers and lipoprotein metabolism: current knowledge and future perspective. *Clinical Lipidology*, 8, 173-181.
- Rodríguez-Contreras, A., Canal, C., Calafell-Monfort, M., Ginebra, M. P., Julio-Moran, G., Marqués-Calvo, M. S. 2013. Methods for the preparation of doxycycline-loaded PHB micro- and nano-spheres. *European Polymer Journal*, 49, 3501-3511.
- Niu, S., Wang, L., He, M., Peng, Y., Li, S. 2015. Exendin-4 regulates redox homeostasis in rats fed with high-fat diet. *Acta Biochimica et Biophysica Sinica*, gmv027.
- Semete, B., Booysen, L., Lemmer, Y. 2010. In vivo evaluation of the biodistribution and safety of PLGA nanoparticles as drug delivery systems. *Nanomedicine Nanotechnology Biology & Medicine*, 6, 662-671.

- Sikaris K. 2009. The Correlation of Hemoglobin A1c to Blood Glucose. *Journal of Diabetes Science & Technology*, 3, 429-438.
- Sun F., Cheng S., Teng L., X. Liu, L. Teng. 2010. Studies on the preparation, characterization and pharmacological evaluation of tolterodine PLGA microspheres. *International Journal of Pharmaceutics*, 397, 44–49.
- Suresha R. N., Ashwini V., Pragathi B. 2013. The effect of carvedilol on blood glucose levels in normal albino rats. *Journal of Clinical and Diagnostic Research*, 7,1900-1903.
- Vaughn W. M., Van Hamont J. E., Setterstrom J. A. Sustained release non-steroidal, anti-inflammatory and lidocaine PLGA microspheres: US patent 6528097 B1. 2003.
- Vysloužil, J., Doležel, P., Kejdušová, M., Mašková, E., Mašek, J., Lukáč, R. 2014. Influence of different formulations and process parameters during the preparation of drug-loaded PLGA microspheres evaluated by multivariate data analysis. *Acta Pharmaceutica*, 64, 403-417.
- Wang, J. W., Xu, J. H., Li, J., Zhao, M. H., Zhang, H. F., Liu, D. C. 2015. Improvement of the antitumor efficacy of intratumoral administration of cucurbitacin poly(lactic-co-glycolic acid) microspheres incorporated in in situ -forming sucrose acetate isobutyrate depots. *Journal of Pharmaceutical Sciences*, 105, 205-211.
- Wang, X, Ao, N, Du, J., Yang, J., Xu, J. 2014. Influence of glp-1 on oxidative stress injury in non-alcoholic fatty liver disease rats. *Chinese Journal of*

- Hepatology, 22, 757-762.
- Wei, G., Pettway, G. J., Mccauley, L. K., Ma, P. X. (2004). The release profiles and bioactivity of parathyroid hormone from poly(lactic-co-glycolic acid) microspheres. *Biomaterials*, 25, 345-352.
- Wei, Y., Wang, Y., Kang, A., Wang, W., Ho, S. V., Gao, J. 2012. A novel sustained-release formulation of recombinant human growth hormone and its pharmacokinetic, pharmacodynamic and safety profiles. *Molecular Pharmaceutics*, 9, 2039-2048.
- Wischke, C., Borchert, H. H. 2006. Influence of the primary emulsification procedure on the characteristics of small protein-loaded PLGA microparticles for antigen delivery. *Journal of Microencapsulation*, 23, 435-448.
- Xia, Z., Wang, G., Tao, K., & Li, J. 2005. Preparation of magnetite–dextran microspheres by ultrasonication. *Journal of Magnetism & Magnetic Materials*, 293, 182-186.
- Xie, X., Lin, W., Xing, C., Yang, Y., Chi, Q., & Zhang, H. 2015. In vitro and in vivo evaluations of PLGA microspheres containing nalmefene. *PLOS One*, 10, e0125953.
- Xuan, J., Lin, Y., Huang, J., Fei, Y., Li, X., Ying, L. 2013. Exenatide-loaded PLGA microspheres with improved glycemic control: in vitro, bioactivity and in vivo, pharmacokinetic profiles after subcutaneous administration to SD rats. *Peptides*, 46, 172-179.
- Yang J. 2011. Molecular design of hyaluronic acid hydrogel networks for long-term

controlled delivery of human growth hormone. *Soft Matter*, 7, 868-870

Yang, Y. Y., Chung, T. S., Ng, N. P. 2001. Morphology, drug distribution, and in vitro release profiles of biodegradable polymeric microspheres containing protein fabricated by double-emulsion solvent extraction/evaporation method. *Biomaterials*, 22, 231–241.

Zavattaro, M., Caputo, M., Samà, M. T., Mele, C., Chasseur, L., Marzullo, P. 2015. One-year treatment with liraglutide improved renal function in patients with type 2 diabetes: a pilot prospective study. *Endocrine*, 50, 620-626.

Zhang, W., Gao, Y., Zhou, Y., Liu, J., Zhang, L., Long, A. 2014. Localized and sustained delivery of erythropoietin from PLGA microspheres promotes functional recovery and nerve regeneration in peripheral nerve injury. *Biomed Research International*, 478103.

Figures

Fig. 1.

Fig. 1. SEM images (a, c, e) and particle size distributions (b, d, f) for the liraglutide-loaded microspheres. Samples were prepared at (a and b) 2400, (c and d) 1200 and (e and f) 600 rpm. The average microsphere size for each sample was calculated by the analysis of around 100 microspheres in SEM images, using the Image J software.

Fig. 2.

Fig. 2. *In vitro* drug release from the liraglutide loaded microspheres. Experiments were performed in triplicate, and data are plotted as mean $\pm$ SEM.

Fig. 3.

Fig. 3. Characterising data on the microspheres. (a) DSC (exo up), (b) XRD and (c) IR spectroscopy data are given. The liraglutide-loaded microspheres shown are those prepared with ultrasonication for 5 min, a 2 % w/v PVA solution, a mixing speed of 1200rpm, and W1/O and O/W2 volume ratios of 1:100 and 1:20 respectively.

Fig. 4.

Fig. 4. Glucose concentration profiles monitored over 6 h after application of a sugar gavage. Measurements were taken (a) 5, (b) 10, (c) 15, (d) 20, (e) 25 and (f) 30 days after the start of the dosage regimen. CG is a negative control group; HFG a positive control high-fat diet group; LCIG the injection group; and, LLG, LMG, and LHG are groups treated with different amounts of microspheres (containing 0.9, 1.8 and 3.6 mg liraglutide, respectively). Data are shown as mean $\pm$ SEM over the 10 rats in each group.

Fig. 5.

Fig. 5. Changes in (a) HbA1c and (b) insulin levels after treatment for 30 days. CG is a negative control group; HFG a positive control high-fat diet group; LCIG the injection group; and, LLG, LMG, and LHG are groups treated with different amounts of microspheres (containing 0.9, 1.8 and 3.6 mg liraglutide, respectively). Data are shown as mean $\pm$ SEM over the 10 rats in each group. The annotation * in (a) denotes where values were found to be statistically different to the HFG ($p < 0.05$.)

Fig. 6.

Fig. 6. HE staining results. Representative images from the (A) lung, (B) liver, (C) spleen, (D) kidney, (E) heart are shown. CG is a negative control group; HFG a positive control high-fat diet group; LCIG the injection group; and, LLG, LMG, and LHG are groups treated with different amounts of microspheres (containing 0.9, 1.8 and 3.6 mg liraglutide, respectively).

Fig. 7.

Fig. 7. Expression of key enzymes for lipid and cysteine metabolism after 30 days' treatment. CG is a negative control group; HFG a positive control high-fat diet group; LCIG the injection group; and, LLG, LMG, and LHG are groups treated with different amounts of microspheres (containing 0.9, 1.8 and 3.6 mg liraglutide, respectively). Other abbreviations are: SREBP1c - sterol regulatory element binding protein-1c, ACC - acetyl-CoA carboxylase, ACOX1 - acyl-CoA oxidase-1, PPAR - peroxisome proliferator-activated receptor, SCD - stearoyl-coenzyme A desaturase, MTHFR - methylenetetrahydrofolate reductase, CBS - cystathionine beta-synthase, and MTR - methyltetrahydrofolate homocysteine.

Tables

Table 1. Encapsulation efficiency and drug loading of microspheres prepared under different conditions (mean $\pm$ SEM, n=3). (PVA is polyvinyl alcohol).

Serial	Inner water phase (μ L)	Oil phase (mL)	External water phase (mL)	PVA (%)	Ultrasonication time (min)	Speed (rpm)	Drug loading (%)	Encapsulation efficiency (%)	production Yield (%)
1	100	5	100	2	5	1200	1.76 $\pm$ 0.05	77.4 $\pm$ 5.6	51.4 $\pm$ 5.2
2	100	10	200	2	5	1200	1.71 $\pm$ 0.06	76.6 $\pm$ 2.6	49.8 $\pm$ 3.9
3	100	15	300	2	5	1200	1.52 $\pm$ 0.14	68.7 $\pm$ 4.2	34.6 $\pm$ 4.9
4	100	10	100	2	5	1200	1.82 $\pm$ 0.12	73.3 $\pm$ 4.7	42.4 $\pm$ 4.6
5	100	10	150	2	5	1200	1.76 $\pm$ 0.21	72.1 $\pm$ 3.7	46.4 $\pm$ 5.8
6	100	10	250	2	5	1200	1.66 $\pm$ 0.23	62.1 $\pm$ 4.8	35.2 $\pm$ 4.3
7	100	10	200	1	5	1200	1.32 $\pm$ 0.11	52.4 $\pm$ 6.2	46.4 $\pm$ 3.8
8	100	10	200	3	5	1200	1.56 $\pm$ 0.14	72.3 $\pm$ 3.2	47.2 $\pm$ 4.4
9	100	10	200	2	10	1200	1.48 $\pm$ 0.21	58.7 $\pm$ 4.1	42.6 $\pm$ 4.8
10	100	10	200	2	15	2400	1.21 $\pm$ 0.15	47.4 $\pm$ 5.6	39.8 $\pm$ 6.6
11	100	10	200	2	5	600	1.77 $\pm$ 0.03	78.3 $\pm$ 3.1	45.2 $\pm$ 3.9
12	100	10	200	2	5	1200	1.65 $\pm$ 0.06	74.1 $\pm$ 2.9	43.6 $\pm$ 5.0

Table 2. Biochemical measurements of blood lipid levels, inflammation, oxidation and antioxidant activities. Measurements were recorded in 3 times per rat on each of the 10 rats in each treatment group, and the results are reported as mean $\pm$ SEM across all measurements. Abbreviations are as follows: negative control group (CG), high fat group (HFG), liraglutide-loaded microspheres (low (LLG), medium (LMG), and high liraglutide (LHG) groups), liraglutide injection control group (LCIG), low-density lipoprotein-cholesterol (LDL-C), high-density lipoprotein-cholesterol (HDL-C), triglycerides (TG), total cholesterol (TC), High-density lipoprotein-cholesterol (HDL-C), superoxide dismutase (SOD), glutathione (GSH), total antioxidant capacity (T-AOC) malondialdehyde (MDA) tumor necrosis factor- α (TNF- α), interleukin-1 α (IL-1 α), interleukin-6 (IL-6) and interleukin-1 β (IL-1 β).

		CG	HFG	LLG	LMG	LHG	LCIG
	TC(mmol/L)	1.13 $\pm$ 0.16	1.63 $\pm$ 0.35	1.46 $\pm$ 0.15*	1.45 $\pm$ 0.87*	1.42 $\pm$ 0.65*	1.41 $\pm$ 0.25*
Blood	TG(mmol/L)	0.16 $\pm$ 0.02	0.27 $\pm$ 0.09	0.23 $\pm$ 0.02*	0.21 $\pm$ 0.03*	0.17 $\pm$ 0.04*	0.20 $\pm$ 0.03*
lipid	HDL-C(mmol/L)	0.42 $\pm$ 0.04	0.78 $\pm$ 0.13	0.63 $\pm$ 0.03*	0.61 $\pm$ 0.07*	0.54 $\pm$ 0.11*	0.61 $\pm$ 0.06*
	LDL-C(mmol/L)	0.33 $\pm$ 0.09	0.58 $\pm$ 0.11	0.51 $\pm$ 0.09*	0.48 $\pm$ 0.07*	0.50 $\pm$ 0.10*	0.51 $\pm$ 0.08*
	IL-1 α (ng/L)	241.13 $\pm$ 32.16	567.63 $\pm$ 123.35	407.86 $\pm$ 87.65*#	363.51 $\pm$ 67.54*#	333.62 $\pm$ 56.77*	321.65 $\pm$ 72.14*
Inflamma	IL-1 β (ng/L)	225.16 $\pm$ 28.45	533.27 $\pm$ 142.09	389.62 $\pm$ 79.37*#	371.26 $\pm$ 65.32*#	352.24 $\pm$ 57.61*#	289.31 $\pm$ 60.54*
tion			1252.48 $\pm$ 365.0				
	IL-6(ng/L)	443.51 $\pm$ 143.11		898.71 $\pm$ 159.54*#	851.23 $\pm$ 143.21*#	806.43 $\pm$ 161.86*#	698.65 $\pm$ 189.23*
factors			6				
	TNF- α (ng/L)	1200.3 $\pm$ 243.0	3200.5 $\pm$ 418.1	1807.6 $\pm$ 305.6*#	1652.6 $\pm$ 321.8*#	1646.6 $\pm$ 265.4*#	1467.5 $\pm$ 249.7*
Oxidative	SOD(U/mL)	170.13 $\pm$ 26.16	56.63 $\pm$ 33.35	88.57 $\pm$ 22.43*	90.45 $\pm$ 34.21*	97.38 $\pm$ 29.87*	91.19 $\pm$ 31.36*
and	GSH(mmol/L)	6.16 $\pm$ 1.04	2.27 $\pm$ 2.09	4.59 $\pm$ 1.89*	4.18 $\pm$ 1.65*	5.82 $\pm$ 2.04*#	4.85 $\pm$ 1.86*
antioxida	T-AOC(U/L)	17.51 $\pm$ 3.11	7.48 $\pm$ 4.06	12.93 $\pm$ 3.89*	13.54 $\pm$ 3.54*	14.33 $\pm$ 3.65*	14.49 $\pm$ 4.03*
nt ability	MDA(mmol/L)	2.33 $\pm$ 0.15	8.58 $\pm$ 2.34	6.57 $\pm$ 1.72*#	5.54 $\pm$ 1.84*	5.17 $\pm$ 1.14*	5.62 $\pm$ 4.65*

Note: "*" indicates that compared to the HFG group, $p < 0.05$. "#" indicates that compared with the LCIG group, $p < 0.05$.

Table 3. Liver, heart, and kidney indices for rats after 30 days' treatment. U/L = units per litre. Measurements were recorded in triplicate on each of the 10 rats in each treatment group, and results are reported as mean $\pm$ SEM across all 30 measurements. Groups and markers are abbreviated as follows: negative control group (CG), high fat group (HFG), liraglutide -loaded microspheres (low (LLG), medium (LMG), and high liraglutide (LHG) groups), liraglutide injection control group (LCIG), aspartate transaminase (AST), alanine aminotransferase (ALT), alkaline phosphatase (AKP), r-valley ammonia acyl transferase (r-GT), creatinine (Cr), uric acid (UA), blood urea nitrogen (BUN), (actose dehydrogenase (LDH), creatine kinase (CK) and creatinekinase-MB (CK-MB).

		CG	HFG	LLG	LMG	LHG	LCIG
Liver function	AST(U/L)	122.67 $\pm$ 13.21	215.25 $\pm$ 40.98	166.81 $\pm$ 20.16*	137.83 $\pm$ 18.24*	128.45 $\pm$ 17.63*	138.21 $\pm$ 16.63*
	ALT(U/L)	34.62 $\pm$ 3.16	48.74 $\pm$ 4.23	45.21 $\pm$ 2.45	42.26 $\pm$ 1.98*	39.27 $\pm$ 2.67*	41.17 $\pm$ 2.52*
	AKP(U/L)	88.33 $\pm$ 21.24	131.33 $\pm$ 11.15	126.32 $\pm$ 24.16	112.36 $\pm$ 18.45*	101.26 $\pm$ 20.41*	110.92 $\pm$ 15.67*
	r-GT(U/L)	0.67 $\pm$ 0.33	2.67 $\pm$ 0.33	2.43 $\pm$ 0.21	2.30 $\pm$ 0.42*	1.67 $\pm$ 0.17*#	2.31 $\pm$ 0.54*
Heart function	CK(U/L)	20.17 $\pm$ 7.72	79.56 $\pm$ 16.98	60.54 $\pm$ 11.23*	51.23 $\pm$ 10.26*	46.54 $\pm$ 8.82*	51.43 $\pm$ 9.83*
	CK-MB(U/L)	78.36 $\pm$ 14.21	190.98 $\pm$ 33.69	150.21 $\pm$ 12.44*	132.16 $\pm$ 15.92*	110.84 $\pm$ 13.21*#	130.23 $\pm$ 11.23*
	LDH(U/L)	81.16 $\pm$ 10.42	168.43 $\pm$ 22.61	121.69 $\pm$ 11.43*	108.52 $\pm$ 12.56*	97.54 $\pm$ 12.16*	104.28 $\pm$ 10.81*
Renal function	CREA(umol/L)	51.13 $\pm$ 7.16	101.63 $\pm$ 20.28	78.23 $\pm$ 12.86*	70.87 $\pm$ 12.74*	65.23 $\pm$ 11.21*#	74.32 $\pm$ 10.17*
	UA(umol/L)	78.16 $\pm$ 11.41	110.27 $\pm$ 30.19	98.26 $\pm$ 18.39*	93.24 $\pm$ 18.82*	90.36 $\pm$ 12.43*	94.24 $\pm$ 11.26*
	BUN(mmol/L)	6.33 $\pm$ 1.29	10.58 $\pm$ 2.12	8.92 $\pm$ 1.16*	8.74 $\pm$ 1.55*	8.70 $\pm$ 1.06*	8.81 $\pm$ 0.94*

Note: "*" indicates that compared to the HFG group, $p < 0.05$. "#" indicates that compared with the LCIG group, $p < 0.05$