An Investigation into the Colloidal Stability of Graphene Oxide Nano-layers in Alite Paste

S. Ghazizadeh^{a,*}, P. Duffour^a, N.T. Skipper^b, M. Billing^b, Y. Bai^a

^a*Department of Civil, Environmental & Geomatic Engineering, University College
London, London, WC1E 6BT, United Kingdom*

^b*London Centre for Nanotechnology, Department of Physics and Astronomy, University
College London, London, WC1E 6BT, United Kingdom*

Abstract

Recent studies have reported that graphene oxide (GO) is capable of enhancing the mechanical properties of hardened Portland cement (PC) pastes. The mechanisms proposed so far to explain this strengthening generally assume that GO is well dispersed in the pore solution of PC paste, serving as a reinforcing agent or nucleation-growth site during hydration. This paper investigates (i) the effect of GO on the hydration of alite, the main constituent of PC cement, using isothermal calorimetry and boundary nucleation-growth modelling, and (ii) the factors controlling the colloidal stability of GO in alite paste environment. Results indicate that GO accelerates the hydration of alite only marginally, and that GO is susceptible to aggregation in alite paste. This instability is due to (i) a pH-dependent interaction between GO and calcium cations in the pore solution of alite paste, (ii) a significant reduction of GO functional groups at high pH.

Keywords: Colloidal dispersion, Graphene oxide, Alite, Portland cement

*Corresponding author

Email address: s.ghazizadeh@ucl.ac.uk (S. Ghazizadeh)

1. Introduction

Graphene oxide (GO) is composed of a distorted graphene mono-layer where a fraction of carbon atoms have been functionalised by various oxygen-containing chemical groups such as carbonyl and carboxyl [1]. In recent years, the use of GO as a potential strength-enhancing additive in Portland cement (PC) paste has been the focus of much research [2–13]. Previous studies have found that GO improves the compressive strength of PC paste, however the reported results are somewhat erratic and difficult to interpret in detail. For instance, Lv et al. [11] found that adding GO to PC paste with an GO:PC mass ratio of 0.02% yields a maximum increase of 60% in the compressive strength, whereas the same authors in a recent article [12] required a higher optimal GO:PC ratio of 0.06% to achieve the same level of strength improvement. Many factors might explain these discrepancies (*e.g.* the size and oxidation level of the GO layers [10, 14]), but the mechanism by which the presence of GO leads to the strength improvements in PC pastes has remained controversial.

Two mechanisms have so far been put forward to describe the role of GO in enhancing the mechanical properties of PC paste: (i) as a derivative of graphene, the GO layers possess a high in-plane tensile strength and therefore could act as a nano-size reinforcing agent in the PC matrix, thereby delaying the formation of cracks [2–9, 15, 16]; (ii) the GO layers could serve as nucleation-growth sites during the hydration of PC, stimulating a higher degree of hydration [10–14, 17].

With respect to the reinforcing mechanism, studies postulated that the functional groups of GO play a pivotal role in providing strong interfacial bonding between the GO nano-layers and C-S-H [2, 5, 16]. In a detailed molecular

dynamics simulation study, Sanchez et al. [16] showed that a sufficient number of oxygen-containing functional groups should exist on the GO surface to achieve a strong interfacial bonding between GO and C-S-H (modelled as 9 Å tobermorite structure). They suggest that the nature of the interaction between GO and C-S-H is electrostatic, and that Ca^{2+} ions in the pore solution of paste could act as a bridge between the polarised oxygen atoms of GO and C-S-H [16]. Regarding the role of GO as extra growth sites, some studies suggest that GO accelerates the hydration of PC, resulting in an increased early-age compressive strength [13, 17]. Others report that GO induces the formation of a new micro-structure with a highly regular flower-like pattern [10, 11]. According to the latter, the GO layers may not act directly as a reinforcing agent, but rather stimulate a micro-structural pattern that gives the PC-GO paste enhanced mechanical properties.

Whether GO directly reinforces the PC matrix or increases nucleation, the mechanisms proposed to date are underpinned by a number of assumptions. First, the individual GO layers must remain well-dispersed in PC paste so that a homogeneous reinforcement and/or nucleation-growth is achieved. While it is established that due to the presence of oxygen-based functional groups, GO forms a stable aqueous colloid [18, 19], the stability of its dispersion in a PC paste environment is so far unknown. Second, the source of interfacial bonding, *i.e.* the GO functional groups, must remain chemically stable during the hydration of PC, otherwise the reinforcing role would not be effective. Using Fourier Transform Infrared Spectroscopy (FT-IR) on solid PC-GO paste, Lin et al. [17] reported that the hydration of PC has no detrimental effect on the functional groups of GO. However, the FT-IR of PC-GO could have been easily misinterpreted due to the overlapping of various stretching vibrations associated with the hydration products and

54 GO.

55 To avoid the complexities involved in the hydration of PC, we herein focus
56 on the hydration of alite, the main constituent of Portland cement. First,
57 the overall effect of GO on the alite hydration is investigated by conducting
58 a series of isothermal calorimetry measurements. The calorimetry patterns
59 show that GO accelerates the alite hydration, but the extent of observed
60 acceleration is quite low. A theoretical boundary nucleation-growth (BNG)
61 model was used to analyse the calorimetric data. According to the BNG
62 analysis, the acceleration observed in the hydration of alite-GO system may
63 stem from a combination of extra surface for the nucleation of hydration
64 precipitates provided by GO; higher nucleation density on the GO surface
65 compared to that of alite; higher rate of precipitation in alite-GO paste
66 compared to alite paste. However, the BNG results indicate that both the
67 amount of extra surface as well as the higher nucleation density added by
68 GO is only a small fraction of what GO could potentially provide. This,
69 together with direct microscopic observation pointed to a clear aggrega-
70 tion of GO in the pore solution of alite paste. This led us to investigate
71 the underlying mechanisms controlling the interaction of GO with various
72 calcium-containing aqueous electrolytes using Inductively Coupled Plasma
73 Atomic Emission Spectroscopy (ICP-AES), FT-IR, thermogravimetric anal-
74 yses (TG), and X-ray diffraction (XRD).

75 **2. Materials and Methods**

76 *2.1. Synthesis and characterisation of materials*

77 Alite was synthesised by sintering pelleted powders of 3:1 stoichiometric mix-
78 ture of high-purity CaCO_3 and SiO_2 (≥ 99 wt.%, Sigma Aldrich) which were

79 doped with 1.1 wt.% MgO and 0.7 wt.% Al₂O₃ (≥ 99 wt.%, Sigma Aldrich)
 80 according to the procedure explained by Wesselsky and Jensen [20]. The
 81 pre-mixed powders were wet-homogenised in a mixer, and then dried and
 82 calcined for 5 hours at 1000°C. The de-carbonated mix was pressed into pel-
 83 lets and subsequently heated at 1500°C for a period of 8 hours in a muffle
 84 furnace. Thereafter, the pellets were removed from the furnace and quenched
 85 immediately in the air. Once cooled, the resultant material was ground us-
 86 ing a ball-mill grinder (PM 100, Retsch). The pelleting-sintering-grinding
 87 procedure was repeated three times in order to produce a high-purity alite
 88 powder, and finally particles passed through a 80 μm sieve were selected
 89 for this study. The final particle size distribution of alite used in this study
 90 was measured by a particle characterisation tool (Morphologi G3, Malvern
 91 Instruments) and is presented in Fig. 1a. The measured Brunauer-Emmett-
 92 Teller (BET) surface area of alite was 0.572 m²/g. The crystal structure and
 93 composition of the final product was characterised using an X-ray diffrac-
 94 tometer (PANalytical X’Pert Pro). The X-ray diffraction (XRD) pattern
 95 was recorded over 2θ ranging from 10° to 70° with the following experimen-
 96 tal conditions: the X-ray tube was operated at 40 kV with 40 mA, fixed
 97 divergence slit with slit size 1°, and step size of 0.033° with 2 seconds per
 98 step. The alite powder used throughout this study was synthesised within
 99 one process and therefore there is no batch-variation in the final product.
 100 Rietveld refinement was used to quantitatively analyse the measured XRD
 101 pattern, as presented in Fig. 1b, indicating a slight trace of free lime.
 102 Graphene oxide was synthesised using the procedure given in Marcano et
 103 al. [21]. Graphite flakes (+100 mesh, Sigma Aldrich) were oxidised using
 104 3 g of graphite added to 360 mL of concentrated H₂SO₄ (≥ 95 wt.%, Fis-
 105 cher Chemicals) and 40 mL of concentrated H₃PO₄ (≥ 95 wt.%, Fischer

106 Chemicals) in a 1 litre bottle equipped with a magnetic stirrer bar. This
 107 suspension was cooled to below 5°C using an ice bath. Once cooled, 18 g of
 108 KMnO_4 ($\geq 99.0\%$, Fluke Biochemika) were added, leading to an exother-
 109 mic reaction. The mixture was left to stir in the ice bath for a further 30
 110 minutes. Following this, the mixture was kept at 25°C and left to stir for 96
 111 hours. Once the desired oxidation time had elapsed, the bottle was cooled
 112 in an ice bath again and the reaction mixture was slowly diluted with 400
 113 mL of distilled water over a period of 15 minutes. H_2O_2 solution (≥ 30 wt%,
 114 Sigma Aldrich) was then added drop-wise to the reaction mixture until the
 115 solution became bright yellow and no further colour change was observed.
 116 The solids were collected by centrifugation at 3500 rpm for 1 hour and were
 117 sequentially washed with deionised water, HCl (~ 3.5 wt.%) and acetone
 118 until the supernatant was free of SO_4^{-2} (tested using BaCl_2). The residual
 119 solid was dried for three days under vacuum at room temperature. The
 120 resulting dried solid is graphite oxide, *i.e.* stacks of GO layers only partially
 121 exfoliated.

122 The BET surface area of the synthesised graphite oxide was measured to
 123 be 220 m^2/g . Note that this value is not related to the GO single layers,
 124 and it only corresponds to the surface area of partially exfoliated GO layers
 125 in graphite oxide form. This is because the nitrogen used in the BET test
 126 cannot easily penetrate within graphite oxide, and therefore it cannot be
 127 adsorbed on all GO layers [22]. Since there is still no reliable experimental
 128 method to accurately measure the surface area of GO single layers (S_{GO})
 129 [22, 23], we estimate S_{GO} theoretically and use it later to discuss the experi-
 130 mental results. S_{GO} was calculated assuming that GO is composed of carbon
 131 hexagons with a minimum C-C bond length of $a=0.142$ nm [1] so that each
 132 hexagon has an area of 0.10477 nm^2 (including both sides). The mass of each

atom (in gram) equals to its molar mass divided by Avogadro's constant,
 $N_{Av}=6.022\times10^{23}$. The number of carbon atoms and hexagons per unit area
 (μm^{-2}) of a single layer was estimated to be approximately 1.94×10^7 and
 9.6×10^6 , respectively. This leads to a surface area of around $2600\text{ m}^2/\text{g}$
which is well-known for graphene [19]. Given that GO usually has a carbon-
to-oxygen atomic ratio of 2-3 [1, 18], S_{GO} can be between $1500\text{-}1700\text{ m}^2/\text{g}$.
This is in agreement with previous estimations [22].

GO layers were exfoliated in aqueous solutions by sonicating dry graphite
oxide in deionised water using a sonication bath (Fisher Scientific, FB15050)
for 1 hour. The quantity of graphite oxide used in sonication depended on
the required concentration of GO in water. The thickness of GO layers
exfoliated in water was measured using the tapping mode of an Atomic
Force Microscope (Bruker Dimension 3100). The sample for AFM imaging
was prepared by depositing an aqueous dispersion of GO (0.5 mg/ml) on
a freshly cleaved Mica surface. Fig. 2a shows the AFM topographic im-
age of GO nano-layers. The height profile measured from the topographic
image, presented in Fig. 2b, indicates that the exfoliated GO has an ap-
proximate thickness of 1 nm . This is in agreement with previously reported
data for the thickness of a GO mono-layer [1, 18, 19, 21]. The Mica surface
was further studied every $5\mu\text{m} \times 5\mu\text{m}$ over an area of $50\mu\text{m} \times 50\mu\text{m}$, and
the topographic images were analysed using an AFM software (NanoScope
Analysis v1.40). Results shown in Fig. 2c indicates that the 1 nm thickness
was dominant.

2.2. Iso-thermal calorimetry

The hydration of alite in the absence and presence of GO was investigated
by conducting a series of isothermal calorimetry experiments. The primary

159 aim of this study was to investigate the extent to which GO alters the rate
160 and level of heat released from the hydration of alite. If GO serves as a
161 nucleation-growth site in the pore solution of alite paste, and accelerates
162 the formation of hydration precipitates, one would expect the rate and level
163 of heat evolution for the alite-GO hydration to increase noticeably compared
164 to that of plain alite paste.

165 The hydration kinetics of plain and GO-containing alite pastes were mea-
166 sured for the first 24-hours of hydration using an isothermal calorimeter
167 (TAM Air model, TA instruments). All samples were prepared using 3 g of
168 alite powder placed into a plastic vial and then mixed in-situ with the re-
169 quired amount of water (de-ionised) which either contained GO or not. Alite
170 powder was mixed with water using a polyethylene stirrer at 350 rpm for 30
171 seconds, following a standard mixing procedure based on ASTM C186-13.
172 Once mixed, the vial was immediately sealed tightly and placed into the
173 calorimeter set at 20 °C.

174 In the case of GO-containing samples, the required quantity of GO (depend-
175 ing on the GO:alite mass ratio) was first dispersed in 20 ml of de-ionised
176 water using sonication, and then depending on the water to alite mass ra-
177 tio, the desired amount of GO-containing solution was taken to prepare the
178 paste. Four water to alite mass ratios of 0.3, 0.4, 0.5 and 0.6 were selected
179 in this study to investigate the effect of GO on alite hydration more thor-
180 oughly. For the pastes containing GO, GO was added in the amount of 0.02,
181 0.04, 0.06, and 0.08%, with respect to the alite mass, and we followed the
182 same stirring procedure as with the plain paste (350 rpm for 30 seconds) to
183 mix the aqueous solutions containing GO with alite powder. The range of
184 GO mass ratios and the standard mixing procedure were chosen on the basis
185 of previous studies where significant strength improvements were reported

186 [10–12, 14].

187 To ensure the repeatability of the results and appreciate the degree of un-
188 certainty of the measurements, calorimetry experiments were repeated three
189 times, and each calorimetry curve was analysed using three parameters
190 which characterise the main features in the trend of heat evolution. As
191 shown in Fig. 3a, these are: (i) the peak value of the derivative of heat-flow
192 during the acceleration period, denoted by $(d^2Q/dt^2)_{acc}$, (ii) the peak value
193 of heat flow, $(dQ/dt)_p$, (iii) the time at which the heat flow reaches the peak,
194 t_p .

195 2.3. Boundary nucleation and growth (BNG) modelling

196 A boundary nucleation and growth (BNG) model was adapted and imple-
197 mented to mathematically describe the calorimetry patterns. The BNG
198 theory employed in this study was based on the concept of time-dependent
199 growth rate of precipitates, as described by Bullard et al. [24]. In this
200 model, the kinetics of alite hydration depends on the precipitation of hy-
201 dration products from the pore solution of paste which always remains un-
202 dersaturated with respect to alite dissolution. The hydration precipitates
203 are assumed to form as ellipsoidal particles on the surface of substrates (*i.e.*
204 anhydrous alite and GO), and initially nucleate on a fixed number of sites,
205 denoted by N_S [25].

206 The BNG model predicts the volume fraction of paste that is transformed
207 into hydration products as a function of time. At any given time t (hours),
208 this volume fraction (referred to as the real volume V_{real}) can be calculated
209 from the extended volume V_{ext} using equation Eq. 1:

$$V_{real}(t) = 1 - \exp(-V_{ext}(t)). \quad (1)$$

210 The extended volume, $V_{ext}(t)$, can be computed at each time step using
 211 equations Eqs. 2-4:

$$V_{ext}(t) = 2.G_{out}(t).r_G.O_V^B.\left(1 - \frac{F_D(x, t)}{x(t)}\right), \quad (2)$$

212

$$F_D(x, t) = \exp\left(-x^2 t^2\right) \int_0^{x.t} \exp(y^2) dy, \quad (3)$$

213

$$x(t) = G_{out}(t)\sqrt{\pi N_S g}, \quad (4)$$

214 where $G_{out}(t)$ ($\mu\text{m}/\text{h}$) is the time-dependent outward growth rate of hydra-
 215 tion product with respect to the surface of substrates, r_G is the ratio of the
 216 growth rates into and out of the substrate (only applies to alite particles), g
 217 is the degree of anisotropy of the growth rate defined as the ratio of parallel
 218 and outward growth rates. O_V^B (μm^{-1}) is the total boundary area (specific
 219 surface area) of substrates per unit volume of paste, which can be calculated
 220 using equations Eq. 5 and Eq. 6:

$$O_V^B = \left[\frac{S_{alite} + \gamma.S_{GO}}{V_w + V_{alite}} \right], \quad (5)$$

221

$$\gamma = \frac{m_{GO}}{m_{alite}}, \quad (6)$$

222 where m_{GO} and m_{alite} are the mass of GO and alite, respectively. S_{alite}
 223 (m^2/g) is the specific surface area of alite as measured by the BET method,
 224 V_w and V_{alite} are the volume of water and alite (per gram of alite) in the
 225 paste, respectively. N_S (μm^{-2}) is the total number of nuclei per unit area
 226 of the substrates, which can be calculated using Eq. 7:

$$N_S = \left[\frac{N_S^{alite}.S_{alite} + N_S^{GO}.\gamma.S_{GO}}{S_{alite} + \gamma.S_{GO}} \right], \quad (7)$$

227 where N_S^{alite} and N_S^{GO} are the number of active nucleation sites per unit
 228 surface area of alite and GO, respectively.
 229 The volume fraction of alite consumed and transformed into hydration prod-
 230 ucts (V_{real}) can be related to α , the dimensionless degree of alite hydration,
 231 by a constant B, as described by equation Eq. 8:

$$\alpha = V_{real} \cdot B, \quad (8)$$

232 B (dimensionless) can be calculated for a specific water to alite mass ratio
 233 (R_{wc}) according to equation Eq. 9 [24]:

$$\frac{1}{B} = \left(\frac{\rho_{alite}/\rho_H}{1 + R_{wc}\rho_{alite}/\rho_w} \right) \cdot \left(\frac{c + 1/\rho_{alite} - 1/\rho_w}{1/\rho_H - 1/\rho_w} \right), \quad (9)$$

234 where, ρ_{alite} is the density of alite (3150 kg/m³), ρ_w is the density of water
 235 (1000 kg/m³), ρ_H is the average density of hydration products (taken as 2230
 236 kg/m³), R_{wc} is the water to alite mass ratio, and $c = -7.04 \times 10^5$ m³/kg is
 237 a constant parameter related to the chemical shrinkage per kilogram of alite
 238 when its hydration is complete [24]. Using the rate of change in the degree
 239 of hydration, the rate of heat flow for the reaction of alite with water can
 240 be calculated using Eq. 10:

$$\frac{dQ}{dt} = \frac{d\alpha}{dt} \cdot H_{alite}, \quad (10)$$

241 where H_{alite} is the enthalpy of alite hydration and is fixed to 517 J/g [26].
 242 A number of assumptions were made in the implementation of the BNG
 243 model in this study: (a) the hydration products grow outward and parallel
 244 to the surface of alite, and the g ratio is considered to be 0.5 [25], (b) the
 245 BNG model is only used here to investigate the acceleration period (see
 246 Fig. 3a) when the formation of hydration products is only allowed outwards
 247 of the substrates into the aqueous phase, and therefore the r_G factor is

248 assumed to be 0.5 [25], (c) the number of active growth sites on the alite
 249 surface (N_S^{alite}) is assumed to be $12 \mu m^{-2}$ [27].
 250 To simulate the calorimetric patterns of plain alite (with no GO) hydration,
 251 the only unknown variable that needs to be calculated at each time t , is
 252 the rate of growth G_{out} . An iteration process was used to determine G_{out}
 253 at each time step such that the value of dQ/dt calculated from the model
 254 matches that measured by isothermal calorimeter. Fig. 3b shows the fitted
 255 calorimetry curve of alite hydration for a paste with water to alite mass
 256 ratio of 0.5, up to 12 hours of hydration. This water to alite ratio is used as
 257 an illustrative example. In Fig. 3c, the rate at which the hydration product
 258 grows on the surface of alite particles is presented as a function of hydration
 259 degree (α) and time. The generally descending pattern of growth rate is
 260 consistent with the simulations in [24], and the values of G_{out} are within the
 261 same order of magnitude as those reported in previous studies [24, 27–29].
 262 In the case of plain alite paste, O_V^B and N_S parameters are known and
 263 can be simply calculated using Eq. 5 and Eq. 7 with $\gamma = 0$. For instance,
 264 $O_V^B = 0.6235 \mu m^{-1}$ and $N_S = 12 \mu m^{-2}$ for a plain paste with water-to-alite
 265 ratio of 0.6. However, these variables cannot be directly estimated for alite-
 266 GO pastes as the nucleation kinetics of hydration precipitates on the GO
 267 surface is as yet not well understood.
 268 Simulating the hydration of alite-GO pastes involves three unknowns: O_V^B ,
 269 N_S and $G_{out}(t)$. Our goal is to estimate the possible O_V^B and N_S values
 270 consistent with the acceleration observed in the alite-GO calorimetry data.
 271 To do this, we first define a lower and an upper bound for $G_{out}(t)$, beyond
 272 which the rate of growth is meaningless for alite-GO systems. $G_{low}(t)$ and
 273 $G_{up}(t)$ denote the lower and upper bounds (resp.) of $G_{out}(t)$ for the alite-GO
 274 system, and are defined as:

275 • $G_{low}(t)$ is the $G_{out}(t)$ calculated from fitting Eq. 10 to the calorimetry
 276 curve of plain alite paste (having the same R_{wc} as alite-GO) using O_V^B
 277 and N_S of plain alite. Any $G_{out}(t)$ computed for alite-GO should lie
 278 above this level since alite-GO always hydrates faster than plain paste
 279 (as shown in the results).

280 • $G_{up}(t)$ is the $G_{out}(t)$ computed from fitting the alite-GO calorimetric
 281 data but using the O_V^B and N_S values of plain paste. According to
 282 the BNG formulation, the acceleration in alite-GO hydration can be
 283 associated to three factors: (i) extra solid surface for nucleation (O_V^B),
 284 (ii) higher nucleation sites (N_S), (iii) higher growth rate of hydration
 285 products ($G_{out}(t)$). In essence, $G_{up}(t)$ neglects the first two factors
 286 and considers the alite surface to be the only place available for the
 287 nucleation. Therefore, $G_{up}(t)$ ignores the contribution of GO as a
 288 nucleation surface and any acceleration observed in the calorimetric
 289 data is solely attributed to the rate of growth (G_{out}). By increasing
 290 O_V^B and N_S for alite-GO system (*i.e.* GO starts to act as a surface in
 291 the model) the $G_{out}(t)$ resulting from the BNG fitting reduces and so
 292 is bound to be lower than $G_{up}(t)$.

293 Once $G_{low}(t)$ and $G_{up}(t)$ are defined, O_V^B and N_S are incremented system-
 294 atically from their plain values considering all possible pairings. For each
 295 pair, $G_{out}(t)$ is computed. Only those $[N_S, O_V^B]$ combinations such that
 296 $G_{low}(t) < G_{out}(t) < G_{up}(t)$ are deemed consistent with the hydration data.
 297 The ranges of N_S and O_V^B obtained from this process are then used in Eqs. 5-
 298 7 to calculate S_{GO} and N_S^{GO} . In this way, the BNG calculation allows us to
 299 consider all possibilities and determine the extent to which GO adds extra
 300 surface and nucleation sites in alite paste.

301 *2.4. Characterisation of GO chemical structure and its aqueous solution*

302 The chemical structure of GO was characterised by recording the X-ray photoelectron spectra (XPS) of solid graphite oxide sample over a spot size of
303 400 μm and dwell time of 50 ms, using a photoelectron spectrometer (K-
304 Alpha XPS, ThermoFisher Scientific) with a monochromated Al K_α source.
305 C1s spectra were recorded 10 times with a resolution of 0.1 eV. In addition,
306 Fourier Transform Infrared spectroscopy (FT-IR) was conducted on
307 the graphite oxide sample using a FT-IR spectrometer (Bruker, Tensor II).
308 The spectra were recorded with 256 scans at 4 cm^{-1} resolution. The specific
309 aim of this characterisation was to identify the functional groups existing
310 in the chemical structure of GO, and to relate their presence to the col-
311 loidal stability of GO in water. To explain this relationship, the pH and
312 zeta-potential of aqueous solutions containing 0.6, 1.2, 2 and 2.4 mg/mL
313 of GO were measured using a pH meter (Sevenmulti, Mettler Toledo) and
314 zeta-potential analyser (Brookhaven, NanoBrook Omni). The measurement
315 of pH was repeated 10 times over a period of 20 minutes for each sample,
316 and the mean value along with the data distribution was reported. The
317 maximum range of pH observed in this study was ± 0.2 .
318

319 *2.5. Interaction of calcium electrolytes and alite pore solution with GO lay-*
320 *ers*

321 In general, the aqueous pore solution of alite paste contains various ionic
322 species produced from the dissolution reaction of alite particles in water,
323 according to Eq. 11.

324 The concentration of calcium in alite paste is much higher than any other
325 divalent cations, such as Mg^{2+} , and therefore, this study mainly focuses on

326 the interaction of Ca^{2+} with GO. In addition to calcium cations, the pH of
 327 alite (and PC) paste is known to be highly alkaline.
 328 The interaction of calcium and hydroxide ions with GO was characterised
 329 using a series of GO solutions, each containing a specific dosage of GO, and
 330 mixed with various solutions containing Ca^{2+} . Three sources of calcium-
 331 solution were considered: (i) saturated calcium hydroxide solution (CH)
 332 with $[\text{Ca}^{2+}] = 23.3 \text{ mmol/L}$, (ii) calcium chloride solution (CC) prepared such
 333 that it contains the same $[\text{Ca}^{2+}]$ as that of CH, (iii) alite pore solution (PS).
 334 The preparation of PS was carried out by mixing 200 ml of de-ionised water
 335 with 4 g of anhydrous alite powder to yield a dilute suspension with a water
 336 to solid mass ratio of 50. The alite suspension was stirred for 30 minutes in
 337 order to ensure that enough ionic species were available in the pore solution,
 338 and thereafter, the undissolved particulates were separated from the solution
 339 by centrifuging the suspension for 10 minutes at a speed of 3500 rpm. Then
 340 the supernatant was removed and passed through a $0.45 \mu\text{m}$ syringe filter,
 341 and the resulting solution was used as PS. Before any use, centrifugation
 342 and filtering were also carried out on the CH and CC solution to ensure the
 343 removal of undissolved particulates.
 344 To help identify the mechanism behind the GO interaction with alite pore so-
 345 lution, the effect of various concentrations of GO (ranging from 0.33 mg/ml
 346 to 2.66 mg/ml) on the uptake of calcium was quantitatively analysed using
 347 ICP-AES. For this quantitative experiment, only the GO-CH and GO-CC
 348 solutions were studied since it was possible that the pore solution of alite
 349 suspension was saturated with respect to C-S-H and some precipitates could
 350 have formed during the sample preparation, affecting the ICP data. For the
 351 ICP study, samples were prepared by mixing 5 ml of GO aqueous colloid
 352 with 5 ml of either CC or CH solution, and then the solid was extracted

353 from the solution by centrifuging for 15 minutes at 3500 rpm speed. 5 ml
354 of supernatant obtained from this process was acidified using 1% HNO_3 so-
355 lution and selected for ICP-AES analysis. For each GO dosage, the whole
356 preparation and ICP measurement were repeated three times to evaluate the
357 variability in measured data, and the mean value as well as the variation
358 were reported.

359 The effect of calcium solutions on the chemical structure of GO was also
360 investigated. To do this, 40 ml of 0.6 mg/ml GO aqueous colloid was mixed
361 separately with 40 ml of the CH, CC and PS solutions, and the GO solid
362 was removed from the aqueous solution using centrifugation and dried for 18
363 hours in a freeze-dryer with no pre-freezing. The dried GO samples, referred
364 to as GO-CC, GO-CH and GO-PS were characterised using FT-IR, XRD
365 and TG. The XRD patterns were recorded over 5° to 50° with the step size
366 of 0.022° . 8 mg of each dried GO solid was analysed in a TG instrument
367 (Netzsch, TG 209 libra) at a heating rate of $2^\circ\text{C}/\text{min}$ from 30 to 400°C
368 under nitrogen atmosphere (20 ml min^{-1}). For this characterisation, the
369 solid of GO was washed-centrifuged 5 times with de-ionised water before
370 freeze-drying to remove the ionic species that could otherwise remain in the
371 sample as a result of drying.

372 **3. Results and Discussion**

373 *3.1. Effect of GO layers on the hydration of alite*

374 Fig. 4 shows the rate of heat evolution for the reaction of alite with water in
375 the absence and presence of GO nano-layers, measured for various water to
376 alite mass ratios. In general, all the heat evolution curves follow the typical
377 pattern of alite hydration, including a period of accelerating heat flow which

thereafter starts to decelerate. It can be observed that for all water to alite mass ratios (Figs. 4a-d), the alite pastes containing GO have a slightly altered hydration pattern compared to the plain samples. GO marginally increases both the rate of heat flow during the acceleration period as well as the peak of heat flow; however, the time required to reach the maximum heat flow remains almost unchanged for all samples, regardless of their water to solid mass ratios. It can also be seen that the higher the water to alite ratio in the paste (higher aqueous volume), the more pronounced the effect on the hydration pattern.

To compare the hydration trends observed in Fig. 4 more systematically, the heat evolution experiment was repeated three times, and each calorimetry curve was analysed using three parameters which characterise the main features in the trend of heat evolution, as described in Section 2.2. Figs. 5a-c show the trend of $(d^2Q/dt^2)_{acc}$, $(dQ/dt)_p$ and t_p as a function of GO concentration. Figs. 5a and 5b confirm that the rate of acceleration period, $(d^2Q/dt^2)_{acc}$, as well as the peak rate, $(dQ/dt)_p$, increase slightly (and vary almost linearly) with the concentration of GO. Fig. 5c shows that the time of peak does not depend appreciably on the concentration of GO in alite paste.

The calorimetric results show that the presence of GO accelerates the hydration of alite. Since the rate of formation of hydration precipitates is a rate-controlling step during the acceleration period [30–33], the calorimetry findings are in line with the role of GO as a nucleation-growth site in cement paste. However, the extent of observed acceleration seems to be quite low and not as significant as expected from previous reports [2]. To further investigate this, we use the BNG model described in Section 2.3.

Our BNG analysis aims to estimate the possible extra surface and nucleation

405 sites provided by GO in alite-GO hydration consistent with the acceleration
 406 observed in the calorimetry data. To do this, we first calculate $G_{low}(t)$
 407 and $G_{up}(t)$ as defined in Section 2.3. Fig. 6a shows the patterns of $G_{low}(t)$
 408 and $G_{up}(t)$ for alite paste containing 0.08%GO with $R_{wc}=0.6$. This system
 409 is selected for illustration. $G_{up}(t)$ describes the acceleration of alite-GO
 410 hydration solely in terms of the growth rate, and it neglects the contribution
 411 of GO as a nucleation surface. The presence of GO as a surface was included
 412 in the BNG model by increasing the N_S and O_V^B values. Figs. 6b-c show
 413 the dependence of G_{out} at times $t=2$ hours and $t=10$ hours as N_S and O_V^B
 414 values are increased. These times were only selected as illustrative examples.
 415 Figs. 6b-c confirm that G_{out} is a decreasing function of N_S and O_V^B . Since
 416 the state of GO in alite paste is unknown, it is not possible to directly
 417 determine O_V^B , N_S and $G_{out}(t)$ for alite-GO pastes. However, we can find
 418 all possible ranges of these variables.
 419 As described in Section 2.3, all $[N_S, O_V^B]$ combinations can be determined
 420 such that their corresponding $G_{out}(t)$ falls between $G_{up}(t)$ and $G_{low}(t)$. For
 421 instance, Fig. 7 shows G_{out} at $t=10$ hours resulting from the BNG fitting for
 422 various combinations of $[N_S, O_V^B]$. The acceptable values of G_{out} in Fig. 7
 423 are those that lie above the orange plane surface (G_{low}) and remain below
 424 point A (G_{up}). Considering all acceptable points in Fig. 7, there are three
 425 kinds of possibilities for the GO as a nucleation surface in alite paste: (i)
 426 high N_S but low O_V^B (towards point B), (ii) low N_S but high O_V^B (towards
 427 point C), (iii) moderate N_S and moderate O_V^B (e.g. point D). The ranges of
 428 acceptable N_S and O_V^B such that $G_{low}(t) < G_{out}(t) < G_{up}(t)$ are given in
 429 Table 1 for alite-0.08%GO pastes at various water-to-alite ratios.
 430 Using the O_V^B value from Table 1, the possible maximum and minimum
 431 values of GO surface area (S_{GO}) involved in the alite-GO hydration was

432 calculated using Eq. 5 and Eq. 6. Taking the calculated S_{GO} and the N_S
 433 values given in Table 1, the number of active nucleation sites per unit area
 434 of GO surface (N_S^{GO}) was calculated using Eq. 7, and the maximum and
 435 minimum values are also given in Table 1. It can be seen from Table 1
 436 that the BNG-calculated S_{GO} values (maximum 230 m²/g) are about one
 437 order of magnitude lower than the theoretical predication of S_{GO} (1500-1700
 438 m²/g). The BNG calculated N_S^{GO} values are 15-500 μm^{-2} . A theoretical
 439 value of N_S^{GO} can be predicted using Eq. 12:

$$N_S^{GO} = \left[\frac{N_{active}}{S_{GO}} \times N_{Av} \right] \times 10^{-15}, \quad (12)$$

440 where N_{active} is the potential quantity of active sites per gram of GO
 441 (mmol/g) which is 5-8 mmol/g according to [34]. This leads to a theo-
 442 retical N_S^{GO} value between $1.99 - 2.75 \times 10^6$ for per unit area of GO single
 443 layer. The N_S^{GO} estimated from BNG fitting is several orders of magnitude
 444 lower than what GO could potentially provide in the paste.

445 The BNG results indicate that the acceleration observed in the calorimet-
 446 ric patterns of alite-GO hydration involves a small fraction of GO surface
 447 area and active sites. This sheds some doubt on the effectiveness of GO as
 448 nucleation site in alite paste in contrast to previous reports [10–12, 14].

449 The micrographs of pastes hydrated for 24 hours with and without GO are
 450 shown in Fig. 8. It can be seen from Fig. 8b that in the alite-GO paste, there
 451 are in-homogeneously scattered dark-brown aggregates which represent the
 452 state of GO in the hydrated paste. From this, as well as the BNG analysis,
 453 we hypothesise that the aggregation of GO in alite paste could be at the
 454 origin of GO ineffectiveness as nucleation-growth sites. The remainder of
 455 the paper investigates this hypothesis by considering the chemical structure
 456 of GO and its interaction with various calcium electrolytes including the

457 pore solution of alite paste.

458 3.2. Characterisation of GO chemical structure

459 The chemical structure of GO is characterised using the FT-IR and C1s
460 XPS patterns shown in Fig. 9. The chemical features of GO are described
461 in some detail in this section as they will be shown to be key in explaining
462 the interaction of GO with the pore solution of alite paste.

463 The FT-IR spectrum of GO shown in Fig. 9a, reveals five main vibration
464 regions. Assigning a definite chemical group to each peak is not straightfor-
465 ward, and the peak identification proposed here is based on a wide survey
466 of the GO literature. The spectrum features a broad region in the range
467 of $2400\text{--}3700\text{ cm}^{-1}$ which is associated with the stretching vibration of O-H
468 (ν_{OH}). The peak band in this region (band 5) has been attributed to the
469 vibration of O-H existing as part of the GO structure as well as the ad-
470 sorbed water molecules on the surface of GO [35, 36]. The peaks at ~ 1225
471 cm^{-1} (band 1) and 1354 cm^{-1} (band 2) are related to the vibration of C-O
472 and the bending vibration of C-OH, respectively [37]. The relatively strong
473 band at $1692\text{--}1728\text{ cm}^{-1}$ (band 4) is attributed to the stretching vibration
474 of non-carboxyl carbonyl (C=O), which may exist in single structures such
475 as ketones, or can be part of chemical structures such as carboxylic anhy-
476 drides [36]. Inset A shown in Fig. 9a highlights the presence of a small
477 shoulder at 1585 cm^{-1} which is the characteristic peak of de-protonated
478 carboxyl (carboxylate) structure. The peak at 1619 cm^{-1} (band 3) is com-
479 monly attributed to the stretching vibration of the carbon network (C=C)
480 [10–12, 21, 38]. However, the assignment of this band is not straightfor-
481 ward as it overlaps with that of water molecules undergoing O-H bending
482 vibration (β_{OH}). Mermoux et al. [35] showed that the FT-IR spectrum of

strongly de-hydrated GO has no significant peak at 1619 cm^{-1} . This has been recently confirmed by Szabo et al. [37] and Dimiev et al. [34] using deuterated GO, suggesting that the 1619 cm^{-1} peak cannot solely represent the carbon network, and the intensity of this peak may be altered in the presence of surface-bound water in GO.

Further to the FT-IR results, the XPS C1s spectrum of GO shown in Fig. 9b, indicates that the carbon atoms are in three chemical states. The first peak at 285 eV corresponds to a non-oxygenated carbon structure which can be present in both forms of C=C and C-C hybridised carbon. The peak at 286.6 eV is attributed to the carbon from C=O and C-O structures which can exist in GO within the carbonyl, hydroxyl and epoxide functional groups. The last peak at 288.5 eV indicates the presence of carboxylate (O-C=O) structures.

Two key features must be highlighted from the analysis of GO: first, a variety of oxygen-containing functional groups exist in the GO structure which have hydrophilic characteristics, second, the 1585 cm^{-1} peak in FT-IR curve and the O-C=O peak in the XPS spectrum indicate that the GO structure contains carboxylate structures.

3.3. Factors controlling the colloidal stability of GO in water

GO forms well-dispersed colloids in water due to its functional groups [1, 18]. The overall effect of these groups is to counteract Van der Waals forces between the GO layers which would otherwise make them agglomerate. In detail, this is achieved through several concurrent mechanisms:

- The GO layers are negatively charged in water. This is primarily due to the presence of carboxyl groups which can dissociate in water,

508 releasing protons (H_+) as described by reaction Eq. 13.

509 This reaction makes the aqueous solution acidic and also causes the
510 GO layers to be negative as confirmed by the pH and zeta-potential
511 measurements shown in Fig. 10. It can be seen that the pH is acidic
512 (~ 3), and the values of zeta-potential are highly negative for all GO
513 solutions. Most agree that the carboxyl group contributes to the neg-
514 ative zeta-potential but other mechanisms still being debated could
515 also play a role [34, 39, 40].

516 • The functional groups of GO are all hydrophilic causing water molecules
517 to be strongly bonded to these groups. Evidence of surface-bound wa-
518 ter has previously been reported by Buchsteiner et al. [41] and Cervený
519 et al. [42], but this has rarely been related to the stability of GO in
520 water.

521 Using these mechanisms as basis for the stability of GO in water, the follow-
522 ing sections describe how the pore solution of alite paste or other calcium-
523 containing electrolytes interact with GO layers in aqueous environment.

524 3.4. Interaction of GO layers with calcium cations

525 Fig. 11a shows an aqueous colloid of GO with a solid concentration of 0.3
526 mg/ml prepared by mixing 5 ml of 0.6 mg/ml GO colloid with 5 ml pure
527 de-ionised water. The GO colloid appears homogeneous with a brownish
528 colour. To test the effect of various ionic species on the colloidal stabil-
529 ity of GO, two separate 5 ml GO colloids (0.3 mg/ml) were mixed with 5
530 ml of saturated calcium hydroxide (Fig. 11b) and 5 ml of pore solution of

alite paste (Fig. 11d). The measured pH values of $\text{Ca}(\text{OH})_2$ (CH) and alite
pore solution (PS) prior to mixing with the GO solution were 12.1 ± 0.18
and 11.6 ± 0.2 , respectively. It can be seen that the GO layers have coag-
ulated in the GO-CH and GO-PS. To verify whether this agglomeration
still occurs with a low-pH calcium electrolyte, a calcium chloride solution
with $\text{pH} = 8 \pm 0.2$ containing the same concentration of Ca^{2+} as that of sat-
urated CH ($[\text{Ca}^{2+}] = 23.3 \text{ mmol/L}$) was mixed with 5 ml GO colloid. This
mix is shown in Fig. 11c. As can be seen, the colloidal stability of GO-CC
is similar to the plain GO colloid, and is significantly different to that of
GO in GO-CH and GO-PS. Note that the image in Fig. 11 was taken al-
most immediately after mixing the Ca-based solutions with the GO colloid,
and although not clear from the picture, the GO-CC solution does in fact
contains very small agglomerates and even precipitate a few hours after the
mixing. From these observations, a pH-dependent interaction between GO
and calcium-containing solutions clearly takes place which causes the GO
layers to flocculate.

To analyse more thoroughly how GO interacts with the Ca-electrolytes, the
concentration of calcium in various GO-Ca solutions was measured using
ICP-AES, as explained in Section 2.5. Fig. 12a shows the concentration of
calcium as a function of GO dosage in water. It appears that for the GO-
CC mix, there is no appreciable change in the concentration of calcium. By
contrast, the calcium content decreases noticeably in the GO-CH mix as the
concentration of GO in the solutions increases. The ICP data suggest that
a cationic interaction between Ca^{2+} and GO only happens when the GO
solution is exposed to a high pH environment. Since the pH of alite pore
solution is similar to that of calcium hydroxide, it can be expected that the
same Ca-interaction occurs between GO layers and alite pore solution.

As an attempt to correlate the calcium uptake with the concentration of carboxylate, the shaded area in Fig. 12a shows the range of quantity of carboxylate functional groups available in the GO-CH solutions. This range was obtained using three XPS C1s surveys conducted on the $400\mu\text{m}$ area of dried GO solid (shown in Fig. 12b). The concentration of carboxylate, denoted α_{O_2C} (mmol/ml) was calculated using equation Eq. 14:

$$\alpha_{O_2C} = \frac{A_{O_2C}}{A_T} \times \frac{M_{GO}}{M_{O_2C}^m}, \quad (14)$$

where A_{O_2C} is the area under the deconvoluted fitting curve corresponding to the O-C=O structure as shown in Fig. 9, A_T is the total area under the XPS C1s spectrum, $M_{O_2C}^m$ is the molar mass of carboxylate group, and M_{GO} is the mass of GO per unit volume of solution (mg/ml). It was found between 7 to 16.5% of the carbons of GO exist within a carboxylate structure. This implies for instance that α_{O_2C} could be in the range of $1.59\text{-}3.75 \times 10^{-3}$ mmol/ml for 1 mg/ml GO solution.

Fig. 12a shows that the concentration of calcium in the solutions follows that of the carboxylate groups suggesting that the carboxylate groups interact with calcium ions. At pH=3, the carboxyl groups have a low degree of dissociation and would not interact much with calcium. As the pH increases, the carboxyl groups become more de-protonated (carboxylated) and more susceptible to form a complex with the calcium cations. Therefore, a plausible mechanism that governs the calcium interaction with GO layers could be based on the complexation of calcium with de-protonated carboxyl (carboxylate) groups. Accordingly, the carboxyl groups which were an important source of negative charges between the GO layers can no longer act in this role, causing the GO layers to aggregate in GO-CH and GO-PS solutions shown in Fig. 11.

583 A number of studies have investigated the aggregation kinetics of GO in
 584 the presence of calcium chloride [43–45]. All pointed out that Ca^{2+} ions
 585 affect the colloidal stability of GO. Without measuring the uptake of cal-
 586 cium directly, they suggest that the mechanism controlling the aggregation
 587 of GO is related to the adsorption of calcium on the functional groups of
 588 GO. However, the ICP data in Fig. 12a shows that there is almost no uptake
 589 of calcium in the GO-CC solution, suggesting that the GO aggregation we
 590 observed in the GO-CC mix cannot simply be explained by the role of cal-
 591 cium and it is likely that the calcium interaction is not the main controlling
 592 mechanism for the colloidal instability of GO in GO-CC.

593 *3.5. pH-dependent stability of GO chemical structure in Ca-based electrolytes*

594 Fig. 13 shows the FTIR spectra of various GO samples extracted from the
 595 GO-CH, GO-CC and GO-PS solutions, prepared according to the method-
 596 ology described in Sections 2.2.2. Comparing the plain GO sample with
 597 GO-CH and GO-PS, it can be seen that the main peak associated with
 598 the non-carboxyl carbonyl group has disappeared from the spectrum (1728
 599 cm^{-1}). The 1223 cm^{-1} peak band which could be related to the epoxide
 600 group, or possibly other C-O structures, is also significantly lower. How-
 601 ever, from the spectrum of GO-CC, it can be seen that these peak bands
 602 are still present in this sample, and there is a sharp amplification of 1619
 603 cm^{-1} peak which was identified before (Fig. 9) as the bending vibration of
 604 water molecules. Note that the spectrum of GO-plain corresponds to the
 605 sample analysed after synthesis, whereas the other spectra were measured
 606 on dried samples extracted from an aqueous solution. It should be noted
 607 that although the major peaks still exist in the spectrum of GO-CC sample,
 608 the chemical structure of this sample is not left intact. It can be seen that

609 the C-O peak band (1223 cm^{-1}) is reduced for this sample.
 610 The FT-IR spectra suggest that GO has been de-oxygenated in all Ca-
 611 containing mixes, and that the degree of structural alteration depends on
 612 the pH of the electrolytes used to prepare each mix. As the GO-CC sample
 613 has more hydrophilic functional groups, it contains more bound-water com-
 614 pared to GO-CH and GO-PC. This can be clearly seen from the 1619 cm^{-1}
 615 peak. This shows that as the hydrophilic functional groups are reduced, the
 616 intensity of water bending vibration is also decreased.
 617 Since most of the non-carboxyl groups are removed at high pH, it is possible
 618 that the de-oxygenation mechanism of GO is controlled by reactions between
 619 the hydroxide ions and those groups, as also shown by Dimiev et. al. [34].
 620 Considering the ICP data and the FT-IR pattern of GO- CC, it can be
 621 concluded that the adsorption of calcium is not the primary mechanism
 622 destabilising the dispersion of GO colloids in GO-CC mix, but that it is
 623 rather the loss of hydrophilic functional groups. The same mechanism along
 624 with the calcium-uptake could occur in the GO-PS and GO-CH mixes.
 625 In discussing the ICP data shown in Figs. 12a and 12b, it was suggested
 626 somewhat tentatively that calcium mostly interacts with the carboxyl groups
 627 in GO-CH. This is further confirmed by the FT-IR spectrum of GO-CH
 628 showing a more pronounced peak associated with the carboxylate structure.
 629 This implies that the carboxylate group is the most stable structure in GO
 630 at high pH range and therefore the only one left to interact with calcium.
 631 The X-ray diffraction patterns of various electrolyte-treated GO samples are
 632 shown in Fig. 14. The pattern of GO-plain shows no background and a single
 633 peak representing a distance of $7.78\text{ \AA}$ between GO layers, created due to
 634 the surface functional groups in GO as well as water molecules (compared
 635 to graphite pattern). The XRD pattern of GO-CC shows that this sample

contains GO structures with various levels of oxidation as there is a clear change in XRD background level with respect to the intensity of the main peak. This background is broadband and indicates an irregular reduction of inter-layer spacing between the GO layers. This is made possible by the disappearance of some of the functional groups. The change in GO-CC structure is consistent with the de-oxygenation of this sample as found in the FT-IR.

Comparing the GO-CH and GO-PS with GO-CC and GO-plain, it can be seen that the extent of the spacing irregularity is significantly increased, implying that there should be even fewer functional groups present in GO-CH and GO-PS samples. From this observation, it can be concluded that the majority of remaining functional groups in GO structure are not placed between the graphitic layers (*i.e.* reduction of functional groups on the GO surface). This confirms the conclusions drawn from the FT-IR spectra according to which carboxylate is the most stable group in GO, which is known to exist at the edge of GO layers [1]. In the XRD pattern of GO-CH and GO-PS, there is a peak corresponding to calcium carbonate which cannot be found in the GO-CC sample. This is consistent with the uptake of calcium in the GO-CH and GO-PS samples, as found in the ICP data. It should also be noted that there is an increase of space between GO layers in GO-CC, GO-CH and GO-PS samples which one might interpret as an intercalation of calcium between the GO layers. However, this should not be seen as an evidence for the uptake calcium in these samples, and the ICP data are more informative in this respect. Overall, the XRD patterns confirm that there is a relationship between the pH of the electrolytes used and the extent of reduction in surface-functionality. The XRD of GO-CH and GO-PS samples indicates that the surface structure of GO is significantly damaged in these

663 mixes.

664 Figs. 15a and 15b show the TG and differential TG curves obtained for
665 the plain-GO, GO-CH, GO-PS, GO-CC and GO-W samples. GO-W was
666 acquired by centrifuging the GO solution in its stable colloidal form at a
667 speed of 11000 rpm. The TG curve for the plain GO sample shows two
668 regions of major mass-loss: one around 30-100 °C which is related to the
669 loss of absorbed water on GO, and one between 100-200 °C corresponding to
670 the decomposition of oxygen-containing functional groups [46]. Comparing
671 the plain GO with the GO-CH sample, it can be seen that the level of
672 mass-loss associated with the decomposition of functional groups is reduced
673 significantly from 32.9% for plain GO to 12% for GO-CH. The thermal
674 stability of GO-PS is also affected but less so with a mass-loss of 19.7%
675 at 150-200 °C. In agreement with the FT-IR data, the GO-CC sample has
676 been de-oxygenated, however the position of functional group decomposition
677 peak has shifted to a higher temperature. An identical shift can be observed
678 between plain GO and GO-W. In this case, the shift can only be attributed
679 to the presence of water in GO-W sample. The XRD pattern of GO-W
680 shown in Fig. 14 also suggests that the inter-layer distance of GO layers
681 are increased in this sample compared to plain GO as a result of water-
682 intercalation between the layers. From the identical position of GO-CC
683 peak, it is reasonable to infer that the peak has shifted because of strongly
684 bonded water molecules to the oxygen-based functional groups of GO. The
685 higher mass-loss below 100 °C for the GO-CC and GO-W samples also
686 confirms this. Comparing the position of the DTG peaks of GO-W and
687 GO-CC with that of GO-CH and GO-PS suggests that latter two contain
688 less bound water as there are fewer functional groups remaining in their GO
689 structure.

690 The TG results confirm that (i) GO-CC contains more functional groups
 691 than GO-CH and GO-PS and (ii) the more functional groups present, the
 692 more water is still bonded on the GO surface. Therefore, one would clearly
 693 expect that the loss of hydrophilic functional groups plays a role in con-
 694 trolling the stability of GO dispersion in water. As GO loses its functional
 695 groups in exposure to high pH electrolytes (*i.e.* GO transforms to a hy-
 696 drophobic material), it tends to form aggregates. This explains the obser-
 697 vations made from Fig. 11: the GO-PS and GO-CH have lost most of their
 698 dispersing capacity and GO-CC occupies a somewhat intermediate position
 699 in terms of dispersion.

700 *3.6. Mechanisms controlling the stability of GO dispersion in alite paste*

701 According to the mechanisms discussed in Sections 3.4 and 3.5, the nano-
 702 layers of GO aggregate in the pore solution of alite paste. This aggregation
 703 occurs while mixing the GO suspension with alite particles, and starts from
 704 the very first seconds of hydration when the alite particles dissolve in water.
 705 Two mechanisms simultaneously cause the instability of GO dispersion in
 706 alite paste: (i) the carboxylated GO layers form complexation with calcium
 707 ions available in the pore solution of paste, (ii) due to the high alkalinity of
 708 the paste environment, GO reduces and loses its hydrophilicity.

709 In addition to the interaction of GO with the paste pore solution, it is
 710 worth mentioning that the negatively charged carboxylated GO layers may
 711 be electrostatically attracted to the surface of alite particles and/or form
 712 complexation with the Ca ions at the alite surface. This interaction is re-
 713 ported for carboxylate-based polyelectrolytes with cement particles, and is
 714 known to retard the cement hydration [47, 48]. The retardation occurs as
 715 the carboxylated groups adsorb onto the surface of cement particles and/or

716 complex with the calcium ions present at the surface, affecting the disso-
 717 lution reaction. Since our calorimetry results show no sign of retardation
 718 (Fig. 4), the surface interaction mechanism does not seem to occur in the
 719 present study. However, it could play a role in other cement systems.

720 4. Conclusions

721 In this paper, the hydration of alite was first investigated in the presence
 722 of GO nano-layers using isothermal calorimetry. Results indicated that the
 723 presence of GO accelerates alite hydration. However, the observed accelera-
 724 tion was found to be quite low. A boundary nucleation-growth (BNG) model
 725 was used to better understand the role of GO as a nucleation-growth site.
 726 The BNG analysis showed that the amount of extra surface and nucleation
 727 sites added by GO was several orders of magnitude lower than what GO
 728 could potentially provide in alite paste. Direct microscopical observations
 729 pointed to the aggregation of GO in the paste. This led us to investigate the
 730 colloidal stability of GO in various calcium electrolytes including the pore
 731 solution of alite paste.

732 Results showed that GO aggregates when exposed to high-pH electrolytes
 733 containing calcium cations. The main mechanisms causing this instability
 734 are:

- 735 • Due to the high pH environment, the carboxyl group of GO nano-
 736 layers are de-protonated, forming complexation with calcium cations
 737 released from the dissolution of alite in water.
- 738 • The hydrophilic functional groups present on the GO surface are re-
 739 duced, possibly as a result of a reaction between hydroxide ions and
 740 GO.

741 As the pore solution of alite paste is highly alkaline and rich in calcium
742 ions, these two mechanisms simultaneously prevent the effective dispersion
743 of individual GO layers in alite paste.
744 Overall, the findings of this study imply that the mechanisms commonly
745 proposed in the literature to explain the role of GO in PC paste are probably
746 invalid as the structure of GO prevents it from being well dispersed in high
747 pH and calcium-rich environments. Considering that GO had little effect on
748 the kinetics of hydration and that it was shown to agglomerate in alite paste,
749 it is unlikely that the significant strength improvements previously reported
750 in the literature resulted from GO single layers serving for the nucleation of
751 hydration precipitates. Since GO reduces at high pH and loses the majority
752 of its surface functional groups, the idea of interfacial bonding between GO
753 and C-S-H suggested in previous studies needs to be revisited. If the aim is
754 to achieve a good dispersion of GO in PC paste, further work should focus
755 on functionalising graphene with different groups such that the mechanisms
756 brought to light here are not encountered.

757 **Acknowledgments**

758 The financial support provided by University College London (UCL) to the
759 first author is gratefully acknowledged. Authors would like to thank Dr
760 Christoph Salzmann and Mr Martin Rosillo-Lopez for their support through-
761 out this study. The first author greatly thanks Mr Tobias P. Neville for ac-
762 cess to his furnace. Dr Enrico Masoero is also greatly acknowledged for his
763 discussions on the modelling of hydration. The authors would also like to
764 thank Mr Warren Gaynor from UCL Laboratory of Advanced Materials, Dr
765 Francis O'Shea and Dr Judith Zhou from UCL Environmental Engineering

766 Laboratory.

767 References

- 768 [1] J. Warner, Graphene: Fundamentals and emergent applications, 1st
769 Edition, Elsevier, London, 2013.
- 770 [2] S. Chuah, Z. Pan, J. Sanjayan, C. Wang, W. H. Duan, Nano reinforced
771 cement and concrete composites and new perspective from graphene
772 oxide, Construction and Building Materials 73 (2014) 113–124.
- 773 [3] X. Li, W. Wei, H. Qin, Y. Hang Hu, Co-effects of graphene oxide sheets
774 and single wall carbon nanotubes on mechanical properties of cement,
775 Journal of Physics and Chemistry of Solids 85 (2015) 39–43.
- 776 [4] Z. Lu, D. Hou, L. Meng, G. Sun, C. Lu, Z. Li, Mechanism of cement
777 paste reinforced by graphene oxide/carbon nanotubes composites with
778 enhanced mechanical properties, RSC Advances 5 (122) (2015) 100598–
779 100605.
- 780 [5] Z. Pan, L. He, L. Qiu, A. Habibnejad Korayema, G. Li, J. Wu Zhu,
781 F. Collins, D. Li, W. Hui Duan, M. Chien Wang, Mechanical properties
782 and microstructure of a graphene oxide-cement composite, Cement &
783 Concrete Composites 58 (2015) 140–147.
- 784 [6] T. Tong, Z. Fan, Q. Liu, S. Wang, S. Tan, Q. Yu, Investigation of the
785 effects of graphene and graphene oxide nanoplatelets on the micro- and
786 macro-properties of cementitious materials, Construction and Building
787 Materials 106 (2016) 102–114.

- 788 [7] R. Shahsavari, P. Ajayan, Multifunctional cement composites: rein-
789 forcement via hexagonal Boron Nitride and Graphite Oxide sheets, in:
790 14th International Congress on the Chemistry of Cement (ICCC 2015),
791 2015.
- 792 [8] H. Alkhateb, A. Al-Ostaz, C. A.H.D., X. Li, Materials genome for
793 graphene-cement nanocomposites, *Journal of nanomechanics and mi-
794 cromechanics* 3 (3) (2013) 67–77.
- 795 [9] K. Gong, Z. Pan, A. Korayem, L. Qiu, D. Li, F. Collins, C. Wang,
796 W. H. Duan, Reinforcing effects of graphene oxide on portland cement
797 paste, *Journal of Materials in Civil Engineering* 27.
- 798 [10] S. Lv, Y. Ma, C. Qiu, T. Sun, J. Liu, Q. Zhou, Effect of graphene
799 oxide nanosheets of microstructure and mechanical properties of cement
800 composites, *Construction and Building Materials* 49 (2013) 121–127.
- 801 [11] S. Lv, C. Qiu, Y. Ma, Q. Zhou, Regulation of GO on cement hydra-
802 tion crystals and its toughening effect, *Magazine of Concrete Research*
803 65 (20) (2013) 1246–1254.
- 804 [12] S. Lv, S. Ting, J. Liu, Q. Zhou, Use of graphene oxide nanosheets to
805 regulate the microstructure of hardened cement paste to increase its
806 strength and toughness, *CrystEngComm* 16 (2014) 8508–8516.
- 807 [13] S. Sharma, N. Kothiyal, Influence of graphene oxide as dispersed phase
808 in cement mortar matrix in defining the crystal patterns of cement hy-
809 drates and its effect on mechanical, microstructural and crystallization
810 properties, *RSC Advances* 5 (2015) 52642–52657.

- 811 [14] S. Lv, J. Liu, T. Sun, Y. Ma, Q. Zhou, Effect of GO nanosheets on
812 shapes of cement hydration crystals and their formation process, Con-
813 struction and Building Materials 64 (2014) 231–239.
- 814 [15] E. Horszczaruk, E. Mijowska, R. Kalenczuk, M. Aleksandrak, S. Mi-
815 jowska, Nanocomposite of cement/graphene oxide – impact on hydra-
816 tion kinetics and Youngs modulus, Construction and Building Materials
817 78 (2015) 234–242.
- 818 [16] F. Sanchez, L. Zhang, Molecular dynamics modeling of the interface be-
819 tween surface functionalized graphitic structures and calcium–silicate–
820 hydrate: Interaction energies, structure, and dynamics, Journal of Col-
821 loid and Interface Science 323 (2008) 349358.
- 822 [17] C. Lin, W. Wei, Y. H. Hu, Catalytic behavior of graphene oxide for
823 cement hydration process, Journal of Physics and Chemistry of Solids
824 89 (2016) 128–133.
- 825 [18] D. Dreyer, S. Park, C. Bielawski, R. Ruoff, The chemistry of graphene
826 oxide, Chemical society reviews 39 (2010) 228–240.
- 827 [19] Y. Zhu, S. Murali, W. Cai, X. Li, J. Won Suk, J. Potts, R. Ruoff,
828 Graphene and graphene oxide: Synthesis, properties, and applications,
829 Advanced materials 22 (35) (2010) 3906–3924.
- 830 [20] A. Wesselsky, O. Jensen, Synthesis of pure portland cement phases,
831 Cement and Concrete Research 39 (2009) 973–980.
- 832 [21] D. Marcano, D. Kosynkin, J. Berlin, A. Sinitskii, Z. Sun, A. Slesarev,
833 L. Alemany, W. Lu, J. Tour, Improved synthesis of graphene oxide,
834 ACS Nano 4 (8) (2010) 4806–4814.

- 835 [22] T. Szabo, E. Tombacz, E. Illes, I. Dekany, Enhanced acidity and
836 pH-dependent surface charge characterization of successively oxidized
837 graphite oxides, *Carbon* 44 (2006) 537–545.
- 838 [23] P. Montes-Navajas, N. Asenjo, R. Santamara, R. Menndez, A. Corma,
839 H. Garca, Surface area measurement of graphene oxide in aqueous so-
840 lutions, *Langmuir* 29 (2013) 13443–13448.
- 841 [24] J. Bullard, G. Scherer, J. Thomas, Time dependent driving forces and
842 the kinetics of tricalcium silicate hydration, *Cement and Concrete Re-
843 search* 74 (2015) 26–34.
- 844 [25] G. Scherer, J. Zhang, J. Thomas, Nucleation and growth models for
845 hydration of cement, *Cement and Concrete Research* 42 (2012) 982–
846 993.
- 847 [26] H. Taylor, *Cement chemistry*, 2nd Edition, Thomas Telford Publishing,
848 London, 1997.
- 849 [27] A. Bazzoni, S. Ma, Q. Wang, X. Shen, M. Cantoni, K. Scrivener, The
850 effect of magnesium and zinc ions on the hydration kinetics of c3s,
851 *Journal of American Ceramic Society* 97 (11) (2014) 3684–3693.
- 852 [28] E. Masoero, J. Thomas, H. Jennings, A reaction zone hypothesis for the
853 effects of particle size and water-to-cement ratio on the early hydration
854 kinetics of c3s, *Journal of the American Ceramic Society* 97 (3) (2014)
855 967–975.
- 856 [29] J. Thomas, A new approach to modeling the nucleation and growth ki-
857 netics of tricalcium silicate hydration, *Journal of the American Ceramic
858 Society* 90 (10) (2007) 3282–3288.

- 859 [30] J. Thomas, H. Jennings, J. Chen, Influence of nucleation seeding on the
860 hydration mechanisms of tricalcium silicate and cement, *The Journal*
861 *of Physical Chemistry C* 113 (11) (2009) 4327–4334.
- 862 [31] J. Bullard, H. Jennings, R. Livingston, A. Nonat, G. Scherer,
863 J. Schweitzer, K. Scrivener, J. Thomas, Mechanisms of cement hydra-
864 tion, *Cement and concrete research* 41 (2011) 1208–1223.
- 865 [32] K. Scrivener, A. Nonat, Hydration of cementitious materials, present
866 and future, *Cement and Concrete Research* 41 (2011) 651–665.
- 867 [33] K. Scrivener, P. Juilland, P. Monteiro, Advances in understanding hy-
868 dration of portland cement, *Cement and Concrete Research* 78 (2015)
869 3856.
- 870 [34] A. Dimiev, L. Alemany, J. Tour, Graphene oxide. origin of acidity, its
871 instability in water, and a new dynamic structural model, *ACS Nano*
872 7 (1) (2013) 576–588.
- 873 [35] M. Mermoux, Y. Chabre, A. Rousseau, FTIR and ^{13}C NMR study of
874 graphite oxide, *Carbon* 29 (3) (1991) 469–474.
- 875 [36] T. Szabo, O. Berkesi, I. Dekany, DRIFT study of deuterium-exchanged
876 graphite oxide, *Carbon* 43 (15) (2005) 3186–3189.
- 877 [37] T. Szabo, O. Berkesi, P. Forgo, K. Josepovits, Y. Sanakis, D. Petridis,
878 I. Dekany, Evolution of surface functional groups in a series of progres-
879 sively oxidized graphite oxides, *Chemistry of Materials* 18 (11) (2006)
880 2740–2749.
- 881 [38] S. Lv, L. Deng, W. Yang, Q. Zhou, Y. Cui, Fabrication of polycar-
882 boxylate/graphene oxide nanosheet composites by copolymerization for

reinforcing and toughening cement composites, *Cement and Concrete Composites* 66 (2016) 1–9.

[39] D. Li, M. Mller, S. Gilje, R. Kaner, G. Wallace, Processable aqueous dispersions of graphene nanosheets, *Nature nanotechnology* 3 (2008) 101–105.

[40] C. Shih, S. Lin, R. Sharma, M. Strano, D. Blankschtein, Understanding the pH-dependent behavior of graphene oxide aqueous solutions: A comparative experimental and molecular dynamics simulation study, *Langmuir* 28 (2012) 235–241.

[41] A. Buchsteiner, A. Lerf, J. Pieper, Water dynamics in graphite oxide investigated with neutron scattering, *Journal of physical Chemistry B* 110 (2006) 22328–22338.

[42] S. Cervený, F. Barroso-Bujans, A. Alegria, J. Colmenero, Dynamics of water intercalated in graphite oxide, *Journal of Physical Chemistry C* 114 (2010) 2604–2612.

[43] I. Chowdhury, N. Mansukhani, L. Guiney, M. Hersam, D. Bouchard, Aggregation and stability of reduced graphene oxide: Complex roles of divalent cations, pH, and natural organic matter, *Environmental Science & Technology* 49 (18) (2015) 10886–10893.

[44] Z. Hua, Z. Tang, X. Bai, J. Zhang, L. Yu, H. Cheng, Aggregation and resuspension of graphene oxide in simulated natural surface aquatic environments, *Environmental Pollution* 205 (2015) 161–169.

[45] L. Wu, L. Liu, B. Gao, R. Munoz-Carpena, M. Zhang, H. Chen, Z. Zhou, H. Wang, Aggregation kinetics of graphene oxides in aque-

- 907 ous solutions: Experiments, mechanisms, and modeling, *Langmuir* 29
908 (2013) 15174–15181.
- 909 [46] S. Stankovich, D. Dikin, R. Piner, K. Kohlhaas, A. Kleinhammes,
910 Y. Jia, Y. Wu, S. Nguyen, R. Ruof, Synthesis of graphene-based
911 nanosheets via chemical reduction of exfoliated graphite oxide, *Carbon*
912 45 (2007) 1558–1565.
- 913 [47] A. Zingg, F. Winnefeld, L. Holzer, J. Pakusch, S. Becker, L. Gauckler,
914 Adsorption of polyelectrolytes and its influence on the rheology, zeta
915 potential, and microstructure of various cement and hydrate phases,
916 *Journal of Colloid and Interface Science* 323 (2008) 301–312.
- 917 [48] Y. Zhang, X. Kong, Correlations of the dispersing capability of NSF
918 and PCE types of superplasticizer and their impacts on cement hydra-
919 tion with the adsorption in fresh cement pastes, *Cement and Concrete*
920 *Research* 69 (2015) 1–9.

w/a ratio	O_V^B (μm^{-1})	N_S (μm^{-2})	S_{GO} -max (m^2/g)	S_{GO} -min (m^2/g)	N_S^{GO} -max (μm^{-2})	N_S^{GO} -min (μm^{-2})
0.3	0.99 $\pm$ 0.06	12.22 $\pm$ 0.22	95.4	2.79	125.2	15.7
0.4	0.882 $\pm$ 0.08	12.28 $\pm$ 0.28	147.74	4.25	106.7	15.27
0.5	0.792 $\pm$ 0.09	12.31 $\pm$ 0.31	186.2	2.32	203.7	15
0.6	0.7245 $\pm$ 0.1	12.4 $\pm$ 0.4	230.55	1.192	493	15.28

Table 1: Range of N_S and O_V^B values involved in the hydration of alite-GO paste containing 0.08%GO, obtained from the BNG analysis. S_{GO} and N_S^{GO} values were calculated using Eq. 5, Eq. 6 and Eq. 7.

Figure 1: (a) Particle size distribution of alite used to study the hydration kinetics, (b) X-ray powder diffraction pattern of synthesised alite along with the Rietveld refinement fitting pattern, suggesting a slight trace of CaO in the sample.

Figure 2: AFM micrograph of GO: (a) tapping mode topographic image of GO deposited on a freshly cleaved mica surface, (b) height profile for the line-section shown in (a) confirming that the synthesised GO is in the form of mono-layer with an approximately 1 nm thickness, (c) height distribution of GO layers studied over $50\mu\text{m} \times 50\mu\text{m}$, indicating that GO is dominantly in the form of single layer.

Figure 3: (a) Typical heat evolution curve of alite hydration along with the parameters extracted in order to quantitatively compare the hydration of plain and GO-containing alite pastes, (b) BNG fitting simulation to the calorimetric pattern obtained for the hydration of alite paste with water:alite mass ratio of 0.5, (c) time-dependent growth rate of hydration product (G_{out}) found as a result of BNG simulation for the calorimetric data shown in figure (b).

Figure 4: Rate of heat evolution (dQ/dt) for the reaction of alite with water in the presence of various concentrations of GO nano-layer43. Rate is normalised by the mass of alite and is measured for four water to alite mass ratios: (a) 0.3, (b) 0.4, (c) 0.5, (d) 0.6.

Figure 5: Influence of GO concentration on three parameters characterising the heat evolution curves of alite hydration: (a) the rate of acceleration period $(d^2Q/dt^2)_{acc}$, (b) the value of heat rate at the peak $(dQ/dt)_p$, (c) the time at which the maximum rate peak occurs, t_p .

Figure 6: (a) Growth rate of hydration precipitates (G_{out}) as a function of time, acquired by fitting the BNG equations to the calorimetry curve of plain alite (straight line) and alite-GO (dashed line) paste. These curves correspond to $G_{low}(t)$ and $G_{up}(t)$ as defined in Section 2.3. Both curves were calculated using $N_S = 12\mu\text{m}^{-2}$ and $O_V^B = 0.6235\mu\text{m}^{-1}$. The growth rate is only presented here for pastes with water to alite ratio of 0.6, and the alite-GO paste contains 0.08% GO. (b) and (c) show the dependence of G_{out} at times $t=2\text{h}$ (circle) and $t=10\text{h}$ (diamond) as total N_S (with $O_V^B = 0.6235\mu\text{m}^{-1}$) and O_V^B (with $N_S = 12\mu\text{m}^{-2}$) are varied in the fitting simulation of alite-GO calorimetry curve. Horizontal dashed lines in (b) and (c) show the lower- and upper bounds in (a) at times 2 and 10.

Figure 7: Growth rate of precipitates (G_{out}) at time $t=10$ hours as a function of N_s and O_V^B used in the BNG fitting (gray surface). The plane surface (orange) corresponds to $G_{low}(t)$, and point A shows the maximum allowed G_{out} ; that is G_{up} . Points B and C are the maximum allowable N_s and O_V^B , respectively. Any G_{out} points located above the plane surface but below point A are deemed consistent with the calorimetry data, for instance point D.

Figure 8: Micrograph of GO aggregation in alite paste captured using a light microscope with magnification X8 (Discovery V8, ZEISS): (a) plain alite paste, (b) GO-alite paste. Image was captured for a sample hydrated for 24 hours with water to alite ratio of 0.5.

(a)

(b)

Figure 9: (a) FT-IR spectrum of GO, suggesting the vibration of C-O (band 1), C-OH (band 2), water molecules bound on the surface of GO (band 3 and 5), non-carboxyl C=O (band 4), O-H group (band 5). Inset A magnifies the FT-IR spectrum at the peak band 3, and it points out to the presence of a shoulder corresponding to the vibration of de-protonated carboxyl group (carboxylate); (b) C1s XPS spectrum of GO, which is de-convoluted into three chemical states, indicated as sp^2 and sp^3 hybridized carbon, carbonyl (C=O), alcohol and epoxide (C-O), and carboxyl (O-C=O) functional groups.

Figure 10: Zeta-potential of GO nano-layers measured in water (right axis) and pH of GO aqueous solution (left axis) as a function of GO dosage in water (mg/ml).

Figure 11: Coagulation of GO solution as a result of introducing Ca-electrolytes: (a) GO mixed with pure de-ionised water, (b) GO-CH prepared by mixing GO solution with saturated $\text{Ca}(\text{OH})_2$ – in this mix there is $[\text{Ca}^{2+}] = 11.5 \text{ mmol/L}$ available to interact with GO layers, (c) GO-CC is the mix of GO solution with CaCl_2 solution, also having $[\text{Ca}^{2+}] = 11.5 \text{ mmol/L}$, (d) Pore solution of alite paste extracted from a dilute aqueous suspension of alite powder ($\text{H}_2\text{O}:\text{alite} = 50$). Note that this image shows the condition of GO solutions almost immediately after the mixing with electrolytes, and small aggregates form in the GO-CC mix which are not visible in this image.

Figure 12: (a) Calcium concentration as a function of GO dosage in aqueous solution, indicating that Ca is removed by GO layers only in the case of GO-CH mix where GO layers are exposed to high alkaline environment ($\text{pH} > 12$). Assuming that each carboxyl group of GO is converted to carboxylate and is an active site to form complexation with calcium, the two dashed lines show the possible upper- and lower-boundary of carboxylate quantity that can remove Ca cations from the solution. (b) C1s XPS spectra (data is normalised and the background is removed) which were used to quantify the amount of carboxylate group in GO sample in order to calculate the dashed lines shown in (a).

Figure 13: FT-IR spectra of plain GO, GO-CH, GO-CC and GO-PS, indicating that the oxygen-based functional groups of GO were reduced in exposure to calcium-containing electrolytes. The extent of this reduction depends on the pH of the electrolytes mixed with the GO aqueous solution.

Figure 14: XRD patterns of graphite, plain GO, GO-W, GO-CH, GO-CC and GO-PS presented as a function of Q (Q equals to $2\pi/d$, where d is the distance between the graphene and GO layers in graphite and graphite oxide crystal structures, respectively). Note that the vertical dashed line with $d=5.711$ Å corresponds to the distance between GO layers in a completely dried GO sample.

(a)

(b)

Figure 15: TG patterns of plain GO, GO-CH, GO-CC, GO-PS and GO-W: (a) mass-loss as a function of heating temperature; (b) differential mass-loss of TG patterns shown in (a).